# MILITARY SPECIFICATION

## CLOTH, NONWOVEN, DISPOSABLE, POLYPROPYLENE

This specification is approved for use by the Navy Clothing and Textile Research Facility, and is available for use by all Departments and Agencies of the Department of Defense.

## 1. SCOPE

1.1 Scope. This specification covers the requirements for one type of non-woven composite cloth made of spunbonded polypropylene (see 6.1).

## 2. APPLICABLE DOCUMENTS

2.1 Government documents.

2.1.1 Specifications and standards. Unless otherwise specified, the following specifications and standards of the issue listed in that issue of the Department of Defense Index of Specifications and Standards (DoDISS) specified in the solicitation form a part of this specification to the extent specified.

SPECIFICATION

FEDERAL

| | |
|---|---|
| V-T-285 | - Thread, Polyester |
| PPP-P-1136 | - Packaging and Packing of Coated (Plastic; Rubber) and Laminated Fabrics |

MILITARY

| | |
|---|---|
| MIL-T-43548 | - Thread, Polyester, Cotton-Covered and Rayon Covered |
| MIL-T-43624 | - Thread, Polyester, Spun |

Beneficial comments (recommendations, additions, and deletions) and any pertinent data which may be of use in improving this document should be addressed to: Officer in Charge, Navy Clothing and Textile Research Facility, 21 Strathmore Road, Natick, MA 01760 by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

FSC 8305

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T02:52Z
Check the source to verify that this is the current version before use.

STANDARDS

FEDERAL

FED-STD-191 - Textile Test Methods

MILITARY

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes

(Copies of specifications, standards, and publications required by contractors in connection with specific procurement functions shall be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless a specific issue is identified, the issue in effect on date of invitation for bids or request for proposal shall apply:

RULES AND REGULATIONS UNDER THE TEXTILE FIBER PRODUCTS IDENTIFICATION ACT

(Copies may be obtained without charge from the Federal Trade Commission, Washington, D.C. 20580).

3. REQUIREMENTS

3.1 Standard sample. When a standard sample is available, the finished cloth shall be equal to or better than the sample with respect to all characteristics for which the standard sample is referenced (see 6.2).

3.2 First article. When specified (see 6.2), the contractor shall furnish sample unit(s) for first article inspection and approval (see 4.2).

3.3 Cloth, nonwoven. The nonwoven cloth shall be a laminate of spunbonded meltblown polypropylene. The color shall be any shade of white. The cloth shall conform to the requirements specified in Table I when tested as specified in 4.5.

Table I. Physical requirements

| | |
|---|---|
| Weight, oz/sq yd (maximum) | 1.6 |
| Breaking strength, lbs (minimum) | |
| Machine direction | 15.0 |
| Cross direction | 15.0 |
| Tearing strength, grams (minimum) | |
| Machine direction | 450 |
| Cross direction | 450 |



Source: https://assist.dla.mil -- Downloaded: 2026-10-20T02:52Z
Check the source to verify that this is the current version before use.

| | |
|---|---|
| Seam strength, lbs (minimum) | |
| Machine direction | 12.0 |
| Cross direction | 12.0 |
| Water resistance, inches (minimum) | 12.0 |
| Flame resistance | |
| Machine and cross directions | |
| After flame, second (maximum) | 3.0 |
| After glow, seconds (maximum) | 3.0 |
| Char length, inches (maximum) | 9.0 |
| Air permeability, cu ft/min/sq ft (minimum) | 30.0 |

3.4 Length, width and put up. The cloth shall be put up on rolls as specified in PPP-P-1136. The length and width shall be as specified (see 6.2).

3.5 Fiber identification. Each roll of cloth shall be labeled or ticketed for fiber content in accordance with the Textile Fiber Products Identification Act.

3.6 Workmanship. The finished cloth shall conform to the quality established by this specification. The occurrence of defects shall not exceed the applicable quality levels.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements as specified herein unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.1.1 Certificate of compliance. Where certificates of compliance are submitted, the Government reserves the right to check test such items to determine the validity of the certification.

4.2 First article inspection. The first article submitted in accordance with 3.2 shall be inspected as specified in 4.3.2 for compliance with construction, workmanship, and end item testing (see 6.5).

4.3 Inspection. Sampling for inspection shall be in accordance with the provisions set forth in MIL-STD-105, except where otherwise indicated hereinafter.

4.3.1 Component and material inspection. In accordance with 4.1, components and materials shall be inspected and tested in accordance with all the requirements of referenced specifications and standards unless otherwise excluded, amended, modified, or qualified in this specification.

Source: https://assist.dla.mil - Downloaded: 2026-10-20T02:52Z
Check the source to verify that this is the current version before use.

4.3.2 Examination of the end item. The end item shall be examined in accordance with the classification of defects and at the inspection levels and acceptable quality levels (AQL's) set forth below.

4.3.2.1 Yard-by-yard examination. The required yardage of each roll shall be examined, and defects clearly noticeable at normal inspection distance (3 feet) shall be classified as listed. The defects found shall be counted regardless of their proximity to each other, except where two or more defects represent a single local condition of the cloth, in which case only the most serious defect shall be counted. A continuous defect shall be counted as one defect for each yard or fraction thereof in which it occurs. The sample unit shall be on linear yard. The acceptable quality level shall be 4.0 defects per 100 units for all defects listed. The sample size shall be in accordance with inspection level II of MIL-STD-105. The lot size shall be expressed in units of one yard each. The number of rolls selected shall be in accordance with Table II. An approximately equal number of yards shall be examined from each roll in the sample.

Defects

Any hole, cut or tear.
Any imbedded foreign matter.
Any unbonded area or delamination.

4.3.2.2 Overall examination. Each defect shall be counted not more than once in each roll examined. The sample unit shall be one roll. The sample size and the acceptance number shall be as shown in Table II.

Defects

Color not as specified.
Overall uncleanness.
Width less than specified.
Objectionable odor.

Table II - Sample size

| Lot size (yards) | Sample size (rolls) | Acceptance number |
|---|---|---|
| Up thru 1200 1/ | 3 | 0 |
| 1201 thru 3200 | 5 | 0 |
| 3201 thru 10,000 | 8 | 0 |
| 10,001 thru 35,000 | 13 | 0 |
| 35,001 thru 150,000 | 20 | 1 |
| 150,001 and over | 32 | 2 |

1/ If the lot contains fewer than 3 rolls, each piece in the lot shall be examined.



Source: https://assist.dla.mil -- Downloaded: 2026-10-20T02:52Z
Check the source to verify that this is the current version before use.

4.3.3 Examination for length.

4.3.3.1 Individual rolls. During the yard-by-yard examination, each roll in the sample shall be examined for length. Any length found to be less than the minimum specified or more than two yards less than the length marked on the ticket, shall be considered a defect with respect to length. The lot shall be unacceptable if two or more rolls in the sample are defective in respect to length.

4.3.3.2 Total yardage in sample. The lot shall be unacceptable if the total of the actual length of rolls in the sample is less than the total of the lengths marked on the tickets.

4.4 Examination of packaging requirements. An examination shall be made in accordance with the provisions of PPP-P-1136 to determine whether packaging, packing, and marking comply with Section 5 requirements.

4.5 Testing of the end item. The methods of testing specified in FED-STD-191 wherever applicable and as listed in Table III shall be followed. The physical and chemical values specified in Section 3 shall apply to the results of the determination made on a sample unit for test purposes as specified in the applicable test method. The sample unit shall be 2 yards full width of the cloth. The lot shall be unacceptable if one or more sample units fail to meet any requirements specified. All test reports shall contain the individual values utilized in expressing the final results. The sample size shall be as follows:

| Lot size in yards | Sample size |
|---|---|
| 800 or less | 2 |
| 801 thru 22,000 | 3 |
| 22,001 and over | 5 |

Table III - Test methods

| Characteristic | Requirement Paragraph | Test Method |
|---|---|---|
| Weight | Table I | 5041 |
| Breaking strength | Table I | 5100 |
| Tearing strength | Table I | 5132 |
| Seam strength | Table I | 5110 1/ |
| Water resistance | Table I | 5514 |
| Flame resistance | Table I | 5903 |
| Air permeability | Table I | 5450 |

1/ Except that the test results shall be reported as seam strength in pounds rather than as percent seam efficiency. The needle shall measure 0.044 inch (+ 0.001) across the blade at the eye. The needle and looper threads shall be one of the following combinations.



Source: https://assist.dla.mil -- Downloaded: 2026-10-20T02:52Z
Check the source to verify that this is the current version before use.

(a) Polyester (continuous filament) V-T-285, sizes AA and A, subclass A, type I, II or III.
(b) Polyester (spun) MIL-T-43624, ticket nos. 50, 3 ply and 70, 2 or 3 ply, class 1 or 2
(c) Polyester (cotton covered) MIL-T-43548, ticket nos. 50, 2 or 3 ply and 70, 2 or 3 ply.

## 5. PACKAGING

5.1 Preservation-packaging. Packaging shall be level A or C, as specified (see 6.2 and 6.2.1).

5.1.1 Levels A and C. The cloth, put up as specified (see 3.4), shall be packaged in accordance with the applicable requirements of PPP-P-1136.

5.2 Packing. Packing shall be level A, B, or C, as specified (see 6.2).

5.2.1 Levels A, B, and C. The cloth shall be packed in accordance with the applicable requirements of PPP-P-1136.

5.3 Marking. In addition to any special marking required by the contract or order (see 6.2), shipments shall be marked in accordance with the applicable requirements of PPP-P-1136.

## 6. NOTES

6.1 Intended use. The nonwoven cloth covered by this specification is uncoated, offers moderate strength, low breathability, fair water resistance and is intended for use in fabricating disposable clothing specifically designed for the protection of personnel working with asbestos and/or fibrous glass materials. Personnel wearing clothing fabricated from this cloth should avoid contact with hot surfaces, sparks or other sources of ignition.

6.2 Ordering data. Procurement documents should specify the following:

a. Title, number and date of this specification.
b. Requirements for the first article (see 3.2).
c. Length and width required (see 3.4).
d. Levels of packaging and packing required (see 5.1 and 5.2).

6.2.1 In the preparation of contracts or orders, it must be noted that various options, choices, and alternatives, as indicated in PPP-P-1136 may be exercised in packaging the cloth.

6.3 Standard sample. For access to the standard sample, address the procuring activity issuing the invitation for bids.

6.4 Source of cloth. Nonwoven cloth conforming to the requirements of this specification may be obtained from the Kimberly-Clark Corporation, Neenah, Wisconsin, 54956 under their designation SMS (CPF).



Source: https://assist.dla.mil -- Downloaded: 2026-10-20T02:52Z
Check the source to verify that this is the current version before use.

6.5 First article. When a first article inspection is required, the item will be tested and should be a preproduction sample. The contracting officer should include specific instructions in acquisition documents regarding arrangements for examinations, quantity, testing, and approval of the first article.

Custodian:
Navy - NU

Review Activity:
Navy - SH
AF - 82
Army - MD
DLA - CT

User Activity:
Navy - MC

Preparing Activity:
Navy - NU

Project No. 8305-0847



Source: https://assist.dla.mil -- Downloaded: 2026-10-20T02:52Z
Check the source to verify that this is the current version before use.

# STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

INSTRUCTIONS: This form is provided to solicit beneficial comments which may improve this document and enhance its use. DoD contractors, government activities, manufacturers, vendors, or other prospective users of the document are invited to submit comments to the government. Fold on lines on reverse side, staple in corner, and send to preparing activity. Attach any pertinent data which may be of use in improving this document. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity. A response will be provided to the submitter, when name and address is provided, within 30 days indicating that the 1426 was received and when any appropriate action on it will be completed.
NOTE: This form shall not be used to submit requests for waivers, deviations or clarification of specification requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

DOCUMENT IDENTIFIER *(Number)* AND TITLE

MIL-C-24908(NU) Cloth, Nonwoven, Disposable, Polypropylene

NAME OF ORGANIZATION AND ADDRESS OF SUBMITTER

☐ VENDOR ☐ USER ☐ MANUFACTURER

1. ☐ HAS ANY PART OF THE DOCUMENT CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE? ☐ IS ANY PART OF IT TOO RIGID, RESTRICTIVE, LOOSE OR AMBIGUOUS? PLEASE EXPLAIN BELOW.

A. GIVE PARAGRAPH NUMBER AND WORDING

B. RECOMMENDED WORDING CHANGE

C. REASON FOR RECOMMENDED CHANGE(S)

2. REMARKS

SUBMITTED BY *(Printed or typed name and address — Optional)*

TELEPHONE NO.

DATE

DD FORM 1426 1 OCT 76

Replaces edition of 1 Jan 72 which may be used.

S/N 0102-LF-001-4260

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T02:52Z
Check the source to verify that this is the current version before use.

FOLD

DEPARTMENT OF THE NAVY

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300

NO POSTAGE NECESSARY IF MAILED IN THE UNITED STATES

**BUSINESS REPLY MAIL**

FIRST CLASS PERMIT NO. 12503 WASHINGTON D. C.

POSTAGE WILL BE PAID BY THE DEPARTMENT OF THE NAVY

OFFICER IN CHARGE
NAVY CLOTHING & TEXTILE RESEARCH FACILITY
21 STRATHMORE ROAD
NATICK, MA 01760

FOLD

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T02:52Z
Check the source to verify that this is the current version before use.