INCH-POUND

MIL-C-24916A
9 January 1991
SUPERSEDING
MIL-C-24916
10 September 1984

MILITARY SPECIFICATION

CLOTH, CHAMBRAY, COTTON (FLAME RETARDANT TREATED)

This specification is approved for use by the Navy Clothing and Textile Research Facility, Department of the Navy, and is available for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

* 1.1 Scope. This specification covers one type of chambray cotton cloth which has been treated with a flame retardant finish.

2. APPLICABLE DOCUMENTS

2.1 Government documents.

* 2.1.1 Specifications, standards, and handbooks. The following specifications, standards, and handbooks form a part of this document to the extent specified herein. Unless otherwise specified, the issues of these documents shall be those listed in the issue of the Department of Defense Index of Specifications and Standards (DODISS) and supplement thereto, cited in the solicitation (see 6.2).

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: Officer in Charge, Navy Clothing and Textile Research Facility, Post Office Box 59, Natick, MA 01760-0001 by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

AMSC N/A FSC 8305

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T02:55Z
Check the source to verify that this is the current version before use.

SPECIFICATIONS

FEDERAL

V-T-276	- Thread, Cotton
PPP-P-1134	- Packaging, Packing of Cotton and Cotton-Synthetic Fiber-Blend Fabrics (Excluding Duck Fabrics)

STANDARDS

FEDERAL

FED-STD 191	- Textile Test Methods
FED-STD-4	- Glossary of Fabric Imperfections

MILITARY

MIL-STD-105	- Sampling Procedures and Tables for Inspections by Attributes
* MIL-STD-2073-1	- DOD Material Procedures for Development & Application of Packaging Requirements
* MIL-STD-2073-2	- Packaging Requirement Codes

(Unless otherwise indicated, copies of federal and military specification, standards, and handbooks are available from the Standardization Documents Order Desk, Building 4D, 700 Robbins Avenue, Philadelphia, PA 19111-5094.)

* 2.1.2 Other Government documents, drawings, and publications. The following other Government documents, drawings, and publications form a part of this document to the extent specified herein. Unless otherwise specified, the issues are those cited in the solicitation.

Rules and Regulations Under the Textile Fiber Products Identification Act

(Copies may be obtained without charge from the Federal Trade Commission, Washington, DC 20580).

* 2.2 Non-Government publications. The following document(s) form a part of this specification to the extent specified herein. Unless otherwise specified, the issue of documents which are DoD adopted shall be those listed in the issue of the DODISS cited in the solicitation. Unless otherwise specified, the issues of documents not listed in the DODISS shall are the issues of the documents cited in the solicitation (see 6.2).

TECHNICAL MANUAL OF THE AMERICAN ASSOCIATION OF TEXTILE CHEMISTS AND COLORISTS

Method No. 8 Colorfastness to Crocking: AATCC Crockmeter Method

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T02:55Z
Check the source to verify that this is the current version before use.

AMERICAN SOCIETY FOR TESTING AND MATERIALS

ASTM D-1424 Tear Resistance of Woven Fabrics By Falling-Pendulum (Elmendorf) Apparatus

* (Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19102-1187).

(Non-Government standards and other publications are normally available from the organizations that prepare or distribute the documents. These documents also may be available in or through libraries or other informational services.)

* 2.3 Order of precedence. In the event of a conflict between the text of this document and the references cited herein, the text of this document takes precedence. Nothing in this document, however, supersedes applicable laws and regulations unless a specific exemption has been obtained.

3. REQUIREMENTS

* 3.1 Standard sample. The finished cloth shall match the standard sample for shade and shall be equal to or better than the standard sample with respect to all characteristics for which the standard sample is referenced (see 6.3). The standard sample is identified under piece no. 85064.

3.2 Formula approval. The prospective contractor or his finishing plant shall submit with his bid to the contracting officer for approval, a list of materials which will be used if contract is awarded. The list shall stipulate amounts, grades, and standards for all materials including solvents, and the manufacturer's name. This list is for the information of the Government and is not to be disseminated to the public. Approval of the quantitative formula submitted shall in no way absolve the contractor from complying with the performance requirements of this specification.

3.3 First article. When specified, the contractor shall furnish sample unit(s) for first article inspection and approval (see 4.3 and 6.2).

3.4 Material.

* 3.4.1 Yarn. Warp and filling shall be carded and/or combed single yarns (see 4.4.1 and 4.5).

3.5 Weave. The weave shall be plain (see 4.5).

3.6 Preparation. The cloth shall be singed and desized (see 4.4.1 and 4.5).

3.7 Color. The color shall be Navy shade Blue 3372 and shall match the standard sample. The warp shall be dyed and the filling natural.

3.7.1 Sulfur content. The use of dyes and compounds containing elementary sulfur capable of oxidation to sulfuric acid is prohibited. The dyestuff shall be chosen and applied so that the dyed and finished cloth shall contain no more labile sulfur than shown by the standard sample when tested as

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T02:55Z
Check the source to verify that this is the current version before use.

specified in 4.5. When a standard sample is not available, the dyed cloth shall show no more than a slight trace of labile sulfur as defined in the test method specified in 4.5.

* 3.7.2 Matching. The color and appearance of the dyed and finished cloth shall match the standard sample when viewed under filtered tungsten lamps which approximate artificial daylight having a correlated color temperature of 7500 (± 200) K, with illumination of 100 (± 20) foot candles, and shall be a good match to the standard sample under incandescent lamplight at 2300 (± 200) K.

* 3.7.3 Colorfastness. The finished cloth shall show fastness to laundering, light (after 40 standard fading hours), crocking and perspiration equal to or better than the standard sample when tested as specified in 4.5. As the limit of acceptability or when no standard sample is available, the finished cloth shall show a minimum of "fair" fastness to light (40 standard fading hours) and perspiration and "good" fastness to laundering and crocking when tested as specified in 4.5.

* 3.8 Physical requirements. The finished cloth shall conform to the physical requirements shown in Table I when tested as specified in 4.5.

Table I - Physical Requirements

Characteristics	Requirements	
	Desized	Finished
Weight - oz/yd^2 (g/m^2)		
Minimum	4.0(136)	
Maximum		6.0(204)
Yarns per inch (2.5cm) - minimum		
Warp		72
Filling		45
Breaking strength - lbs (Newtons) minimum		
Warp		80(356)
Filling		50(222)
Tearing strength - lbs (Newtons) minimum		
Warp		4.0(18)
Filling		3.0(13)
Stiffness - in. lbs (Newton meters) maximum		
Warp		0.002 (0.0002)
Filling		0.002 (0.0002)
Air permeability ft^3/min/ft^2 (cm3/sec/cm^2)		
Minimum		65(33.0)

* 3.8.1 Width. The width of the cloth shall be as specified (see 6.2) and shall be the minimum acceptable width inclusive of selvages when fly shuttle looms or shuttleless looms, with tuck-in selvage looms are used. For all other shuttleless looms the width measurement shall be made between the last warp yarn on each side excluding the protruding fringe.

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T02:55Z
Check the source to verify that this is the current version before use.

3.9 Seam efficiency. The cloth shall have a seam efficiency of not less than 85 percent when tested as specified in 4.5.

* 3.10 Dimensional stability. The finished cloth shall not shrink nor elongate more than 2.0% in either the warp or filling when tested as specified in 4.5. The pre-shrinking process used shall not be identified by name or by trademark, either on the cloth, ticket, or package.

* 3.11 Treatment. The cloth shall be given an approved flame resistant treatment (see 6.5 and 6.6). The finished cloth shall have an average after flame time of not more than 2.0 seconds, not more than 5.0 seconds average after-glow time and an average char length of not more than 5.0 inches (12.5cm), both initially and after 25 launderings when tested as specified in 4.5.

3.12 pH. The pH value of the water extract of the finished cloth shall be no less than 5.0 nor more than 8.5 when tested as specified in 4.5.

3.13 Non-fibrous material. The cloth, prior to treatment, shall show no more than 2.0 percent starch and protein content including chloroform-soluble and water-soluble material, when tested as specified in 4.5.

3.14 Toxicity approval. Only those flame retardant treatments already evaluated and approved by the appropriate medical service in regards to toxicity and so listed in the invitation for bids or request for proposal shall be considered acceptable for the related procurement (see 6.5).

3.15 Length and put-up. Unless otherwise specified (see 6.2), the cloth shall be furnished in continuous lengths, each not less than 40 yards (36m). Each length shall be put-up in a roll as specified in PPP-P-1134.

3.16 Face identification. The face side of the cloth shall be identified by stamping "FACE" on that side of the cloth at each end of the piece and roll.

3.17 Fiber identification. Each piece shall be labeled or ticketed for fiber content in accordance with the Rules and Regulations under the Textile Fiber Products Identification Act.

3.18 Workmanship. The finished cloth shall conform to the quality established by this specification. The demerit points per 100 square yards ($83.6m^2$), when calculated as specified in section 4, shall not exceed the established maximum point values.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements (examinations and tests) as specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any other facilities suitable for performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to ensure supplies and services conform to prescribed requirements.

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T02:55Z
Check the source to verify that this is the current version before use.

* 4.1.1 Responsibility for compliance All items must meet all requirements of sections 3 and 5. The inspection set forth in this specification shall become a part of the contractor's overall inspection system or quality program The absence of any inspection requirements in the specification shall not relieve the contractor of the responsibility of ensuring that all products or supplies submitted to the Government for acceptance comply with all requirements of the contract. Sampling inspection, as part of manufacturing operations, is acceptable practice to ascertain conformance to requirements, however, this does not authorize submission of known defective material, either indicated or actual, nor does it commit the government to acceptance of defective material.

4.1.2 Certificate of compliance Where certificates of compliance are submitted, the Government reserves the right to check test such items to determine the validity of the certification.

4.2 Classification of inspection. The inspection requirements specified herein are classified as follows:

1. First article inspection (see 4.3).
2. Quality conformance inspection (see 4.4).

4.3 First article inspection. When required (see 6.2), the first article of finished cloth submitted in accordance with 3.3 shall be visually inspected for appearance, color, and finish, and shall be tested in accordance with methods specified in 4.5.

4.4 Quality conformance inspection. Sampling for inspection shall be performed in accordance with MIL-STD-105, except where otherwise indicated.

4.4.1 Component and material inspection. In accordance with 4.1 above, components and materials shall be tested in accordance with all the requirements of referenced specifications, drawings, and standards unless otherwise excluded, amended, modified, or qualified in this specification or applicable procurement documents. A certificate of compliance may be submitted for the requirements of fiber identification of 3.4.1 and the singeing of 3.6.

4.4.2 Examination of the end item. Examination of the end item shall be in accordance with 4.4.2.1 through 4.4.2.4.

* 4.4.2.1 Yard-by-yard examination. Each roll in the sample shall be examined on face side only. When the total yardage in the roll does not exceed 100 yards (91.4m) the entire yardage in the roll shall be examined. When the total yardage in the roll exceeds 100 yards (91.4m), only 100 yards (91.4m) shall be examined. All defects are defined in Section 1 of FED-STD-4, which are clearly noticeable at normal inspection distance (3 feet) (0.91m) shall be scored and assigned demerit points as listed in 4.4.2.1.1, except that only the slubs and knots which exceed the limits shown on Sears Fabric Defect Scale (see 6.4), "3 or E as applicable" for slubs and "C" for knots shall be scored. No linear yard (increments of 1 yard (0.91m) on the measuring device of the inspection machine) from any one roll within the sample shall be penalized more than 4 points. The sample size shall be in accordance with the following:

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T02:55Z
Check the source to verify that this is the current version before use.

Lot Size (yards)	Sample Size(rolls) 1/
3200 or less	8
3201 thru 10,000	13
10,001 and over	20

1/ Only one roll shall be taken from any shipping container, unless the number of shipping containers in the lot are less than the number of rolls required for sampling, in which case, all shipping containers shall be sampled.

The lot shall be unacceptable if the points per 100 square yards ($83.6m^2$) of the total yardage examined exceeds 28 points. The lot shall be unacceptable if the individual points per 100 square yards ($83.6m^2$) of two or more individual rolls exceeds 38 points. If one roll exceeds the point level per 100 square yards ($83.6m^2$), a second sample, the same size as the final sample, shall be examined only for individual roll quality examination. The lot shall be unacceptable if one or more rolls in the second sample exceeds 40 points per 100 square yards ($83.6m^2$). Point computation for lot quality and individual roll quality shall be as follows:

$$\frac{\text{Total points scored in sample} \times 3600}{\text{Contracted width of cloth (inches)} \times \text{Total yards inspected}} = \text{Points per 100 square yards } (83.6m^2)$$

4.4.2.1.1 Demerit points. Demerit points shall be assigned as follows:

For defects up to and including 3 inches (7.6cm) in any dimension	= one point
For defects exceeding 3 inches (7.6cm) but not exceeding 6 inches (15.2cm) in any dimension	= two points
For defects exceeding 6 inches (15.2cm) but not exceeding 9 inches (22.8cm) in any dimension	= three points
For defects exceeding 9 inches (22.8cm) in any dimension	= four points

NOTE: The following defects, when present, shall be scored 4 points for each yard (0.9m) in which they occur:

Baggy, ridgy or wavy cloth
Width less than specified
Non-uniformity of shade (poor dye penetration, mottled, streaky or cloudy)
Excessive neppiness
Objectionable odor
Characteristics of finish, hand, and shade not equal to the standard sample

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T02:55Z
Check the source to verify that this is the current version before use.

4 4 2 2 Examination for length.

* 4.4 2.2.1 Individual rolls. During the yard-by-yard examination, each roll in the sample shall be examined for length Any length found to be less than the minimum specified or more than two yard (1 6m) less than the length marked on the ticket shall be considered a defect with respect to length. The lot shall be unacceptable if two or more rolls in the sample are defective in respect to length

4.4.2.2.2 Total yardage in sample. The lot shall be unacceptable if the total of the actual lengths of rolls in the sample is less than the total of the lengths marked on the tickets. The rolls examined shall be those selected for the examination of individual rolls.

4.4.2.3 Examination for shade variation. During the yard examination, each roll in the sample shall be examined for shade variations. Any roll in the sample exhibiting uneven shade, shade variation side to side, side to center, or end to end shall be cause for rejection of the entire lot represented by the sample.

4.4.2.4 Examination for face identification, non-identification of preshrinking process, and compliance with Textile Fiber Products Identification Act. During the yard-by-yard examination, each roll in the sample shall be examined for defects listed below. The lot shall be unacceptable if two or more of the following defects are present in the sample:

Face identification missing from either or both ends
Face identification on wrong side
Preshrinkage process identified by name or trademark on cloth or ticket
Not labeled or ticketed in accordance with the Rules and Regulations under the Textile Fiber Products Identification Act

* 4.4.2.5 Examination for shade sampling. Each lot shall be examined visually for shade match (see para 3.7.2) in accordance with the Table listed below and the provisions contained in the contract. The lot shall be unacceptable if one or more pieces fail to meet the requirement for shade match. The sample unit shall be a 4 inch by 20 inch swatch of the cloth. The sampled unit shall be drawn from each piece in the sample size.

Lot Size	Piece to be Sampled
1 - 8 pieces	Each piece
9 - 25 pieces	8 pieces
26 - 90 pieces	20 pieces
91 - 160 pieces	32 pieces
over 160 pieces	1 of 5 pieces

4.4.3 Examination of packaging requirements. An examination shall be made in accordance with the provisions of PPP-P-1134 to determine whether packaging, packing, and marking comply with section 5 requirements.

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T02:55Z
Check the source to verify that this is the current version before use.

* 4.5 Testing of the end item. The methods of testing specified in FED-STD-191, wherever applicable, and as listed in Table II shall be followed. The physical and chemical values specified in section 3 apply to the results of the determinations made on a sample unit for test purposes as specified in the applicable test method. The sample unit shall be 5 continuous yards (4.5m), full width of finished cloth, and 1/4 yard (2m) prepared cloth before treatment. The sample size shall be expressed in units of 1 yard (0.91m). The lot shall be unacceptable if one or more sample units fail to meet any test requirement specified. All test reports shall contain the individual values utilized in expressing the final results.

Lot Size (yards)	Sample Size
800 or less	2
801 up to and including 22,000	3
22,001 and over	5

Table II - Test Methods

Characteristic	Requirement Paragraph	Test Method
Fiber identification	3.4.1	1200 1/
Yarn ply	3.4.1	Visual 2/
Weave	3.5	Visual 2/
Singeing	3.6	1/
Presence of labile sulfur	3.7.1	2020
Colorfastness to:		
Light(40 SFH)	3.7.3	5660 3/
Laundering (after 3 cycles)	3.7.3	5610 4/ 5/
Perspiration	3.7.3	5680
Crocking	3.7.3	AATCC No. 8
Weight	3.8	5041
Yarns per inch		
Warp	3.8	5050
Filling	3.8	5050
Breaking strength		
Warp	3.8	5100
Filling	3.8	5100
Tearing strength		
Warp	3.8	ASTM D1424
Filling	3.8	ASTM D1424
Stiffness		
Warp	3.8	5202
Filling	3.8	5202
Air permeability	3.8	5450
Seam efficiency	3.9	5110 6/
Dimensional stability	3.10	5550
Flame resistance:		
Initial		
After flame time, sec.	3.11	5903
After glow time, sec.	3.11	5903

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T02:55Z
Check the source to verify that this is the current version before use.

Table II - Test Methods (Cont'd)

Characteristic	Requirement Paragraph	Test Method
Char length, inch	3.11	5903
Following 25 launderings		
After flametime, sec.	3.11	5556 and 5903
After glow time, sec.	3.11	5556 and 5903
Char length, inch	3.11	5556 and 5903
pH	3.12	2811
Nonfibrous material	3.13	2611

1/ Unless otherwise specified, a certificate of compliance shall be submitted and will be acceptable for the stated requirement.

2/ One determination for each sample unit and the result reported as "pass" or "fail".

3/ The calibration of the fadeometer and the definition of AATCC Fading Units shall be according to AATCC Test Method 16-1982. Using the formula below, 16 to 22 AFU's are acceptable as 20 SFH's.

$$\text{AATCC Fading Units} = \frac{(\Delta E^*)\ (20)}{1.7}$$

Where (ΔE^*) is the color difference in CIELAB* units of color difference.

4/ The specimens must be dried after each of the 3 laundering cycles.

5/ Only the stain of the cotton fiber shall be rated when evaluating the color transfer cloth.

6/ The thread shall conform to type IA1 of V-T-276. The needle size shall be 0.036 (± 0.001) inch, and the top (needle) thread shall be ticket No. 30, 3 ply, and the bottom (looper) thread shall be ticket No. 50, 3 ply.

5. PACKAGING

5.1 Preservation. Preservation shall be level A or C as specified (see 6.2).

5.1.1 Level A or C. The cloth, put up as specified (see 3.15), shall be packaged in accordance with the applicable requirements of PPP-P-1134.

5.2 Packing. Packing shall be level A, B, or C as specified (see 6.2).

5.2.1 Levels A, B, and C. The cloth shall be packed in accordance with the applicable requirements of PPP-P-1134.

5.3 Marking. In addition to any special marking required by the contract or order, shipping containers shall be marked in accordance with the applicable requirements of PPP-P-1134.

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T02:55Z
Check the source to verify that this is the current version before use.

* 5.4 MIL-STD-2073. When specified (see 6.2), preservation and packing shall be in accordance with MIL-STD 2073-1 and MIL-STD-2073-2.

6. NOTES

* (This section contains information of a general or explanatory nature that may be helpful, but is not mandatory.)

* 6.1 Intended use. The cloth covered by this specification is intended for use in the fabrication of flame resistant Navy shipboard utility clothing.

* 6.2 Acquistion requirements. Acquistion requirements should specify the following:

a. Title, number, and date of this specification.
b. Issue of DODISS to be cited in the solicitation, and if required, the specific issue of individual documents referenced (see 2.1 and 2.2).
c. Width required (see 3.8.1).
d. Minimum and maximum lengths for cloth (see 3.15).
e. When first article sample is required (see 3.3). The item will be tested and should be a first article sample. The contracting officer should include specific instructions in acquisition documents regarding arrangements for examinations, quantity, and testing and approval of the first article.
f. Levels of packaging and packing required (see 5.1 and 5.2).
g. When all packaging data is to be found in MIL-STD-2073-1 and MIL-STD-2073-2 (see 5.4).

6.3 Standard sample. For access to standard sample, address the procuring activity issuing the invitation for bids (see 3.1).

* 6.4 Sears Fabric Defect Scales are available from Sears Roebuck and Company, Department 817 (Attn: BSC 23-29), Sears Tower, Chicago, IL 60684 (see 4.4.2.1).

6.5 Only those treatments listed in the invitation for bids or request for proposal shall be considered acceptable for related procurement. Information on currently approved material may be obtained from Defense Personnel Support Center, Philadelphia, PA 19101 (see 3.11 and 3.14).

6.6 A cotton flame retardant treatment (FRT) with a precondensate of a tetrakishydroxymethyl phosphonium salt cured in a gaseous ammonia atmosphere (precondensate/ammonia cure) has been found to meet the specification requirements (see 3.11).

* 6.7 Changes from previous issue. The margins of this specification are marked with an asterisk to indicate where changes (additions, modifications, corrections, deletions) from the previous issue were made. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content irrespective of the marginal notations and relationship to the last previous issue.

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T02:55Z
Check the source to verify that this is the current version before use.

* 6.8 Subject term (key word) listing:

a. Fabric, utility
b. Fabric, fire resistant
c. Shipboard, fabric
d. Utility, shipboard

Custodians:
Navy - NU
Army - GL
Air Force - 99

Review activity:
DLA - CT

Preparing activity:
Navy - NU

Project 8305-0332

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T02:55Z
Check the source to verify that this is the current version before use.

INSTRUCTIONS: In a continuing effort to make our standardization documents better, the DoD provides this form for use in submitting comments and suggestions for improvements. All users of military standardization documents are invited to provide suggestions. This form may be detached, folded along the lines indicated, taped along the loose edge *(DO NOT STAPLE)*, and mailed. In block 5, be as specific as possible about particular problem areas such as wording which required interpretation, was too rigid, restrictive, loose, ambiguous, or was incompatible, and give proposed wording changes which would alleviate the problems. Enter in block 6 any remarks not related to a specific paragraph of the document. If block 7 is filled out, an acknowledgement will be mailed to you within 30 days to let you know that your comments were received and are being considered.

NOTE This form may not be used to request copies of documents, nor to request waivers, deviations, or clarification of specification requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document*(s)* or to amend contractual requirements.

(Fold along this line)

(Fold along this line)

DEPARTMENT OF THE NAVY

NO POSTAGE NECESSARY IF MAILED IN THE UNITED STATES

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300

BUSINESS REPLY MAIL
FIRST CLASS PERMIT NO 12503 WASHINGTON D C

POSTAGE WILL BE PAID BY THE DEPARTMENT OF THE NAVY

Navy Clothing and Textile Research Facility
Post Office Box 59
Natick, MA 01760-0001

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T02:55Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

(See Instructions – Reverse Side)

1. DOCUMENT NUMBER	2. DOCUMENT TITLE
MIL-C-24916A	CLOTH, CHAMBRAY, COTTON (FLAME RETARDANT TREATED)

3a. NAME OF SUBMITTING ORGANIZATION	4. TYPE OF ORGANIZATION *(Mark one)*
	☐ VENDOR
b. ADDRESS *(Street, City, State, ZIP Code)*	☐ USER
	☐ MANUFACTURER
	☐ OTHER *(Specify)* _____

5. PROBLEM AREAS

a. Paragraph Number and Wording

b. Recommended Wording

c. Reason/Rationale for Recommendation

6. REMARKS

7a. NAME OF SUBMITTER *(Last, First, MI)* – Optional	b. WORK TELEPHONE NUMBER *(Include Area Code)* – Optional
c. MAILING ADDRESS *(Street, City, State, ZIP Code)* – Optional	8. DATE OF SUBMISSION *(YYMMDD)*

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T02:55Z
Check the source to verify that this is the current version before use.