MIL-P-45117E
18 January 1972
SUPERSEDING
MIL-P-45117D
28 October 1966

MILITARY SPECIFICATION

PROJECTILE, 20MM, TARGET PRACTICE, M55A2

This specification is mandatory for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 This specification covers one model of 20mm target practice projectiles produced from bar stock.

2. APPLICABLE DOCUMENTS

2.1 The following documents of the issue in effect on date of invitation for bids, or request for proposal, form a part of this specification to the extent specified herein:

SPECIFICATIONS

FEDERAL

TT-C-490 - Cleaning Methods and Pretreatment of Ferrous Surfaces for Organic Coatings

STANDARDS

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes
MIL-STD-109 - Quality Assurance Terms and Definitions
MIL-STD-651 - Visual Inspection Standards for 20mm Ammunition and Components
MIL-STD-1168 - Lot Numbering of Ammunition
MIL-STD-1169 - Packaging, Packing and Marking for Shipment of Inert Ammunition Components
MIL-STD-1235 - Single and Multilevel Continuous Sampling Procedures and Tables for Inspection by Attributes

FSC 1305

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T02:24Z
Check the source to verify that this is the current version before use.

2.1 (Cont)

DRAWINGS

U.S. ARMY MUNITIONS COMMAND

D7258812	- Projectile, 20mm, Target Practice, M55A2
F7258861	- Carton, for Interplant Shipment of Projectile, 20mm, Assemblies and Metal Parts Assemblies (200)
D7259136	- Shipping Container for Inert Projectile; 20mm, Assemblies and Metal Parts Assemblies (10,000)
D7259191	- Cartridge, 20mm, for M55A2, TP, and M55A2B1, TP, Projectile Metal Parts Test
IEL 7259334	- Index of Inspection Equipment Lists for: Projectile, 20mm, Target Practice, M55A2

PUBLICATIONS

U.S. ARMY MATERIEL COMMAND

AMCR 715-505	- Ammunition Ballistic Acceptance Test Methods, Volume 8, Test Procedures for 20mm Cartridges

(Copies of specifications, standards, drawings, and publications required by contractors in connection with specific procurement functions shall be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publications.- The following documents form a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitation for bids or request for proposal shall apply.

American Society for Testing and Materials (ASTM)
ASTM B117-64 -- Method of Test for Salt Spray (Fog) Testing

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia; Pa. 19103)

(Technical Society and Technical Association specifications and standards are generally available for reference from libraries. They are also distributed among technical groups and using federal agencies.)

3. REQUIREMENTS

3.1 General.- The projectile shall comply with the requirements of Drawing (Dwg.) D7258812 and with all requirements of the drawings and specifications shown thereon.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T02:24Z
Check the source to verify that this is the current version before use.

3.2 Manufacturing process. -All parts and assemblies shall be manufactured by a process approved by the contracting officer and no deviation from that process shall be made without his prior approval. (see 6.3)

3.3 Banding. -The rotating band blank and the rotating band seat shall be clean the time of banding. Shot or sandblasting shall not be used to clean the serrated band seat-after knurling. The rotating band blank shall fill the band seat.

3.4 Soundness. -Metal discontinuity in the projectile body, as determined by eddy current inspection, shall be less than that represented by Production Check Standard (PCS) No. 1.

3.5 Protective coating.

3.5.1 Phosphate coating. -The pretreatment process used shall comply with applicable requirements of Dwg. D7258812. The phosphate coating shall comply with the requirements of TT-C-490 for appearance and minimum weight, as applicable to the type of phosphate coating.

3.5.2 Paint coating. -The paint coating shall comply with applicable requirements of Dwg. D7258812. Paint adhesion shall comply with applicable requirements of TT-C-490.

3.5.3 Corrosion resistance. -The painted projectile body shall show no evidence of corrosion (red rust) after exposure to a 5 percent solution of atomized salt spray for 24 hours.

3.6 Metal parts security. -The projectile, assembled into test cartridges loaded in accordance with the requirements of Dwg. D7259191, shall not separate or breakup in the test for metal parts security.

3.7 Workmanship. -The requirements for workmanship are as specified by applicable drawings, referenced specifications and the following:

3.7.1 Processing defects. -The pxojectile shall be free of dents, deep scratches, cuts, sharp edges, burrs, metal flaws, excessive surface roughness, and other forms of substandard workmanship.

3.7.2 Cleanliness.- The projectile shall be free of all foreign matter.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. -Unless otberwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or order, the supplier may utilize his own or other facilities suitable for the performance of the inspection

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T02:24Z
Check the source to verify that this is the current version before use.

4.1 (Cont)

requirements specified herein unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.1.1 Quality assurance terms and definitions.-Reference shall be made to MIL-STD-109 for definition of quality assurance terms.

4.2 First article sample.

4.2.1 Initial production sample.-At the beginning of regular production a sample applicable to the approved process shall be submitted in accordance with contract requirements and shall consist of:

a. Inspection and nonfiring tests:

100 Rotating band blanks
100 Noses
100 Bodies, projectile
100 Projectiles (unpainted)
100 Projectiles (painted)
3 Standard panels

b. Firing test:

4,000 Projectiles (painted)

The sample shall be manufactured using the same materials, equipment, processes and procedures as will be used in regular production. Identification shall be in accordance with MIL-STD-1168.

4.2.1.1 Examination and test.-After inspection and provisional acceptance at source, the sample will be inspected for all requirements of the drawings and specifications at a Government laboratory or such other facility specified by the contract.

4.2.1.2 Initial production sample failure.-Failure of the sample to comply with requirements of the drawings and specifications will result in sample disapproval.

4.3 Inspection provisions.

4.3.1 Submission of product.-The product shall be submitted in accordance with MIL-STD-105 or MIL-STD-1235, as applicable.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T02:24Z
Check the source to verify that this is the current version before use.

4.3.1.1 Lot. -A lot shall consist of projectiles produced by one manufacturer in one unchanged process, in accordance with the same drawings and drawing revisions, and same specification and specification revision.

4.3.1.2 Lot identification.-Each projectile and each packed projectile lot shall be identified in accordance with applicable drawings and MlL-STD-1168, supplemented as directed by the procuring activity.

4.3.2 Examination.- One hundred percent examination shall be performed by the contractor for all critical defects. Examination for major and minor defects shall be performed as specified herein. Each part and each assembly found to be defective shall be rejected.

4.3.2.1 Sampling and acceptance criteria.-Except as otherwise indicated, sampling plans and procedures shall be in accordance with MIL-STD-105 or MIL-STD-1235. Defect characteristics may be grouped into a class and considered collectively, or defect characteristics may be considered individually to determine acceptability. When acceptability is determined on a class basis, in addition to the Acceptable Quality Level (AQL) assigned to the major class, an AQL shall be assigned to individual characteristics within the major class, limiting the number of defectives containing a particular major defect to less than the number of defective permitted for the class. However, where sampling procedures of MIL-STD-1235 are used, acceptability shall not be determined on a class basis for major defects. In addition, where three or less defects appear in a classification, sampling plans applicable to a class shall not be used for major defects. (see 6.4)

4.3.2.2 AQL's.-The following AQL's are assigned to major and minor defects:

a. Individual:

Major	**0.25%**
Minor	**0.40%**

b. Class basis:

Major	**1.50%**
Minor	**2.50%**

c. Individual defects associated with the class basis:

Major	**0.40%**

4.3.3 Classification of defects. **-1/** The classification of defects shall be as specified herein. (see 6.5)

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T02:24Z
Check the source to verify that this is the current version before use.

4.3.3.1 Rotating band blank (see Dwg. B7258816 covering a detail of Dwg. D7258812).

Categories and Defects	Method of Inspection
Critical: None defined.	
Major:	
101. Foreign matter	Visual (see 3.3)
102. Defective metal, including lamination	Visual
103. Incomplete or deformed	Visual 2/
Minor:	
201. Width, max.	Gage

4.3.3.2 Nose (see Dwg. C7258814, covering a detail of Dwg. D7258812).

Categories and Defects	Method of Inspection
Critical: None defined.	
Major:	
101. Diameter, ogive at shoulder, min.	Gage
102. Length, spherical surface to shoulder, max.	Gage
Minor:	
201. Diameter, ogive at shoulder, max.	Gage
202. Length, spherical surface to shoulder, min.	Gage
203. Diameter, cylindrical surface	Gage
204. Over-all length, min.	Gage
205. Profile, ogive, except length, spherical surface to shoulder	Gage
206. Finish	Visual/Feel
207. Foreign matter	Visual
208. Mutilated	Visual

Body (see Dwg. D7258815 covering a detail of D7259059 and D7258812).

Categories and Defects	Method of Inspection
Critical: None defined.	
Major:	
101. Knurling missing or incomplete	Visual
102. Base thickness, min.	Gage
103. Depth to datum diameter, max.	Gage
104. Diameter, bourrelet, min.	Gage

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T02:24Z
Check the source to verify that this is the current version before use.

4.3.3.3 (Cont)

Categories and Defects	Method of Inspection
Major: (Cont)	
105. Over-all length, max.	Gage
106. Length, mouth to rear edge of rotating band seat	Gage
107. Depth, knurling, min.	Visual/Gage 3/
108. Foreign matter in rotating band seat	Visual (see 3.3)
Minor:	
201. Indent(s) missing in mouth	Visual
202. Diameter, rotating band seat (knurled)	Gage
203. Width, rotating band seat	Gage
204. Large inside diameter	Gage
205. Small inside diameter	Gage
206. Width knurling, min.	Visual/Gage 3/
207. Base thickness, max.	Gage

4.3.3.4 Projectile, unpainted (see Dwg. D7259059 covering a detail of D7258812).

Categories and Defects	Method of Inspection
Critical:	
1. Ferrous metal discontinuity	Soundness 1
2. Crack or split in nose	Visual
Major:	
101. Runout, nose with datum surface	Gage
102. Diameter, bourrelet, min.	Gage
103. Gap between nose and body	Gage
104. Body not flush or below at junction with nose	Visual
105. Over-all length	Gage
106. Length, nose to rear edge of rotating band	Gage
107. Diameter, body, rear of rotating band, min.	Gage
108. Diameter, rotating band	Gage
109. Runout, rotating band with datum surface	Gage
110. Runout, body, rear of rotating band with datum surface	Gage
111. Location, crimp groove	Gage
112. Profile, crimp groove	Gage
113. Radius, rear edge of crimp groove, max.	Gage
114. Void at junction of rotating band and projectile body	Visual

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T02:24Z
Check the source to verify that this is the current version before use.

4.3.3.4 (Cont)

Categories and Defects	Method of Inspection
Minor:	
201. Finish improper	Visual 4/
202. Base radius missing	Visual
203. Diameter of bourrelet, max.	Gage
204. Depth and width of undercut, front and rear of rotating band, max.	Gage
205. Mutilated	Visual
206. Loose nose	Manual 5/
207. Width of rotating band	Gage

4.3.3.5

Categories and Defects	Method of Inspection
Critical: None defined.	
Major:	
101. Diameter, bourrelet, max.	Gage
102. Diameter, body, rear of rotating band, max.	Gage
103. Weight	Balance
Minor:	
201. Paint not dry	Tactile
202. Marking incorrect, incomplete, illegible, or missing	Visual
203. Paint inadequate	Visual
204. Paint on rotating band	Visual
205. Foreign matter	Visual
206. Rotating band damaged	Visual

1/ MIL-STD-651 shall apply in defining and evaluating visual defects.

2/ A rotating band blank which is deformed or judged to lack sufficient metal in any part of its width or thickness to provide for complete band seat fill and minimum rotating band profile dimensions shall be classed defective.

3/ Measurement of knurling for compliance with the minimum depth and width requirements shall apply where visual inspection indicates that the depth or width dimension is borderline.

4/ Measurement of surface roughness shall apply where visual inspection indicates that the specified finish is exceeded.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T02:24Z
Check the source to verify that this is the current version before use.

5/ If the nose moves with respect to the projectile body under thumb and finger pressure applied in the lateral or axial direction, the projectile. shall be classified defective.

4.3.4 Tests.-The tests listed in Table I shall be conducted on each lot in accordance with the applicable methods and procedures prescribed in 4.4. For acceptance, the results of each test shall comply with the applicable requirement(s).

4.3.4.1 Test samples.-The sample sizes for the various tests shall be as specified in Table I.

Table I

Test	Sample Size		Item	Req. Para.
Band tightness	1/	315	Projectiles, unpainted	3.3
Automatic inspection effectiveness	2/		PCS No. 1 (see 4.4.3)	--
Soundness verification	3/	315	Projectiles, unpainted	3.4
Phosphate coating (appearance & weight)	4/	3	Standard panels (see TT-C-490)	3.5.1
Paint adhesion	5/	13	Projectiles, painted	3.5.2
Corrosion resistance	6/	32	Projectiles, painted	3.5.3
Metal parts security	7/	250	Projectiles, painted	3.6

1/ If two or more units of the sample have an average radial void, between the seated band and the band seat, greater than 0.004 inch, the lot shall be rejected. If one unit of the sample has an average radial void, greater than 0.004 inch, a second sample consisting of the same number of units as specified for the first sample shall be tested. If in the accumulated samples, two or more units have an average radial void greater than 0.004 inch, the lot shall be rejected.

2/ Failure of the flaw detector to reject PCS No. 1 shall be cause for rejection of all assemblies inspected for "soundness" since the preceding test and shall require requalification of the equipment for automatic inspection. (see 4.4.3)

3/ Rejection of one or more units of the sample by the flaw detector in the test for body metal soundness shall be cause for rejection of the lot.

Source: https://assist.dla.mil -- Downloaded: 202610-22T02:24Z
Check the source to verify that this is the current version before use.

4.3.4.1 (Cont)

4/ Failure of the phosphate coating on the standard panels to comply with the applicable requirements shall be cause for rejection of all projectiles phosphate since the preceding test.

5/ If two or more units of the sample fail to comply with the requirement for paint adhesion, the lot shall be rejected. If one unit of the sample fails to comply with the requirement, a second sample consisting of the same number of units as specified for the first sample shall be tested. If in the accumulated samples two or more units fail to comply with the requirement for paint adhesion, the lot shall be rejected.

6/ If two or more units of the sample fail to comply with the corrosion resistance requirement, the lot shall be rejected. If one unit fails to comply with the requirement, a second sample consisting of the same number of units as specified for the first sample shall be tested. If in the accumulated samples, two or more units fail to comply with the corrosion resistance requirement, the lot shall be rejected.

7/ The occurrence of one or more of the following casualties, as witnessed by hole(s) in the fragmentation screen(s), or recovery of the part(s) or fragment(s) shall be cause for rejection of the lot, except as otherwise provided:

a. Body breakup.

b. Loss of nose.

c. Complete rotating band separation. This is defined as detachment of all of the band having band seat knurling imprint.

d. Partial rotating band separation. This is defined as detachment of part of the band having band seat knurling imprint.

e. The following acceptance criteria shall apply to thrown band fragments having no evidence of band seat knurling imprint:

(1) The lot will reaccepted if two or less assemblies throw band fragments having length not greater than 0.500 inch.

(2) The lot will be rejected if three or more assemblies throw band fragments having length not greater than 0.500 inch.

(3) The lot will be rejected if any assembly throws a band fragment having length greater than 0.500 inch (indicative of deep-seated band lamination).

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T02:24Z
Check the source to verify that this is the current version before use.

4.3.4.1 (Cont)

(4) The lot will not be penalized for band particles thrown as a result of normal band fringing or slivering.

4.3.5 Packaging, packing and marking inspection. -Inspection for packaging, packing and marking shall comply with applicable requirements of MIL-STD-1169.

4.3.6 Inspection equipment. -Index of Inspection Equipment List IEL 7259334 identifies the applicable inspection equipment lists indicating the equipment required to perform examination and tests prescribed herein, Equipment design shall be in accordance with code designation on the applicable IEL (reference is made to Inspection Equipment List for definition of coding format).

4.4 Test methods and procedures.

4.4.1 Band tightness. -The method of test shall comply with all requirements of the operating instructions for the band tightness tester (Dwg. B7259545, a detail-of IEL-7259334). The inspection sample shall be cycled through the tester to determine compliance with the rotating band tightness requirement. The total measurement of radial void, registered on the tester indicator at final ram pressure, shall be divided by four (number of indenters) to determine the average radial void.

4.4.2 Soundness. -The method of inspection shall comply with all requirements of Operating Instructions Manual, Eddy Current Flaw Detector, Dwg. D11075203 (a detail of IEL 7259334) for Detecting Metal Discontinuity in Projectile Bodies for 20mm Ammunition, except for those inspection requirements which are reserved for Government application, as specified herein.

4.4.2.1 Application of defect standards. -Master defect standards, referenced in the Operating Instruction Manual, shall apply to resolve inspection discrepancies occurring between the results of defect standards supplied for contractor “soundness” inspection and those supplied for Government “soundness” verification. (see 6.6)

4.4.3 Automatic eddy current inspection effectiveness. -Equipent checkout shall be performed as stated in the Operation Instruction Manual at the start of each shift and after any adjustment or shutdown. Upon completion of checkout, cycle the PCS #1, front slot and rear slot standards through the inspection system during automatic operation. All three standards must be rejected to assure correct adjustment for reject level and scan limits. During remainder of shift the PCS #1 shall be cycled through the equipment at intervals of 20 ± 5 minutes during automatic operation.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T02:24Z
Check the source to verify that this is the current version before use.

4.4.3.1 Equipment verification. -The government inspector will maintain, independent of the contractor, a set of standards and may cycle these standards through the equipment at any time. Failure of equipment to reject standards will be evidence that the equipment is not properly adjusted and the contractor will be so notified.

4.4.4 Soundness verification. -After equipment checkout and verification as specified in 4.4.3 and 4.4.3.1 the entire lot sample will be inspected with the equipment operating automatically. Any rejected unit of the sample will be automatically cycled through the equipment with the CAL. button pressed (to lower the sensitivity one step below that used for production inspection). Any unit which is rejected at the lower sensitivity shall be classed as a defective.

4.4.5 Phosphate coating. -The method of test shall be as Prescribed by TT-C-490 for the type of coating used (see Dwg. D7258812). The prescribed panels shall be processed, with the projectiles to be represented, at the start of daily production and at 4-hour intervals, maximum, thereafter. Appearance and weight of the coating shall be recorded.

4.4.6 Paint adhesion. -The method of test shall be as prescribed by TT-C-490. The test shall be made on the painted bourrelet of each unit of the sample forward of the rotating band. Visible exposure of underlying phosphate coating or ferrous metal of any unit of the sample as a result of the test, shall be recorded as a defect.

4.4.7 Corrosion resistance. -The method of test shall be as prescribed in American Society for Testing and Materials (ASTM), ASTM B117. The paint shall not be disturbed, however, the rotating band and unpainted surfaces of the sample projectiles may be masked out by a wax coating or other suitable material. The salt spray solution and exposure time shall be as specified in 3.5.3.

4.4.8 Metal parts security. -The method of test will be as prescribed by AMCR 715-505, Volume 8, as applicable. The test sample will be assembled to comply with requirements of Dwg. D7259191, Cartridge, 20mm, for M55A2 TP, and M55A2B1, TP, projectile metal parts test. The test cartridges, at ambient temperature, will be fired in an M39 gun in bursts Of 50 shots. The gun barrel will be at ambient temperature for the firing of each burst. The cyclic rate of fire will be recorded for informational purposes.

5. PREPARATION FOR DELIVERY

5.1 Packing, Level C. -Each lot of projectiles shall be packed as specified by Dwg. F7258861 or Dwg. D7259136.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T02:24Z
Check the source to verify that this is the current version before use.

5.2 Marking and labeling.-Marking or labeling of packed cartons shall comply with applicable requirements of MIL-STD-1169.

6. NOTES

6.1 Ordering data.-Invitations for bids and contracts or orders will specify the following:

6.1.1 Title, number, and date of this specification.

6.1.2 Place of inspection, if not place of manufacture.

6.1.3 Packing and marking instructions. (see 5.1 and 5.2)

6.1.4 Provision for shipment and testing of production lot samples for metal parts security. (see 4.4.8)

6.1.5 Provision for the Supply, maintenance and disposition of mandatory ballistic test equipment for acceptance inspection purposes.

6.2 First article sample.-Where an initial production sample is required by the contract, the contracting officer will notify the test facility when ***to*** proceed with the metal parts security test. (see 4.2) Additional projectiles may be required by the test facility.

6.3 Process deviation.-A process deviation is defined as a change in the approved basic method of manufacture, or an operational change which alters the metallurgical or physical properties of the item of contract.

6.4 AQL's.-The optional use of AQL values for either individual defects or classes of defects, with individual major defect limitation, is intended to minimize inspection agency administrative burden which might result from an exclusive assignment of individual defect AQL's. The option also permits flexibility where sampling inspection for acceptance is integrated into the manufacturing process.

6.5 Intermediate point inspection.-The classification of defects identifies the defect characteristics (among other things) for acceptance inspection. It may be necessary to modify the sequence of inspection stations to best suit the manufacturing process. Inspection for defect characteristics which will be hidden or altered by subsequent processing operations (including unrelated operations), should be scheduled to prevent premature acceptance which could be detrimental to the attainment of optimum product quality in the end item.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T02:24Z
Check the source to verify that this is the current version before use.

6.6 Defect standards. -The initial supply of defect standards and instructions for contractor and Government application to the eddy current method of inspection, will be furnished with the inspection equipment. Replacement standards shall be requisitioned through normal channels by the Government agency Having contract administration responsibility.

NOTE: Asterisks are not used in this revision to identify changes with respect to the previous issue due to the extensiveness of the changes.

Custodian:

Army - Mu
Air Force - 70

Preparing Activity:

Army - MU

Review Activity:

Army - MU
Air Force - 70

Project No. 1305-0413

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T02:24Z
Check the source to verify that this is the current version before use.

SPECIFICATION ANALYSIS SHEET

Form Approved
Budget Bureau No. 22-R255

INSTRUCTIONS: This sheet is to be filled out by personnel, either Government or contractor, involved in the use of the specification in procurement of products for ultimate use by the Department of Defense. This sheet is provided for obtaining information on the use of this specification which will insure that suitable products can be procured with a minimum amount of delay and at the least cost. Comments and the return of this form will be appreciated. Fold on lines on reverse side, staple in corner, and send to preparing activity. Comments and suggestions submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or serve to amend contractual requirements.

SPECIFICATION

ORGANIZATION

CITY AND STATE

CONTRACT NUMBER

MATERIAL PROCURED UNDER A

☐ DIRECT GOVERNMENT CONTRACT ☐ SUBCONTRACT

1. HAS ANY PART OF THE SPECIFICATION CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE?

A. GIVE PARAGRAPH NUMBER AND WORDING.

B. RECOMMENDATIONS FOR CORRECTING THE DEFICIENCIES

2. COMMENTS ON ANY SPECIFICATION REQUIREMENT CONSIDERED TOO RIGID

3. IS THE SPECIFICATION RESTRICTIVE?

☐ YES ☐ NO *(If "yes", in what way?)*

4. REMARKS *(Attach any pertinent data which may be of use in improving this specification. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity)*

SUBMITTED BY *(Printed or typed name and activity - Optional)*

DATE

DD FORM 1 JAN 66 1426

REPLACES EDITION OF 1 OCT 64 WHICH MAY BE USED.

Source: https://assist.dla.mil -- Downloaded: 202610-22T02:24Z
Check the source to verify that this is the current version before use.

FOLD

POSTAGE AND FEES PAID
Department of the Army

OFFICIAL BUSINESS

Commanding Officer
Frankford Arsenal
ATTN: SMUFA-J4000
Philadelphia, Pa. 19137

FOLD

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T02:24Z
Check the source to verify that this is the current version before use.