MILITARY SPECIFICATION

VARNISH, PHENOLIC, BAKING

This amendment forms a part of Military Specification MIL-V-12276D(MR) dated 4 January 1971.

PAGE 12

Paragraph 4.4.7, corrosion resistance, line 7: Delete fourth sentence and substitute "Expose the panels for 250 hours to 20 percent salt spray in accordance with method 6061 of Fed. Test Method Std. No. 141."

Custodian:
Army - MR

Review activities:
Army - MR, MU, MD

Preparing activity:
Army - MR

Project No. 8010-A087

FSC 8010

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T22:38Z
Check the source to verify that this is the current version before use.