MIL-C-36699A
15 March 1979
SUPERSEDING
MIL-C-36699
8 July 1970

MILITARY SPECIFICATION

CATHETER AND CONNECTOR, SUCTION, ENDOTRACHEAL

This specification is approved for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This specification covers suction endotracheal catheter and connector assemblies which are for use with endotracheal tubes and airways to remove obstructive material.

1.2 Classification. The suction endotracheal catheter and connector assemblies shall be of the following sizes as specified (see 6.2 and 6.3).

6 French
8 French
10 French
14 French
18 French

2. APPLICABLE DOCUMENTS

2.1 Issues of documents. The following documents of the issue in effect on date of invitation for bid or request for proposal form a part of this specification to the extent specified herein.

SPECIFICATIONS

FEDERAL

MMM-A-250	- Adhesive, Water Resistant, (for Sealing Fiberboard Boxes).
PPP-B-585	- Boxes, Wood, Wirebound.
PPP-B-601	- Boxes, Wood, Cleated-Plywood.

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: Defense Personnel Support Center, Directorate of Medical Material, DPSC-ATT, 2800 South 20th Street, Philadelphia, PA 19101, by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

FSC 6515

Source: https://assist.dla.mil -- Downloaded: 202610-21T09:09Z
Check the source to verify that this is the currentversion before use.

PPP-B-621 - Boxes, Wood, Nailed and Lock-Corner.
PPP-B-636 - Boxes, Shipping, Fiberboard.
PPP-T-76 - Tape, Pressure-Sensitive Adhesive Paper, (for Carton Sealing).

MILITARY

MIL-S-36586 - Sterilization Test Strip Set, Bacterial Spore.
MIL-A-36080 - Anesthesia Set, Endotracheal.

STANDARDS

MILITARY

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes.
MIL-STD-129 - Marking for Shipment and Storage.

DRAWINGS

DEFENSE PERSONNEL SUPPORT CENTER (DPSC)

24229 - Catheter and Connector, Suction, Endotracheal, Plastic, Disposable.

(Copies of specifications, standards, drawings, and publications required by contractors in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitation for bid or request for proposal shall apply.

U.S. PHARMACOPEIAL CONVENTION, INC.

The United States Pharmacopeia, (USP).

(Application for copies should be addressed to the Mack Publishing Company, Easton, PA 18042.)

AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM)

ASTM D412 - Tension Testing of Vulcanized Rubber.

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.)

Source: https://assist.dla.mil -- Downloaded: 202610-21T09:09Z
Check the source to verify that this is the currentversion before use.

U.S. DEPARTMENT OF HEALTH, EDUCATION, AND WELFARE,
FOOD AND DRUG ADMINISTRATION (FDA)

Federal Food, Drug, and Cosmetic Act and Regulations Promulgated Thereunder.

(Application for copies should be addressed to the Food and Drug Administration, Washington, DC 20204.)

3. REQUIREMENTS

3.1 Material.

3.1.1 Suction catheter. The suction catheter shall be made of transparent, medical grade, pliant vinyl plastic complying with the requirements for USP class IV plastic when tested as specified in 4.4.1.

3.1.2 Finger valve connector. The finger valve connector shall be fabricated from a rigid, suitable plastic.

3.2 Design and construction. The suction catheter shall be permanently affixed to the finger valve connector in a secure and leak-proof manner. The finger valve connector and suction catheter shall be in strict accordance with Defense Personnel Support Center Drawing No. 24229. The suction catheter and connector shall be suitable for use with the Anesthesia Set, Endotracheal specified in MIL-S-36080.

3.3 Freedom from pyrogens. The suction catheter and finger valve connector shall be pyrogen-free when tested as specified in 4.4.2.

3.4 Safety (nontoxic). The suction catheter and finger valve connector shall be nontoxic when tested as specified in 4.4.3.

3.5 Extractable metals. The combined quantity of barium, cadmium and lead in the suction catheter material shall not exceed 5 parts per million (ppm) when tested as specified in 4.4.4.

3.6 Security of assembly. The finger valve connector shall not separate or loosen from the catheter tube when tested as specified in 4.4.5.

3.7 Tensile strength. The catheter tube shall have a minimum tensile strength of 1800 pounds per square inch (psi) when tested as specified in 4.4.6.

Source: https://assist.dla.mil -- Downloaded: 202610-21T09:09Z
Check the source to verify that this is the current version before use.

3.8 Ultimate elongation. The catheter tube shall have a minimum elongation of 160 percent when tested as specified in 4.4.7.

3.9 Friction. When tested as specified in 4.4.8, the maximum force required to pull a 12 inch long piece of catheter through the test fixture shall be as stated below:

Catheter size	Force (maximum)
6 French	70 grams
8 French	70 grams
10 French	120 grams
14 French	120 grams
18 French	180 grams

3.10 Strength of valve connector. When tested as specified in 4.4.9, the valve connector shall withstand, without breakage or apparent damage to the valve body, one application of a 3 pound (1361 grams) load.

3.11 Sterility. The catheter and connector shall be sterile when tested with a biological indicator as specified in 4.4.10.

3.11.1 Sterility lot. A sterility lot is that single quantity of product subjected to the same manufacturing operation and simultaneously sterilized in the same sterilizer chamber. Each unit package shall be clearly marked with a sterility lot (control) number and date of sterilization as specified in 5.3.1. Each sterility lot shall be traceable to the pertinent manufacturing lot(s).

3.12 Certificates.

3.12.1 Certificate of sterility. A certificate of sterility, stating that samples from each sterilizer lot have been tested and found to be sterile, shall be submitted to the procuring activity. The certificate of sterility shall include.

a. Item identification.
b. National stock number (NSN).
c. Contract or purchase order number.
d. Sterility lot or control number.
e. Date of sterilization.
f. Quantity of product in sterilizer lot.
g. Type of sterilization (gas, radiation, heat, steam, etc.).
h. Form of biological indicator (i.e., inoculated paper spore strip or carrier, inoculated product, or inoculated simulated product).

Source: https://assist.dla.mil -- Downloaded: 202610-21T09:09Z
Check the source to verify that this is the currenversion before use.

i. Test organism(s) and population density used.
j. Test medium, incubation temperature, incubation time, and dates of tests.
k. Number of test units.
l. Statement that samples comply with sterility tests.
m. Signature of head of a laboratory or a designated qualified alternate.

When inspection is made at destination, the certificate of sterility shall be submitted by the contractor to the Directorate of Medical Materiel, ATTN: DPSC-ATQ, Defense Personnel Support Center, 2800 South 20th Street, Philadelphia, PA 19101, and a copy forwarded with each shipment to the consignee. When inspection is made at source, certificate of sterility shall be furnished to the cognizant Government Quality Assurance Representative for submission to the procuring activity.

3.12.2 Certificates of freedom from pyrogens, safety, and animal implantation tests. Certificate(s), listing all lot or control numbers, shall state that representative sample(s) from each lot or control have been tested and found to be free from pyrogens and have passed the animal implantation test. Certificate(s) shall include the specific tests performed and the test results. The record of the animal implantation test and its results shall be certified by the pathologist who performed or supervised performance of the animal implantation test. For destination inspection, certificates shall be submitted by the contractor to the Directorate of Medical Materiel, ATTN: DPSC-ATQ, Defense Personnel Support Center, 2800 South 20th Street, Philadelphia, PA 19101, and a copy of each shall be forwarded with each shipment to the consignee. When inspection is made at source certificates shall be furnished to the cognizant Government Quality Assurance Representative for submission to the procuring activity.

3.13 Compatibility. The materials from which the suction catheter and finger valve connector are fabricated, shall not react with, or be reacted upon, by the liquids with which they will be in contact during normal use and operation; nor shall there be any materials incorporated in the suction catheter and connector which will cause any deleterious effect when used for the purpose intended.

3.14 Manufacturer's records. The manufacturer shall place a code or lot number on the paper label, and on the printed carton, which can be verified against the manufacturer's records of all tests made on nontoxic, animal implantation-tested, sterile, pyrogen-free sets. These records shall be made available for inspection by any duly authorized Government representative. No shipment shall be made until all tests have been completed, verified, and recorded in the permanent records of the manufacturer.

Source: https://assist.dla.mil -- Downloaded: 202610-21T09:09Z
Check the source to verify that this is the currentversion before use.

3.15 Identification marking. The proximal end of each catheter, or the valve body shall be permanently and legibly marked with the French size and the manufacturer's name or trademark.

3.16 Workmanship. Workmanship shall be first class throughout. The suction catheter and connector assembly shall be free from defects which detract from their appearance or impair their serviceability.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification to assure supplies and services conform to prescribed requirements.

4.1.1 Records. Records of examinations and tests performed by or for the contractor shall be maintained by the contractor and made available to the Government, upon the Government's request, at any time, or from time to time, during the performance of the contract and for a period of three years after delivery of the supplies to which such records relate.

4.1.2 Inspection. Inspection, as used in this specification, is defined as both examination (such as visual and auditory investigation without the use of special laboratory appliances or procedures) and testing (determination by technical means of physical and chemical properties) of the item.

4.1.3 Certificates of quality. Certificates of quality, supplied by the manufacturer of the materials may be furnished in lieu of actual performance of such testing by the contractor, provided lot identity has been maintained and can be demonstrated to the Government and provided also that the test methods and the results obtained comply with those described in this specification. The certificate shall include the name of the contractor, the contract number, the name of the manufacturer or supplier, the NSN, the Item Identification, the name of the component/material, the lot number, the lot size, the sample size, the date of testing, the test method, individual test results, and the specification requirements.

4.2 Sampling.

4.2.1 For examination. Sampling for examination shall be conducted in accordance with MIL-STD-105 and as indicated in table I. The unit of product for examination purposes shall be one catheter and connector.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T09:09Z
Check the source to verify that this is the current version before use.

TABLE I. Sampling for examination.

Type of defect	Inspection level	AQL (percent defective)
Major	S-2	1.0
Minor	S-1	1.5
Dimensional	S-1	1.5

4.2.2 For tests.

4.2.2.1 Sterility test. Sampling for sterility test shall be in accordance with the USP for parenteral devices and as specified in 4.4.10.

4.2.2.2 Physical tests. Sampling for physical tests shall be conducted in accordance with MIL-STD-105 and as indicated in table II. Where feasible, the same sample unit shall be used for the determination of two or more test characteristics. The unit of product for test purposes shall be one catheter and connector.

TABLE II. Sampling for tests

Component	Characteristic	Requirement	Test procedure	Inspection level	AQL (percent defective)
Raw material (catheter)	Type IV plastic	3.1.1	4.4.1	S-2	2.5
Catheter/ connector	Freedom from pyrogens	3.3	4.4.2	S-2	2.5
	Safety	3.4	4.4.3	S-2	2.5
Catheter tubing	Extractable metals	3.5	4.4.4	S-2	2.5
Catheter/ connector	Security of assembly	3.6	4.4.5	S-2	2.5
Catheter tube	Tensile strength	3.7	4.4.6	S-2	2.5
	Ultimate elongation	3.8	4.4.7	S-2	2.5
	Friction	3.9	4.4.8	S-2	2.5
Connector	Strength	3.10	4.4.9	S-2	2.5
Catheter/ connector	Sterility	3.11	4.4.10	USP	USP

Source: https://assist.dla.mil -- Downloaded: 202610-21T09:09Z
Check the source to verify that this is the current version before use.

4.3 Examination.

4.3.1 Catheter and connector. The catheter and connector shall be examined to determine compliance with all requirements contained in this specification. Examination shall be conducted in accordance with tables I and III. Examination, however, shall not be restricted to defects listed in table III.

TABLE III. Classification of defects

Categories	Defects
Major:	
101	Outside surface of catheter tube not smooth or not free from burrs or surface imperfections.
102	Catheter eyes not free from burrs, slivers, or loose particles.
103	Catheter tube not straight.
104	Catheter tube not free from kinks.
105	Immediate container does not open readily, thereby compromising sterility.
Minor:	
201	Identification marking not clearly imprinted.

4.3.2 Packaging inspection. The inspection of the packaging, packing and marking for shipment and storage shall be in accordance with the quality assurance provisions of the applicable container specification and the marking requirements of MIL-STD-129.

4.4 Tests. Tests shall be conducted to determine compliance with specification requirements.

4.4.1 Type IV plastic. The material for the catheter tube shall be tested for type IV plastic in accordance with the USP, except for the implantation test where the following changes shall be made: The test period shall be not less than 72 hours and shall not exceed 144 hours, and the examination shall be performed both grossly and microscopically, on the muscle tissue surrounding the implants, by a pathologist certified by the American Board of Pathology, or the American College of Veterinary Pathologists.

4.4.2 Freedom from pyrogens. The catheter and connector assembly shall be tested for freedom from pyrogens in accordance with the USP for transfusion and infusion assemblies.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T09:09Z
Check the source to verify that this is the current version before use.

4.4.3 Safety. The catheter and connector assembly shall be tested for safety (toxicity) in accordance with the USP for transfusion and infusion assemblies.

4.4.4 Extractable metals. A 2-gram composite sample shall be obtained from the tube only of each catheter to be tested. The material shall be cut into small slivers, so that no thickness exceeds 3 mm, and eluted for 72 hours at 50°C., 24 hours at 70°C., or 60 minutes at 121°C. in two menstrua: 0.9% sodium chloride and cottonseed oil. Each gram of the material shall be covered with 5 milliliters (ml) of the menstruum. The menstrua are collected, agitated after elution, and then submitted to spectrographic analysis for lead, barium, and cadmium. The metals are reported in parts per million (ppm) in the eluate. Thus 1.0 ppm in eluate is equivalent to extrating 1.0 mg from 200g test material dispersed in 1,000 ml of elution menstruum.

4.4.5 Security of assembly. A five pound load shall be gradually applied to the catheter while the connector is held in a clamping device with the catheter hanging vertically downward. The five pound load shall be maintained for 12 ± 2 minutes.

4.4.6 Tensile strength. The catheter tube shall be tested for tensile strength in accordance with ASTM D412.

4.4.7 Ultimate elongation. The percent elongation of the catheter tube shall be tested in accordance with ASTM D412.

4.4.8 Friction. A 12-inch length of Tygon tubing, Formulation S50HL, with a 3/8-inch I.D. and a 1/16-inch wall shall be bent into a semi-circle with the ends up and so that there is an 8-3/4-inch distance between the ends. It shall be mounted on a wooden panel. A 12-inch length of the catheter tube to be tested shall be prepared by cutting off the proximal portion. Nylon cord shall be attached through the eye of the catheter tube and shall be used as a lead and pull cord. The catheter tube shall be pulled through the U-shaped tube until the eye of the catheter tube appears at the exit end. The free end of the nylon cord shall be attached to a clamp which is in turn attached to a dynamometer of about 5 kilograms capacity and sensitive to 10 grams or less. The dynamometer shall be mounted above the floor so that the panel with the U tube can be moved downward and the 12-inch length of catheter tube shall be pulled through the U tube. The highest reading on the dynamometer shall be recorded. Each sample shall be tested in this manner three times. The downward movement of the panel shall be at as uniform a speed as possible.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T09:09Z
Check the source to verify that this is the current version before use.

4.4.9 Strength of valve body at tubing junction. The valve body shall be cut at a point 3/8 inch (9.5 mm) from the proximal end of dimension "C" of DPSC Drawing No. 24229. The valve body shall be held firmly and the cut end applied to the platform of a scale until the force attained is 3 pounds (1361 grams). The fingers of the hand shall not touch the platform and the long axis of the valve body shall be held as parallel as possible to the scale platform during the test.

4.4.10 Sterility test. The catheter and connector shall be tested for sterility in accordance with the method specified in the USP for parenteral devices using inoculated product, or paper spore strip (carrier). Product containing a biological indicator shall be marked or labeled so that it clearly differentiates from product intended for distribution. The incubation medium and minimum time in each case shall be soybean casein digest for 7 days for inoculated product, or paper spore strip (carrier). The incubation temperature shall be as indicated in 4.4.10.1. The minimum number of test units, regardless of lot size, shall be 10, except for inoculated carrier which shall be 20 for type I sterilization and 30 for type II sterilization including inoculated carrier and product test units. The inspection level shall be as indicated in table II.

4.4.10.1 Inoculated product. For each type of sterilization, the organism used shall be as listed below:

Type of Sterilization	Organism	Incubation Temperature
Steam	B. stearothermophilus	55° - 65°C
Dry Heat	B. stearothermophilus, or	55° - 65°C
	B. subtilis var. niger (or globigii)	30° - 35°C
Gas	B. subtilis var. niger (or globigii)	30° - 35°C
Radiation	B. pumilus	30° - 35°C

The number of viable cells shall be sufficient to provide assurance that the product has been sterilized.

4.4.10.2 Inoculated carrier. Inoculated carriers (paper spore strips) if used, shall be in accordance with MIL-S-36586. Other paper carriers shall be inoculated to be of equivalent resistance. The method of incubation and number of test units shall be as indicated in 4.4.10 and 4.4.10.1. The method of sterilization will control the organism in the spore strip to be tested for as shown in 4.4.10.1. NOTE: When an inoculated carrier is chosen, product samples must also be tested as required by the USP.

4.4.10.3 Alternate method. Suppliers conducting sterility tests or designating lots in a manner other than that indicated herein shall submit proof that the alternate method provides equal assurance concerning the sterility of the product. However, all sterility tests of any alternate method of testing for sterility shall be made to the Contracting Officer, and approval obtained before employment of the alternate method on a government contract.

Source: https://assist.dla.mil -- Downloaded: 202640-21T09:09Z
Check the source to verify that this is the currenversion before use.

4.4.10.4 Product testing. Testing for sterility of the product after receipt by the government shall be without a biological indicator and in accordance with the USP.

5. PACKAGING

5.1 Packaging. Packaging shall be level A or C, as specified (see 6.2).

5.1.1 Unit of issue. One package containing fifty catheters and connectors as specified constitutes one unit of issue.

5.1.2 Level A.

5.1.2.1 Individual package. Each catheter and connector assembly shall be packaged straight (not coiled) in a sealed, water-resistant peel open type container. The container shall be capable of maintaining sterility of contents unless damaged or opened. The container shall not be capable of being resealed.

5.1.2.2 Unit package. Fifty individually packaged catheter and connector assemblies of one size only shall be packaged in a box conforming to PPP-B-636, class domestic. Closure shall be as specified in the appendix of the box specification.

5.1.3 Level C. Each catheter and connector shall be individually packaged as specified in 5.1.2.1. Fifty individually packaged catheters and connectors shall be further packaged in a manner that will afford adequate protection against deterioration and physical damage during shipment from the supply source to the first receiving activity.

5.2 Packing. Packing shall be level A, B or C, as specified (see 6.2).

5.2.1 Level A. Four unit packages, containing catheter and connector assemblies of one size only, shall be packed in a shipping container designed for a type 2 load and conforming to PPP-B-636 class weather-resistant. Closure, strapping and waterproofing shall be as specified in the appendix of the box specification.

5.2.2 Level B. Four unit packages, containing catheter and connector assemblies of one size only, shall be packed in a shipping container designed for a type 2 load and conforming to PPP-B-636, box specification.

5.2.3 Level C. The packaged catheter and connector assemblies shall be packed in shipping containers in a manner that will afford adequate protection against damage during direct shipment from the supply source to the first receiving activity. These packs shall conform to the carrier's rules and regulations.

Source: https://assist.dla.mil -- Downloaded: 202640-21T09:09Z
Check the source to verify that this is the current version before use.

5.3 Marking.

5.3.1 Individual package. In addition to any commercial markings, each individual package shall be marked in accordance with the requirements of the Federal Food, Drug and Cosmetic Act. The sterility lot (control) number, item size, and the legend "STERILITY GUARANTEED UNLESS PACKAGE IS DAMAGED OR OPENED", or similar statement, shall be shown.

5.3.2 Unit package. Each unit package shall be marked in accordance with the requirements of the Federal Food, Drug and Cosmetic Act and MIL-STD-129. The sterility lot or control number, contract or purchase order number and name of contractor shall be shown. The method of sterilization (G-Gas, R-Radiation, S-Steam, C-Cold or D-Dry Heat) shall be shown following the level of packaging and date of packaging. Example: "A4/78-G". Final sterilization shall be on or after indicated packaging date.

5.3.3 Shipping container. Shipping containers shall be marked as specified in MIL-STD-129. The sterility lot or control number and method of sterilization as specified in 5.3.2 shall also be shown.

6. NOTES

6.1 Intended use. The item covered by this specification is intended for use with Anesthesia Set, Endotracheal, NSN 6515-00-299-8687, in controlling suction for aspiration during anesthesia.

6.2 Ordering data. Purchasers should select the preferred options permitted herein and include the following information in procurement documents.

a. Title, number and date of this specification.
b. Selection of applicable levels of packaging and packing (see 5.1 and 5.2).
c. Size required (see 1.2).

6.3 This specification covers the following item(s) appearing in the Federal Supply Catalog:

National Stock Number	Item Identification
6515-00-458-8411	CATHETER AND CONNECTOR, SUCTION, ENDOTRACHEAL, Plastic, Disposable, 14 FR, 50s
6515-00-458-8413	CATHETER AND CONNECTOR, SUCTION, ENDOTRACHEAL, Plastic, Disposable, 10 FR, 50s

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T09:09Z
Check the source to verify that this is the current version before use.

6515-00-458-8414	CATHETER AND CONNECTOR, SUCTION, ENDOTRACHEAL, Plastic, Disposable, 8 FR, 50s
6515-00-458-8415	CATHETER AND CONNECTOR, SUCTION, ENDOTRACHEAL, Plastic, Disposable, 6 FR, 50s
6515-00-458-8416	CATHETER AND CONNECTOR, SUCTION, ENDOTRACHEAL, Plastic, Disposable, 18 FR, 50s

Custodians:
Army - MD
Navy - MS
Air Force - 03

Review activity:
DoD - MB

Preparing activity:
DLA-DM

Project No. 6515-2128

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T09:09Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

INSTRUCTIONS: This form is provided to solicit beneficial comments which may improve this document and enhance its use. DoD contractors, government activities, manufacturers, vendors, or other prospective users of the document are invited to submit comments to the government. Fold on lines on reverse side, staple in corner, and send to preparing activity. Attach any pertinent data which may be of use in improving this document. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity. A response will be provided to the submitter, when name and address is provided, within 30 days indicating that the 1426 was received and when any appropriate action on it will be completed.

NOTE: This form shall not be used to submit requests for waivers, deviations or clarification of specification requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

DOCUMENT IDENTIFIER *(Number)* AND TITLE
MIL-C-36699A CATHETER AND CONNECTOR, SUCTION, ENDOTRACHEAL

NAME OF ORGANIZATION AND ADDRESS OF SUBMITTER

☐ VENDOR ☐ USER ☐ MANUFACTURER

1. ☐ HAS ANY PART OF THE DOCUMENT CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE? ☐ IS ANY PART OF IT TOO RIGID, RESTRICTIVE, LOOSE OR AMBIGUOUS? PLEASE EXPLAIN BELOW.

A. GIVE PARAGRAPH NUMBER AND WORDING

B. RECOMMENDED WORDING CHANGE

C. REASON FOR RECOMMENDED CHANGE(S)

2. REMARKS

SUBMITTED BY *(Printed or typed name and address — Optional)*	TELEPHONE NO.
	DATE

DD FORM 1426 EDITION OF 1 JAN 72 WILL BE USED UNTIL EXHAUSTED.

Source: https://assist.dla.mil -- Downloaded: 2026l0-21T09:09Z
Check the source to verify that this is the currentversion before use.

FOLD

DEFENSE PERSONNEL SUPPORT CENTER
2800 SOUTH 20TH STREET
PHILADELPHIA, PA 19101

POSTAGE AND FEES PAID

U.S.MAIL

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300

DEFENSE PERSONNEL SUPPORT CENTER
DIRECTORATE OF MEDICAL MATERIEL, CODE ATT
2800 SOUTH 20TH STREET
PHILADELPHIA, PA 19101

FOLD

Source: https://assist.dla.mil -- Downloaded: 202640-21T09:09Z
Check the source to verify that this is the current version before use.