MILITARY SPECIFICATION

PAPER, GLASSINE, WEIGHING

This limited coordination Military Specification has been prepared by the Defense Personnel Support Center based upon currently available technical information, but it has not been approved for promulgation as a coordinated document. It is subject to modification. However, pending its promulgation as a coordinated Military Specification, it may be used in procurement.

1. SCOPE

1.1 This specification covers glassine paper suitable for weighing and transferring powders, crystals and other preparations in pharmaceutical and laboratory procedures.

2. APPLICABLE DOCUMENTS

2.1 The following documents, of the issue in effect on date of invitations for bid or requests for proposal, form a part of this specification to the extent specified herein:

SPECIFICATIONS

Federal

MMM-A-250	Adhesive, Water-Resistant (For Sealing Waterproof Paper).
PPP-B-566	Boxes, Folding, Paperboard.
PPP-B-585	Boxes, Wood, Wirebound.
PPP-B-601	Boxes, Wood, Cleated-Plywood.
PPP-B-621	Boxes, Wood, Nailed and Lock-Corner.
PPP-B-636	Box, Fiberboard.
PPP-B-676	Box, Setup.
PPP-T-76	Tape, Pressure-Sensitive Adhesive Paper (for Carton Sealing).

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T09:11Z
Check the source to verify that this is the current version before use.

STANDARDS

Military

MIL-STD-105	Sampling Procedures and Tables for Inspection by Attributes.
MIL-STD-129	Marking for Shipment and Storage.

(Copies of specifications and standards required by suppliers in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitations for bid or requests for proposal shall apply.

TECHNICAL ASSOCIATION OF PULP AND PAPER INDUSTRY

(TAPPI) PUBLICATIONS

T403 ts-63	Bursting Strength of Paper.
T410 os-61	Basis Weight of Paper and Paperboard.
T411 m-44	Thickness and Density of Paper.
T414 ts-65	Internal Tearing Resistance of Paper.
T428 su-67	Hot Water Extractable Acidity or Alkalinity of Paper.
T435 m-52	Hydrogen Ion Concentration (pH) of Paper Extracts.
T454 ts-66	Turpentine Test for Grease Resistance Paper.

(Application for copies should be addressed to the Technical Association of the Pulp and Paper Industry, 155 East 44th Street, New York, New York 10017.)

3. REQUIREMENTS

3.1 Material. Glassine paper shall be fabricated from a semi-chemical wood pulp and shall conform to the requirements specified herein.

3.2 Physical properties.

3.2.1 Basis weight. The glassine paper shall have a basis weight (24 by 36-480) of 25 $\pm$ 5 pounds, when tested as specified in 4.4.1.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T09:11Z
Check the source to verify that this is the current version before use.

3.2.2 Bursting strength. The glassine paper shall have a bursting strength of not less than 15 pounds per square inch (p.s.i.) when tested as specified in 4.4.2.

3.2.3 Tear resistance. The glassine paper shall have an internal tear resistance of not less than 12 grams, when tested as specified in 4.4.3.

3.2.4 Grease resistance. The glassine paper shall have a turpentine transduation time of not less than 600 seconds, when tested as specified in 4.4.4.

3.3 Chemical properties.

3.3.1 Acidity (pH). The glassine paper shall have a pH value of 7.0 ± 1.0, when tested as specified in 4.4.5.

3.3.2 Water soluble acidity. The acidity of glassine paper shall be not greater than 0.02 percent calculated as sulfite (SO_3 =) ion, when tested as specified in 4.4.6.

3.4 Form. Glassine paper shall be furnished in sheet form. Each sheet shall be 4-1/2 inches (in.) long by 3-1/2 in. wide. The tolerance on the dimensions shall be ±1/8 in.

3.5 Thickness. The glassine paper shall have a thickness of 0.00125 ± 0.00020 in., when tested as specified in 4.4.7.

3.6 Count. The number of sheets of glassine paper per unit package may vary by ± 2 percent. The average count shall be 1000 sheets, when tested as specified in 4.4.8.

3.7 Color. The glassine paper shall have a smooth glazed surface on both sides and a uniform light green tint for background contrast. The paper shall be sufficiently clear and transparent to allow easy reading of 10-point bold type, when tested as specified in 4.4.8.

3.8 Workmanship. Workmanship shall be first class throughout. Glassine paper shall be free from tears, cuts, punctures, holes, creases or corrugations. The paper surface shall be clean and free from foreign or undigested matter, shives, lumps or slime spots. Glassine paper shall be free from defects which detract from its appearance or may impair its serviceability.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T09:11Z
Check the source to verify that this is the current version before use.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or purchase order, the supplier may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.1.1 Records. Records of examinations and tests performed by or for the contractor shall be maintained by the contractor and made available to the Government, upon the Government's request, at any time, or from time to time, during the performance of the contract and for a period of three years after delivery of the supplies to which such records relate.

4.1.2 Inspection. Inspection, as used in this specification, is defined as both examination (such as visual, or auditory, investigation without the use of special laboratory appliances or procedures) and testing (determination by technical means of physical and chemical properties) of the item.

4.1.3 Certificate of quality. Certificate of quality, supplied by the manufacturer of the glassine paper, may be furnished in lieu of actual performance of such testing by the contractor, provided lot identity has been maintained and can be demonstrated to the Government. The Certificate shall include the name of the contractor, the contract number, the name of the manufacturer or supplier, the FSN, the Item Identification, the name of the component/material, the lot number, the lot size, the sample size, the date of testing, the test method, individual test results, and the specification requirements.

4.2 Sampling.

4.2.1 For examination. Sampling for examination shall be conducted in accordance with MIL-STD-105. The inspection levels and acceptable quality levels shall be as indicated in table I. Unit of product for examination purposes shall be the unit package.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T09:11Z
Check the source to verify that this is the current version before use.

Table I. Sampling for Examination

	Inspection level	AQL (percent defective)
For visual examination		
Major defects	II	2.5
Minor defects	II	4.0
For dimensional examination	S-2	2.5

4.2.2 For tests. Sampling for tests shall be conducted in accordance with MIL-STD-105, as indicated in table II. Unit of product for test purposes shall be the unit package. The acceptance number shall be zero.

4.2.2.1 Raw material. Sufficient sample of each lot of glassine paper shall be used to perform the tests indicated in table II.

Table II. - Test Requirements

Characteristic	Requirement	Test procedure
Basis Weight	3.2.1	4.4.1
Bursting strength	3.2.2	4.4.2
Tear resistance	3.2.3	4.4.3
Grease resistance	3.2.4	4.4.4
Acidity (pH)	3.3.1	4.4.5
Water soluble acidity	3.3.2	4.4.6
Thickness	3.5	4.4.7
Count	3.6	4.4.8
Transparency	3.7	4.4.9

4.2.2.2 End item count. Sampling for count shall be conducted in accordance with MIL-STD-105. Inspection level shall be S-3 and the acceptance number shall be zero.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T09:11Z
Check the source to verify that this is the current version before use.

4.3 Examination. The glassine paper shall be examined to determine compliance with all requirements contained in this specification. Examination shall be conducted in accordance with table I. The glassine paper shall be examined for defects including, but not limited to, those listed in table III.

Table III - Classification of defects

Categories	Defects
Major	
101	Paper not free from foreign or undigested matter, shives, lumps or slime spots.
102	Paper not free from wrinkles, sharp creases or folds.
103	Paper not free from tears, cuts, holes or ragged edges.
104	Paper not uniform in color within the lot.
Minor	
201	Paper not free from dirt, grease or other foreign materials.

4.4 Tests. Tests shall be conducted to determine compliance with specification requirements.

4.4.1 Basis weight. The basis weight shall be determined in accordance with TAPPI Test Method T410 os-61.

4.4.2 Bursting strength. The bursting strength shall be determined in accordance with TAPPI Test Method T403 ts-63.

4.4.3 Tear resistance. The tear resistance shall be determined in accordance with TAPPI Test Method T414 ts-65.

4.4.4 Grease resistance. The grease resistance shall be determined in accordance with TAPPI Test Method T454 ts-66.

4.4.5 Acidity (pH). The pH value shall be determined in accordance with TAPPI Test Method T435 m-52.

4.4.6 Water soluble acidity. The water soluble acidity shall be determined in accordance with TAPPI Test Method T428 su-67.

4.4.7 Thickness. The thickness shall be determined in accordance with TAPPI Test Method T411 m-44.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T09:11Z
Check the source to verify that this is the current version before use.

4.4.8 Count. The number of sheets of glassine paper shall be determined by actual count or based on weight.

4.4.9 Transparency. The transparency shall be determined as follows: Type the following sentence on a suitable grade of typing paper using 10 point bold type: "Glassine paper shall be sufficiently clear and transparent to allow easy reading of 10 point type." Place the glassine paper directly over the typed sheet. There shall be no difficulty in reading the typed sentence.

5. PREPARATION FOR DELIVERY

5.1 Packaging. Packaging shall be level A or C as specified (see 6.2).

5.1.1 Unit of issue. One box containing 1000 sheets of paper, as specified, constitutes one unit of issue.

5.1.2 Packaging quantities. The number of units of issue indicated in table IV shall be packaged in each unit, intermediate, and exterior container, as applicable, for the required level of protection specified in the procurement document.

Table IV. Packaging Quantities

Unit package	Intermediate package	Exterior container
1 unit	8 units	48 units

5.1.2.1 Packing variation permitted. If the required number of units in the entire shipment is less than the number of units specified to be overpacked in an exterior container, such units may be packed in an exterior container of suitable size and design, acceptable to a common carrier, which shall insure safe delivery to destination.

5.1.3 Level A.

5.1.3.1 Unit package. Unit package shall be a box of appropriate size constructed in accordance with PPP-B-566 or PPP-B-676 except that commercial colors are acceptable. Closure shall be adequate to prevent spilling of contents under normal handling.

5.1.3.2 Intermediate package. Intermediate package shall be a box of appropriate size and design constructed in accordance with PPP-B-636, type CF, class weather-resistant. Boxes shall be closed by taping the top and bottom flaps with 2 inch wide tape conforming to PPP-T-76. Closing of bottom flap with adhesive conforming to MMM-A-250 or metal stitches is permitted.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T09:11Z
Check the source to verify that this is the current version before use.

5.1.4 Level C. Units shall be packaged in standard commercial containers of the size and kind commonly used, which will afford the degree of protection required for shipment and use of the product for its intended purpose.

5.2 Packing. Packing shall be level A, B or C as specified (see 6.2).

5.2.1 Level A.

5.2.1.1 Exterior container. Exterior container shall be designed for a type 2 load and constructed in accordance with PPP-B-585, class 3, style 3; PPP-B-601, overseas type; PPP-B-621, class 2; or PPP-B-636, class weather-resistant, grade V3c. Closure and strapping shall be as specified in the appendix of the applicable box specification.

5.2.2 Level B.

5.2.2.1 Exterior container. Exterior container shall be designed for a type 2 load and constructed in accordance with PPP-B-585, class 1, style 3; PPP-B-601, domestic type; PPP-B-621, class 1; or PPP-B-636, class domestic. Closure shall be as specified in the appendix of the applicable box specification.

5.2.3 Level C. The subject commodity shall be packed in substantial commercial containers of the type, size, and kind commonly used for the purpose, so constructed as to insure acceptance and safe delivery by common or other carriers, at the lowest rate, to point of delivery called for in the contract or purchase order.

5.3 Marking.

5.3.1 Interior packages. Each unit package and each intermediate package shall be marked in accordance with MIL-STD-129. When labels are utilized, waterproofing shall be required only when applicable carton is fabricated of water-resistant material. Contract or purchase order number and name of contractor shall be shown.

5.3.2 Exterior container. Exterior container shall be marked in accordance with MIL-STD-129.

6. NOTES

6.1 Intended use. Glassine paper covered by this specification is intended for use in weighing and transferring powders, crystals and other preparations in laboratory procedures.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T09:11Z
Check the source to verify that this is the current version before use.

6.2 Ordering data. Procurement document should specify the following:

(a) Number and date of this specification.
(b) Federal stock number (FSN).
(c) Selection of applicable levels of packing (see 5.1 and 5.2).

6.3 This specification does not cover all types, classes, grades, or sizes of the commodity indicated by the title of this specification, or those which are commercially available, but is intended to cover the types which are normally procured to meet requirements.

6.4 This specification covers the following item shown in the Federal Supply Catalog:

FSN	Item Identification
8135-407-3453	PAPER, GLASSINE, Weighing, 3-1/2 by 4-1/2 inches, 1000s

Custodians:
Army - MD
Navy - MS
Air Force - 03

Review activities:
Army - MD
Navy - MS
Air Force - 03

Preparing activity:
Defense Supply Agency - DM

Project No. 8135-0359

Review information is current as of the date of this document. For future coordination of changes to this document, draft circulation should be based on the information in the current DODISS.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T09:11Z
Check the source to verify that this is the current version before use.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T09:11Z
Check the source to verify that this is the current version before use.

SPECIFICATION ANALYSIS SHEET

Form Approved
Budget Bureau No. 22-R255

INSTRUCTIONS: This sheet is to be filled out by personnel, either Government or contractor, involved in the use of the specification in procurement of products for ultimate use by the Department of Defense. This sheet is provided for obtaining information on the use of this specification which will insure that suitable products can be procured with a minimum amount of delay and at the least cost. Comments and the return of this form will be appreciated. Fold on lines on reverse side, staple in corner, and send to preparing activity. Comments and suggestions submitted on this form do not constitute or imply authorization to waive any portion of the referenced document (s) or serve to amend contractual requirements .

SPECIFICATION

MIL-P-36709 (DSA-DM) FSN:

ORGANIZATION

CITY AND STATE

CONTRACT NUMBER

MATERIAL PROCURED UNDER A

☐ DIRECT GOVERNMENT CONTRACT ☐ SUBCONTRACT

1. HAS ANY PART OF THE SPECIFICATION CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE?

A. GIVE PARAGRAPH NUMBER AND WORDING.

B. RECOMMENDATIONS FOR CORRECTING THE DEFICIENCIES

2. COMMENTS ON ANY SPECIFICATION REQUIREMENT CONSIDERED TOO RIGID

3. IS THE SPECIFICATION RESTRICTIVE?

☐ YES ☐ NO *(If "yes", in what way?)*

4. REMARKS *(Attach any pertinent data which may be of use in improving this specification. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity)*

SUBMITTED BY *(Printed or typed name and activity - Optional)*

DATE

DD FORM 1 JAN 66 1426 REPLACES EDITION OF 1 OCT 64, WHICH MAY BE USED.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T09:11Z
Check the source to verify that this is the current version before use.

CAUTION

NOTICE TO BIDDERS/OFFERORS

DO NOT CONDITION OR BASE YOUR BID/OFFER ON ANY CURRENT PROCUREMENT ON THE INFORMATION SUBMITTED ON THIS FORM SINCE ANY CHANGES OR DELETIONS IN THE SPECIFICATIONS MAY RENDER YOUR BID/OFFER NON-RESPONSIVE IN WHICH CASE IT CANNOT BE CONSIDERED FOR AWARD.

Fold

DEFENSE PERSONNEL SUPPORT CENTER
2800 SOUTH 20TH STREET
PHILADELPHIA, PA. 19101

DEFENSE SUPPLY AGENCY
OFFICIAL BUSINESS

POSTAGE AND FEES PAID
DEFENSE SUPPLY AGENCY

HEADQUARTERS, DEFENSE PERSONNEL SUPPORT CENTER
ATTN: DIRECTORATE OF MEDICAL MATERIEL, CODE ATT
2800 SOUTH 20TH STREET
PHILADELPHIA, PA. 19101

Fold

DPSC FORM 2418
MAR 68

EDITION AUG 66, WILL BE USED UNTIL EXHAUSTED

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T09:11Z
Check the source to verify that this is the current version before use.