INCH-POUND

The documentation and process conversion measures necessary to comply with this revision shall be completed by 9 April 2023.

MIL-PRF-19500/477N
w/AMENDMENT 1
9 December 2022
SUPERSEDING
MIL-PRF-19500/477N
28 June 2022

PERFORMANCE SPECIFICATION SHEET

SEMICONDUCTOR DEVICE, DIODE, SILICON, POWER RECTIFIER, ULTRAFAST RECOVERY, ENCAPSULATED (THROUGH-HOLE AND SURFACE MOUNT PACKAGES), AND UN-ENCAPSULATED, TYPES 1N5802, 1N5804, 1N5806, 1N5807, 1N5809, AND 1N5811, QUALITY LEVELS JAN, JANTX, JANTXV, JANS, JANHC, AND JANKC

This specification is approved for use by all Departments and Agencies of the Department of Defense.

The requirements for acquiring the product described herein shall consist of this specification sheet and MIL-PRF-19500.

1. SCOPE

1.1 Scope. This specification covers the performance requirements for silicon, ultrafast recovery, power rectifier diodes. Four levels of product assurance (JAN, JANTX, JANTXV, and JANS) are provided for each encapsulated device types as specified in MIL-PRF-19500. Two levels of product assurance (JANHC and JANKC) are provided for each unencapsulated device type.

1.2 Package outlines and die topography. The device package for the encapsulated device type are as follows: Axial leaded in accordance with figure 1, square end-cap (US) surface mount version in accordance with figure 2, round and square end-cap (URS) surface mount version in accordance with figure 3, and planar ceramic (UMC) surface mount version in accordance with figure 4. The characteristics, dimensions and topography for JANHC and JANKC un-encapsulated die are as follows: E version die in accordance with figure 5, F version die in accordance with figure 6, G version die in accordance with figure 7 and H version die in accordance with figure 8.

1.3 Maximum ratings. Unless otherwise specified, T_A = +25°C.

1.3.1 Ratings applicable to all types. T_{STG} = $T_{J(max)}$ = -65°C to +175°C.

1.3.2 Ratings applicable to individual types.

Col. 1	Col. 2	Col. 3	Col. 4	Col. 5	Col. 6	Col. 7	Col. 8	Col. 9	Col. 10
Types (1)	V_{RWM}	I_{O1} T_A = +55°C (4) (5)	$I_{O(L)}$ T_L = +75°C (6) (7)	I_{FSM} T_A = +25°C (8)	t_{rr}	$R_{\theta JL}$ (7)	$R_{\theta JEC}$ (7) (9)	$R_{\theta JX}$ (5)	$R_{\theta JSP}$ (10)
	V	A	A	A(pk)	ns	°C/W	°C/W	°C/W	°C/W
1N5802, US, URS (2)	50	1.0	2.5	35	25	36	13	154	
1N5804, US, URS (2)	100	1.0	2.5	35	25	36	13	154	
1N5806, US, URS (2)	150	1.0	2.5	35	25	36	13	154	
1N5802UMC	50	1.0	2.5	35	25			127.7	22.4
1N5804UMC	100	1.0	2.5	35	25			127.7	22.4
1N5806UMC	150	1.0	2.5	35	25			127.7	22.4
1N5807, US, URS (3)	50	3.0	6.0	125	30	22	6.5	52	
1N5809, US, URS (3)	100	3.0	6.0	125	30	22	6.5	52	
1N5811, US, URS (3)	150	3.0	6.0	125	30	22	6.5	52	

See notes on next page.

Comments, suggestions, or questions on this document should be addressed to DLA Land and Maritime, ATTN: VAC, P.O. Box 3990, Columbus, OH 43218-3990, or emailed to Semiconductor@dla.mil. Since contact information can change, you may want to verify the currency of this address information using the ASSIST Online database at https://assist.dla.mil.

AMSC N/A
FSC 5961

DISTRIBUTION STATEMENT A. Approved for public release. Distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T02:20Z
Check the source to verify that this is the current version before use.

1.3.2 Ratings applicable to individual types − Continued.

(1) Electrical characteristics for the surface mount devices are identical to the non-suffix axial leaded device.
(2) Axial leaded, US, URS and UMC devices.
(3) Axial leaded, US and URS devices only.
(4) Derate at 8.33 mA/°C for T_A above +55°C for 1.0 amp ratings. Derate at 25 mA/°C for T_A above +55°C for 3.0 amp ratings.
(5) For the 1 and 3 A ratings at 55°C ambient, these I_O ratings are for a thermal mounting methods (PC boards or other) where the lead or end-cap temperatures cannot be maintained and where the thermal resistance from mounting point to ambient is still sufficiently controlled where $T_{J(MAX)}$ in 1.3.1 is not exceeded. This equates to $R_{\theta JX} \leq 154$°C/W for the 1N5802 thru 1N5806 and $R_{\theta JX} \leq 52$°C/W for the 1N5807 thru 1N5811 as shown in col. 9. Also see application notes in 6.6.1.
(6) Derate at 25 mA/°C for T_L above +75°C for 2.5 amp ratings. Derate at 60 mA/°C for T_L above +75°C for 6.0 amp ratings.
(7) T_L at L = .375 in. (9.52 mm) for axial leaded devices; $T_{EC} = T_L$ at L = 0 for US suffix devices.
(8) Operating at I_{O1} with t_P = 8.3 ms.
(9) US suffix devices only.
(10) UMC suffix devices only.

1.4 Primary electrical characteristics. Unless otherwise specified, T_A = +25°C.

Types	V_{BR} at 100 µA, pulse ≤ 20 ms	I_{R1} at $V_R = V_{RWM}$ T_A = +25°C, pulsed $V_R \leq 20$ ms	I_{R2} at $V_R = V_{RWM}$ T_A = +125°C, pulsed $V_R \leq 20$ ms
	V	µA	µA
1N5802, US, URS, UMC	60	1.0	175
1N5804, US, URS, UMC	110	1.0	175
1N5806, US, URS, UMC	160	1.0	175
1N5807, US, URS	60	5.0	525
1N5809, US, URS	110	5.0	525
1N5811, US, URS	160	5.0	525

1.5 Part or Identifying Number (PIN). The PIN is in accordance with MIL-PRF-19500, and as specified herein. See 6.4 for PIN construction example and 6.5 for a list of available PINs.

1.5.1 JAN certification mark and quality level.

1.5.1.1 Quality level designators for encapsulated devices. The quality level designators for encapsulated devices that are applicable for this specification sheet from the lowest to the highest level are as follows: "JAN", "JANTX", "JANTXV", and "JANS".

1.5.1.2 Quality level designators for unencapsulated devices (die). The quality level designators for unencapsulated devices (die) that are applicable for this specification sheet from the lowest to the highest level are as follows: "JANHC" and "JANKC".

1.5.2 Device type. The designation system for the device types of semiconductors covered by this specification sheet are as follows.

1.5.2.1 First number and first letter symbols. The semiconductors of this specification sheet use the first number and letter symbols "1N".

1.5.2.2 Second number symbols. The second number symbols for the semiconductors covered by this specification sheet are as follows: "5802", "5804", "5806", 5807", "5809", and "5811".

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T02:20Z
Check the source to verify that this is the current version before use.

1.5.3 Suffix symbols. The following suffix symbols are incorporated in the PIN as applicable.

	A blank suffix symbol indicates a through-hole mount axial leaded package (see figure 1).
US	Indicates a surface mount package with square end-caps (see figure 2).
URS	Indicates a surface mount package with one round end-cap and one square end-cap (see figure 3).
UMC	Indicates a planar ceramic surface mount package (see figure 4).

1.5.4 Lead finish. The lead finishes applicable to this specification sheet are listed on QPDSIS-19500.

1.5.5 Die identifiers for unencapsulated devices (manufacturers and critical interface identifiers). The manufacturer die identifiers that are applicable for this specification sheet are "E", "F", "G", and "H" (see figures 5, 6, 7, 8, and 6.5).

2. APPLICABLE DOCUMENTS

2.1 General. The documents listed in this section are specified in sections 3 and 4 of this specification. This section does not include documents cited in other sections of this specification or recommended for additional information or as examples. While every effort has been made to ensure the completeness of this list, document users are cautioned that they must meet all specified requirements of documents cited in sections 3 and 4 of this specification, whether or not they are listed.

2.2 Government documents.

2.2.1 Specifications, standards, and handbooks. The following specifications, standards, and handbooks form a part of this document to the extent specified herein. Unless otherwise specified, the issues of these documents are those cited in the solicitation or contract.

DEPARTMENT OF DEFENSE SPECIFICATIONS

MIL-PRF-19500 – Semiconductor Devices, General Specification for.


DEPARTMENT OF DEFENSE STANDARDS

MIL-STD-750 – Test Methods For Semiconductor Devices.

(Copies of these documents are available online at https://quicksearch.dla.mil).

2.3 Order of precedence. Unless otherwise noted herein or in the contract, in the event of a conflict between the text of this document and the references cited herein, the text of this document takes precedence. Nothing in this document, however, supersedes applicable laws and regulations unless a specific exemption has been obtained.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T02:20Z
Check the source to verify that this is the current version before use.



Dimensions for types 1N5802, 1N5804, 1N5806

Symbol	Inch	Inch	mm	mm	Notes
	Min	Max	Min	Max	
BD	.065	.085	1.65	2.16	3
BL	.125	.250	3.18	6.35	4
LD	.027	.032	0.69	0.81	4
LL	.700	1.30	17.78	33.02	

Dimensions for types 1N5807, 1N5809, 1N5811


Symbol	Inch	Inch	mm	mm	Notes
	Min	Max	Min	Max	
BD	.115	.142	2.92	3.61	3
BL	.130	.300	3.30	7.62	4
LD	.036	.042	0.91	1.07	4
LL	.900	1.30	22.86	33.02	

NOTES:

1. Dimensions are in inches. Millimeters are given for general information only.
2. Dimensions are pre-solder dip.
3. Dimension BD shall be measured at the largest diameter.
4. Dimension BL shall include the entire body including plugs and sections of the lead over which the diameter is uncontrolled. This uncontrolled area is defined as the zone between the edge of the diode body and extending .050 inch (1.27 mm) onto the leads.
5. The shape of the body, within the bounds of the dimensions is optional.

FIGURE 1. Physical dimensions of axial leaded package.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T02:20Z
Check the source to verify that this is the current version before use.



Dimensions for types 1N5802US, 1N5804US, 1N5806US

Symbol	Inch	Inch	mm	mm
	Min	Max	Min	Max
BD	.091	.103	2.31	2.62
BL	.168	.200	4.27	5.08
ECT	.019	.028	0.48	0.71
S	.003		0.08	


Dimensions for types 1N5807US, 1N5809US, 1N5811US

Symbol	Inch	Inch	mm	mm
	Min	Max	Min	Max
BD	.137	.148	3.48	3.76
BL	.200	.225	5.08	5.72
ECT	.019	.028	0.48	0.71
S	.003		0.08	

NOTES:
1. Dimensions are in inches. Millimeters are given for general information only.
2. Dimensions are pre-solder dip.
3. The S dimension is minimum clearance of glass body to mounting surface on all orientations.

FIGURE 2. Physical dimensions of square end-cap surface mount (US) package.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T02:20Z
Check the source to verify that this is the current version before use.



Dimensions for device types 1N5802URS, 1N5804URS, 1N5806URS

Symbol	Inch	Inch	mm	mm	Notes
	Min	Max	Min	Max	
BD	.091	.103	2.31	2.62	2
BL	.168	.200	4.27	5.08	
ECT	.019	.028	0.48	0.71	2
S	.003		0.08		


Dimensions for device types 1N5807URS, 1N5809URS, 1N5811URS

Symbol	Inch	Inch	mm	mm	Notes
	Min	Max	Min	Max	
BD	.137	.148	3.48	3.76	2
BL	.200	.225	5.08	5.72	
ECT	.019	.028	0.48	0.71	2
S	.003		0.08		

NOTES:
1. Dimensions are in inches. Millimeters are given for general information only.
2. One endcap shall be square and the other end-cap shall be round.
3. Dimensions are pre-solder dip.
4. Minimum clearance of glass body to mounting surface on all orientations.

FIGURE 3. Physical dimensions of round and square end-cap surface mount (URS) package.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T02:20Z
Check the source to verify that this is the current version before use.




Symbol	Inches	Inches	mm	mm		Symbol	Inches	Inches	mm	mm
	Min	Max	Min	Max			Min	Max	Min	Max
BCH	.058	.064	1.46	1.63		CH	.038	.040	0.98	1.01
BH	.018	.022	0.46	0.56		CL	.199	.211	5.06	5.36
BL	.242	.254	6.15	6.45		CW	.109	.120	2.76	3.06
BLM	.098	.110	2.49	2.79		LMW	.062	.074	1.58	1.88
BW	.151	.163	3.84	4.14		PH	.001	.003	0.03	0.07
BPB	.003 Nominal		0.08 Nominal			R1	.006 Nominal		0.15 Nominal	

NOTES:
1. Dimensions are in inches. Millimeters are given for general information only.
2. Shaded areas denote metallized areas.

FIGURE 4. Physical dimensions of planar ceramic (UMC) surface mount package.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T02:20Z
Check the source to verify that this is the current version before use.



E-version

Dimensions for 1N5802, 1N5804, 1N5806

Letter	Inches	Inches	mm	mm
	Min	Max	Min	Max
A	.043	.047	1.10	1.20
B	.032	.036	0.82	0.92
C	.008	.012	0.20	0.30


Dimensions for 1N5807, 1N5809, 1N5811

Letter	Inches	Inches	mm	mm
	Min	Max	Min	Max
A	.068	.072	1.73	1.83
B	.057	.061	1.45	1.55
C	.008	.012	0.20	0.30

NOTES:
1. Dimensions are in inches. Millimeters are given for general information only.
2. The metallization characteristics of the die are:
   Top metal: Anode is aluminum at 38,000 Å minimum.
   Back metal: Cathode is gold at 3,500 Å minimum.

FIGURE 5. Physical dimensions and characteristics for JANC (E-version) die.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T02:20Z
Check the source to verify that this is the current version before use.



F-version

Dimensions for 1N5802, 1N5804, 1N5806

Letter	Inches	Inches	mm	mm
	Min	Max	Min	Max
A	.043	.047	1.09	1.19
B	.031	.035	0.79	0.89
C	.008	.012	0.20	0.30


Dimensions for 1N5807, 1N5809, 1N5811

Letter	Inches	Inches	mm	mm
	Min	Max	Min	Max
A	.062	.068	1.57	1.73
B	.046	.052	1.17	1.32
C	.008	.012	0.20	0.30

NOTES:
1. Dimensions are in inches. Millimeter equivalents are given for general information only.
2. The metallization characteristics of the die are:
   Top metal: Anode is aluminum at 34,000 Å minimum.
   Back metal: Cathode is Ti 1,200Å nominal, Ni 1,800Å nominal, Au 4,000Å nominal

FIGURE 6. Physical dimensions and characteristics for JANC (F-version) die.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T02:20Z
Check the source to verify that this is the current version before use.




G-version

Letter	Inches	Inches	mm	mm
	Min	Max	Min	Max
A	.040	.050	1.016	1.270
B	.055	.065	1.397	1.651
C	.024	.034	0.610	0.864
D	.039	.049	0.991	1.245
E	.003	.013	0.076	0.330

NOTES:
1. Dimensions are in inches. Millimeters are given for general information only.
2. The metallization characteristics of the die are:
   Top metal: Anode is aluminum at 30,000 Å ± 5,000 Å.
   Back metal: Cathode is gold at 5,000 Å ± 1,000 Å.

FIGURE 7. Physical dimensions and characteristics for JANC (G-version) die.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T02:20Z
Check the source to verify that this is the current version before use.



H-version

Dimensions for 1N5802, 1N5804, 1N5806

Letter	Inches	Inches	mm	mm
	Min	Max	Min	Max
A	.043	.047	1.09	1.19
B	.031	.035	0.79	0.89
C	.008	.012	0.20	0.30

Dimensions for 1N5807, 1N5809, 1N5811

Letter	Inches	Inches	mm	mm
	Min	Max	Min	Max
A	.062	.068	1.57	1.73
B	.046	.052	1.17	1.32
C	.008	.012	0.20	0.30

NOTES:
1. Dimensions are in inches. Millimeter equivalents are given for general information only.
2. The metallization characteristics of the die are:
   Top metal: Anode is aluminum at 34,000 Å minimum.
   Back metal: Cathode is Ti 1,200Å nominal / Ni 1,800Å nominal / Ag 30,000Å nominal

FIGURE 8. Physical dimensions and characteristics for JANC (H-version) die.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T02:20Z
Check the source to verify that this is the current version before use.

3. REQUIREMENTS

3.1 General. The individual item requirements shall be as specified in MIL-PRF-19500 and as modified herein.

3.2 Qualification. Devices furnished under this specification shall be products that are manufactured by a manufacturer authorized by the qualifying activity for listing on the applicable qualified manufacturer's list (QML) before contract award (see 4.2 and 6.3).

3.3 Abbreviations, symbols, and definitions. Abbreviations, symbols, and definitions used herein shall be as specified in MIL-PRF-19500 and as follows:

$I_{(BR)}$	Current for testing breakdown voltage.
P_{RM}	Peak reverse power.
UMC	Planar ceramic surface mounted diode with ceramic lid.
V_{FR}	Forward recovery voltage.

3.4 Interface and physical dimensions. The interface and physical dimensions shall be as specified in MIL-PRF-19500, and figures 1, 2, 3, 4, 5, 6, 7, and 8 herein.

3.4.1 Lead finish. Unless otherwise specified, lead, end-cap or pad finish shall be solderable in accordance with MIL-PRF-19500, MIL-STD-750, and herein. When solder alloy is used for finish, the maximum lead temperature is limited to 175°C maximum. Where a choice of finish is desired, it shall be specified in the acquisition document (see 6.2).

3.4.2 Diode construction.

3.4.2.1 Axial leaded. The axial leaded devices shall be constructed utilizing non-cavity double plug construction with high temperature metallurgical bonding between both sides of the silicon die and terminal pins. Metallurgical bond shall be in accordance with the requirements of category I of MIL-PRF-19500. Point contact construction shall not be allowed. Silver button Dumet design shall not be acceptable.

3.4.2.2 Surface mount. US and URS version devices shall be structurally identical to the non-surface mount devices except for lead terminations. The surface mount URS version shall be considered structurally identical to the US version except for end-cap shape. One end-cap shall be square and the other end-cap shall be round. The UMC version devices shall be eutectically mounted and wire bonded in a ceramic package.

3.5 Marking. Marking shall be in accordance with MIL-PRF-19500.

3.5.1 Marking of US and URS versions. For US versions only, all marking (except for polarity) may be omitted from the device. For URS versions only, all marking may be omitted from the device. All marking which is omitted from the body of the devices shall appear on the label of the initial container.

3.5.2 Polarity. The polarity of all types except URS and UMC shall be indicated with a contrasting color band to denote the cathode end. Alternately, for US version surface mount devices, a minimum of three evenly spaced contrasting color dots around the periphery of the cathode end may be used. No color coding will be permitted. For URS version surface mount devices only, cathode shall be connected to the round end-cap. For UMC version surface mount devices polarity shall consist as a minimum of 4 contrasting color dots marked on the lid.

3.6 Electrical performance characteristics. Unless otherwise specified herein, the electrical performance characteristics are as specified in 1.3, 1.4, and table I herein.

3.7 Electrical test requirements. The electrical test requirements shall be the subgroups specified in table I herein.

3.8 Workmanship. Semiconductor devices shall be processed in such a manner as to be uniform in quality and shall be free from other defects that will affect life, serviceability, or appearance.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T02:20Z
Check the source to verify that this is the current version before use.

4. VERIFICATION

4.1 Classification of inspections. The inspection requirements specified herein are classified as follows:

a. Qualification inspection (see 4.2).

b. Screening (see 4.3).

c. Conformance inspection (see 4.4 and table I, table II, and table III).

d. Element evaluation of un-encapsulated die (see 4.6).

4.2 Qualification inspection. Qualification inspection shall be in accordance with MIL-PRF-19500 and as specified herein.

4.2.1 Group E inspection. Group E inspection shall be performed for qualification or re-qualification only. In case qualification was awarded to a prior revision of the specification sheet that did not request the performance of table II tests, the tests specified in table II herein that were not performed in the prior revision shall be performed on the first inspection lot to this revision to maintain qualification.

4.2.2 JANHC and JANKC die. Qualification shall be in accordance with appendix G of MIL-PRF-19500 and as specified herein.

4.3 Screening (quality levels JANS, JANTXV and JANTX only). Screening of packaged devices shall be in accordance with table E-IV of MIL-PRF-19500, and as specified herein. The following measurements shall be made in accordance with table I herein. Devices that exceed the limits of table I herein shall not be acceptable.

Screen	Measurement for quality level JANS	Measurement for quality levels JANTXV and JANTX
(1) 3c	Thermal impedance (see 4.3.1)	Thermal impedance (see 4.3.1)
9	I_{R1}, V_{FM1} or V_{FM4}.	Not required
10	Method 1038 of MIL-STD-750, condition A	Method 1038 of MIL-STD-750, condition A
11	Required I_{R1}, V_{FM1}, or V_{FM4}; ΔI_{R1} ≤ ±100 percent of initial reading or ±150 nA dc (1N5802, 1N5804, 1N5806) or ±500 nA dc (1N5807, 1N5809, 1N5811), whichever is greater. ΔV_{FM} ≤ ±0.05 V dc.	Required I_{R1}, V_{FM1}, or V_{FM4}
12	Required, see 4.3.2	Required, see 4.3.2
(2) 13	Subgroups 2 and 3 of table I herein; ΔI_{R1} ≤ ±100 percent of initial reading or ±150 nA dc (1N5802, 1N5804, 1N5806) or ±500 nA dc (1N5807, 1N5809, 1N5811), whichever is greater. ΔV_{FM} ≤ ±0.05 V dc. Scope display evaluation (see 4.5.3)	Subgroup 2 of table I herein; ΔI_{R1} ≤ ±100 percent of initial reading or ±250 nA dc (1N5802, 1N5804, 1N5806) or ±1 µA dc (1N5807, 1N5809, 1N5811), whichever is greater. ΔV_{FM} ≤ ±0.05 V dc. Scope-display evaluation (see 4.5.3).

(1) Thermal impedance shall be performed anytime after sealing provided temperature cycling is performed in accordance with MIL-PRF-19500, screen 3a prior to this thermal test. Quality levels TX and TXV levels do not need to be repeated in screening requirements.
(2) Thermal impedance is not required in screen 13, if already previously performed.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T02:20Z
Check the source to verify that this is the current version before use.

4.3.1 Thermal impedance. The thermal impedance measurements shall be performed in accordance with method 3101 of MIL-STD-750 using the guidelines in that method for determining I_M, I_H, t_{MD}, t_H, t_{MD}, and K factor where appropriate. The limits will be statistically derived. See table E-IX of MIL-PRF-19500, group E, and table II, subgroup 4 herein.

4.3.2 Free air power burn-in conditions. Power burn-in shall be performed in accordance with condition B of method 1038 of MIL-STD-750. The details of 4.5.2 and those that follows shall apply: $I_{O(min)}$ = rated I_{O1} (see 1.3 herein). T_A = 55°C maximum. Adjust I_O or T_A to achieve the required T_J. T_J = 135°C minimum. With approval of the qualifying activity and preparing activity, alternate burn-in criteria (hours, bias conditions, T_J, mounting conditions) may be used for JANTX and JANTXV quality levels. A justification demonstrating equivalence is required. In addition, the manufacturing site's burn-in data and performance history will be essential criteria for burn-in modification approval.

4.4 Conformance inspection. Conformance inspection shall be in accordance with MIL-PRF-19500 and as specified herein.

4.4.1 Group A inspection. Group A inspection shall be conducted in accordance with table E-V of MIL-PRF-19500, and table I herein. The $Z_{\theta JX}$ end-point shall be derived by the supplier and approved by the qualifying activity. This $Z_{\theta JX}$ end-point shall also be documented in the qualification report.

4.4.2 Group B inspection. Group B inspection shall be conducted in accordance with the tests and conditions specified for subgroup testing in table E-VIA (JANS) and table E-VIB (JAN, JANTX, and JANTXV) of MIL-PRF-19500 and herein. Delta measurements, when applicable, shall be as specified in table III herein.

4.4.2.1 Quality level JANS (see table E-VIA of MIL-PRF-19500).

Subgroup	Method	Condition
B3	4066	Condition A, I_{FSM} = rated I_{FSM} (see col. 5 of 1.3.2); ten surges of 8.3 ms each at 1 minute intervals, superimposed on I_{O1} (See col. 3 of 1.3.2), V_{RWM} = rated V_{RWM} (see col. 2 of 1.3.2), T_A = 25°C.
B4	1037	See 4.5.2. I_O = I_{O1} rated minimum (see col. 3 of 1.3.2); V_R = rated V_{RWM} (see col. 2 of 1.3.2); 2,000 cycles.
B5	1027	See 4.5.2. I_O = I_{O1} rated minimum (see col. 3 of 1.3.2); apply V_R = rated V_{RWM} (see col. 2 of 1.3.2) adjust I_O or T_A to achieve T_J = 175°C minimum; f = 50 to 60 Hz; t = 1,000 hours; n=45, c =0. Temporary leads may be added for surface mount devices. For irradiated devices, include t_{rr} as an end-point measurement.
B8	4065	For 1N5802 through 1N5806, P_{RM} ≥ 318 W for square wave and P_{RM} ≥ 500 W for half sine-wave. For 1N5807 through 1N5811, P_{RM} ≥ 636 W for square wave and P_{RM} ≥ 1,000 W for half sine-wave. Test shall be performed on each sublot; sampling plan: n = 10, c = 0, electrical end-points, see table I, subgroup 2 herein.

4.4.2.2 Quality levels JAN, JANTX and JANTXV (see table E-VIB of MIL-PRF-19500).

Subgroup	Method	Condition
B3	1027	See 4.5.2; I_O = I_{O1} rated minimum (see col. 3 of 1.3.2). Adjust I_O or T_A to achieve the required T_J of +150°C minimum. Apply V_R = rated V_{RWM} (see col. 2 of 1.3.2), f = 50 to 60 Hz. Temporary leads may be added for surface mount devices. For irradiated devices, include t_{rr} as an end-point measurement.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T02:20Z
Check the source to verify that this is the current version before use.

4.4.3 Group C inspection. Group C inspection shall be conducted in accordance with the conditions specified for subgroup testing in table E-VII of MIL-PRF-19500, and as follows. Delta measurements when applicable shall be as specified in table III herein.

Subgroup	Method	Condition
C2	2036	Axial leaded devices only: Tension: For 1N5802, 1N5804, 1N5806; Condition A, weight = 8 pounds (3.62 Kg) (silver leads), 12 pounds (5.44 Kg) (copper leads), t = 15s. For 1N5807, 1N5809, 1N5811; Condition A, weight = 12 pounds (5.44 Kg) (silver leads), 20 pounds (9.07 Kg) (copper leads), t = 15s. Lead fatigue: Condition E for all types, 2 pounds (0.91 Kg).
C2	2038	US, URS surface mount devices only: Tab pull: For 1N5802US, 1N5804US, 1N5806US Condition B, 8 pounds (silver tabs), 12 pounds (5.44 Kg) (copper tabs), t = 15s. For 1N5807US, 1N5809US, 1N5811US Condition B, 12 pounds (silver tabs), 20 pounds (9.07 Kg) (copper tabs), t = 15s. Test method 2038 not required for UMC devices.
C5	4081	See 4.3.1. For axial leaded devices, $R_{\theta JL}$ (maximum) see col. 7 of 1.3.2; L = .375 inch (9.53 mm). For US surface mount devices, $R_{\theta JEC}$, see col. 8 of 1.3.2. For UMC surface mount devices, $R_{\theta JSP}$ see col. 10 of 1.3.2.
C6	1027	See 4.5.2. $I_O = I_{O1}$ rated minimum (see col. 3 of 1.3.2); adjust I_O or T_A to achieve T_J = 150°C minimum, apply V_R = rated V_{RWM} (see col. 2 of 1.3.2), f = 50 to 60 Hz. Temporary leads may be added for surface mount devices. For irradiated devices, include t_{rr} as an end-point measurement.

4.4.4 Group E inspection. Group E inspection shall be conducted in accordance with the conditions specified for subgroup testing in table E-IX of MIL-PRF-19500 and as specified herein. See table III herein for delta measurements when applicable.

4.5 Methods of inspection. Methods of inspection shall be as specified in the appropriate tables as follows.

4.5.1 Pulse measurements. Conditions for pulse measurement shall be as specified in section 4 of MIL-STD-750.

4.5.2 Burn-in and life tests. These tests shall be conducted with a half-sine waveform of the specified peak voltage impressed across the diode in the reverse direction followed by a half-sine waveform of the specified average rectified current. The forward conduction angle of the rectified current shall be neither greater than 180 degrees, nor less than 150 degrees. The use of a current limiting or ballast resistor is permitted provided that each DUT still sees the full required T_J and I_o and that the minimum required voltage, where applicable, is maintained through-out the burn-in period. Method 3100 of MIL-STD-750 shall be used to measure T_J. T_J shall be 135°C minimum for screening and 150°C minimum for life tests. T_A = 55°C maximum.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T02:20Z
Check the source to verify that this is the current version before use.

4.5.3 Scope display evaluation. Scope display evaluation shall be performed using condition A (stable only) in accordance with method 4023 of MIL-STD-750. Scope display may be performed on ATE (automatic test equipment) for screening only with the approval of the qualifying activity. Scope display in table I, subgroup 4 shall be performed on a curve tracer. The reverse current (I_{BR}) over the knee shall be 500 µA peak.

4.5.4 Thermal resistance. Thermal resistance measurement shall be performed in accordance with method 4081 of MIL-STD-750 using the guidelines in that method for determining I_M, I_H, and t_H. See table E-IX of MIL-PRF-19500, subgroup 4, and figures 9, 10, 11, 12, and 13 herein. Forced moving air or draft shall not be permitted across the devices during test.

4.5.5 Peak reverse power characterization. The testing to characterize P_{RM} shall be conducted in accordance with method 4065 of MIL-STD-750. The following details shall apply:

a. During the test, the voltage (V_{BR}) shall be monitored to verify it has not collapsed.

b. Any collapse in V_{BR} during or after the test, or rise in leakage current (I_R) after the test that exceeds I_{R1} in table I, shall be considered a failure to that level of applied P_{RM}.

c. Progressively higher levels of P_{RM} shall be applied until failure occurs on all devices within the chosen sample size to characterize each sublot.

4.6 Element evaluation of un-encapsulated die. The element evaluation of unencapsulated die shall be in accordance with appendix G of MIL-PRF-19500. As a minimum, die shall be 100-percent probed to ensure compliance with table I, subgroup 2. Burn-in duration for the JANKC level follows JANS requirements; the JANHC follows JANTX requirements.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T02:20Z
Check the source to verify that this is the current version before use.

TABLE I. Group A inspection.

Inspection 1/	MIL-STD-750		Symbol	Limit	Limit	Unit
	Method	Conditions		Min	Max	
Subgroup 1						
Visual and mechanical examination	2071					
Subgroup 2						
Thermal impedance 2/	3101	See 4.3.1	$Z_{\theta JX}$			°C/W
Forward voltage	4011	Condition B, Duty cycle ≤ 2 percent (pulsed see 4.5.1); tp = 8.3 ms (max)				
1N5802, US, URS, UMC 1N5804, US, URS, UMC 1N5806, US, URS, UMC		I_{FM} = 1.0 A	V_{FM1}		0.875	V
1N5802, US, URS, UMC 1N5804, US, URS, UMC 1N5806, US, URS, UMC		I_{FM} = 2.5 A	V_{FM2}		0.975	V
Forward voltage	4011	Condition B, Duty cycle ≤ 2 percent (pulsed see 4.5.1); tp = 8.3 ms (max)				
1N5807, US, URS 1N5809, US, URS 1N5811, US, URS		I_{FM} = 3.0 A	V_{FM3}		0.865	V
1N5807, US, URS 1N5809, US, URS 1N5811, US, URS		I_{FM} = 4.0 A	V_{FM4}		0.875	V
1N5807, US, URS 1N5809, US, URS 1N5811, US, URS		I_{FM} = 6.0 A	V_{FM5}		0.925	V

See footnotes at end of table.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T02:20Z
Check the source to verify that this is the current version before use.

TABLE I. Group A inspection − Continued.

Inspection 1/	MIL-STD-750		Symbol	Limit	Limit	Unit
	Method	Conditions		Min	Max	
Subgroup 2 – continued						
Reverse current	4016	Condition A or B	I_{R1}			
1N5802, US, URS, UMC		V_R = 50 V			1.0	µA
1N5804, US, URS, UMC		V_R = 100 V			1.0	µA
1N5806, US, URS, UMC		V_R = 150 V			1.0	µA
1N5807, US, URS		V_R = 50 V			5.0	µA
1N5809, US, URS		V_R = 100 V			5.0	µA
1N5811, US, URS		V_R = 150 V			5.0	µA
Breakdown voltage	4021	$I_{(BR)}$ = 100 µA pulse ≤ 20 ms	$V_{(BR)1}$			
1N5802, US, URS, UMC 1N5807, US, URS				60		V
1N5804, US, URS, UMC 1N5809, US, URS				110		V
1N5806, US, URS, UMC 1N5811, US, URS				160		V
Subgroup 3						
High temperature operation:		T_A = +125°C minimum.				
Reverse current	4016	Condition A or B	I_{R2}			
1N5802, US, URS, UMC		V_R = 50 V			175	µA
1N5804, US, URS, UMC		V_R = 100 V			175	µA
1N5806, US, URS, UMC		V_R = 150 V			175	µA
1N5807, US, URS		V_R = 50 V			525	µA
1N5809, US, URS		V_R = 100 V			525	µA
1N5811, US, URS		V_R = 150 V			525	µA

See footnotes at end of table.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T02:20Z
Check the source to verify that this is the current version before use.

TABLE I. Group A inspection − Continued.

Inspection 1/	MIL-STD-750		Symbol	Limit	Limit	Unit
	Method	Conditions		Min	Max	
Subgroup 3 - continued						
Forward voltage	4011	Condition B, duty cycle ≤ 2 percent (pulsed see 4.5.1); tp = 8.3 ms (max)				
1N5802, US, URS, UMC 1N5804, US, URS, UMC 1N5806, US, URS, UMC		I_{FM} = 1.0 A	V_{FM6}		0.800	V
1N5807, US, URS 1N5809, US, URS 1N5811, US, URS		I_{FM} = 4.0 A	V_{FM7}		0.800	V
Low-temperature operation:		T_A = -65°C minimum.				
Forward voltage	4011	Condition B, duty cycle ≤ 2 percent (pulsed see 4.5.1); tp = 8.3 ms (max)	V_{FM8}			
1N5802, US, URS, UMC 1N5804, US, URS, UMC 1N5806, US, URS, UMC		I_{FM} = 1.0 A			1.075	V
1N5807, US, URS 1N5809, US, URS 1N5811, US, URS		I_{FM} = 4.0 A			1.075	V
Breakdown voltage	4021	$I_{(BR)}$ = 100 µA dc	$V_{(BR)2}$			
1N5802, US, URS, UMC 1N5807, US, URS				50		V dc
1N5804, US, URS, UMC 1N5809, US, URS				100		V dc
1N5806, US, URS, UMC 1N5811, US, URS				150		V dc

See footnotes at end of table.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T02:20Z
Check the source to verify that this is the current version before use.

TABLE I. Group A inspection − Continued.

Inspection 1/	MIL-STD-750		Symbol	Limit	Limit	Unit
	Method	Conditions		Min	Max	
Subgroup 4						
Reverse recovery time	4031	Condition B	t_{rr}			
1N5802, US, URS, UMC 1N5804, US, URS, UMC 1N5806, US, URS, UMC		$I_F = I_{RM} = 0.5$ A; $i_{(REC)} = 0.05$ A; di/dt = 65 A/µs (min)			25	ns
1N5807, US, URS 1N5809, US, URS 1N5811, US, URS		$I_F = I_{RM} = 1.0$ A, $i_{(REC)} = 0.1$ A, di/dt = 100 A/µs (min)			30	ns
Capacitance	4001	$V_R = 10$ V; f = 1 Mhz; $V_{sig} = 50$ mV (p-p)	C_J			
1N5802, US, URS, UMC 1N5804, US, URS, UMC 1N5806, US, URS, UMC					25	pF
1N5807, US, URS 1N5809, US, URS 1N5811, US, URS					60	pF
Forward recovery voltage	4026	$t_r = 8$ ns	V(peak)			
1N5802, US, URS, UMC 1N5804, US, URS, UMC 1N5806, US, URS, UMC		$I_F = 250$ mA			2.2	V
1N5807, US, URS 1N5809, US, URS 1N5811, US, URS		$I_F = 500$ mA			2.2	V
Forward recovery time	4026	tp ≥ 20 ns, tr = 8 ns, the test is measured at $V_{FR} = 1.1 \times V_F$	t_{fr}			
1N5802, US, URS, UMC 1N5804, US, URS, UMC 1N5806, US, URS, UMC		$I_F = 250$ mA			15	ns
1N5807, US, URS 1N5809, US, URS 1N5811, US, URS		$I_F = 500$ mA			15	ns
Scope display evaluation	4023	See 4.5.3, n = 116, c = 0				

See footnotes at end of table.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T02:20Z
Check the source to verify that this is the current version before use.

TABLE I. Group A inspection − Continued.

Inspection 1/	MIL-STD-750		Symbol	Limit	Limit	Unit
	Method	Conditions		Min	Max	
Subgroup 5						
Not applicable						
Subgroup 6						
Forward surge current	4066	Condition A, I_{FSM} = rated I_{FSM} (see 1.3.2); ten surges of 8.3 ms each at 1 minute intervals superimposed on I_O = rated I_{O1} (see 1.3.2); V_{RWM} = rated V_{RWM} (see 1.3.2); T_A = + 25°C.				
Electrical measurements		See table I, subgroup 2 except $Z_{\theta JX}$.				
Subgroup 7						
Not applicable						

1/ For sampling plan, see MIL-PRF-19500.
2/ Not applicable to JANHC and JANKC devices. For end-point measurements, this test is required for the following subgroups:
Group B, subgroups 3, 4 and 5 (JANS).
Group B, subgroups 2 and 3 (JAN, JANTX, JANTXV).
Group C, subgroups 2 and 6.
Group E, subgroup 1.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T02:20Z
Check the source to verify that this is the current version before use.

TABLE II. Group E inspection (all quality levels) for qualification and requalification only.

Inspection	MIL-STD-750		Sampling plan
	Method	Conditions	
Subgroup 1			45 devices, c = 0
Thermal shock (liquid to liquid)	1056	20 cycles, except low temperature shall be achieved using liquid nitrogen (-195°C). Perform a visual for cracked glass. (Not applicable for UMC package.).	
Temperature cycling (air to air)	1051	-65°C to +175°C, 500 cycles.	
Hermetic seal 1/	1071		
Electrical measurement		See table I, subgroup 2 and table III, steps 1 and 2.	
Subgroup 2			45 devices, c = 0
Steady-state dc blocking life	1048	t = 1,000 hours; T_A = +150°C; V_R dc = 80 to 85 percent rated V_{RWM} (see 1.3.2).	
Electrical measurement		See table I, subgroup 2 herein, except $Z_{\theta JX}$ need not to be performed, and table III, steps 1 and 2 herein. For irradiated devices, include t_{rr} as an end-point measurement.	
Subgroup 4			Sample size N/A
Thermal impedance curves		See MIL-PRF-19500.	
Subgroup 5			
Not applicable			
Subgroup 8			45 devices
Peak reverse power	4065	P_{RM} shall be characterized by the supplier and this data shall be available to the Government. Test shall be performed on each sublot.	
Electrical measurement		See 4.5.5.	

See footnotes at end of table.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T02:20Z
Check the source to verify that this is the current version before use.

TABLE II. Group E inspection (all quality levels) for qualification and requalification only - Continued.

Inspection	MIL-STD-750		Sampling plan
	Method	Conditions	
Subgroup 9			45 devices
Resistance to glass cracking	1057	Test condition B. Step stress to destruction by increasing cycles or up to a maximum of 25 cycles. Not applicable for UMC package.	
Subgroup 10			22 devices, c = 0
Forward surge current	4066	Condition A, I_{FSM} = rated I_{FSM} (see col. 5 of 1.3.2); ten surges of 8.3 ms each at 1 minute intervals superimposed on I_O = rated I_{O1} (see col. 3 of 1.3.2); V_{RWM} = rated V_{RWM} (see col. 2 of 1.3.2); T_A = + 25°C.	
Electrical measurement		See table I, subgroup 2.	

1/ Opaque glass double plug non-cavity axial leaded diodes may use test method 2068 in lieu of test method 1071 of MIL-STD-750.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T02:20Z
Check the source to verify that this is the current version before use.

TABLE III. Delta measurements for groups B, C, and E inspections. 1/ 2/ 3/ 4/ 5/

Step	Inspection	MIL-STD-750		Symbol	Limit	Unit
		Method	Conditions			
1.	Forward voltage	4011	Condition B, Duty cycle ≤ 2 percent (pulsed see 4.5.1); tp = 8.3 ms (max)			
	1N5802, US, URS, UMC 1N5804, US, URS, UMC 1N5806, US, URS, UMC		I_{FM} = 1.0 A(pk)	ΔV_{FM1}	±50 mV dc change from initial value	
	1N5807, US, URS, 1N5809, US, URS, 1N5811, US, URS,		I_{FM} = 4.0 A(pk)	ΔV_{FM4}	±50 mV dc change from initial value	
2.	Reverse current	4016	Condition A or B	ΔI_{R1}		
	1N5802, US, URS, UMC 1N5804, US, URS, UMC 1N5806, US, URS, UMC		V_R = 50 V dc V_R = 100 V dc V_R = 150 V dc		100-percent or ±150 nA dc change from initial reading, whichever is greater.	
	1N5807, US, URS, 1N5809, US, URS, 1N5811, US, URS		V_R = 50 V dc V_R = 100 V dc V_R = 150 V dc		100-percent or ±500 nA dc change from initial reading, whichever is greater.	

1/ The delta measurements taken during group B inspections for quality level JANS (table E-VIA of MIL-PRF-19500) shall be as follows: In addition to the measurements specified for subgroups 4 and 5, the measurements of steps 1 and 2 of this table shall also be taken.


2/ The delta measurements taken during group B inspections for quality levels JAN, JANTX and JANTXV (table E-VIB of MIL-PRF-19500) shall be as follows: In addition to the measurements specified for subgroup 3, the measurements of steps 1 and 2 of this table shall also be taken.

3/ The delta measurements taken during group C inspections for all quality levels (table E-VII of MIL-PRF-19500) shall be as follows: In addition to the measurements specified for subgroup 6, the measurements of steps 1 and 2 of this table shall also be taken.

4/ The delta measurements taken during group E inspections for all quality levels (table E-IX of MIL-PRF-19500) shall be as follows: In addition to the measurements specified for subgroups 1 and 2, the measurements of steps 1 and 2 of this table shall also be taken.

5/ Devices which exceed the table I limits for this test shall not be accepted.


Source: https://assist.dla.mil -- Downloaded: 2026-10-19T02:20Z
Check the source to verify that this is the current version before use.



NOTES:
1. $Z_{\theta JX}$ = 4°C/W at 10 ms.
2. $R_{\theta JL}$ = 36°C/W.

FIGURE 9. Thermal impedance curve ($R_{\theta JL}$) of axial leaded package for 1N5802, 1N5804, and 1N5806.


Source: https://assist.dla.mil -- Downloaded: 2026-10-19T02:20Z
Check the source to verify that this is the current version before use.



NOTES:
1. $Z_{\theta JX}$ = 4°C/W at 10 ms.
2. $R_{\theta JEC}$ = 13°C/W.

FIGURE 10. Thermal impedance curve ($R_{\theta JEC}$) of US package for 1N5802US, 1N5804US, and 1N5806US.


Source: https://assist.dla.mil -- Downloaded: 2026-10-19T02:20Z
Check the source to verify that this is the current version before use.



NOTES:
1. $Z_{\theta JX}$ = 1.5°C/W at 10 ms.
2. $R_{\theta JL}$ = 22°C/W.

FIGURE 11. Thermal impedance curve ($R_{\theta JL}$) of axial leaded package for 1N5807, 1N5809, and 1N5811.


Source: https://assist.dla.mil -- Downloaded: 2026-10-19T02:20Z
Check the source to verify that this is the current version before use.



NOTES:
1. $Z_{\theta JX}$ = 1.5°C/W at 10 ms.
2. $R_{\theta JEC}$ = 6.5°C/W.

FIGURE 12. Thermal impedance curve ($R_{\theta JEC}$) of US package for 1N5807US, 1N5809US, and 1N5811US.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T02:20Z
Check the source to verify that this is the current version before use.



NOTES:
1. $Z_{\theta JX}$ = 6.75 °C/W at 10 ms.
2. $R_{\theta JSP}$ = 22.4 °C/W.
3. PCB pad size = 1.5 inch x 1.5 inch (38.1 mm x 38.1 mm).
4. Base material type = FR4.
5. Copper weight = 1.0 ounce/ft^2.

FIGURE 13. Thermal impedance curve ($R_{\theta JSP}$) of UMC package for 1N5802UMC, 1N5804UMC, and 1N5806UMC.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T02:20Z
Check the source to verify that this is the current version before use.

5. PACKAGING

5.1 Packaging. For acquisition purposes, the packaging requirements shall be as specified in the contract or order (see 6.2). When packaging of materiel is to be performed by DoD or in-house contractor personnel, these personnel need to contact the responsible packaging activity to ascertain packaging requirements. Packaging requirements are maintained by the Inventory Control Point's packaging activities within the Military Service or Defense Agency, or within the Military Service's system commands. Packaging data retrieval is available from the managing Military Department's or Defense Agency's automated packaging files, CD-ROM products, or by contacting the responsible packaging activity.

6. NOTES

(This section contains information of a general or explanatory nature that may be helpful, but is not mandatory. The notes specified in MIL-PRF-19500 are applicable to this specification.)

6.1 Intended use. Semiconductors conforming to this specification are intended for original equipment design applications and logistic support of existing equipment.

6.2 Acquisition requirements. Acquisition documents should specify the following:

a. Title, number, and date of this specification.

b. Packaging requirements (see 5.1).

c. Lead finish (see 3.4.1).


d. The complete PIN, see 1.5 and 6.4.

e. For die acquisition, the JANHC or JANKC letter version shall be specified (see figures 5, 6, 7, and 8).

6.3 Qualification. With respect to products requiring qualification, awards will be made only for products which are, at the time of award of contract, qualified for inclusion in Qualified Manufacturers List (QML-19500) whether or not such products have actually been so listed by that date. The attention of the contractors is called to these requirements, and manufacturers are urged to arrange to have the products that they propose to offer to the Federal Government tested for qualification in order that they may be eligible to be awarded contracts or orders for the products covered by this specification. Information pertaining to qualification of products may be obtained from DLA Land and Maritime, ATTN: VQE, P.O. Box 3990, Columbus, OH 43218-3990 or e-mail vqe.chief@dla.mil. An online listing of products qualified to this specification may be found in the Qualified Products Database (QPD) at https://qpldocs.dla.mil.


6.4 PIN construction examples.

6.4.1 Encapsulated devices The PINs for encapsulated devices are constructed using the following form.



Source: https://assist.dla.mil -- Downloaded: 2026-10-19T02:20Z
Check the source to verify that this is the current version before use.

6.4.2 Un-encapsulated devices. The PINs for un-encapsulated devices are constructed using the following form.



6.5 List of PINs.

6.5.1 List of PINs for encapsulated devices. The following is a list of possible PINs for encapsulated devices available on this specification sheet.

PINs for devices of the base quality level	PINs for devices of the "TX" quality level	PINs for devices of the "TXV" quality level	PINs for devices of the "S" quality level
Devices in an axial leaded package			
JAN1N5802	JANTX1N5802	JANTXV1N5802	JANS1N5802
JAN1N5804	JANTX1N5804	JANTXV1N5804	JANS1N5804
JAN1N5806	JANTX1N5806	JANTXV1N5806	JANS1N5806
JAN1N5807	JANTX1N5807	JANTXV1N5807	JANS1N5807
JAN1N5809	JANTX1N5809	JANTXV1N5809	JANS1N5809
JAN1N5811	JANTX1N5811	JANTXV1N5811	JANS1N5811
Devices in a US package			
JAN1N5802US	JANTX1N5802US	JANTXV1N5802US	JANS1N5802US
JAN1N5804US	JANTX1N5804US	JANTXV1N5804US	JANS1N5804US
JAN1N5806US	JANTX1N5806US	JANTXV1N5806US	JANS1N5806US
JAN1N5807US	JANTX1N5807US	JANTXV1N5807US	JANS1N5807US
JAN1N5809US	JANTX1N5809US	JANTXV1N5809US	JANS1N5809US
JAN1N5811US	JANTX1N5811US	JANTXV1N5811US	JANS1N5811US
Devices in a URS package			
JAN1N5802URS	JANTX1N5802URS	JANTXV1N5802URS	JANS1N5802URS
JAN1N5804URS	JANTX1N5804URS	JANTXV1N5804URS	JANS1N5804URS
JAN1N5806URS	JANTX1N5806URS	JANTXV1N5806URS	JANS1N5806URS
JAN1N5807URS	JANTX1N5807URS	JANTXV1N5807URS	JANS1N5807URS
JAN1N5809URS	JANTX1N5809URS	JANTXV1N5809URS	JANS1N5809URS
JAN1N5811URS	JANTX1N5811URS	JANTXV1N5811URS	JANS1N5811URS
	Devices in a UMC package		
JAN1N5802UMC	JANTX1N5802UMC	JANTXV1N5802UMC	JANS1N5802UMC
JAN1N5804UMC	JANTX1N5804UMC	JANTXV1N5804UMC	JANS1N5804UMC
JAN1N5806UMC	JANTX1N5806UMC	JANTXV1N5806UMC	JANS1N5806UMC

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T02:20Z
Check the source to verify that this is the current version before use.

6.5.2 List of PINs for un-encapsulated devices. The following is a list of possible PINs available on this specification sheet for unencapsulated die. The qualified JANHC and JANKC suppliers with the applicable letter version (example, JANHCE1N5802) will be identified on the QML.

PIN		Manufacturers	
	43611, 52GC4	13409	34156
1N5802	JANHCE1N5802, JANKCE1N5802	JANHCF1N5802, JANKCF1N5802 JANHCH1N5802 JANKCH1N5802	JANHCG1N5802, JANKCG1N5802
1N5804	JANHCE1N5804, JANKCE1N5804	JANHCF1N5804, JANKCF1N5804 JANHCH1N5804 JANKCH1N5804	JANHCG1N5804, JANKCG1N5804
1N5806	JANHCE1N5806, JANKCE1N5806	JANHCF1N5806, JANKCF1N5806 JANHCH1N5806 JANKCH1N5806	JANHCG1N5806, JANKCG1N5806
1N5807	JANHCE1N5807, JANKCE1N5807	JANHCF1N5807, JANKCF1N5807 JANHCH1N5807 JANKCH1N5807	
1N5809	JANHCE1N5809, JANKCE1N5809	JANHCF1N5809, JANKCF1N5809 JANHCH1N5809 JANKCH1N5809	
1N5811	JANHCE1N5811, JANKCE1N5811	JANHCF1N5811, JANKCF1N5811 JANHCH1N5811 JANKCH1N5811	

6.6 Applications data.

6.6.1 Half-sine-wave application with 1N5807, 1N5809, and 1N5811 (axial leaded and US). For a printed board mounting example with FR4 base material where the full 3 amp I_O rating (half-sine-wave) is used at a T_J of 175°C and ambient temperature of 55°C, the following steps guide the user in what the printed board copper mounting pad size will need to be with 1 ounce, 2 ounce, and 3 ounce copper for 1N5807(US), 1N5809(US), and 1N5811(US). For axial leaded, the lead length for mounting will be .187 inch (4.76 mm) or less from body to entry point on PCB surface. See 6.6.3 for the smaller example devices 1N5802 to 1N5806 or 1N5802US to 1N5806US.

a. Use the I_O versus P_O curve on figure 14 to look up 3 amps (X-axis) and follow up to the T_J =175°C curve (lower) for 2.30 watts.

b. Calculate maximum thermal resistance needed (175°C – 55°C) / 2.30 W = 52 °C/W.

c. Look up thermal resistance of 52 °C/W on Y-axis using a thermal resistance versus copper mounting pad area plot on one of the three curves on figure 15 for different weights of copper foil and then intersect curve horizontally to get the answer. These curves assume still air and horizontal printed board position.

d. In this example, the copper mounting pad sizes for the different copper foil weights would be as follows:

1) .50 in^2 (322.6 mm^2) for 1 ounce copper foil.
2) .30 in^2 (193.5 mm^2) for 2 ounce copper foil.
3) .20 in^2 (129.0 mm^2) for 3 ounce copper foil.

e. Add a conservative guard-band to the copper mounting pad size (larger) to keep T_J below 175°C.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T02:20Z
Check the source to verify that this is the current version before use.

6.6.2 Square-wave application with 1N5807, 1N5809, and 1N5811 (axial leaded and US package). For a printed board mounting example with FR4 base material to support a 1 amp I_O square wave switching at a 0.50 duty factor (50 percent duty cycle) at T_J=125°C and ambient temperature of 55°C, the following steps guide the user in what the printed board copper mounting pad size will need to be with 1 ounce, 2 ounce, and 3 ounce copper.

a. Find size of copper mounting pads on standard FR4 base material to support operation at 1 amp I_O square wave switching at a 0.50 duty factor (50 percent duty cycle) at T_J = 125°C with T_A = 55°C.

b. Calculate peak I_F = 1 A / 0.50 duty factor = 2 amps.

c. Use the V_F versus I_F curve on figure 16 to look up I_F = 2 A (Y-axis) and follow across to the T_J = 125°C curve (middle) for V_F = 0.65 V.

d. Calculate power = $I_F * V_F *$ duty factor = $2 * 0.65 * 0.50 = 0.65$ W.

e. Calculate maximum thermal resistance needed (125°C - 55°C) / 0.65 W = 107 °C/W.

f. Look up thermal resistance of 107°C/W on the Y-axis using a thermal resistance versus copper mounting pad area plot on one of the three curves on figure 16 for different weights of copper foil cladding and then intersect curve horizontally to get the answer. Curves assume still air and horizontal printed board position.

g. In this example, the copper mounting pad sizes for the different copper foil weights would be as follows:
   1) .058 in^2 (37.42 mm^2) for 1 ounce copper foil.
   2) .038 in^2 (24.52 mm^2) for 2 ounce copper foil.
   3) .024 in^2 (15.48 mm^2) for 3 ounce copper foil.

h. A conservative pad guard-band is optional since T_J is only 125°C.

   NOTE: Multilayer printed boards or forced air cooling will improve performance. Closed confinement of the printed boards or will do the opposite. Use sound thermal management.

6.6.3 Half-sine-wave application with 1N5802, 1N5804, 1N5806 (axial leaded and US package). For a PCB mounting example with FR4 base material where the full 1 amp I_O rating (half-sine-wave) is used at a T_J of 175°C and ambient temperature of 55°C, the following steps guide the user in what the PCB copper mounting pad size will need to be with 1 ounce, 2 ounce, and 3 ounce copper for a 1N5802US, 1N5804US, and 1N5806US. For axial-leaded, the lead length for mounting will be .187 inch (4.76 mm) or less from body to entry point on PCB surface.

a. Use the I_O versus P_O curve on figure 17 to look up 1 amp (X-axis) and follow up to the T_J = 175°C curve (lower) for 0.78 watts.

b. Calculate maximum thermal resistance needed (175°C - 55°C) / 0.78 W = 154 °C/W.

c. Locate the thermal resistance of 154 °C/W on Y-axis using a thermal resistance versus copper mounting pad area plot on one of the three curves on figure 18 for different weights of copper foil and then intersect curve horizontally to get the answer. These curves assume still air and horizontal printed board position.

d. In this example, the copper mounting pad sizes for the different copper foil weights would be as follows:

   1) .013 in^2 (8.39 mm^2) for 1 ounce copper foil.
   2) .0080 in^2 (5.161 mm^2) for 2 ounce copper foil.
   3) .0053 in^2 (3.42 mm^2) for 3 ounce copper foil.

e. Add a conservative guard-band to the copper mounting pad size (larger) to keep T_J below 175°C.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T02:20Z
Check the source to verify that this is the current version before use.

6.6.4 Square-wave application with 1N5802US, 1N5804US, 1N5806US. For a PCB mounting example with FR4 base material to support a 0.5 amp I_O square wave switching at a 0.50 duty factor (50 percent duty cycle) at T_J=125°C and ambient temperature of 55°C, the following steps guide the user in what the PCB copper mounting pad size will need to be with 1 ounce, 2 ounce, and 3 ounce copper.

a. Find size of copper mounting pads on standard FR4 base material to support operation at 0.5 Amp I_O square wave switching at a 0.50 duty factor (50 percent duty cycle) at T_J = 125°C with T_A = 55°C.

b. Calculate peak I_F = 0.5A / 0.50 duty factor = 1 amp.

c. Use the V_F versus I_F curve on figure 19 to look up I_F = 1 A (Y-axis) and follow across to the T_J = 125°C curve (middle) for V_F = 0.70 V.

d. Calculate power = $I_F * V_F *$ duty factor = $2 * 0.70 * 0.50 = 0.70$ W.

e. Calculate maximum thermal resistance needed (125°C - 55°C) / 0.70 W = 100°C/W.

f. Locate the thermal resistance of 100°C/W on the Y-axis using a thermal resistance versus copper mounting pad area plot on one of the three curves on figure 18 for different weights of copper foil cladding and then intersect curve horizontally to get the answer. Curves assume still air and, horizontal printed board position.

g. In this example, the. copper mounting pad sizes for the different copper foil weights would be as follows:

1) .084 in^2 (54.19 mm^2) for 1 ounce copper foil.
2) .051 in^2 (32.90 mm^2) for 2 ounce copper foil.
3) .034 in^2 (21.94 mm^2) for 3 ounce copper foil.

h. A conservative pad guard-band is optional since T_J is only 125°C.

NOTE: Multilayer PCBs or, forced air cooling will improve performance. Closed confinement of the printed boards or will do the opposite. Use sound thermal management.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T02:20Z
Check the source to verify that this is the current version before use.





FIGURE 14. Rectifier power P_O versus I_O (average forward current) for 1N5807US, 1N5809US, and 1N5811US.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T02:20Z
Check the source to verify that this is the current version before use.



NOTES:
1. Base material type is FR4.
2. Copper foil weights are 1, 2, and 3 ounce per ft^2.
3. PCB mounting is horizontal in still air.

FIGURE 15. Thermal resistance versus pad area (for each pad) for 1N5807US, 1N5809US, and 1N5811US.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T02:20Z
Check the source to verify that this is the current version before use.




FIGURE 16. Forward voltage versus forward current for 1N5807US, 1N5809US, and 1N5811US.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T02:20Z
Check the source to verify that this is the current version before use.





FIGURE 17. Rectifier power P_O versus I_O (average forward current) for 1N5802US, 1N5804US, and 1N5806US.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T02:20Z
Check the source to verify that this is the current version before use.



NOTES:
1. Base material type is FR4.
2. Copper foil weights are 1, 2, and 3 ounce.
3. PCB mounting is horizontal in still air.

FIGURE 18. Thermal resistance versus pad area (for each pad) for 1N5802US, 1N5804US, and 1N5806US.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T02:20Z
Check the source to verify that this is the current version before use.




FIGURE 19. Forward voltage versus forward current for 1N5802US, 1N5804US, and 1N5806US.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T02:20Z
Check the source to verify that this is the current version before use.

6.7 Request for new types and configurations. Requests for new device types or configurations for inclusions in this specification sheet should be submitted to: DLA Land and Maritime, ATTN: VAC, Post Office Box 3990, Columbus, OH 43218-3990 or by electronic mail at Semiconductor@dla.mil or by facsimile (614) 693-1642 or DSN 850-6939.

6.8 Amendment notations. The margins of this specification are marked with vertical lines to indicate modifications generated by this amendment. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content irrespective of the marginal notations and relationship to the previous issue.

Custodians:
Army − CR
Navy − SH
Air Force − 85
NASA − NA
DLA − CC

Review activities:
Army − AR, AV, MI, SM
Navy − AS, MC
Air Force − 19, 71

Preparing activity:
DLA − CC

(Project 5961-2023-010)

NOTE: The activities listed above were interested in this document as of the date of this document. Since organizations and responsibilities can change, you should verify the currency of the information above using the ASSIST Online database at https://assist.dla.mil.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T02:20Z
Check the source to verify that this is the current version before use.