MIL-C-47127A(MI)
18 November 1983
SUPERSEDING
MIL-C-47127(MI)
24 May 1974

MILITARY SPECIFICATION

CLOTH, POLYESTER FABRIC, CHLOROSULFONATED POLYETHYLENE COATED, FLAME RESISTANT

This apecification is approved for use by the US Army Missile Command, Department of the Army, and is available for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This specification covers one type of flame resistant, chlorosulfonated polyethylene coated polyester fiber cloth.

* 1.2 Military part number. The military part number shall consist of the letter B, the basic number of this specification, and a dash number specifying the number of total yards required.

Example:	B	47127	-	200
		Basic number of MIL SPEC		Number of total yards (see 3.2.2.2)

* 2. APPLICABLE DOCUMENTS

* 2.1 Government documents.

* 2.1.1 Specifications, standards, and handbooks. Unless otherwise specified, the following specifications, standards, and handbooks of the issue listed in that issue of the Department of Defense Index of Specifications and Standards (DoDISS) specified in the solicitation form a part of this specification to the extent specified therein.

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: Commander, US Army Missile Command, ATTN: DRSMI-RSDS, Redstone Arsenal, AL 35898 by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) at the end of this document or by letter.

FSC 8305

Source: https://assist.dla.mil -- Downloaded: 202610-22T07:51Z
Check the source to verify that this is the current version before use.

SPECIFICATIONS

Federal

*	PPP-P-1136	Packaging and Packing of Coated (Plastic Rubber) and Laminated Fabrics

Military

	MIL-A-5540	Adhesive, Polychlorophrene
	MIL-L-6082	Lubricating Oil, Aircraft Reciprocating Engine (Piston)
	MIL-C-20696	Cloth, Coated, Nylon, Waterproof

STANDARDS

Federal

	FED-STD-191	Textile Test Methods
	FED-STD-595	Color

Military

	MIL-STD-105	Sampling Procedures and Tables For Inspection by Attributes
	MIL-STD-129	Marking for Shipment and Storage
*	MIL-STD-1188	Commercial Packaging of Supplies and Equipment
*	MIL-STD-1487	Glossary of Cloth Coating Imperfections

* (Copies of specifications, standards, handbooks, drawings, and publications required by manufacturers in connection with specific acquisition functions should be obtained from the contracting activity or as directed by the contracting officer.)

* 2.2 Other publications. The following document(s) form a part of this specification to the extent specified herein. The issues of the documents which are indicated as DoD adopted shall be the isue listed in the current DoDISS and the supplement thereto, if applicable.

Source: https://assist.dla.mil -- Downloaded: 20260-22T07:51Z
Check the source to verify that this is the current version before use.

American Society for Testing and Materials

ASTM D 518	Resistance to Surface Cracking of Stretched Rubber Compounds, Test for
ASTM D 1149	Accelerated Ozone Cracking of Vulcanized Rubber, Test for

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, Pennsylvania 19103.)

* Industry association specifications and standards are generally available for reference from libraries. They are also distributed among technical groups and using Federal agencies.

* 2.3 Order of precedence. In the event of a conflict between the text of this specification and the references cited herein, the text of this specification shall take precedence.

3. REQUIREMENTS

* 3.1 First Article sample. Unless otherwise specified (see 6.2), a first article sample shall meet all the requirements of this specification.

3.2 Materials.

3.2.1 Composition and construction.

3.2.1.1 Composition. The material shall consist of a fabric woven of 220 denier polyster yarn which has been thoroughly impregnated by coating with chlorosulfonated polyethylene elastomer.

3.2.1.2 Construction. The construction of the base fabric shall be a polyester yarn woven in 2 by 2 basket weave configuration. The coating material shall be applies as a balanced coating on both sides of the base fabric.

3.2.2 Dimensions.

3.2.2.1 Width. Unless otherwise specified, the overall width of the coated cloth shall be 39 inches plus 1 inch, minus zero inches.

3.2.2 Length of roll. Unless otherwise specified, the coated cloth shall be furnished in rolls containing 100 to 125 yards. There shall be not more than 2 pieces in each roll, and each piece shall contain not less than 40 yards.

3.2.3 Color. The color of the coated cloth shall be olive drab Color Number 34087 in accordance with FED-STD-595.

Source: https://assist.dla.mil -- Downloaded: 202640-22T07:51Z
Check the source to verify that this is the current version before use.

3.2.4 Weight. The weight of the coated cloth shall be 16 ounces plus or minus 0.5 ounce per square yard.

3.2.5 Thread count. The thread count of the coated cloth shall be as specified in Table I.

Table I. Thread count

Thread count	Ends per inch minimum
Warp	67
Filling	68

3.2.6 Coating adhesion. The coating adhesion of the coated cloth shall be not less than 5 pounds per inch.

3.3 Performance characteristics.

3.3.1 Breaking strength. The breaking strength, Grab Method, of the coated cloth shall be as specified in Table II.

Table II. Breaking strength

Breaking strength	Pounds per inch, minimum
Warp	275
Filling	275

3.3.2 Tearing strength. The tearing strength, Tongue Method, shall be as specified in Table III.

Source: https://assist.dla.mil -- Downloaded: 202640-22T07:51Z
Check the source to verify that this is the current version before use.

Table III. Tearing strength

Tearing strength	Pounds, minimum
Warp	12
Filling	12

3.4 Environmental conditions.

3.4.1 Blocking. Blocking at 77 degrees plus or minus 3 degrees Celsius (C) (170 degrees plus or minus 5 degrees Fahrenheit (F)), shall be not more than the scale rating of 3.

3.4.2 Accelerated aging. The coated cloth shall show no signs of becoming stiff or brittle, nor shall the coating become soft or tacky.

3.4.3 Flame resistance. The coated cloth shall have a maximum flaming time of 10 seconds and a maximum char length of 5 inches.

3.4.4 Resistance to water leakage. The coated cloth shall withstand a static head of 20 inches of water for not less than 10 minutes with a leakage of not more than 5 milliliters of water through an abraded portion. The unbraided portion shall show no signs of leakage.

3.4.5 Low temperature flexibility. The coating shall show no signs of cracking, breaking, or flaking.

3.4.6 Oil resistance. The coated cloth shall not leak.

3.4.7 Ozone resistance. There shall be no cracking of the coated material visible under 7 power magnification.

3.4.8 Resistance to accelerated weathering. The coated cloth shall not lose more than 20 percent of its original breaking strength when exposed to accelerated weathering. It shall not crack when folded sharply on itself nor shall it show signs of blooming.

3.4.9 Mildew resistance. The breaking strength of the coated cloth shall not decrease more than 10 percent upon exposure to mildew.

* 3.5 Workmanship. The finished coated cloth shall conform to the quality of product established by this document, and the occurrence of defects shall not exceed the applicable acceptable quality levels.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T07:51Z
Check the source to verify that this is the current version before use.

4. QUALITY ASSURANCE PROVISIONS

* 4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspection set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

* 4.2 First article inspection. When specified in the contractual document (see 6.2), a sample consisting of 2 square yards of coated cloth manufactured under the same conditions as those proposed for subsequent production, shall be subjected to First Article inspection. Accomplishment of First Article inspection shall be as specified herein. Subsequent units will not be considered for acceptance until Government approval of the First Article sample has been obtained. Units subjected to First Article inspection shall have successfully passed acceptance inspection. Testing of the First Article sample, to determine compliance with the characteristics listed in Table IV, shall be conducted in accordance with the corresponding test paragraphs.

* Table IV. First Article inspection

Characteristic	Requirement source	Test paragraph
Thread count	3.2.5	4.5.4.5
Coating adhesion	3.2.6	4.5.4.6
Blocking	3.4.1	4.5.5.1
Accelerated aging	3.4.2	4.5.5.2
Resistance to water leakage	3.4.4	4.5.5.4
Low temperature flexibility	3.4.5	4.5.5.5
Oil resistance	3.4.6	4.5.5.6
Ozone resistance	3.4.7	4.5.5.7
Resistance to accelerated weathering	3.4.8	4.5.5.8
Mildew resistance	3.4.9	4.5.5.9

Source: https://assist.dla.mil -- Downloaded: 202610-22T07:51Z
Check the source to verify that this is the current version before use.

* 4.3 End item examination.

4.3.1 Yard-by-yard examination. The required yardage of each roll in the sample shall be examined on one side only; however, the side shall be alternated for every other roll examined. Visual defects shall be as listed below and as defined in MIL-STD-1487. The same yardage shall be give a through-lighting inspection for pinholes and thinly coated areas. The through-lighting inspection shall be performed in accordance with MIL-STD-1487. The defects found shall be counted regardless of their proximity to each other, except where two or more defects represent a single local condition of the cloth, in which case only the more serious defect shall be counted. A continuous defect shall be counted as one defect for each warpwise yard or fraction thereof in which it occurs. The sample unit shall be 1 linear yard. The inspection level shall be level II of MIL-STD-105 and the acceptable quality level (AQL), expressed in terms of defects per hundred units, shall be 4.0 for major defects and 10.0 for total (major and minor combined) defects. The number of rolls from which the sample is to be selected shall be in accordance with Table V. An approximately equal number of yards shall be examined from each roll in the sample.

Defect	Classification	
	Major	Minor
Any cut, hole, tear, scratch, or abrasion mark that results in baring the base cloth.	X	
Any pinhole.	X	
Any surface scratch or abrasion mark that does not result in baring the base cloth.		X
Any uncoated area.	X	
Any pit, blister, tunnel, or delamination of coating.	X	
Any lump or heavily coated area.		X
Any crease or wrinkle resulting in doubling or adhesion of surfaces that cannot be corrected by manual pressure.	X	
Uneven coating, thin area where coating is missing or noticeably thinner.	X	
Any light area or window due to absence or poor blending of pigmentation.		X
Cloth edges rolled, curled, folded, doubled, scalloped or wavy precluding a flat lay of the cloth.	X	
Any spot, stain, or streak more than one inch in combined directions. 1/	X	
Width less than minimum specified.	X	
Any objectionable odor. 2/		X
Any tackiness (coating will adhere and not unroll readily).	X	
Deposition of coating not as required, i.e., not balanced or unbalanced as specified.	X	

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T07:51Z
Check the source to verify that this is the current version before use.

1/ Clearly visible at normal inspection distance (approximately 3 feet).

2/ Odors of chemicals used in coating compounds shall not be regarded as objectionable.

Table V. Sample size and acceptance criteria

Lot size (yards)	Sample size (rolls)	Maximum number of defects acceptable in sample 2/
Up to 1200 inclusive 1/	3	0
1201 up to and including 3200	5	0
3201 up to and including 10,000	8	0
10,001 up to and including 35,000	13	0
35,001 up to and including 150,000	20	1
150,001 and over	32	2

1/ If a lot contains fewer than three rolls, each roll in the lot shall be examined.

2/ Applicable to length examination only (see 4.3.2.1).

* 4.3.2 Length examination.

* 4.3.2.1 Individual rolls. Each individual roll in the sample shall be examined for the defects listed below. If the total number of defects in the sample rolls exceed the maximum number specified in the Table V, the lot shall be rejected.

Any roll containing more than two pieces.
Any piece in roll less than 40 yards.
Any roll with a total length of less than 100 yards or more than 125 yards.
Any roll with a total length more than 2 yards less than marked on ticket.

* 4.3.2.2 Total yardage in sample. The rolls examined shall be those selected for examination of individual rolls as specified in 4.3.2.1. The lot shall be unacceptable if the total of the actual gross lengths of the rolls in the sample is less than the total gross lengths marked on the roll tickets.

* 4.4 Quality conformance inspection.

* 4.4.1 Sampling for acceptance inspection. When sampling for acceptance inspection is specified, it shall be conducted in accordance with MIL-STD-105, at an acceptable quality level (AQL) of 4.0 percent defective.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T07:51Z
Check the source to verify that this is the current version before use.

* 4.4.2 Lot formation. A lot shall consist of all the material manufactured in one continuous operation by the same process, by the same manufacturer in accordance with this specification and submitted for inspection at one time.

* 4.4.3 Acceptance inspection. Acceptance inspection of the sample specified in 4.4.1 to determine compliance with the characteristics specified in Table VI, shall be conducted in accordance with the corresponding test and inspection paragraphs.

Table VI. Acceptance inspection

Characteristic	Requirement Source	Test and inspection paragraph
Composition and construction	3.2.1	4.5.4.1
Dimensions	3.2.2	4.5.4.2
Color	3.2.3	4.5.4.3
Weight	3.2.4	4.5.4.4
Breaking strength	3.3.1	4.5.4.7
Tearing strength	3.3.2	4.5.4.8
Flame resistance	3.4.3	4.5.5.3
Packaging and packing	5.1	4.6
Marking	5.2	4.6

4.5 Test methods and procedures.

4.5.1 Test conditions. Unless otherwise specified herein, the following conditions shall be used as a basis to establish performance requirements:

a. Temperature, room ambient (16 degrees to 32 degrees C (60 degrees to 90 degrees F)).

b. Altitude, facility ground.

c. Humidity, facility ambient up to 95 percent relative humidity.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T07:51Z
Check the source to verify that this is the current version before use.

* 4.5.2 Test sequence. Test sequence within each classification of inspection (first article or acceptance) shall be at the option of the supplier.

* 4.5.3 Test specimen preparation. Test specimens shall be prepared from the sample selected as specified in 4.4.1. The size and the method of preparation of test specimens shall be as specified in the test method paragraphs.

4.5.4 Tests.

4.5.4.1 Composition and construction. The composition shall be certified by the supplier and the construction shall be examined visually to established compliance with 3.2.1.

4.5.4.2 Dimensions. The coated fabric shall be measured by a standard scale graduated to read within 0.1 inch to established compliance with 3.2.2.

4.5.4.3 Color. A specimen of the coated cloth, 1 by 3 inches minimum, shall then be compared with the applicable standard in FED-STD-595 to determine compliance with 3.2.3. Color comparison shall be made under natural (north sky) daylight or artificial daylight daylight having a color temperature of 7500 degrees Kelvin.

4.5.4.4 Weight. Testing for weight shall be in accordance with FED-STD-191, Method 5041, to determine compliance with 3.2.4.

4.5.4.5 Thread count. Testing for thread count shall be in accordance with FED-STD-191, Method 5050.1, to determine compliance with 3.2.5.

4.5.4.6 Coating adhesion. The coating adhesion shall be determined in accordance with FED-STD-191, Method 5970, using an adhesive conforming to MIL-A-5540, Class 3, to prepare the specimens, and shall conform to 3.2.6.

4.5.4.7 Breaking strength. The test for breaking strength shall be conducted in accordance with FED-STD-191, Method 5100, grab method, to determine compliance with 3.3.1.

4.5.4.8 Tearing strength. The test for tearing strength shall be conducted in accordance with FED-STD-191, Method 5134, tongue method, to determine conformance with 3.3.2.

4.5.5 Environmental tests.

4.5.5.1 Blocking. The test for blocking shall be conducted in accordance with FED-STD-191, Method 5872, except that the material shall be exposed to 77 degrees plus or minus 3 degrees C (170 degrees plus or minus 5 degrees F) for a minimum of 2 hours. Test results shall conform to 3.4.1.

Source: https://assist.dla.mil -- Downloaded: 202640-22T07:51Z
Check the source to verify that this is the currentversion before use.

4.5.5.2 Accelerated aging. Resistance to accelerated aging shall be determined in accordance with FED-STD-191, Method 5850. The material specimen shall be heated in the oven for 70 hours plus or minus 15 minutes at 125 degrees plus or minus 2 degrees C (257 degrees plus or minus 3 degrees F) to determine compliance with 3.4.2. The coating shall be examined for signs of becoming soft and tacky by folding the specimen so that it touches itself.

4.5.5.3 Flame resistance. The test for flame resistance shall be in accordance with FED-STD-191, Method 5903-T, to determine conformance to 3.4.3.

4.5.5.4. Resistance to water leakage.

4.5.5.4.1 Test specimens. The test specimens of the size specified in FED-STD-191, Method 5516, shall be prepared by abrading on both sides as follows:

a. Place the specimen on a flat surface.

b. Over the specimen, place a metal block, 2 inches square, weighing 8 ounces plus or minus 0.1 ounce, with a grade 1/0 garnet paper cemented to the bottom side of the block.

c. Grasp the block at the base with the thumb and the index finger and pull gently, without increasing the pressure on the specimen, back and forth 5 strokes each way in the filling direction of the specimen.

d. Turn the specimen over and abrade in the same way on the other side.

4.5.5.4.2 Test procedure. The resistance to water leakage shall be determined with the apparatus described in Method 5516 of FED-STD-191, except that the temperature of water shall be 27 degrees plus or minus 6 degrees C (80 degrees plus or minus 10 degrees F). The specimens shall be placed across the center line of the clamping head of the apparatus so that the center of the abraded area shall coincide with the center of the exposed part of the specimen. The water height shall be raised to 20 inches to determine compliance with 3.4.4.

4.5.5.5. Low temperature flexibility. Low temperature flexibility shall be determined in accordance with MIL-C-20696. The specimens shall be stored at minus 40 degrees plus or minus 1 degree C (minus 40 degrees plus or minus 2 degrees F). They shall then be bent sharply over a 0.25 inch diameter rod and examined for compliance with 3.4.5.

* 4.5.5.6 Oil resistance. Oil resistance shall be determined using oil in accordance with MIL-L-6082 for conformity to 3.4.6.

4.5.5.7 Ozone resistance. Ozone resistance shall be determined in accordance with ASTM D 1149, using a specimen mounted in accordance with procedure B

Source: https://assist.dla.mil -- Downloaded: 202610-22T07:51Z
Check the source to verify that this is the current version before use.

of ASTM D 518. The ozone concentration shall be 50 plus or minus 5 parts per hundred million at the temperature of 40 degrees plus or minus 2 degrees C (104 degrees plus or minus 3 degrees F), and the duration of exposure shall be 7 days plus or minus 1 hour. The specimen shall be examined visually to determine compliance with 3.4.7.

4.5.5.8 Resistance to accelerated weathering. Six specimens, 4 by 6 inches minimum, with the long dimension in the warp direction, and 6 specimens, 4 by 6 inches minimum, with the long dimension in the filling direction, shall be tested in accordance with Method 5804 of FED-STD-191. The specimens shall be exposed in the accelerated weathering unit in accordance with the testing procedures for 150 hours plus or minus 0.5 hour. After exposure, the specimens shall be removed and allowed to condition for at least 24 hours. One specimen with the long dimension in the warp direction and one with the long dimension in the filling direction shall be folded by hand sharply upon itself and visually inspected for cracking. The remaining specimens shall then be tested for breaking strength in accordance with Method 5104.1 of FED-STD-191. Prior to determining the breaking strength after weathering, the samples shall be cycled as follows:

a. 2 hours minimum at 82 degrees plus or minus 3 degrees C (180 degrees plus or minus 5 degrees F).

b. 40 hours to 48 hours at 65 percent plus or minus 2 percent relative humidity, 22 degrees plus or minus 1 degree C (72 degrees plus or minus 2 degrees F).

Compliance with 3.4.8 shall be determined.

4.5.5.9 Mildew resistance. The mildew resistance of the coated cloth shall be determined in accordance with Method 5762 of FED-STD-191. The specimen shall be buried in the sand in the horizontal position and shall be kept there for at least 2 weeks before determining compliance with 3.4.9.

* 4.6 Packaging, packing, unitization and marking inspection. The inspection shall ascertain that the packaging, packing, unitization and marking of the material conforms to section 5.

* 5. **PACKAGING**

* 5.1 Preservation, packing, unitization and marking. Level A, B, or Industrial (see 6.2).

* 5.1.1 Level A or B. Packaging and packing shall be in accordance with requirements of PPP-P-1136.

* 5.1.2 Industrial. Packaging and packing shall be in accordance with requirements of MIL-STD-1188.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T07:51Z
Check the source to verify that this is the current version before use.

* 5.2. Marking.

* 5.2.1 Level A or B. Marking shall be in accordance with MIL-STD-129 and the Textile Fiber Products Identification Act. Additional markings shall include, but not be limited to the following:

a. Manufacturer's name and address.

b. Manufacturer's designation.

c. Lot number or roll number.

d. Date of manufacture.

e. Number of this specification.

* 5.2.2 Industrial. Marking shall be in accordnce with MIl-STD-1188. Additional markings shall include, but not be limited to the following:

a. Manufacturer's name and address.

b. Manufacturer's designation.

c. Lot number or roll number.

d. Date of manufacture.

e. Number of this specification.

6. NOTES

6.1 Intended use. The cloth covered by this specification is intended for use in equipment covers and other support equipment applications where high strength, weather and flame resistance properties are desired.

6.2 Ordering data. Procurement documents should specify the following:

a. Title, number, and date of this specification.

* b. Military part number (see 1.2) including total number of yards required (see 3.2.2.2).

c. Whether a First Article sample is required (see 3.1), and if so, pertinent details.

* d. Width and length of roll if other than specified (see 3.2.2.2).

e. Requirement for certification of composition (see 4.5.4.1).

* f. Selection of applicable level of preservation, packaging, and packing (see 5.1).

Source: https://assist.dla.mil -- Downloaded: 202610-22T07:51Z
Check the source to verify that this is the current version before use.

* 6.3 Changes from previous issue. The margins of this specification are marked with an asterisk to indicate where changes were made. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content irrespective of the marginal notations and relationship to the last previous issue.

Custodian:
Army - MI

Preparing Activity:
Army - MI

Project No. 8305-A858

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T07:51Z
Check the source to verify that this is the current version before use.

(TO DETACH THIS FORM, CUT ALONG THIS LINE.)

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

(See Instructions – Reverse Side)

1. DOCUMENT NUMBER	2. DOCUMENT TITLE

3a. NAME OF SUBMITTING ORGANIZATION	4. TYPE OF ORGANIZATION *(Mark one)*
	☐ VENDOR
b. ADDRESS *(Street, City, State, ZIP Code)*	☐ USER
	☐ MANUFACTURER
	☐ OTHER *(Specify)*: _____

5. PROBLEM AREAS

a. Paragraph Number and Wording:

b. Recommended Wording:

c. Reason/Rationale for Recommendation:

6. REMARKS

7a. NAME OF SUBMITTER *(Last, First, MI)* – Optional	b. WORK TELEPHONE NUMBER *(Include Area Code)* – Optional
c. MAILING ADDRESS *(Street, City, State, ZIP Code)* – Optional	8. DATE OF SUBMISSION *(YYMMDD)*

DD FORM 82 MAR 1426 PREVIOUS EDITION IS OBSOLETE.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T07:51Z
Check the source to verify that this is the current version before use.

INSTRUCTIONS: In a continuing effort to make our standardization documents better, the DoD provides this form for use in submitting comments and suggestions for improvements. All users of military standardization documents are invited to provide suggestions. This form may be detached, folded along the lines indicated, taped along the loose edge *(DO NOT STAPLE)*, and mailed. In block 5, be as specific as possible about particular problem areas such as wording which required interpretation, was too rigid, restrictive, loose, ambiguous, or was incompatible, and give proposed wording changes which would alleviate the problems. Enter in block 6 any remarks not related to a specific paragraph of the document. If block 7 is filled out, an acknowledgement will be mailed to you within 30 days to let you know that your comments were received and are being considered.

NOTE: This form may not be used to request copies of documents, nor to request waivers, deviations, or clarification of specification requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document*(s)* or to amend contractual requirements.

(Fold along this line)

(Fold along this line)

DEPARTMENT OF THE ARMY

NO POSTAGE NECESSARY IF MAILED IN THE UNITED STATES

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300

BUSINESS REPLY MAIL
FIRST CLASS PERMIT NO. 12062 WASHINGTON D. C.
POSTAGE WILL BE PAID BY THE DEPARTMENT OF THE ARMY

Commander
US Army Missile Command
ATTN: DRSMI-RSDS
Redstone Arsenal, AL 35898

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T07:51Z
Check the source to verify that this is the current version before use.