A-A-0051921(DM)
21 March 1987

# INTERIM COMMERCIAL ITEM DESCRIPTION

## INFUSION SET, SCALP VEIN, 25 Gage

The General Services Administration has authorized the use of this interim commercial item description which was developed by the Defense Personnel Support Center, Directorate of Medical Materiel, DPSC-RST, 2800 South 20th Street, Philadelphia, PA, 19101, based upon currently available technical information.

This interim commercial item description covers a single type of pediatric scalp vein infusion set used in administering medication.

Salient characteristics:

Materials. The cannulae shall be made of Type 304 stainless steel in accordance with ASTM F899. The tubing shall be made of plasticized polyvinyl chloride and conform to Class IV Plastic requirements of the USP. The tubing shall be clear or clear with a frosted surface. The wings shall be plasticized polyvinylchloride. The hub shall be made of polyvinylchloride, polypropylene or nylon. The protective cap on the hub shall be made of polyethylene or polypropylene. The needle shall be protected with a polyethylene sleeve or cap.

Construction. The needle shall be a 25 gage thin wall needle 3/8 inch long. The bore of the needle shall be 0.0110 to 0.0130 inch. The tubing length shall be 3-1/2 inches and have an ID of 0.040 inch. The tubing volume shall be 0.17 ± 0.03 ml. The set shall have two wings permanently attached to the proximal end of the needle. The wing spread shall be 1-1/8 inches by 3/8 inch by 0.040 inch thick. Tolerances unless otherwise stated are ± 10%. The hub shall have a Luer taper in accordance with ANSI/HIMA MD70.1. The set with the needle stoppered by putting the tip into a piece of rubber shall withstand 20 psig air pressure for one minute without leakage of air. This test shall be conducted with the hub attached to a Luer fitting having a lumen for the air entrance. The entire set shall be submerged in water during the test.

AMSC N/A FSC 6515

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:03Z
Check the source to verify that this is the current version before use.

The tubing shall have a minimum ultimate tensile strength of 2800 psi and ultimate elongation of 250%.

The tubing shall have a 100% modulus of 1000 to 1900 psi determined by the tensile reading at the moment the tubing has been stretched to twice its original length.

A. Sterility test. The infusion set shall be tested for sterility in accordance with the method specified in the USP using inoculated product, inoculated simulated product, or paper spore strip (carrier). Product containing a biological indicator shall be marked or labeled so that it is clearly differentiated from product intended for distribution. The incubation medium for the paper spore strip (carrier) shall be soybean-casein digest. The incubation medium for the inoculated product, or inoculated simulated product shall be fluid thioglycollate or alternative thioglycollate at 30° to 35° C for one half of the specimens and soybean-casein digest at 20° to 25° C for the remaining half of the specimens. The minimum incubation time shall be ten days. Sampling shall be as follows:

| Medium | Paper spore strip | Inoc. Prod. or Inoc. Simulated Prod. |
|---|---|---|
| Soybean-casein digest | S-3* | S-3* |
| Fluid thioglycollate or Alternative thioglycollate | | S-3* |

*Use a minimum of 20 specimens. Acceptance number is zero.

B. Inoculated product or simulated product. For each type of sterilization, the organism used shall be as listed below:

| Type of Sterilization | Organism |
|---|---|
| Steam | B. stearothermophilus |
| Dry Heat | B. stearothermophilus |
| | B. subtilis |
| Ethylene oxide | B. subtilis |
| Gamma radiation | B. pumilus |

The number of viable spores shall be sufficient to provide assurance that the product has been sterilized.



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:03Z
Check the source to verify that this is the current version before use.

C. Inoculated carrier. Inoculated carriers (paper spore strips) if used, shall be in accordance with MIL-S-36586A, Sterilization Test Strip Set, Bacterial Spore. Other paper carriers shall be inoculated to be of equivalent resistance. The method of incubation and number of test units shall be as indicated in A. Sterility test and B. Inoculated product or simulated product. The method of sterilization will control the organism in the spore strip to be tested for as shown in B. NOTE: When an inoculated carrier is chosen, product samples must also be tested as required by the USP and paragraphs A and B.

D. Alternate method. Suppliers conducting sterility tests or designating lots in a manner other than that indicated herein shall submit proof that the alternate method provides equal assurance concerning the sterility of the product. However, all sterility tests shall be conducted using biological indicators. Requests for approval of any alternate method of testing for sterility shall be made to the Contracting Officer, and approval obtained before employment of the alternate method on a government contract.

E. Product testing. Testing for sterility of the product after receipt by the government shall be without a biological indicator and in accordance with the USP. The inspection level shall be as stated in paragraph A above.

Workmanship. The set shall be free from defects which detract from its appearance or impair its serviceability.

Unit. Package (PG). One package containing forty infusion set, sterile, as specified, constitutes one unit.

Quality Assurance Provisions.

Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

Records. Records of examinations and tests performed by or for the contractor shall be maintained by the contractor and made available to the Government upon the Government's request, at any time, or from time to time, during the performance of the contract and for a period of three years after delivery of the supplies to which such records relate.



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:03Z
Check the source to verify that this is the current version before use.

Inspection. Inspection, as used herein, is defined as both examination (such as visual or auditory investigation without the use of special laboratory appliances or procedures) and testing (determination by technical means of physical and chemical properties) of the item.

Tests. Tests shall be conducted to determine compliance with specification requirements. Where feasible, the same sample shall be used for the determination of two or more test characteristics.

Sampling for tests. Sampling for tests shall be conducted in accordance with MIL-STD-105 and as specified herein. The unit of product for test purposes shall be one scalp vein infusion set.

Sampling criteria for tests.

| Characteristic | Inspection level | AQL |
|---|---|---|
| Pressure test | S-2 | 1.0 |
| Tensile strength & elongation | S-2 | 1.0 |
| Elastic modulus | S-1 | 1.5 |
| Sterility | (See sterility clauses) | |
| Class IV plastic | S-1 | 0 |

Contractor certification. The contractor shall certify that the product offered meets the salient characteristics of this description and conforms to the producers' own drawings, specifications, standards, and quality assurance practices. The Government reserves the right to require proof of such conformance prior to first delivery and thereafter as may be otherwise provided for under the provisions of the contract.

Regulatory requirements.

Federal Food, Drug and Cosmetic Act. If the product covered by this document has been determined by the U.S. Food and Drug Administration to be under its jurisdiction, the offeror/contractor shall comply, and be responsible for compliance by its subcontractors/suppliers, with the requirements of the Federal Food, Drug and Cosmetic Act, as amended, and regulations promulgated thereunder. In addition, the offeror/contractor shall comply, and be responsible for compliance by its subcontractors/suppliers, with the requirements of all other applicable Federal, State, and local statutes, ordinances, and regulations.

Recovered materials. The offeror/contractor is encouraged to use recovered material in accordance with Public Law 94-580 to the maximum extent practical.



Source: https://assist.dla.mil -- Downloaded: 202640-26T09:03Z
Check the source to verify that this is the currenversion before use.

Preservation, packaging, packing, labeling, and marking. Unless otherwise specified, preservation, packaging, and packing shall be to a degree of protection to preclude damage to containers and/or contents thereof under normal shipping conditions, handling, etc., involving shipment from the supply source to the receiving activity, plus reshipment from receiving activity, and shall conform to applicable carrier's rules and regulations. Intermediate and exterior package quantities and labeling and marking shall be as specified in the contract and/or order.

NOTE: The following National Stock Number is covered by this document:

| NSN | ITEM IDENTIFICATION |
|---|---|
| 6515-01-230-3080 | INFUSION SET, SCALP VEIN |

Ordering data (Intermediate/exterior packaging quantities and labeling and marking must be specified in the contract and/or order).

MILITARY INTERESTS:

Custodians:

Army - MD
Navy - MS
Air Force - 03

Preparing Activity:

DoD-MB

Agent:

DLA-DM

CIVIL AGENCY COORDINATING ACTIVITIES:

VA-OSS
PHS
FDA-MPQAS

Project No. 6515-4007



Source: https://assist.dla.mil -- Downloaded: 202640-26T09:03Z
Check the source to verify that this is the current version before use.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:03Z
Check the source to verify that this is the current version before use.