MILITARY SPECIFICATION

SEALING COMPOUND, JOINT, TWO COMPONENT,

FOR BOLTED ALUMINUM OR STEEL PETROLEUM-STORAGE TANKS

This amendment forms a part of Military Specification MIL-S-14231C, dated 4 August 1971, and is approved for use by all Departments and Agencies of the Department of Defense.

Page 1

2.1, under "SPECIFICATIONS, Federal", delete

"QQ-A-250	- Aluminum and Aluminum Alloy Plate and Sheet; General Specification for.
PPP-B-636	- Box, Fiberboard.
PPP-T-60	- Tape: Pressure-Sensitive Adhesive, Waterproof, for Packaging."

and substitute

"QQ-A-250/2	- Aluminum Alloy 3003, Plate and Sheet.
PPP-B-636	- Boxes, Shipping, Fiberboard.
PPP-T-60	- Tape: Packaging, Waterproof."

Page 2

2.2, under "AMERICAN SOCIETY FOR TESTING AND MATERIALS" delete

"D-381 - Test for Existant Gum by Jet Evaporation."

and substitute

"D-381 - Test for Existant Gum In Fuels by Jet Evaporation."

Delete all reference to D-1084.

2.2, under "UNIFORM CLASSIFICATION COMMITTEE, AGENT", change address from "Room 202, Union Station, 516 West Jackson Boulevard, Chicago, Illinois 60606.)" to "Room 1106, 222 South Riverside Plaza, Chicago, IL 60606.)"

Page 3

3.1, line 1, between "component" and "system" insert: "Polysulfide".

3.5, line 2, delete "40,000 to 80,000" and substitute "50,000 to 110,000".

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T02:57Z
Check the source to verify that this is the current version before use.

Page 4

3.6.8, line 1, delete "aromatic fluid." and substitute "test medium No. 6."

3.6.9, line 1, delete "aromatic fuel." and substitute "test medium No. 6."

3.6.11, delete and substitute:

"3.6.11 Nonvolatile content. The nonvolatile content of the freshly mixed sealing compound, when tested as specified in 4.5.3.13, shall be not less than 90 percent of the total weight of the compound mixed in the ratio as recommended by the supplier."

Page 12

4.5.3.13, delete and substitute:

"4.5.3.13 Nonvolatile content. Five to 10 grams of the freshly mixed sealant compound shall be transferred to a dish approximately 8 centimeters in diameter and 2 centimeters in depth. The weight shall be quickly determined to the nearest milligrams. The sealant shall be heated for 72 plus or minus 2 hours at 158° plus or minus 2° F. (70° plus or minus 1° C.), transferred to a desiccator, cooled to standard conditions, and weighed to the nearest milligram. The percent nonvolatile content shall be calculated as follows:

$$\text{Percent nonvolatile content} = \frac{\text{Final weight of base compound}}{\text{Initial weight of base compound}} \times 100"$$

Custodians:

Army - ME
Navy - YD
Air Force - 84

Review activities:

Army - MR
Air Force - 11

User activities:

Navy - MC, SH

Preparing activity:

Army - ME

Project No. 8030-0407

Source: https://assist.dla.mil -- Downloaded: 202610-18T02:57Z
Check the source to verify that this is the current version before use.