DD-B-00585b (DSA-DM)
29 November 1967
SUPERSEDING
Int. Fed. Spec. DD-B-00585a (DSA-DM)
24 May 1966
and Interim revision of
Fed. Spec. DD-B-585
1 September 1959

INTERIM FEDERAL SPECIFICATION

BOTTLES AND JARS, GLASS, PRESCRIPTION DISPENSING

This interim Federal specification was developed by the Defense Personnel Support Center, 2800 South 20th Street, Philadelphia, Pennsylvania 19101, based upon currently available technical information. It is recommended that Federal agencies use it in procurement and forward recommendations for changes to the preparing activity at the address shown above. The General Services Administration has authorized the use of this interim Federal specification as a valid exception to Federal specification DD-B-585.

1. SCOPE AND CLASSIFICATION

1.1 Scope. This specification covers glass bottles and jars suitable for use in dispensing prescriptions.

1.2 Classification.

1.2.1 Types and styles. Glass bottles and jars shall be of the following types and styles, as specified (see 6.2):

Type I. Bottles, dropper.
Type II. Bottles, screwcap.

Style 1. For liquids.
Style 2. For tablets and capsules.

Type III. Jars, screwcap.

Style 1. For ointments.
Style 2. For powders.

FSC 6530

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:43Z
Check the source to verify that this is the current version before use.

1.2.2 Colors. The color of the bottles and jars shall be as specified (see 6.2):

Colorless
White (opaque or ceramic coated)
Green
Amber
Blue

1.2.3 Capacity. The capacity of the bottles and jars shall be as specified in Table II, III, IV, V, or VI for the applicable type and style (see 6.2).

2. APPLICABLE DOCUMENTS

2.1 Specifications and standards. The following specifications and standards, of the issue in effect on date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein:

SPECIFICATIONS

Federal

PPP-B-636	Box, Fiberboard.
PPP-T-45	Tape, Gummed, Paper, Reinforced and Plain, for Sealing and Securing.
PPP-T-76	Tape, Pressure-Sensitive Adhesive Paper (For Carton Sealing).

STANDARDS

Federal

FED-STD-123	Marking for Domestic Shipment, Civilian Agencies.

Military

MIL-STD-105	Sampling Procedures and Tables for Inspection by Attributes.
MIL-STD-129	Marking for Shipment and Storage.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:43Z
Check the source to verify that this is the current version before use.

(Activities outside the Federal Government may obtain copies of Federal Specifications, Standards, and Handbooks as outlined under General Information in the Index of Federal Specifications and Standards and at the prices indicated in the Index. The Index, which includes cumulative monthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, U.S. Government Printing Office, Washington, D.C. 20402.

(Single copies of this specification and other product specifications required by activities outside the Federal Government for bidding purposes are available without charge at the General Services Administration Regional Offices in Boston, New York, Washington, D.C., Atlanta, Chicago, Kansas City, Mo., Dallas, Denver, San Francisco, Los Angeles, and Seattle, Wash.

(Federal Government activities may obtain copies of Federal Specifications, Standards, and Handbooks and the Index of Federal Specifications and Standards from established distribution points in their agencies.)

(Copies of Military Standards required by contractors in connection with specific procurement functions should be obtained as directed by the contracting officer.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitation for bids or request for proposal shall apply.

The United States Pharmacopeial Convention, Inc.

The Pharmacopeia of the United States of America (U.S.P.)

(Application for copies should be addressed to the Mack Publishing Company, Easton, Pa. 18042.)

The American Society for Testing and Materials

ASTM Designation D 543

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, Pa. 19103.)

U.S. Department of Health, Education, and Welfare

Food and Drug Adminstration (FDA)

Code of Federal Regulations, Title 21, Food and Drugs, Parts 1 to 129

(Application for copies should be addressed to the Superintendent of Documents, U.S. Government Printing Office, Washington D.C. 20402.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:43Z
Check the source to verify that this is the current version before use.

The American Iron and Steel Institute

Tin Mill Products

(Application for copies should be addressed to the American Iron and Steel Institute, 150 East Forty-Second Street, New York, N.Y. 10017.)

3. REQUIREMENTS

3.1 Material. Material shall be of high quality throughout, and shall be as specified herein.

3.1.1 Bottles and jars. The bottles and jars shall be fabricated from glass, in accordance with the applicable requirements for chemical resistance for Type II, Type III, or Type NP glass, as described in the U.S.P., when tested as specified in 4.4.1. Selection of the type of glass to be used shall be made at the option of the procuring activity (see 6.2). Colored oxides such as boron oxide may be used in the fabrication of the glass. For colored bottles, additional color shall be added; for colorless bottles, no additional color shall be added.

3.1.2 Screwcaps. Plastic screwcaps shall be fabricated from molded plastic material suitable for the purpose intended. Metal screwcaps (applicable to Type III, Style 1 jars only) shall be fabricated from No. 50 or No. 75 electrolytic tin plate as specified in "Tin Mill Products".

3.1.3 Liners. The backing for the screwcap liners shall be fabricated from tight-fitting resilient cork, cork composition, pulp, or newsboard mat. The facing for the liners shall be fabricated from vinylite, saran film, or pliofilm, mounted on white sulfite paper. As an alternate, the liner shall be fabricated from rubber, which shall be secured by cement.

3.1.4 Pipets. Pipets for Type I, dropper bottles, shall be fabricated from high grade, clear glass tubing, or from natural-colored, plastic material. Plastic pipets shall be nontoxic, in accordance with FDA food additive regulations 121.2501 and 121.2510. Plastic pipets shall show no decomposition, discoloration, swelling, clouding, bubbling, crazing, or loss of gloss, when exposed to weak acids, in accordance with ASTM Designation D 543.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:43Z
Check the source to verify that this is the current version before use.

3.1.5 Bulbs. The bulbs for Type I, dropper bottles, shall be made of oil-resistant rubber. The bulbs shall not exceed the maximum values listed in Table I, when tested for oil resistance, as specified in 4.4.2:

Table I. Oil resistance

Test media	Increase in weight, percent maximum	
	at 72° Fahrenheit (F.)	at 99° F.
Light mineral oil	8.3	12.8
Corn oil	5.2	11.5

3.2 Design and construction. Bottles, jars, screwcaps, and liners shall conform to the following general requirements.

3.2.1 Bottles and jars. The bottles and jars shall be free from deformation and shall be smoothly finished. The sidewalls of the bottles and jars shall be of uniform thickness. The bottles and jars shall be provided with the screwcap closures in place, and shall have well-defined, continuous threads to receive the screwcap. The color of the bottles and jars shall be as specified (see 1.2.2 and 6.2). The bottles and jars shall be free from blisters over 3/32 inch in diameter, stones over 1/32 inch in diameter, and any cracks, chips, and seeds. The bottles and jars shall be furnished clean and dry.

3.2.2 Screwcaps. All closures shall be screwcaps. The inner edges of the cap shall be threaded with a continuous thread formed as an integral part of the cap. The screwcaps shall mate and form a tight fit with the finish of the bottle or jar. The exterior of the screwcaps shall be plain and smooth; or as an alternate, the exterior top shall be smooth and plain, and the exterior side shall have vertical serrations, ridges, or ribs to facilitate gripping. Screwcaps with nominal thread diameters of 38 millimeters (mm.) and larger shall have a flat top to facilitate stacking. The colors for the screwcaps shall be black, brown, or white, as specified (see 6.2).

3.2.2.1 Plastic screwcaps. Plastic screwcaps shall have sidewalls of adequate strength and weight for the purpose intended.

3.2.2.2 Metal screwcaps. Metal screwcaps shall have a rolled edge.

3.2.3 Liners. The liners shall form a seal and shall be in full contact with the upper edge of the bottle or jar.

3.3 Detail requirements, Type I. The bottle assembly shall consist of a bottle, a screwcap without a liner, a pipet, and a bulb.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:43Z
Check the source to verify that this is the current version before use.

3.3.1 Bottle. The dropper bottle shall be oval shaped, or flat on one side and oval on the other side, to allow full display of labels. The bottle shall be narrow-mouthed, and shall conform to the requirements specified in Table II.

Table II. Type I bottles

Nominal capacity,* fluid ounce(s)	Minimum weight, exclusive of closure, ounce(s)	Height, exclusive of closure, inches	Nominal thread diameter of finish, millimeters
1/4	7/8	2-1/4 ± 1/16	18 or 20
1/2	1-1/16	2-5/8 ± 3/32	18 or 20
1	1-5/8	3 ± 1/8	18 or 20
2	2-3/8	3-3/4 ± 3/16	18 or 20

* The total capacity of the dropper bottles shall be greater than the nominal capacity to allow for displacement caused by the pipet.

3.3.2 Screwcap. The screwcap shall contain a centrally located hole for placement of a dropper assembly consisting of a pipet with attached bulb. The cap with the dropper assembly shall fit the bottle snugly, forming a liquid-tight seal, when tested as specified in 4.4.3. Only plastic screwcaps shall be furnished for Type I bottles.

3.3.3 Pipet. The pipet shall have a smooth, straight tip, a tapered tip, or a blunt point tip. The pipet shall fit tightly and securely into the rubber bulb.

3.3.4 Bulb. The bulb shall have a sealing flange of uniform thickness and diameter. The bulb shall be round and of uniform size to match the inside diameter of the retaining plastic closure. The bulb shall be free of holes in the nipple portion, free of bloom, free of irregularities of color, free of invisible impurities or mold scale, and free of mold lubricant both inside and outside. The openings for receipt of the pipet should be smaller than the diameter of the pipets to provide a tight fit. The groove to receive the flange of the pipet shall be uniform and shall be of adequate depth to retain the pipet flange.

3.4 Detail requirements, Type II, Style 1. The bottle assembly shall consist of a bottle fitted with a screwcap and liner.

3.4.1 Bottle. The bottle for liquids shall be rectangular or oval shaped or flat on one side and oval on the other side. The bottle shall be narrow-mouthed, and shall conform to the requirements specified in Table III. The normal capacity point shall not extend above the bottom level of the neck, nor below the bottom level of the shoulder. The bottle may contain horizontal ridges around the outer surface to facilitate gripping.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:43Z
Check the source to verify that this is the current version before use.

Table III. Type II, Style 1 bottles

Capacity, fluid ounce(s)	Minimum weight, exclusive of closure, ounce(s)	Nominal thread diameter of finish, millimeters
1/2	13/16	15 to 33 for all capacities
1	1 3/16	
2	1 15/16	
3	2 3/4	
4	3 1/2	
6	4 11/16	
8	5 7/8	
12	8 1/8	
16	10 3/8	
32	17 3/8	

3.4.2 Screwcap and liner. Only plastic screwcaps shall be furnished.

3.5 Detail requirements, Type II, Style 2. The bottle assembly shall consist of a bottle fitted with a screwcap and liner.

3.5.1 Bottle. The bottle for tablets and capsules shall be cylindrical shaped, and shall conform to the requirements specified in Table IV.

Table IV. Type II, Style 2 bottles

Capacity, drams (tolerance + 1, - 0)	Height inches	Outside diameter, inch(es)	Weight ounce(s)	Nom. thread diameter of finish, mm.
2	2 3/32 ± 3/32	15/16 ± 1/16	7/16 to 15/16	20 or 22
4	2 5/32 ± 3/32	1 1/16 ± 3/32	11/16 to 1 1/4	22 or 24
6	2 7/16 ± 3/32	1 3/16 ± 3/32	7/8 to 1 13/16	24 or 28
10	3 5/32 ± 1/8	1 9/32 ± 3/32	1 5/8 to 2 3/16	28
13	3 25/32 ± 1/8	1 9/32 ± 3/32	1 13/16 to 2 1/2	28

3.5.2 Screwcap and liner. Only plastic screwcaps shall be furnished.

3.6 Detail requirements, type III, style 1. The jar assembly shall consist of a jar fitted with a screwcap and liner.

3.6.1 Jar. The jar for ointments shall be cylindrical-shaped, wide-mouthed, and shall conform to the requirements specified in Table IV. The sidewalls of the jar shall be perpendicular to the bottom of the jar. The bottom of the jar shall be rounded on the inside. The jar shall contain a finish which provides a tight seal with the screwcap supplied. A bead may be present at the bottom of the finish.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:43Z
Check the source to verify that this is the current version before use.

Table V. Type III, style 1 jars

Minimum overflow capacity, fluid ounce(s)	Outside height excluding closure, inches		Outside diameter (including bead, if any) inches		Minimum weight excluding closure, ounces
	Min.	Max.	Min.	Max.	
1/2	1 1/4	2 1/16	1 1/8	1 9/16	1 1/8
1	1 5/8	2 1/4	1 3/8	2 1/16	1 11/16
2	2	2 11/16	1 3/4	2 1/4	2 7/16
4	2 1/2	3 1/8	2 5/16	2 11/16	4 3/4
8	2 15/16	3 7/8	2 3/4	3 1/2	9 1/4
16	3 5/8	4 1/2	3 1/2	4 3/16	12 5/8

3.6.2 Screwcap. The screwcap shall be either plastic or metal, as specified in 3.1.2. If a metal screwcap is furnished, it shall be coated on both inside and outside with lacquer or opaque, baked enamel.

3.6.3 Liner. The liner shall be backed with resilient pulp or newsboard not less than 0.030-inch thick, and faced with the materials specified in 3.1.3. The liner may also be wax coated.

3.7 Detail requirements, type III, style 2. The jar assembly shall consist of a jar fitted with a screwcap and liner.

3.7.1 Jar. The powder jar shall be square shaped and wide-mouthed, and shall conform to the requirements specified in Table VI. The actual capacity for each size shall be at least the nominal capacity specified in the table.

Table VI. Type III, style 2 jars

Nominal capacity ounce(s)	Height, inches	Width, inches	Nominal thread diameter of finish, mm.	Weight, ounces
1	2 11/16 ± 1/16	1 5/16 ± 3/16	28	1 3/4 ± 1/2
2	3 5/16 ± 1/8	1 5/8 ± 3/16	33	2 7/8 ± 1/2
3	3 21/32 ± 1/4	1 3/4 ± 3/16	38	3 7/8 ± 1/2
4	4 5/32 ± 1/4	1 7/8 ± 3/16	38	4 1/2 ± 1/2
6	4 1/2 ± 1/4	2 1/16 ± 3/16	48	5 5/8 ± 1
8	5 ± 1/4	2 5/16 ± 3/16	48	7 1/4 ± 1
16	6 ± 1/2	2 7/8 ± 3/16	63 or 58	12 ± 1

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:43Z
Check the source to verify that this is the current version before use.

3.7.2 Screwcap. Only plastic screwcaps shall be furnished.

3.7.3 Liner. The backing of the liner shall be either of pulp or of cork composition. If a pulp backing is supplied, the overall thickness shall be 0.050 ± 0.005 inch for the 28 and 33 mm. nominal thread diameter of finish, and 0.040 ± 0.004 inch for the remaining sizes specified in table VI. If a cork composition is supplied, the overall thickness shall be 0.0625 ± 0.0063 inch.

3.8 Leaks. Type I bottles and type II, style 1 bottles shall not leak, when tested as specified in 4.4.3.

3.9 Identification marking. Bottles and jars shall be permanently and legibly marked with the name or registered trademark of the manufacturer. Bottles and jars shall be marked with a symbol to show their capacity.

3.10 Workmanship. Workmanship shall be first class throughout. Bottles and jars shall be free from defects which affect their appearance or may impair their serviceability.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified, the supplier may utilize his own facilities or any commercial laboratory acceptable to the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to insure that supplies and services conform to prescribed requirements.

4.1.1 Inspection. Inspection, as used in this specification, is defined as both examination (such as visual or auditory investigation without the use of special laboratory appliances or procedures) and testing (determination by technical means of physical and chemical properties).

4.1.2 Certificates of quality. When available, certificates of quality, supplied by the manufacturer of the component or material, listing the specified test method and test results obtained, may be furnished in lieu of actual performance of such testing by the contractor.

4.2 Sampling.

4.2.1 For examination. Sampling for examination shall be conducted in accordance with MIL-STD-105, and as specified in Table VII.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:43Z
Check the source to verify that this is the current version before use.

Table VII. Examination

	Inspection level	AQL (percent defective)
For visual examination		
Major defects	II	2.5
Minor defects	II	4.0
For dimensional examination	S-2	4.0
For preparation for delivery	S-2	4.0

4.2.2 For tests. Sampling for tests shall be conducted in accordance with MIL-STD-105 and as specified in table VIII.

Table VIII. Tests

Component (Unit of product)	Characteristic	Requirement	Test Procedure	Insp. level	AQL
Bottle or jar	Chemical resistance	3.1.1	4.4.1	S-2	*
Bulb (Type I)	Oil resistance	3.1.5	4.4.2	S-3	*
Bottle assembly (Types I and II)	Leaks	3.8	4.4.3	S-3	*

* The acceptance number shall be zero.

4.3 Examination. The bottles shall be examined to determine compliance with all requirements contained in this specification.

4.3.1 Classification of defects. Examination shall be conducted in accordance with the classification of defects in table IX.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:43Z
Check the source to verify that this is the current version before use.

Table IX. Classification of Defects

Category	Defect*
Major:	
101	Open blisters.
102	Blisters over 3/32 inch.
103	Stones over 1/32 inch.
104	Glass and plastic not free of cracks, chips, rough seams or edges.
105	Thread distorted, not continuous.
106	Seams or edges not smooth.
107	Bottle or jar not free of deformation.
108	Bottom of bottle or jar does not rest evenly upon a flat, smooth level surface.
109	Liner in closure not faced (not applicable to type I).
110	Liner in closure missing (not applicable to type I).
Minor:	
201	Identification markings, registered trademark of manufacturer not present, complete, correct, legible, or permanent.
202	Bottle not clean or dry.
203	Top of closure not flat or smooth.

*Examination shall not be restricted to the classified possible defects listed in table IX.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:43Z
Check the source to verify that this is the current version before use.

4.3.2 Dimensional examination. The screwcap bottles shall be examined for defects in linear dimensions, capacity, and weight. Any linear dimension, capacity or weight not within the tolerance specified, or not meeting the minimum requirement specified, shall be classified as a defect.

4.3.3 Preparation for delivery. Examination shall be made to determine that packaging, packing and marking comply with the requirements of Section 5 of this specification and special requirements of the contract when applicable. The sample unit shall be one shipping container fully packed, selected just prior to the closing operation. Shipping containers fully prepared for delivery shall be examined for closure defects. Examination of defects shall be in accordance with table X.

Table X. Defects in Preparation for Delivery

Category	Defect
301	Any packaging or packing component or material not as specified.
302	Any packaging or packing component missing or malformed.
303	Any packaging or packing component or material not as specified.
304	Any component missing or malformed.
305	Not packaged in cartons of appropriate size, carton does not have full height partitions arranged to firmly hold each bottle or jar, as applicable, in individual cells, partition not full height of carton, not securely sealed to prevent accidental opening.
306	Unit carton not designed with suitable, interior fittings or sufficient cushioning material to insure against shifting of, or damage to, the contents.
307	Intermediate container, when applicable, not of sufficient size to contain the quantity of bottles specified; does not have full height partitions arranged to hold firmly each bottle or jar as applicable in individual cells.
308	Not the proper quantity of bottles or jars, as applicable, per intermediate container (Table XI).

NOTE: All unit or intermediate containers in each shipping container in the sample shall be examined for the above requirements.

309	Not the specified or indicated number of unit or intermediate containers per shipping container (Table XI).
310	Inadequate application of components, such as insufficient, insecure or incomplete closure of case liner, when applicable; incomplete or insecure closure of container flaps; crooked, loose or insecure strapping or tape banding; bulge or distortion of shipping container.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:43Z
Check the source to verify that this is the current version before use.

311 Shipping container broken, bruised, crushed or otherwise damaged in a manner which may result in loss or injury to contents.
312 Marking on interior packages and shipping containers omitted, incomplete, incorrect, or illegible; of improper size, location, or sequence of application.

4.4 Test procedures. Tests shall be conducted to determine compliance with specification requirements.

4.4.1 Chemical resistance. The glass bottles and jars shall be tested in accordance with the procedures described in the U.S.P. for type II, type III, or type NP glass, as applicable.

4.4.2 Oil resistance. Bulbs shall be tested as follows:

(a) Divide samples into four equal groups and accurately weigh each group.
(b) Immerse two groups in separate containers of mineral oil.
(c) Immerse two groups in separate containers of corn oil.
(d) Allow one mineral oil container and one corn oil container to stand for 72 hours at 72° F. ± 2° F.
(e) Allow one mineral oil container and one corn oil container to stand for 72 hours at 99° F. ± 2° F.
(f) Remove the bulbs from the test media keeping the groups separate, place on a screen with the bulb opening facing down, and allow to drain for 30 minutes.
(g) Wipe bulbs clean of oil with a towel, and allow to stand at room temperature for 16 hours.
(h) Reweigh and calculate percentage increase in weight.

4.4.3 Leaks. The bottles shall be filled with tap water and the closure shall be applied, hand tight. The filled bottle or jar shall be suspended in an inverted position for 4 hours at a temperature of 72° F. ± 5° F.

5. PREPARATION FOR DELIVERY

5.1 Packaging.

5.1.1 Unit of issue. The number of bottles or jars as specified in Table XI constitutes one unit of issue.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:43Z
Check the source to verify that this is the current version before use.

5.1.2 Packaging quantitites. The number of units of issue indicated in table XI shall be packaged in each unit, intermediate, and exterior container, as applicable, for the required level of protection specified in the procurement document.

Table XI. Packaging and packing quantities

Type and style	Size	No. of bottles or jars constituting one unit	Unit to each package	Units per intermediate package	Units per shipping container
Type I	1/4 oz.	1	Not required	12	576
	1/2 oz.	12	1	Not required	24
	1 oz.	12	1	Not required	24
	2 oz.	72	1	Not required	4
Type II, style 1	1/2 oz. & 1 oz.	72	1	Not required	6
	2 oz. & 3 oz.	72	1	Not required	4
	4 oz.	72	1	Not required	2
	6 oz. & 8 oz.	36	1	Not required	2
	12 oz. & 16 oz.	18	1	Not required	2
	32 oz.	1	Not required	18	18
Type II, style 2	2 Dr.	72	1	Not required	12
	4 Dr.	72	1	Not required	8
	6 Dr.	72	1	Not required	6
	10 Dr. & 13 Dr.	72	1	Not required	4
Type III, style 1	1/2 oz.	12	1	Not required	36
	1 oz.	12	1	Not required	24
	2 oz.	12	1	Not required	12
	4 oz.	12	1	Not required	6
	8 oz.	1	Not required	12	48
	1 lb.	1	Not required	12	36
Type III, style2	1 oz.	12	1	Not required	24
	2 oz.	12	1	Not required	18
	4 oz.	12	1	Not required	12
	6 oz.	12	1	Not required	8
	8 oz.	12	1	Not required	6
	16 oz.	12	1	Not required	4

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:43Z
Check the source to verify that this is the current version before use.

5.1.2.1 Packing variation permitted. If the required number of units in the entire shipment is less than the number of units specified to be overpacked in an exterior container, such units shall be packed in an exterior container of suitable size and design, acceptable to a common carrier, which shall insure safe delivery to destination.

5.1.3 Level A.

5.1.3.1 Unit package.

5.1.3.1.1 Type I. Type I dropper bottles, in quantities as specified in table XI, shall be packaged in a close-fitting box conforming to PPP-B-636, class domestic. Chipboard or corrugated fiberboard partitions shall be provided to form individual cells for each bottle. The box shall be closed in accordance with the appendix to the box specification. As an alternate style, the box may have a lock-type bottom and tuck-in top.

5.1.3.1.2 Type II, style 1. Type II, style 1, sizes 1/2 oz. through 16 oz. in quantities as specified in table XI, shall be packaged in a close-fitting box conforming to PPP-B-636, class domestic. Chipboard or corrugated fiberboard partitions shall be provided to form individual cells for each bottle, except that three 1/2 ounce or 1-ounce bottles, two 2-ounces or 3-ounce bottles may be packaged to a cell. The box shall be closed in accordance with the appendix to the box specification.

5.1.3.1.3 Type II, style 2 and type III, styles 1 and 2. Type II, style 2, type III, style 1, sizes 1/2 oz. through 4 oz., and type III, style 2, in quantities as specified in table shall be packaged in a close-fitting box conforming to PPP-B-636, class domestic. Chipboard or corrugated fiberboard partitions shall be provided to form individual cells for each bottle. Alternatively, interior protection may be provided with other commercial cushioning material or fittings. The box shall be closed in accordance with the box specification.

5.1.3.2 Intermediate package. Type II, style 1, 32 oz. and type III, style 1, 8 oz. and 1 lb. shall be packaged in a close-fitting box conforming to PPP-B-636, class domestic. Chipboard or corrugated fiberboard partitions shall be provided to form individual cells for each bottle or jar. The box shall be closed in accordance with the appendix to the box specification.

5.1.4 Level C. The bottles and jars shall be packaged in accordance with the supplier's commercial practice.

5.2 Packing. Packing shall be level A, B, or C as specified (see 6.2).

5.2.1 Level A. Bottles and jars, in quantities specified in table XI, shall be packed in a close-fitting box conforming to PPP-B-636, class weather-resistant, style RSC. Closure shall be as specified in 30.3.2.1 thereof and in addition, the center seam shall be closed by means of tape conforming to PPP-T-45 or PPP-T-76. The tape shall be not less than 3 inches wide and extend at least 2 inches onto each of the end panels.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:43Z
Check the source to verify that this is the current version before use.

5.2.2 Level B. Bottles and jars, packaged as specified in 5.1.3, shall be packed in a close-fitting box conforming to PPP-B-636, class domestic, minimum bursting strength not less than 275 p.s.i. Closure shall be in accordance with the appendix to the box specification.

5.2.3 Level C. The bottles and jars shall be packed to insure carrier acceptance and safe delivery to destination in containers complying with the rules and regulations applicable to the mode of transportation.

5.3 Marking.

5.3.1 Civil agencies. In addition to markings required by the contract or order, the shipping containers shall be marked in accordance with FED-STD-123.

5.3.2 Military activities.

5.3.2.1 Interior packages. Each unit package and each intermediate package shall be marked in accordance with MIL-STD-129. When labels are utilized, waterproofing shall be required only when applicable carton is fabricated of water-resistant material. Contract or purchase order number and name of contractor shall be shown.

5.3.2.2 Exterior container. Exterior container shall be marked in accordance with MIL-STD-129.

6. NOTES

6.1 Intended use.

6.1.1 Type I, bottles, dropper. Intended for use in dispensing small or drop doses of medicaments, as well as eye, ear, and nose preparations.

6.1.2 Type II, bottles, screwcap.

6.1.2.1 Style 1, for liquids. Intended for use in dispensing pharmaceutical liquid preparations from prescriptions.

6.1.2.2 Style 2, for tablets and capsules. Intended for use in packaging tablets and capsules in the dispensing of prescriptions.

6.1.3 Type III, jars.

6.1.3.1 Style 1, for ointments. Intended for use in dispensing and packaging ointments from prescriptions.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:43Z
Check the source to verify that this is the current version before use.

6.1.3.2 Style 2, for powders. Intended for use for packaging powders in dispensing of prescriptions.

6.2 Ordering data. Procurement documents should specify the following:

(a) Number and date of this specification.

(b) Type, style, and color required (see 1.2.1 and 1.2.2).

(c) Capacity of bottles and/or jars required (see 1.2.3).

(d) Type of glass required (see 3.1.1).

(e) Color of closure required (see 3.2.2).

(f) Selection of applicable levels of packaging and packing (see 5.1 and 5.2).

6.3 This specification does not cover all types, classes, grades, or sizes of the commodity indicated by the title of this specification, or those which are commercially available, but is intended to cover the types which are normally procured to meet Federal Government requirements.

Custodians:
Army - MD
Navy - MS
Air Force - 03

Preparing activity:
Defense Supply Agency - DM

Review activities:
Army - MD
Navy - MS
Air Force - 03

Review information is current as of the date of this document. For future coordination of changes to this document, draft circulation should be based on the information in the current DODISS.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:43Z
Check the source to verify that this is the current version before use.

CAUTION

NOTICE TO BIDDERS/OFFERORS

DO NOT CONDITION OR BASE YOUR BID/OFFER ON ANY CURRENT PROCUREMENT ON THE INFORMATION SUBMITTED ON THIS FORM SINCE ANY CHANGES OR DELETIONS IN THE SPECIFICATIONS MAY RENDER YOUR BID/OFFER NON-RESPONSIVE IN WHICH CASE IT CANNOT BE CONSIDERED FOR AWARD.

Fold

DEFENSE PERSONNEL SUPPORT CENTER
2800 SOUTH 20TH STREET
PHILADELPHIA, PA. 19101

DEFENSE SUPPLY AGENCY
OFFICIAL BUSINESS

POSTAGE AND FEES PAID
DEFENSE SUPPLY AGENCY

HEADQUARTERS, DEFENSE PERSONNEL SUPPORT CENTER
ATTN: DIRECTORATE OF MEDICAL MATERIEL
2800 SOUTH 20TH STREET
PHILADELPHIA, PA. 19101

Fold

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:43Z
Check the source to verify that this is the current version before use.

SPECIFICATION ANALYSIS SHEET

Form Approved
Budget Bureau No. 22-R255

INSTRUCTIONS: This sheet is to be filled out by personnel, either Government or contractor, involved in the use of the specification in procurement of products for ultimate use by the Department of Defense. This sheet is provided for obtaining information on the use of this specification which will insure that suitable products can be procured with a minimum amount of delay and at the least cost. Comments and the return of this form will be appreciated. Fold on lines on reverse side, staple in corner, and send to preparing activity. Comments and suggestions submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or serve to amend contractual requirements.

SPECIFICATION

DD-B-00585b(DSA-DM)

ORGANIZATION

CITY AND STATE

CONTRACT NUMBER

MATERIAL PROCURED UNDER A

☐ DIRECT GOVERNMENT CONTRACT ☐ SUBCONTRACT

1. HAS ANY PART OF THE SPECIFICATION CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE?

A. GIVE PARAGRAPH NUMBER AND WORDING.

B. RECOMMENDATIONS FOR CORRECTING THE DEFICIENCIES

2. COMMENTS ON ANY SPECIFICATION REQUIREMENT CONSIDERED TOO RIGID

3. IS THE SPECIFICATION RESTRICTIVE?

☐ YES ☐ NO *(If "yes", in what way?)*

4. REMARKS *(Attach any pertinent data which may be of use in improving this specification. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity)*

SUBMITTED BY *(Printed or typed name and activity - Optional)*

DATE

DD FORM 1 JAN 66 1426

REPLACES EDITION OF 1 OCT 64, WHICH MAY BE USED.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:43Z
Check the source to verify that this is the current version before use.