DD-B-585
Interim Amendment-1

September 4, 1962

INTERIM AMENDMENT

FEDERAL SPECIFICATION

BOTTLES AND JARS, GLASS PRESCRIPTION DISPENSING

This Interim Amendment was developed by the Federal Supply Service, General Services Administration, Washington 25, D. C., based upon currently available technical information. It is recommended that Federal agencies use it in procurement and forward recommendations for changes to the preparing activity at the address shown above.

The General Services Administration has authorized Federal agencies to use this Interim Amendment as a valid part of Federal Specification DD-B-585, Bottles and Jars, Glass Prescription Dispensing.

Page 2, paragraph 3.1.1 - Delete in its entirety and substitute the following:

3.1.1 Glass. - Bottles and jars shall be made of high grade commercial glass, meeting the requirements for chemical resistance for type III or type NP glass as described in the Pharmacopoeia of the United States.

Page 5, table V - Add:

Capacity Ounce	Height Inches	Width Inches	Nominal thread diameter of finish in millimeters	Weight Ounces
3	3-21/32 ± 1/4	1-51/64 ± 3/64	38	3-7/8 ± 1/2

Page 6, paragraphs 4 thru 4.4 inclusive, also Tables VI & VII - Delete and substitute the following:

"4. QUALITY ASSURANCE PROVISIONS:

4.1 Inspection responsibility. - The supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified, the supplier may utilize his own or any other inspection facilities and service acceptable to the Government. Inspection records of the examinations and tests shall be kept complete and available to the Government as specified in the contract or order. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

FSC 8125

Source: https://assist.dla.mil -- Downloaded: 20261O-26T11:43Z
Check the source to verify that this is the current version before use.

4.2 Sampling for inspection and acceptance. - Sampling for inspection and acceptance shall be performed in accordance with the provisions set forth in Standard MIL-STD-105, except where otherwise indicated. For purposes of sampling, an inspection lot for examination and tests shall consist of all material of the same type and style submitted for acceptance and delivery at one time. When multiple sizes of any one type and style of bottles or jars are ordered, the inspection lot may consist of all sizes presented at one time, in which case, sampling shall be in proportion or ratio to the respective sizes. The acceptable quality level (AQL) shall be applicable to the entire lot regardless of defects, as they may occur in any one or more size of bottles or jars.

4.2.1 Inspection of materials and components. - In accordance with 4.1 above, the supplier is responsible for insuring that materials and components used were manufactured, tested and inspected in accordance with the requirements of referanced subsidiary specifications and standards to the extent specified, or, if none, in accordance with this specification. In the event of conflict, this Specification shall govern.

4.3 Inspection of the end item.-

4.3.1 Examination of the end item. - Examination of the end item shall be made in accordance with the classification of defects, inspection levels and acceptable quality levels (AQLs) set forth below. The lot size, for purpose of determining the sample size in accordance with MIL-STD-105, shall be expressed in units of bottles or jars, as applicable, for examination in 4.3.1.1, 4.3.1.2, 4.3.1.2. For examination in 4.3.1.4, the lot size shall be expressed in units of shipping containers.

4.3.1.1 Examination of the end item for defects in construction, appearance and workmanship. - The sample unit for this examination shall be one bottle or jar, with closure, as applicable.

EXAMINE	DEFECT
Type I Bottle (dropper) Constructinn & Appearance	Bottle not oval, or semi-oval shape, with narrow mouth.
	Closure not as specified; screwcap and dropper assembly does not fit snugly on bottle; not adequately cushioned by closure liner, not tight fitting, liner missing.
	Glass pipette not tight and secure fit in the rubber bulb.
	Bulb not formed to fit properly, not free of holes, bloom, color irregularities or other defects.
	Tip of pipette not smooth and straight.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:43Z
Check the source to verify that this is the current version before use.

EXAMINE	DEFECT
Type II, Style 1 & 2 Bottle Construction & Appearance	Bottle not shape specified, not narrow mouth, as applicable.
	Closures for Style 1 (3.4.1.1) and Style 2 (3.4.2.1) not as specified.
Type III, Style 1 & 2 Jar	Not glass, cylindrical in shape with perpendicular sidewalls, or square in shape with wide mouth, as specified.
	Closures not as specified, not plain, smooth or with ribbed side walls, as applicable.
Workmanship Types I & II, Bottles & Type III, Jars	Glass not uniform; any cracks, chips, blisters, stones, seeds, striae or other defects affecting appearance or serviceability.
	Any rough seams or edges; any distortion of threads receiving closure.
	Bottom of bottle or jar does not rest evenly upon a flat, smooth, level surface.
	Color of bottle or jar not as specified.
	Color of closures not as specified or not in accordance with contract requirements.
	Not symmetrical in shape.
	Contracting edges of closure not formed to fit properly.
	Exterior of closure not plain smooth.
	Screwcap liners not of resilient material of suitable facing to give tight fit to closure.
	Not clean and dry.
Markings	Identification markings, registered trademark of manufacturer omitted, illegible, incorrect or not in accordance with contract requirements.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:43Z
Check the source to verify that this is the current version before use.

4.3.1.2 Examination of the end item for dimensional defects. - The sample unit for this examination shall be one bottle or jar with closure, as applicable.

EXAMINE	DEFECT
Type I, Bottle	
Height exclusive of closure	Not within tolerances specified (Table I).
Thread diameter	Not as specified (Table I).
Type II, Style 1	
Thread diameter	Not as specified (see 3.4.1).
Type II, Style 2	
Height	Not within tolerances specified (Table III).
Outside diameter	Not within tolerances specified (Table III).
Thread diameter	Not as specified (Table III).
Type III, Style 1	
Height not including closure	Not within tolerances specified (Table IV).
Outside diameter including bead below closure, as applicable	Not within tolerances specified (Table IV).
Type III, Style 2	
Height	Not within tolerances specified (Table V).
Width	Not within tolerances specified (Table V).
Thread diameter	Not as specified (Table V).

4.3.1.3 Examination of the end item for weight. - The sample unit for this examination shall be one bottle or jar as applicable.

EXAMINE	DEFECT
Type I, Bottle	Less than minimum weight specified (Table I).
Type II, Style 1 Bottle	Less than minimum weight specified (Table II).
Type II, Style 2 Bottle	Not within weight range specified.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:43Z
Check the source to verify that this is the current version before use.

EXAMINE	DEFECT
Type III, Style 1 Jars	Less than minimum weight specified (Table IV).
Type III, Style 2 Jars	Not within tolerances specified (Table V).

4.3.1.4 Examination of preparation for delivery. - Examination shall be made to determine that packaging, packing and marking comply with the requirements of Section 5 of this specification and special requirements of the contract when applicable. The sample unit shall be one shipping container fully packed, selected just prior to the closing operation. Shipping containers fully prepared for delivery shall be examined for closure defects.

EXAMINE	DEFECT
Material	Any packaging or packing component or material not as specified
	Any component missing or malformed.
P Packaging	Not packaged in cartons of appropriate size, carton does not have full height partitions arranged to firmly hold each bottle or jar, as applicable, in individual cells, partition not full height of carton, not securely sealed to prevent accidental opening.
	Unit carton not designed with suitable interior fittings or sufficient cushioning material to insure against shifting of, or damage to, the contents.
	Intermediate container, when applicable, not of sufficient size to contain the quantity of bottles specified; does not have full height partions arranged to firmly hold each bottle or jar as applicable in individual cells.
	Not the quantity of bottles or jars, as applicable, per intermediate container (Table VIII).

NOTE: All intermediate containers in each shipping container in the sample shall be examined for the above requirements.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:43Z
Check the source to verify that this is the current version before use.

EXAMINE	DEFECT
Packaging (con't)	Not the specified or indicated number of unit or intermediate containers per shipping container (Table VIII).
	Inadequate application of components, such as: insufficient, insecure or incomplete closure of case liner, when applicable; incomplete or insecure closure of container flaps; crooked, loose or insecure strapping or tape banding; bulge or distortion of shipping container.
	Broken, bruised, crushed or otherwise damaged shipping container in a manner which may result in loss or injury to contents.
Marking (Interior packages and shipping containers)	Omitted, incomplete, incorrect, illegible; of improper size, location or sequence of application.

4.3.1.5 Inspection levels, acceptable quality levels (AQLs) for examination. The inspection levels for the purpose of determining the sample size and the acceptable quality levels (AQLs) expressed in defects per 100 units, shall be as follows:

Examination Paragraph	Inspection Level	AQL
4.3.1.1	II	2.5
4.3.1.2	L-4	4.0
4.3.1.3	L-4	4.0
4.3.1.4	L-4	4.0

4.3.2 Testing of the end item. - The end item shall be tested for the characteristic requirement as indicated in Table VI, on samples selected from each lot of each type, style and size bottle or jar presented for Government acceptance. The sample unit shall be four bottles or jars, as applicable. The inspection level and the acceptable quality level shall be as indicated in Table VI. No less than five (5) sample units shall be tested. Failure to meet requirements shall be cause for rejection."

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:43Z
Check the source to verify that this is the current version before use.

							1/			
Glass (Bottles & Jars)										
Water attack	3.1.1	4.5.1	--	-	Avg of 2 on composited extract	-	0.1 cc	L-3	-	
Acid attack	3.1.1	4.5.1	--	-	"	-	0.1 cc	L-3	-	
Bottle, Type I										
Capacity	3.3.1 & Table I	3.3.1	X	-	1	X	--	L-3	4.0	
Bottle, Type II Style 1										
Capacity	3.4.1 & Table II	3.4.1	X	-	1	X	-	L-3	4.0	
Type II Style 2										
Capacity	3.4.2 & Table III	3.4.2	X	-	1	X	-	L-3	4.0	
Bottle, Type III Style 1										
Capacity	3.5.1 & Table IV	3.5.1	X	-	1	X	-	L-3	4.0	
Type III Style 2										
Capacity	3.5.2 & Table V	3.5.2	X	-	1	X	-	L-3	4.0	

NOTE: 1/ If failure is indicated, report either descriptionor numerical point of failure, as applicable

MILITARY INTERESTS

Army - M
Navy - Md
Air Force

GSA-WASH DC 63-3168

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:43Z
Check the source to verify that this is the current version before use.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:43Z
Check the source to verify that this is the current version before use.