DD-B-585

SEPTEMBER 1, 1959

SUPERSEDING
Fed. Spec. DD-B-591b
September 3, 1957,
In'. Fed. Spec. DD-J-00123a (GSA-FSS)
March 15, 1957, and
Fed. Spec. DD-J-123
July 6, 1946

FEDERAL SPECIFICATION

BOTTLES AND JARS, GLASS, PRESCRIPTION DISPENSING

This specification was approved by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal agencies.

1. SCOPE AND CLASSIFICATION

1.1 **Scope.**—This specification covers glass bottles and jars suitable for use in dispensing prescriptions.

1.2 **Classification.**

1.2.1 *Types and styles.*—Glass bottles and jars shall be of the following types and styles, as specified (see 6.2):

Type I—Bottles, dropper.

Type II—Bottles, screwcap.

Style 1—For liquids.
Style 2—For tablets and capsules.

Type III—Jars, screwcap.

Style 1—For ointments.
Style 2—For powders.

1.2.2 *Color.*—The bottles and jars shall be of the following colors, as specified (see 6.2):

Clear
White opaque
Green
Amber
Blue

1.2.3 *Capacity.*—The capacity of the bottles and jars shall be as specified in tables I, II, III, IV or V (see 6.2).

2. APPLICABLE SPECIFICATIONS, STANDARDS, AND OTHER PUBLICATIONS

2.1 **Specifications and standards.**—The following specifications and standards, of the issues in effect on date of invitation for bids, form a part of this specification:

Federal Specifications:

PPP-B-636—Boxes, Fiber.
PPP-T-45—Tape, Gummed, Paper, Reinforced.
PPP-T-76 — Tape, Pressure-Sensitive Adhesive, Paper, Water Resistant.

Federal Standards:

Fed. Std. No. 102—Preservation, Packaging, and Packing Levels.
Fed. Std. No. 123—Marking for Domestic Shipment (Civilian Agencies).

(Activities outside the Federal Government may obtain copies of Federal Specifications, Standards, and Handbooks as outlined under General Information in the Index of Federal Specifications, Standards, and Handbooks and at the prices indicated

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:43Z
Check the source to verify that this is the current version before use.

in the Index. The Index, which includes cumulative monthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, U. S. Government Printing Office, Washington 25, D. C.

(Single copies of this specification and other product specifications required by activities outside the Federal Government for bidding purposes are available without charge at the General Services Administration Regional Offices in Boston, New York, Atlanta, Chicago, Kansas City, Mo., Dallas, Denver, San Francisco, Los Angeles, Seattle, and Washington, D. C.

(Federal Government activities may obtain copies of Federal Specifications, Standards, and Handbooks and the Index of Federal Specifications, Standards, and Handbooks from established distribution points in their agencies.)

Military Standards:

MIL-STD-105 — Sampling Procedures and Tables for Inspection by Attributes.

MIL-STD-129 — Marking for Shipment and Storage.

(Copies of specifications and standards required by contractors in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publication. — The following document forms a part of this specification. Unless otherwise indicated, the issue in effect on date of invitation for bids shall apply.

Pharmacopoeia of the United States.

(Application for copies should be addressed to the Mack Publishing Company, Easton, Pa.)

3. REQUIREMENTS

3.1 Material.

3.1.1 *Glass.* — Bottles and jars shall be made of high grade commercial glass, meeting the requirements for chemical resistance for type III glass as described in the Pharmacopoeia of the United States.

3.1.2 *Closures.* — The screwcap closures shall be made of suitable molded plastic material or metal, as hereinafter specified.

3.1.2.1 *Liners.* — The screwcap closures shall be fitted with a tight-fitting, resilient cork, cork composition, pulp or newsboard mat and faced with a vinylite, saran film, or pliofilm facing mounted on white paper, or a cemented-in rubber liner.

3.1.3 *Pipettes.*—The pipettes shall be made of a good grade, clear glass tubing.

3.1.3.1 *Bulbs.*—The bulbs shall be made of a good quality, oil resistant, natural or synthetic rubber.

3.2 General requirements.

3.2.1 *Glass bottles and jars.*—Glass bottles and jars shall be symmetrically made and smoothly finished. Glass shall be of uniform thickness in side walls with bottom somewhat thicker than the shoulders. The bottles and jars shall be provided with screwcap closures and shall have well-defined, properly made threads to receive the closure. Color of the bottles and jars shall be as specified (see 1.2.2 and 6.2).

3.2.2 *Closures.*—The closures shall have a plain, smooth exterior. Sizes of 38 millimeter (mm) and larger shall have a flat top to facilitate stacking. The colors for the closures shall be black, brown, or white, as specified (see 6.2).

3.2.2.1 *Plastic screwcaps.*—Plastic screwcaps shall be of suitable molded plastic (see 3.1.2), with side walls of adequate strength and weight. The screwcaps shall be provided with liners as specified (see 3.1.2.1). The screwcaps shall be of the screw-on type, the inner edges of the cap sufficiently threaded with a continuous-type thread formed as an integral part of the cap for a close fit with the container.

3.2.2.2 *Metal screwcaps.*—Metal screwcaps shall be fabricated of 1.25 hot-dipped tinplate, or 0.50 electrolytic tinplate, lacquered or coated inside and outside to resist corrosion. Metal caps shall have a rolled edge and shall have liners as specified (see 3.1.2.1).

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:43Z
Check the source to verify that this is the current version before use.

3.2.3 *Liners.*—Screwcaps shall be provided with a tight-fitting, resilient material as specified in 3.1.2.1 with suitable facing. The liners shall be of sufficient thickness to form an effective seal and be in full contact with the upper edge of the bottle or jar, when the cap is tightened to the degree required, to prevent loss of contents by leakage or evaporation.

3.3 **Type I, bottles, dropper.**—Type I, dropper bottles, shall be made of glass as specified in 3.1.1. The bottles shall be oval or semi-oval shape to allow full display of labels and shall have a narrow mouth with a normal commercially used continuous thread. The dropper bottles shall conform to the details shown in table I.

TABLE I.

Nominal capacity in fluid ounces	Minimum weight of bottle, exclusive of closure, in ounces	Height of bottle, exclusive of closure, in inches	Nominal thread diameter of finish, in millimeters
½	15/16	2 19/32 ± 1/16	18 or 20
1	1 1/8	2 63/64 ± 5/64	18 or 20

3.3.1 *Capacity.*—The total capacity of the dropper bottles shall be sufficiently greater than the nominal capacity to allow for displacement caused by the pipette.

3.3.2 *Closures.*—Bottles shall be fitted with a molded screwcap having a glass pipette with attached synthetic or natural rubber bulb specified in 3.1.3.1. Cap and dropper assembly shall fit snugly on the bottle to form a liquid-tight seal, cushioned by a liner. The glass pipette shall be fitted tightly and securely in the rubber bulb, and shall have a smooth straight tip.

3.3.3 *Bulbs.*—Bulbs shall have a sealing flange of uniform thickness and diameter. They shall be round and of uniform size to match the inside diameter of the retaining plastic closure. They shall be free of holes in the nipple portion, free of bloom, free of irregularities of color, free of invisible impurities or mold scale, free of mold lubricant both inside and outside. The openings for receipt of the pipette glass should be smaller than the diameter of the pipettes to provide a tight fit. The groove to receive the flange of the pipette shall be uniform and of adequate depth to retain the pipette flange.

3.4 **Type II, bottles, screwcap.**—Type II bottles, screwcap, shall be made of glass as specified (see 3.1.1).

3.4.1 *Style 1, bottles for liquids.* — The screwcap bottles for liquids shall be of the size specified (see table II) and shall be fitted with plastic screwcaps (see 3.2.2.1). The bottles for liquids shall be rectangular, oval or semi-oval shape, with a narrow mouth having a normal commercially used thread. The nominal thread diameter of finish shall be not less than 15 nor more than 33 millimeters. The normal capacity point shall not extend above the bottom level of the neck nor below the bottom level of the shoulder. The opening of the bottle shall be large enough to permit ready filling and dispensing of its contents. Bottles shall meet weight requirements of table II.

TABLE II.

Capacity in fluid ounces	Minimum weight of bottle, exclusive of closure, in ounces
½	1 3/16
1	1 3/16
2	1 15/16
3	2 3/4
4	3 1/2
6	4 13/16
8	5 7/8
12	8 1/8
16	10 3/8
32	17 3/8

3.4.1.1 *Closures.*—Closures shall be of the screw-on type. The inner edges of the cap

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:43Z
Check the source to verify that this is the current version before use.

TABLE III

Capacity in drams (tolerance +1, -0)	Height	Outside diameter	Weight	Nominal thread diameter of finish in millimeters
	Inches	*Inches*	*Ounces*	
2	2 3/32 ± 3/32	7/8 ± 1/32	7/16 to 11/16	20
4	2 5/32 ± 1/16	1 1/16 ± 3/32	11/16 to 1 1/4	22 or 24
6	2 1/16 ± 3/32	1 1/16 ± 3/32	7/8 to 1 13/16	24 or 28
10	3 5/32 ± 1/8	1 1/32 ± 3/32	1 5/8 to 2 3/16	28
13	3 25/32 ± 1/32	1 1/32 ± 3/32	1 13/16 to 2 1/2	28

shall be sufficiently threaded with a continuous-type thread formed as an integral part of the cap. The caps shall be made or molded to fit bottles listed in 3.4.1. (See 3.1.2 and 3.2.2.).

3.4.1.1.1 *Liners.* — The screwcap closure shall be lined with a tight-fitting, resilient liner as specified in 3.1.2.1 with suitable facing.

3.4.2 *Style 2, bottles for tablets and capsules.*—The tablet and capsule bottles shall be cylindrical in shape, provided with plastic closures, as specified (see 3.4.2.1). Bottles shall conform to table III.

3.4.2.1 *Closures.*—The screwcap closures shall be made of phenol-formaldehyde mixture or other suitable molded plastic as specified in 3.1.2. The caps shall be made or molded to fit bottles listed in 3.4.2. (See 3.2.2.)

3.4.2.1.1 *Liners.*—The screwcap closures shall be fitted with a tight-fitting, resilient liner as specified in 3.1.2.1 with a suitable facing.

3.5 Type III, jars, screwcap.—Type III, jars, screwcap, shall be made of glass as specified in 3.1.1.

3.5.1 *Style 1, jars for ointments.*—The ointment jars shall be cylindrical in shape. The sidewalls of the jar shall be essentially perpendicular to the bottom with the exception of the irregularity at the bottom of the finished area. The bottoms shall be suitably rounded on the inside. The jar shall have a finish suitable for a satisfactory seal with the closure supplied. Jars shall meet requirements of table IV:

3.5.1.1 *Closures.*—Closures shall be of the screw-on type, fabricated of black molded plastic or sheet metal coated with opaque-baked enamel and shall be resistant to corrosion. (See 3.1.2 and 3.2.2.) The caps shall be made or molded to fit the jars listed in 3.5.1.

3.5.1.1.1 *Liners.*—Closures shall be fitted with a liner of resilient pulp or newsboard, not less than 0.30 inch thick, faced with vinylite, saran or pliofilm (see 3.1.2.1). Liners may also be wax coated.

3.5.2 *Style 2, jars for powders.*—Powder jars shall be square in shape, shall have wide mouth, shall be provided with screwcap closures, and shall comply with the requirements of table V.

Source: https://assist.dla.mil -- Downloaded: 202610-26T11:43Z
Check the source to verify that this is the currentversion before use.

TABLE IV

Minimum overflow capacity	Outside height not including closure	Outside diameter including bead below closure if any	Minimum weight not including closure
Fl. Ozs.	*Inches*	*Inches*	*Ounces*
0.5	1⅛–2⅛	1⅛–1⅛	1⅛
1.0	1⅛–2¼	1⅛–2⅛	1⅛
2.0	2 –2⅛	1¼–2¼	2⅛
4.0	2½–3⅛	2⅛–2⅛	5
8.0	2⅛–3⅛	2¼–3½	9¼
16.0	3½–4½	3½–4⅛	12½

TABLE V

Capacity	Height	Width	Nominal thread diameter of finish, in millimeters	Weight
Ounces	*Inches*	*Inches*		*Ounces*
1	2⅛ ± ⅛	1⅛ ± ⅛	28	1½ ± ½
2	3⅛ ± ⅛	1⅛ ± ⅛	33	2½ ± ½
4	4⅛ ± ¼	1⅜ ± ⅛	38	4½ ± ½
6	4½ ± ¼	2⅛ ± ⅛	48	5½ ± 1
8	5 ± ¼	2⅛ ± ⅛	48	7¼ ± 1
16	6 ± ½	2⅛ ± ⅛	63 or 58	12 ± 1

(Actual capacity shall be at least the nominal capacity for each size).

3.5.2.1 *Closures.*—Screwcap closures shall be made of a urea formaldehyde mixture, or other suitable plastic. (See 3.1.2 and 3.2.2.) Screwcaps shall be molded to fit jars listed in 3.5.2, shall be satisfactorily resistant to impact, and shall make a sufficiently tight closure to prevent accidental opening. Caps shall be of adequate weight and design.

3.5.2.1.1 *Liners.*—Cap shall be fitted with a liner consisting of a cork composition or pulp backing, and a saran film, pliofilm, or vinylite facing mounted on white sulfite paper (see 3.1.2.1). If pulp backing is supplied, overall thickness shall be 0.050 inch ± 10 percent for 28 mm. and 33 mm. cap size, and 0.040 inch ± 10 percent for the remaining

Source: https://assist.dla.mil -- Downloaded: 202610-26T11:43Z
Check the source to verify that this is the currentversion before use.

cap sizes. If cork composition is supplied, thickness shall be 0.0625 inch ± 10 percent.

3.6 Identification marking.—Bottles shall be permanently and legibly marked with the name or registered trademark of the manufacturer. Bottles shall be marked with a symbol to show their capacity.

3.7 Workmanship.—Workmanship shall be in accordance with good commercial practice. Bottles and jars shall be symmetrically made, and reasonably free from seeds, blisters, and other imperfections which may impair their serviceability, strength, appearance or efficiency. Bottles and jars shall be supplied with the screwcap in place and shall be clean and dry.

4. SAMPLING, INSPECTION, AND TEST PROCEDURES

4.1 Supplier responsibilities for inspection.—Such examinations and tests as are set forth in this specification or as shall otherwise be appropriate or necessary to insure that supplies conform to specification requirements, shall be performed by and at the expense of the supplier. Suppliers who do not have facilities adequate for such tests shall arrange for the use of test facilities acceptable to the Government. Records of examination and tests performed by the supplier shall be maintained by the supplier and made available to the Government, upon the Government's request, at any time, or from time to time, for a period of 2 years after delivery of the supplies to which such records relate.

4.1.1 Inspection, as used in this specification, is defined as both examination (such as visual, auditory, etc. investigation without the use of special laboratory appliances or procedures) and testing (determination by technical means of physical and chemical properties) of the item.

4.1.2 *Inspection lot.* — Unless otherwise specified, a lot shall consist of bottles or jars, of the same style and size, manufactured by the same process by one manufacturer and submitted for delivery at one time.

4.1.3 *Inspection unit.* — Inspection unit shall be one bottle or jar, with closure.

4.1.4 *Certificates of quality.*—When available, certificates of quality, supplied by the manufacturer of the component or material, listing the specified test method and test results obtained may be furnished in lieu of actual performance of such testing by the contractor.

4.2 **Sampling.**

4.2.1 *Method of drawing samples.*

4.2.1.1 *Containers.*—Containers of bottles or jars shall be selected at random in accordance with table VI.

TABLE VI.

Lot size	2 dozen or less per container	Over 2 dozen, less than 6 dozen per container	6 dozen or more per container
	Number of containers to be selected		
Gross			
2 to 4	7	5	2-3
5 to 10	25	20	10
11 to 22	50	35	25
23 to 55	75	50	35
56 to 152	110	75	50
153 to 763	150	110	75
764 to 3819	225	150	110
Over 3819	450	300	225

4.2.1.2 *Bottles and jars.*—A sufficient number of bottles and/or jars with closures to give the total sample required by Military Standard MIL–STD–105 shall be drawn in approximately equal numbers from each selected case or carton.

Source: https://assist.dla.mil -- Downloaded: 202610-26T11:43Z
Check the source to verify that this is the current version before use.

4.2.2 *For visual and dimensional examination.*—A random sample of items shall be selected in accordance with Military Standard MIL–STD–105. The inspection level shall be as specified in table VII.

4.2.3 *For tests.* — A random sample of items shall be selected in accordance with Military Standard MIL–STD–105. The inspection level shall be as specified in table VII. However, the sample shall be not less than 5 bottles or jars, with closures.

4.3 Inspection.

4.3.1 *For visual and dimensional.*—Each sample selected in accordance with 4.2.2 shall be examined for defects listed in 4.4. The acceptable quality level (AQL) shall be as specified in table VII.

4.3.2 *For tests.*—Each sample selected in accordance with 4.2.3 shall be tested as specified in 4.5. The acceptable quality level (AQL) shall be as specified in table VII.

4.3.2.1 Where possible, the same sample unit shall be used for the determination of two or more test characteristics.

TABLE VII.

Inspection and Acceptable Quality Levels

	Inspection level	*AQL (percent defective)*
Visual and dimensional examination:		
Major defects	II	1.5
Minor defects	II	4.0
Materials testing:		
Chemical resistance	L3	0.

4.4 Classification of defects.—Visual and dimensional examination shall be conducted in accordance with the following classification of defects:

Categories and defects

Major

101. Does not comply with capacity requirements (see tables I through V).
102. Open blisters.
103. Blisters over 5/32 inch.
104. Stones over 1/32 inch.
105. Glass not free of cracks or chips.
106. Glass not uniformly distributed.
107. Distorted thread.
108. Not clean and dry.
109. Liners in closures not tight fitting.
110. Liners in closures not faced.
111. Contacting edges of closure not formed to fit properly.
112. Closure not leakproof.
113. Pipette for type I bottle not tight and secure fit in the rubber bulb.
114. Bulb for type I bottle not formed to fit properly.
115. Bulb for type I bottle not free of holes, bloom, color irregularities, impurities, or other defects.
116. Tip of pipette in type I bottle not smooth and straight.

Minor

201. Does not comply with dimensional requirements (see tables I, III, IV, and V).
202. Does not comply with weight requirements (see tables I through V).
203. Blisters 1/16 inch to 5/32 inch.
204. Glass not free of rough seams or edges, seeds, striae, tears, checks, crizzles, or deformed areas.
205. Not symmetrical in shape.
206. Permanent legible identification and capacity marking not present.
207. Exterior of closure not plain and not smooth.
208. Tops of closures 38 millimeter and larger not flat.
209. Labels on type I bottles not fully displayed.

4.5 Test procedures.

4.5.1 *Chemical resistance.*—Glass bottles and jars shall be tested in accordance with procedures described for type III glass as shown in the Pharmacopoeia of the United States. Any variation from the requirements will be considered a defect.

5. PREPARATION FOR DELIVERY

For civil agency procurement the definitions and applications of the levels of packaging and packing shall be in accordance with Federal Standard No. 102.

Source: https://assist.dla.mil -- Downloaded: 202610-26T11:43Z.
Check the source to verify that this is the currentversion before use.

TABLE VIII—*Packaging quantities*.

Type and style	Size	No. of bottles or jars constituting one unit	Units to each package	Units per intermediate package	Units per exterior shipping container
Type I	½ oz. & 1 oz.	12	1	Not required	24
Type II, style 1	½ oz. & 1 oz.	72	1	Not required	6
	2 oz. & 3 oz.	72	1	Not required	4
	4 oz.	72	1	Not required	2
	6 oz. & 8 oz.	36	1	Not required	2
	12 oz. & 16 oz.	18	1	Not required	2
	32 oz.	1	Not required	18	16
Type II, style 2	2 Dr.	72	1	Not required	12
	4 Dr.	72	1	Not required	8
	6 Dr.	72	1	Not required	6
	10 Dr. & 13 Dr.	72	1	Not required	4
Type III, style 1	½ oz.	12	1	Not required	36
	1 oz.	12	1	Not required	24
	2 oz.	12	1	Not required	12
	4 oz.	12	1	Not required	6
	8 oz.	1	Not required	12	48
	1 lb.	1	Not required	12	36
Type III, style 2	1 oz.	12	1	Not required	24
	2 oz.	12	1	Not required	18
	4 oz.	12	1	Not required	12
	6 oz.	12	1	Not required	8
	8 oz.	12	1	Not required	6
	16 oz.	12	1	Not required	4

5.1 **Packaging.**

5.1.1 *Unit.*—The number of bottles or jars specified in table VIII constitutes one unit.

5.1.2 *Packaging quantities.*—The number of units indicated in table VIII shall be packaged in each unit, intermediate and exterior container as applicable for the required level of protection specified in procurement document.

5.1.2.1 *Packing variation permitted.* — If the required number of units to be shipped is less than the number of units specified to be overpacked in an exterior container, such units shall be packed in an exterior container of suitable size and design, acceptable to a common carrier, which will insure safe delivery to destination.

5.1.3 *Level A.*

5.1.3.1 *Unit package.*

5.1.3.1.1 *Type I.*—Type I, dropper bottles, in quantities as specified in table VIII, shall be packaged in a corrugated fiberboard carton constructed in accordance with Federal Specification PPP–B–636, type I, class 1. Carton shall be provided with full height partitions, fabricated of 0.030 inch chipboard, so arranged that each bottle is securely held in an individual cell. Closure shall be adequate to prevent spillage of contents under normal handling. As an alternate style, carton may have a lock type bottom and tuck-in top.

5.1.3.1.2 *Type II, style 1.*—Type II, style 1, sizes ½ oz. through 16 oz. in quantities as specified in table VIII, shall be packaged in

Source: https://assist.dla.mil -- Downloaded: 202610-26T11:43Z
Check the source to verify that this is the currentversion before use.

a carton of appropriate size constructed in accordance with the requirements of Federal Specification PPP–B–636. Package design shall include suitable corrugated fiberboard or chipboard separators to form individual cells for each bottle, except that three ½-ounce or 1-ounce bottles or two 2-ounce or 3-ounce bottles may be packaged to the cell. Closure shall be adequate to prevent spillage of contents under normal handling.

5.1.3.1.3 *Type II, style 2 and type III, styles 1 and 2.*—Type II, style 2, type III, style 1, sizes ½ oz. through 4 oz., and type III, style 2, in quantities as specified in table VIII, shall be packaged in a carton of appropriate size constructed in accordance with Federal Specification PPP–B–636, type I, class 1. Carton shall be designed with suitable interior fittings, or shall contain sufficient cushioning material to insure against shifting of, or damage to, the contents. Carton shall be adequately secured to prevent accidental opening.

5.1.3.2 *Intermediate package.* — Type II, style 1, 32 oz. and type III, style 1, 8 oz. and 1 lb. shall be individually packaged in a carton of appropriate size constructed in accordance with Federal Specification PPP–B–636, type I, class 1. Package design shall include suitable corrugated fiberboard or chipboard separators to form individual cells for each bottle or jar. Closure shall be adequate to prevent spillage of contents under normal handling.

5.1.4 *Level C.*—Units shall be packaged in standard commercial containers of the size and kind commonly used, which will afford the degree of protection required for shipment and use of the product for its intended purpose within the continental limits of the United States of America.

5.2 Packing.

5.2.1 *Level A.*

5.2.1.1 *Protective pack.*—The number of units specified in column 6 of table VIII shall be packed in a carton of appropriate size constructed in accordance with Federal Specification PPP–B–636, type I, class 1 and fabricated of not less than 275-pound test fiberboard. Carton shall be secured as indicated in the appendix to the box specification.

5.2.1.2 *Exterior container.* — Bottles and jars packaged as specified in 5.1.3, 5.1.4, and 5.2.1.1 shall be overpacked in a box of appropriate size constructed in accordance with Federal Specification PPP–B–636, class 2, style RSC, compliance symbol V3c. Closure shall be as specified in 30.2.2.1 thereof and in addition, the center seam shall be closed by means of tape conforming to the requirements of Federal Specification PPP–T–76 or PPP–T–45. The tape shall be not less than 3 inches wide and shall extend at least 2 inches onto each of the end panels. Strapping will not be required.

5.2.2 *Level B.*

5.2.2.1 *Exterior container.* — Bottles and jars packaged as specified in 5.1.3 shall be overpacked in a box of appropriate size constructed in accordance with Federal Specification PPP–B–636, type I, class 1 and fabricated of not less than 275-pound test fiberboard.

5.2.3 *Level C.* — The subject commodity shall be packed in substantial commercial containers of the type, size, and kind commonly used for the purpose, so constructed as to insure acceptance and safe delivery by common or other carriers, at the lowest rate, to point of delivery called for in the contract or purchase order.

5.3 Marking.

5.3.1 *Civil agencies.*—In addition to any special marking required by the contract or order, marking shall be in accordance with Federal Standard No. 123.

5.3.2 *Military agencies.*

5.3.2.1 *Interior packages.*—Each unit package or each intermediate package, as applicable, shall be marked in accordance with

Source: https://assist.dla.mil -- Downloaded: 202610-26T11:43Z
Check the source to verify that this is the currentversion before use.

section 5 of Military Standard MIL-STD-129.

5.3.2.2 *Exterior container.*—Exterior container shall be marked in accordance with Military Standard MIL-STD-129, except that 6.2(c), 6.2(d), 6.5 and 7.5.1 shall not be applicable. Service color and service symbol markings are required only on direct shipments from the contractor's plant to overseas activities.

6. NOTES

6.1 Intended use.

6.1.1 *Type I, bottles, dropper.*—Intended for use in dispensing small or drop doses of medicaments, as well as eye, ear, and nose preparations.

6.1.2 *Type II, bottles, screwcap.*

6.1.2.1 *Style 1, for liquids.*—Intended for use in dispensing pharmaceutical liquid preparations from prescriptions.

6.1.2.2 *Style 2, for tablets and capsules.*—Intended for use in packaging tablets and capsules in the dispensing of prescriptions.

6.1.3 *Type III, jars.*

6.1.3.1 *Style 1, for ointments.*—Intended for use in dispensing and packaging ointments from prescriptions.

6.1.3.2 *Style 2, for powders.*—Intended for use for packaging powders in dispensing of prescriptions.

6.2 **Ordering data.** — Procurement documents should specify the following:

(*a*) Number and date of this specification.
(*b*) Type, style, and color required (see 1.2.1 and 1.2.2).
(*c*) Color of closures required (see 3.2.2).
(*d*) Capacity of bottles and/or jars required (see 1.2.3).
(*e*) Selection of applicable levels of packaging and packing (see 5.1 and 5.2).

6.3 This specification covers the following items appearing in the Armed Services Medical Stock List:

8125-404-7500 BOTTLE, DROPPER, Prescription, ½ oz., 12s.
8125-404-7700 BOTTLE, DROPPER, Prescription, 1 oz., 12s.
8125-406-0120 BOTTLE, SCREW CAP, Prescription, 1 oz., 72s.
8125-406-0150 BOTTLE, SCREW CAP, Prescription, 2 oz., 72s.
8125-406-0180 BOTTLE, SCREW CAP, Prescription, 4 oz., 72s.
8125-406-0210 BOTTLE, SCREW CAP, Prescription, 8 oz., 36s.
8125-406-0240 BOTTLE, SCREW CAP, Prescription, 16 oz., 18s.
8125-406-0270 BOTTLE, SCREW CAP, Prescription, 32 oz.
8125-408-3520 BOTTLE, SCREW CAP, Tablet and Capsule, 2 Dr., 72s.
8125-408-3525 BOTTLE, SCREW CAP, Tablet and Capsule, 4 Dr., 72s.
8125-408-3530 BOTTLE, SCREW CAP, Tablet and Capsule, 6 Dr., 72s.
8125-408-3540 BOTTLE, SCREW CAP, Tablet and Capsule, 10 Dr., 72s.
8125-408-3545 BOTTLE, SCREW CAP, Tablet and Capsule, 13 Dr., 72s.
8125-430-5380 JAR, SCREW CAP, Ointment, ½ oz., 12s.
8125-430-5390 JAR, SCREW CAP, Ointment, 1 oz., 12s.
8125-430-5400 JAR, SCREW CAP, Ointment, 2 oz., 12s.
8125-430-5410 JAR, SCREW CAP, Ointment, 4 oz., 12s.
8125-430-5420 JAR, SCREW CAP, Ointment, 8 oz.
8125-430-5436 JAR, SCREW CAP, Ointment, 1 lb.
8125-430-5540 JAR, SCREW CAP, Powder, 1 oz., 12s.

Source: https://assist.dla.mil -- Downloaded: 202610-26T11:43Z
Check the source to verify that this is the currentversion before use.

8125–430–5545 JAR, SCREW CAP, Powder, 2 oz., 12s.
8125–430–5550 JAR, SCREW CAP, Powder, 4 oz., 12s.
8125–430–5555 JAR, SCREW CAP, Powder, 6 oz., 12s.
8125–430–5560 JAR, SCREW CAP, Powder, 8 oz., 12s.
8125–430–5565 JAR, SCREW CAP, Powder, 16 oz., 12s.

6.4 This specification does not include all types, classes, grades, sizes, etc., of the commodity indicated by the title of this specification, or which are commercially available, but is intended to cover the types, etc., which are normally procured to meet Federal Government requirements.

Notice. — When Government drawings, specifications, or other data are used for any purpose other than in connection with a definitely related Government procurement operation, the United States Government thereby incurs no responsibility nor any obligation whatsoever; and the fact that the Government may have formulated, furnished, or in any way supplied the said drawings, specifications, or other data, is not to be regarded by implication or otherwise as in any manner licensing the holder or any other person or corporation, or conveying any rights or permission to manufacture, use, or sell any patented invention that may in any way be related thereto.

MILITARY INTERESTS:
Army—M
Navy—Mid
Air Force.

Copies of this specification may be purchased for 10 cents each.

Source: https://assist.dla.mil -- Downloaded: 202610-26T11:43Z
Check the source to verify that this is the current version before use.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:43Z
Check the source to verify that this is the current version before use.

SPECIFICATION ANALYSIS SHEET

Form Approved
Budget Bureau No. 119-R004

INSTRUCTIONS

This sheet is to be filled out by personnel either Government or contractor, involved in the use of the specification in procurement of products for ultimate use by the Department of Defense. This sheet is provided for obtaining information on the use of this specification which will insure that suitable products can be procured with a minimum amount of delay and at the least cost. Comments and the return of this form will be appreciated. Fold on lines on reverse side, staple in corner, and send to preparing activity *(as indicated on reverse hereof)*.

SPECIFICATION

ORGANIZATION *(Of submitter)* | CITY AND STATE

CONTRACT NO. | QUANTITY OF ITEM PROCURED | DOLLAR AMOUNT
$

MATERIAL PROCURED UNDER A

☐ DIRECT GOVERNMENT CONTRACT ☐ SUBCONTRACT

1. HAS ANY PART OF THE SPECIFICATION CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE?

A. GIVE PARAGRAPH NUMBER AND WORDING.

B. RECOMMENDATIONS FOR CORRECTING THE DEFICIENCIES.

2. COMMENTS ON ANY SPECIFICATION REQUIREMENT CONSIDERED TOO RIGID

3. IS THE SPECIFICATION RESTRICTIVE?

☐ YES ☐ NO IF "YES", IN WHAT WAY?

4. REMARKS *(Attach any pertinent data which may be of use in improving this specification. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity)*

SUBMITTED BY *(Printed or typed name and activity)* | DATE

DD, FORM 1426 APR 63

REPLACES NAVSHIPS FORM 4863, WHICH IS OBSOLETE

PLATE NO. 19419

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:43Z
Check the source to verify that this is the current version before use.

FOLD

DEPARTMENT OF THE NAVY

POSTAGE AND FEES PAID
NAVY DEPARTMENT

OFFICIAL BUSINESS

Commander
Defense General Supply Center
Attn: DGSCT-S
Richmond, Va. 23212

FOLD

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:43Z
Check the source to verify that this is the current version before use.