DD-G-541b
w/INT. AMENDMENT 1
23 Sep 1974
USED IN LIEU OF
DD-G-541b
12 Jan 1966

INTERIM AMENDMENT TO FEDERAL SPECIFICATION

GLASS (LABORATORY)

This interim amendment was developed by the Defense Personnel Support Center, 2800 South 20th Street, Philadelphia, PA 19101, based upon currently available technical information. It is recommended that Federal agencies use it in procurement and forward recommendations for changes to the preparing activity at the address shown above.

The General Services Administration has authorized the use of this interim amendment as a valid exception to Federal Specification DD-G-541b.

Page 2

Table I, Type I, Class B. Revise as follows:

Softening point °C. delete "799 ± 10" and substitute "799 +10, -24"

Coefficient of expansion
cm./cm. °C delete "50.0 +2, -4 x 10^{-7}" and substitute "50 +8, -4 x 10^{-7}".

Military Custodians:
Army – MD
Navy - MS
Air Force – 03

Review Activities:
Army – MD
Navy – MS
Air Force - 03

Preparing Activity
Defense Supply Agency – DM

Project No. 6640-0906

FSC 6640

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:43Z
Check the source to verify that this is the current version before use.