MILITARY SPECIFICATION

RUBBER, SYNTHETIC, SOLID, SHEET, STRIP AND FABRICATED PARTS, SYNTHETIC OIL RESISTANT

This amendment forms a part of Military Specification MIL-R-7362D, dated 2 May 1967, and is approved for use by all Departments and Agencies of the Department of Defense.

PAGE 1

Paragraph 2.1, under "SPECIFICATIONS, Federal": Delete "NN-P-515 Plywood, Container Grade" and substitute "NN-P-530 Plywood, Flat Panel". Delete "UU-T-111 Tape; Paper, Gummed (Sealing and Securing)", and substitute "PPP-T-45 Tape; Gummed Paper, Reinforced and Plain (Sealing and Securing)".

PAGE 3

Paragraph 2.2: After the ASTM listings, add the following:

"SOCIETY OF AUTOMOTIVE ENGINEERS (SAE)

AMS 3021 Reference Fluid for Testing Di-Ester (Polyol) Resistant Material

(Application for copies should be addressed to the Society of Automotive Engineers, Inc., 400 Commonwealth Drive, Warrendale, PA 15096.)"

Paragraph 3.1: After the last sentence, add the following:

"Preproduction tests are not necessarily required on all new orders (see 6.3). If there are any changes in materials or manufacturing processes, new preproduction tests are required."

FSC 5330

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T08:26Z
Check the source to verify that this is the current version before use.

PAGE 4

Table I: Delete and substitute:

"TABLE I. Thickness tolerances of sheet.

Nominal thickness (inch)	Tolerances (inch)
.031 and less	± .010
Over .031 to .063 inclusive	± .012
Over .063 to .125 inclusive	± .016
Over .125 to .188 inclusive	± .020
Over .188 to .375 inclusive	± .031
Over .375 to .563 inclusive	± .047
Over .563 to .750 inclusive	± .063
Over .750 to 1.000 inclusive	± .093
Over 1.000 inclusive	± 10%"

PAGE 5

Table II: Add:

"Air aged - 22 hours at 257° ± 2°F

	Type I	Type II
Compression set, percent, max.		40
under 0.110 inch	60	
over 0.110 inch	55"	

PAGE 6

Paragraph 4.1: Delete and substitute:

"4.1 Responsible for inspection. Unless otherwise specified in the contract, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified, the contractor may utilize his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements."

PAGE 7

Paragraph 4.4: Delete and substitute:

"4.4 Quality conformance inspection. Sampling for quality conformance inspection shall be in accordance with MIL-STD-105, except where otherwise indicated herein. Quality conformance tests are required for all production lots of material."

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T08:26Z
Check the source to verify that this is the current version before use.

Paragraph 4.4.1.1: Delete and substitute following paragraphs:

"4.4.1.1 Lot. A lot shall consist of all material of the same identity cured in the same production run, from the same batch, and submitted at the same time for inspection.

4.4.1.2 Batch. A batch shall be the quantity of material compounded on a mill or mixer at one time."

PAGE 10

Paragraphs 4.4.6 and 4.4.6.1: Delete and substitute:

"4.4.6. Quality conformance tests. The following tests shall be conducted on each lot of material:

Original	Air aged
Tensile Strength	22 hours at 257° ± 2°F
Elongation	Compression Set
Hardness	

If the items are unsuitable for use as test samples, tests shall be performed on samples of identical composition and state of cure as the end item.

4.4.6.1 Rejection criteria. A lot shall be rejected upon the failure of any sample to meet the test requirements specified herein. A lot that has been rejected may be reworked to correct the deficiencies and resubmitted for acceptance."

Paragraph 4.5.1, line 2: Delete "Stauffer Blend 7700" and substitute "AMS 3021".

PAGE 13

Paragraph 4.6.4.3, line 10: Delete "Stauffer Blend 7700" and substitute "AMS 3021 fluid".

Add the following paragraph:

"4.6.4.4 Air aged compression set. Compression set shall be determined in accordance with ASTM D395, Method B unless otherwise specified. Specimens for Type I material shall be two o-rings. Two circular plied-up buttons with dimensions of 1.129 ± 0.010 inches diameter and approximately 0.5 inch thick shall be used for Type II material. The percentage of compression employed shall be 25 percent."

Add the following paragraph:

"4.7 Packaging inspection - Sample packages and packs and the inspection

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T08:26Z
Check the source to verify that this is the current version before use.

of the packaging, packing and marking for shipment and storage shall be in accordance with the requirements of Section 5 and the documents specified therein, or as otherwise specified in the contract or order."

Section 5, delete "Preparation for Delivery" and substitute the following:

5. Packaging

Paragraph 5.1: Delete in its entirety and substitute the following:

5.1 Preservation - packaging - Preservation - packaging shall be level A or C as specified (See 6.2).

Paragraph 5.1.1.2.2, line 5: Delete "UU-T-111" and substitute "PPP-T-45".

PAGE 14

Paragraph 5.2.1.2, line 11: Delete "NN-P-515" and substitute "NN-P-530".

Paragraph 6.2.h: Delete in its entirety and substitute the following:

"h. Applicable levels of preservation - packaging and packing (see Section 5)."

PAGE 15

Paragraph 6.3: Delete and substitute:

"6.3 Preproduction test. Unless otherwise specified, the supplier is responsible for all preproduction tests required for each type and class of material furnished to this specification. A copy of the preproduction test report shall be furnished the Air Force Wright-Aeronautical Laboratories, MLSA, Wright-Patterson AF Base, Ohio 45433. The preproduction tests need not be repeated for new orders or different parts provided the materials and processes have not been changed and a certified statement to this effect is furnished to the procuring activity. The waiving of the preproduction test will be strictly at the discretion of the procuring activity. Test results to previous revisions of the specification are not acceptable. Preproduction tests will not be acceptable if they are more than 3 years old."

Paragraph 6.4: Delete in its entirety.

Custodians:
Army - MR
Navy - AS
Air Force - 11

Preparing activity:
Air Force - 11

(Project No. 5330-0535)

Review activities
Army - MI, MU
Air Force - 99
DLA - IS

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T08:26Z
Check the source to verify that this is the current version before use.