MIL-T-7378A(USAF)
AMENDMENT 4
24 December 1963
Superseding
AMENDMENT 3
6 February 1962

MILITARY SPECIFICATION

TANKS, FUEL, AIRCRAFT, EXTERNAL
AUXILIARY, REMOVABLE

This amendment forms a part of Military Specification MIL-T-7378A(USAF) dated 20 October 1958.

Pages 1 through 3, paragraph 2.1:
Under "SPECIFICATIONS, Federal", delete:

"TT-P-664	Primer, Coating, Synthetic, Rust-Inhibiting, Lacquer-Resisting"

Under "SPECIFICATIONS, Military":
Delete:

"MIL-D-5028	Drawings and Data Lists: Preparation Of Manufacturers' (For Production Aeronautical and Associated Equipment)
"MIL-L-6047	Lacquer, Aromatic Fuel Resistant
"MIL-P-6889	Primer; Zinc-Chromate, For Aircraft Use
"MIL-T-9107	Test Reports; Preparation Of"

Add:

"MIL-P-7962	Primer Coating, Cellulose-Nitrate Modified Alkyd Type, Corrosion Inhibiting, Fast-Drying (For Spray Application Over Pretreatment Coating)
"MIL-I-8500	Interchangeability and Replaceability of Component Parts For Aircraft and Missiles
"MIL-C-8507	Coating, Wash Primer (Pretreatment) For Metals, Application Of (For Aeronautical Use)
"MIL-C-8514	Coating Compound, Metal Pretreatment, Resin/Acid
"MIL-P-8585	Primer Coating, Zinc Chromate, Low-Moisture-Sensitivity
"MIL-F-18264	Finishes, Organic, Aircraft, Application and Control Of

FSC 1640

Source: https://assist.dla.mil -- Downloaded: 202640-17T08:27Z
Check the source to verify that this is the current version before use.

"MIL-L-19537	Lacquer, Acrylic Nitrocellulose Gloss (For Aircraft Use)
"MIL-D-70327	Drawings, Engineering and Associated Lists"

Under "STANDARDS, Military", add:

"MIL-STD-143	Specifications and Standards; Order of Precedence for Selection Of
"MIL-STD-831	Test Reports, Preparation Of"

Under "PUBLICATIONS", delete:

"No. 143	Specifications and Standards; Use Of"

Page 3, paragraph 3.3, line 3: Delete ANA "Bulletin 143" and substitute "MIL-STD-143."

Page 5, paragraph 3.5.3.1, line 5: Delete "all metal type" and substitute "all metal or nylon insert types".

Page 14, paragraph 3.9: Delete and substitute:

"3.9 Interchangeability. All parts having the same manufacturer's part number shall be functionally and dimensionally interchangeable in accordance with the requirements of Specification MIL-I-8500. The drawing number requirements of Specification MIL-D-70327 shall govern changes in the manufacturer's part numbers."

Page 14, paragraph 3.10.1: Delete and substitute:

"3.10.1 Aluminum and aluminum alloy tanks

"3.10.1.1 All aluminum parts shall be treated in accordance with MIL-A-8625 or MIL-C-5541.

"3.10.1.2 The exterior surfaces of tanks and integral pylons for tanks shall be finished as required in 3.10.1.1 with the following additional coatings:

a. One coat of Specification MIL-C-8514 wash primer applied in accordance with the procedure given in MIL-C-8507.

b. One coat of Specification MIL-P-7962 lacquer primer applied in accordance with the procedure given in Specification MIL-F-18264.

Source: https://assist.dla.mil -- Downloaded: 202610-17T08:27Z
Check the source to verify that this is the current version before use.

c. Two coats of Specification MIL-L-19537 acrylic nitro-cellulose lacquer applied in accordance with the procedure given in Specification MIL-F-18264.

"3.10.1.2.1 Inspection of quality and process control shall be conducted in accordance with Specification MIL-F-18264.

"3.10.1.3 The interior surfaces of parts not exposed to fuel such as integral pylons, fins, tail cones, **etc., shall** be finished with two coats of Specification MIL-P-8585 zinc-chromate primer in addition to the treatment specified in 3.10.1.1."

Page 15, paragraph 3.10.2: Delete and substitute:

"3.10.2 Steel tanks

"3.10.2.1 The interior surfaces exposed to fuel shall be finished using Specification MIL-C-490 phosphate treatment and then coated in accordance with Specification MIL-C-4556.

"3.10.2.2 Exterior surfaces shall be finished using Specification MIL-C-490 phosphate treatment and shall then be processed to the requirements of 3.10.1.2.a, 3.10.1.2.b, 3.10.1.2.c, and 3.10.1.2.1.

"3.10.2.3 Interior surfaces not exposed to fuel, such as fins, fairings, and etc., shall be finished in accordance with MIL-C-490 and then two coats of Specification MIL-P-8585 zinc chromate primer."

Page 25, paragraph 4.5.3, line 3: Delete "MIL-T-9107" and substitute "MIL-STD-831".

RSM/nss
SETPF

Source: https://assist.dla.mil -- Downloaded: 202610-17T08:27Z
Check the source to verify that this is the currentversion before use.