(METRIC)

A-A-2853
October 27, 1993

COMMERCIAL ITEM DESCRIPTION

PAPER, FACSIMILE

The General Services Administration has authorized the use of this commercial item description, for all Federal Agencies.

1. Scope: This description covers coated facsimile papers in roll form.

2. Salient Characteristics.

2.1 Materials. All facsimile paper rolls shall be designed for use in direct thermal facsimile machines. The facsimile paper shall be made from bleached chemical wood pulp and the coating shall not contain any toxic or allergic agent that may be harmful to the user. The image produced shall be legible for a minimum of three years and black in color.

2.2 Paper Dimensions. The length and width of the facsimile paper shall be as specified. The tolerances for the length and width shall be - 30.48 cm (- 1 foot) and +/- 1.6 mm (+/- 1/16 inch) respectively.

2.3 Cores. Inside core diameter sizes for roll facsimile paper shall be as specified per contract or order with a tolerance of + 1.27 mm, - 0.00 mm (+ 0.05 inch, - 0.00 mm). The width shall be as specified per contract or order with a tolerance of + 0.0 mm, - 1.6 mm (+ 0.0 inch, - 0.0625 inch).

2.4 Coating. Facsimile paper shall be coated side in or out as specified.

2.5 Rolls. Rolls shall have the outer end secured by spot gluing or pressure adhesive tape to keep the roll from unraveling, yet permit separation, without the need for cutting the top layers of the roll. The finished facsimile paper shall be white on both sides and one continuous length. No splices are permitted. The rolls' outside diameter shall not interfere with the insertion and dispensing of the roll.

Beneficial comments, recommendations, additions, deletions, clarifications, etc. and any data which may improve this document should be sent to General Services Administration, Federal Supply Service, Engineering Branch, 26 Federal Plaza, New York, N.Y. 10278.

Distribution Statement A:
Approved for public release
Distribution is unlimited

FSC 7530

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:26Z
Check the source to verify that this is the current version before use.

2.6 Warning signal. All roll facsimile paper shall have a contrasting colored warning stripe to signal that the end of the roll is near. The stripe shall start 1.5-3.0 m (5-10 feet) from the end of the roll. The stripe shall not impair the legibility of the produced image on the paper.

2.7 Workmanship. Facsimile paper shall be free of any defects that may affect appearance or serviceability. The paper shall be clean, free of lint, paper dust, grit spots, wrinkles, folds, holes, tears and smudges. The edges of the roll shall be clean cut and not nicked or uneven.

3. Requirements. Facsimile paper shall not malfunction such as, jamming, tearing, poor imaging or no imaging and comply with Table 1, below.

Table 1

Characteristic	Requirement	Test Method
Optical Density, Max., unimaged area	0.08	para. 4.1
Optical Density, Min. at 0.34 mj, imaged area	1.14	ASTM F1405
Heat Stability Optical Density	1.14 min./0.20 max.*	para. 4.3
Caliper, mm	0.057-0.068	TAPPI T 411
Smoothness, Bekk, Min.	200 seconds	TAPPI T 479
Tear Strength, gms., Min., CD	20	TAPPI T 41[illegible]
Brightness, %, Min., Coated Side	70	TAPPI T 45[illegible]

*optical density values for imaged area/unimaged area, respectively

3.1 Tests. Optical Density Test. Determine the optical density of unimaged facsimile paper by randomly selecting an approximately one square foot in area of facsimile paper. Using a Tobias or Macbeth densitometer and following the procedure in the densitometer's manual, take 5 readings from the unimaged areas of the imaging side of the facsimile paper and averaging the five readings.

3.1.1. The optical density of facsimile paper shall also be determined in accordance with ASTM F1405 using the following test conditions:

Printhead - Thin film Kyocera KST-216-8MPD1, 622 Ohms
Print Speed 1 inch/sec; T cycle = 5.00 msec
Ambient Temperature - 30°C
Printhead Pressure - 8 lbs
Print Platen - 50
Printhead Voltage - 21.0 volts
Densitometer - Tobias or Macbeth
T_{on} Time (Strobe Time) - Sequenced up to 0.50 msec. Ten individual section imaged per print sample each with an increasing amount of Ton or energy. The strobe or T_{on} time for each of the print sections during the test shall begin with 0.05 msec. and increase at increments of 0.05 msec.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:26Z
Check the source to verify that this is the current version before use.

To be considered acceptable, the minimum optical density of the imaged area at 0.34 mj shall be 1.14. After testing, save the imaged paper for the heat stability test.

3.2 Performance test Set the GSA designated facsimile machine, maintained in accordance with the manufacturer's instructions, on copy mode. Using at least the last 20 feet of facsimile paper on the roll, make copies of an original having characters whose font size is 6 or smaller. Continue to copy until the roll's warning signal appears. The facsimile machine shall be maintained in accordance with the manufacturer's instructions. To be considered acceptable:

1) The paper shall function without jamming or interrupting the operation of the fax machine
2) The imaged area shall be uniform, permanent, black and clearly legible.
3) There shall be no voids or streaks on the imaged area.
4) The unimaged area shall remain white.before and after processing
5) The roll shall fit easily into the facsimile machine and dispense properly.
6) If applicable, the facsimile paper shall be easily and cleanly cut by the facsimile machine paper cutter.
7) The warning signal shall appear at least 5 feet from the end of the paper.
8) The warning signal shall not impair the legibility of the imaged area on the paper.

3.3 Heat Stability Test Place the tested facsimile paper from the Optical Density test in an oven chamber set at 60°C for 24 hours. After heat stability testing, to be considered acceptable:

1) The imaged area shall be uniform, black and clearly legible.
2) The minimum optical density of the imaged area at 0.34 mj of print energy shall be 1.14.
3) The optical density reading of the unimaged areas shall be 0.2 maximum.
4) The coating on the paper shall not exhibit defects such as, flake, loosen, brittle or powdery, or adversely affect the legiblity of the imaged facsimile paper.

4. Quality Assurance. The contractor shall certify and maintain substantiating evidence that the product offered meets the salient characteristics of this Commercial Item Description, and that the product conforms to the producer's own drawings, specifications, standards, and quality assurance practices. The government reserves the right to require proof of such conformance prior to first delivery and thereafter as may be otherwise provided for under the provisions of the contract.

4.1. Unless otherwise specified, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract, the contractor may utilize their own facilities or any commercial laboratory acceptable to the Government. The Government reserves the right to perform any of the inspections set forth in this commercial item description where such inspections are deemed necessary to assure that supplies and services conform to prescribed requirements.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:26Z
Check the source to verify that this is the current version before use.

4.2. Sampling shall be in accordance with MIL-STD-105 using the plans as specified in Table 2, unless stated otherwise. The sample unit for visual and dimensional examinations shall be one roll, unless stated otherwise. The sample unit for preparation for delivery shall be one completed shipping container.

Table 2

Examine	Inspection Level	AQL (% defective
Visual Defects	S-4	4.0
Tests	S-4	4.0
Examination for Dimensions	S-3	4.0
Preparation for Delivery	S-2	4.0

TAPPI TESTS - shall be in accordance with TAPPI T400 for the applicable TAPPI test methods.

5. Regulatory requirements. The contractor shall certify that the product shall contain the minimum of 50% waste paper. The contractor shall also certify that the product offered shall include a minimum of 10% postconsumer recovered material. The postconsumer recovered material shall be considered as part of the overall minimum total of 50% waste paper in accordance with 40 CFR, Part 250. The Government reserves the right to require proof of such conformance prior to first delivery and thereafter as may be otherwise provided for under the provisions of the contract.

5.1 Bleaching. To obtain an acceptable brightness, a chemical bleaching process may be used. When specified, (see Section 10), the bleaching process shall not include the use of chlorine, chlorine dioxide, or hypochlorite. Certification of compliance shall be made available upon request by the Government.

6. Warranty requirement The contractor shall warrant that if, at any time under normal use and periodic maintenance, their facsimile paper causes abnormal wear to and/or damage the facsimile machine, the contractor shall replace the defective facsimile paper and reimburse any charges for parts and labor necessary to repair the facsimile machine upon receipt of evidence of periodic maintenance and invoice/work order from the servicing company.

7. Preparation for Delivery. Packaging, packing, and marking of the rolls shall be as specified in the contract or purchase order.

8. Reference Document. The reference documents in effect on the date of the solicitation shall be used to determine compliance with the stated requirements.

(A) TAPPI test methods are available from the Technical Association of the Pulp and Paper Industry, P.O. Box 105113, Atlanta, GA 30348.
(B) ASTM test methods are available from the American Society for Testing and Materials, 1916 Race St., Philadelphia, PA 19103.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:26Z
Check the source to verify that this is the current version before use.

(C) MIL-STD-105 is available from Standardization Documents Order Desk, Bldg. 4D, 700 Robbins Ave., Philadelphia, PA 19111-5094.

(D) Title 40, Code of Federal Regulation, Protection of Environment, Part 250, Guideline for Federal Procurement of Paper and Paper Products containing Recovered Materials.

Copies of the U.S. Code of Federal Regulations may be purchased with a VISA, Master Card, or prepaid check through:

Government Printing Office
Washington, D.C.
Phone: (202) 783-3238

When ordering, ask for:

Title 40, Parts 190-250
Stock Number: 869-013-00-146-0

9. **Ordering Data.** Purchasers should select the preferred options permitted herein, and include the following information in procurement documents:

A) Title, number, and date of this specification
B) Length and width of paper
C) Inside diameter and width of core
D) Coating side in or out
E) Whether bleaching without the use of chlorine, chlorine dioxide, or hypochlorite is required.
F) Packaging, packing and marking requirements

PREPARING ACTIVITY:
GSA-FSS

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:26Z
Check the source to verify that this is the current version before use.