INCH-POUND

A-A-50864A
April 22,1996
SUPERSEDING
A-A-50864
June 21, 1983

COMMERCIAL ITEM DESCRIPTION

BEDSPREAD, COTTON, POLYESTER, COTTON/RAYON, COTTON/POLYESTER, OR POLYESTER/RAYON

The General Services Administration has authorized the use of this commercial item description as a replacement for DDD-B-151 for all Federal agencies

1 SCOPE This commercial item description covers the requirements for finished bedspreads to includes cotton, polyester, cotton/rayon, cotton/polyester, or polyester/rayon blends The bedspreads are intended for use by the Department of Defense and the General Services Administration.

Type I - Defense
Type II - Medical
Type IV - GSA
Types V, VI - Defense

2 CLASSIFICATION The bedspreads shall be in the following types, styles, and sizes.

Type I - Crinkle
Sizes 3, 4

Type II - Dimity

Type III - deleted

Beneficial comments, recommendations additions, deletions, clarifications etc and any data which may improve this document should be sent to Defense Personnel Support Center Clothing and Textiles Directorate, Attn: DPSC-FNS, 2800 South 20th Street, Philadelphia, PA 19145-5099

AMSC N/A

FSC 7210

DISTRIBUTION STATEMENT A

Approved for public release; distribution is unlimited

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:48Z
Check the source to verify that this is the current version before use.

Type IV - Corded
Style A
Sizes 1, 2, 3, 4, 5
Style B - deleted

Type V - Corded
Style A
Sizes 1, 2, 3, 4, 5
Style B - deleted

Type VI - Corded
Style A
Sizes 1, 2, 3, 4 5
Style B - deleted

3 SALIENT CHARACTERISTICS The bedspreads shall be fabricated from one piece of fabric that has straight, woven selvages with the ends cut parallel to the filling yarns For the types I and II only, the bedspreads may be fabricated with the ends cut parallel to the warp yarns The four corners shall be cut square The cut edges or cut sides of the bedspread shall be hemmed Bedspreads may be treated with a non-pressed finish Unless otherwise specified in the contract, selected commercial designs shall be furnished for the bedspreads Bedspreads shall be furnished in the sizes specified in Table I

Table I - Physical Requirements

Type	Size of finished bedspread (after laundering) (minimum) (inches)	Weight of finished bedspread (minimum) (ounces)	Yarns per inch (minimum) Warp	Filling	Breaking strength (minimum) (pounds) Warp	Filling
I Crinkle						
Size 3	72 by 97	27 0	72 in plain ground 62 in crinkle	62	50	50
Size 4	72 by 106	29 0	72 in plain ground 62 in crinkle	62	50	50
II Dimity	81 by 103	32 5	70	50	75	45
IV Corded Style A	Including cords					
Size 1	63 by 103	32 0	45	30	35	25
Size 2	76 by 103	39 0	45	30	35	25
Size 3	76 by 113	43 0	45	30	35	25
Size 4	90 by 113	51 0	45	30	35	25
Size 5	56 by 88	24 0	45	30	35	25

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:48Z
Check the source to verify that this is the current version before use.

Table I - Physical Requirements (cont'd)

Type	Size of finished bedspread (after laundering) (minimum) (inches)	Weight of finished bedspread (minimum) (ounces)	Yarns per inch (minimum) Warp	Filling	Breaking strength (minimum) (pounds) Warp	Filling
V Corded Style A	Including cords					
Size 1	63 by 103	32 0	54	23	100	75
Size 2	76 by 103	39 0	54	23	100	75
Size 3	76 by 113	43 0	54	23	100	75
Size 4	90 by 113	51 0	54	23	100	75
Size 5	56 by 88	24 0	54	23	100	75
VI Corded Style A	Including cords					
Size 1	63 by 103	31 5	54	23	100	75
Size 2	76 by 103	38 0	54	23	100	75
Size 3	76 by 113	42 0	54	23	100	75
Size 4	90 by 113	49 5	54	23	100	75
Size 5	56 by 88	24 0	54	23	100	75

3 1 The yarn for the cotton bedspreads shall be made from cotton which has been carded, drawn, and spun into single yarns for both warp and filling

3 2 The yarn for the cotton/rayon blend bedspread, except for the cords for type IV bedspreads which shall be all cotton, shall consist of a blend of 50 percent cotton and 50 percent high wet-strength modules-type rayon with a tolerance of ± 5 0 percent for fiber content on a conditioned basis

3 3 The yarn for the cotton/polyester type IV bedspreads shall consist of a blend of cotton and up to 50 percent polyethylene glycol terephthalate with a tolerance of ± 5 0 percent for fiber content on a conditioned basis

3 4 The yarn for cotton/polyester blend type V bedspreads shall consist of a blend of 75 percent polyethylene glycol terephthalate and 25 percent rayon with a tolerance of ± 5 0 percent for either fiber component on a conditioned basis

3 5 The yarn for the polyester type VI bedspreads shall be made of 100 percent polyethylene glycol therphthalate

3 6 The cotton thread used for hemming shall be 3 ply, ticket no 40, conforming to type I of A-A-52094 The color of the thread shall match the color of the basic material As a minimum level of acceptability, the dyed thread shall show good colorfastness to laundering, light and bleaching not applicable to undyed yarn As an alternate a clear monofilament thread may be used

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:48Z
Check the source to verify that this is the current version before use.

3.7 As an alternate to the cotton thread, all bedspreads manufactured of a blend material may use a 2- or 3-ply polyester-covered thread, conforming to ticket no 40 of A-A-50199 The polyester-covered, polyester-core thread shall not be used The color of the thread shall match the color of the basic material As a minimum level of acceptability, the dyed thread shall show a minimum of good colorfastness to laundering, light and bleaching not applicable to undyed yarn

3 8 The finished hems shall be not less than 3/4 nor more than 1 inch wide, with the raw edges turned under not less than 1/4 inch, using stitch type 6 03 01 conforming to ISO 4916 All hems shall be stitched with not less than 5, nor more than 10 stitches per inch, using stitch type 301 conforming to ISO 4915 The stitching shall be 1/16 to 1/8 inch from the turned edge Bedspreads furnished with selvage sides need not be side hemmed

3 9 Type I crinkle style bedspreads shall be of any weave or combination of weaves that will produce an alternate crinkle stripe and smooth stripe in the finished bedspreads The ground ends, adjacent to all crinkle stripes which measure 3/8 inch or more, shall be reinforced as follows Eight ground ends on each side of the crinkle stripes shall be drawn in so that two ends are weaving as one (eight ends weaving as four) The stripe shall run lengthwise in the bedspreads

3 10 The cloth for type I crinkle style bedspreads shall be either bleached white or of alternating bleached and yarn-dyed colored stripes The colored stripes shall be crinkled warp yarns and shall be of the color specified As a minimum level of acceptability the colored stripes shall have a minimum of good colorfastness to laundering light and bleaching when tested as specified in Table II

3 11 When specified, type I crinkle style bedspreads shall be marked with the letters "U S " in block style 1 (± 1/16) inch high, in a black marking medium centered 16 to 18 inches from one end of the underside As a minimum level of acceptability, the marking shall show a minimum of good colorfastness to laundering and bleaching when tested as specified in Table II

3 12 The dimity type II bedspreads shall be of any weave or combination of weaves that will produce a series of narrow medium, and wide corded stripes which run lengthwise in the bedspread The color for the type II bedspreads shall be bleached white

3 13 When specified for medical procurement type II bedspreads shall be marked with black indelible ink with the stock number 1/4 inch high with a caduceus of appropriate size centered between the letters "U" and "S" The marking shall be centered between the two sides on the underside of the 3/4 inch hem As a minimum level of acceptability, the marking shall show a minimum of good colorfastness to laundering and bleaching when tested as specified in Table II

3 14 Types IV, V, and VI bedspreads shall be of a plain weave construction with a pronounced cord The cord shall be a single or two or more ply corded yarn not less than 1/16 inch in width The color shall contain not less than 4 cords per inch

3 15 The cloth for types IV, V, and VI bedspreads shall be of the color specified As a minimum level of acceptability, the bedspreads shall show a minimum of good colorfastness to laundering and light when tested as specified in Table II

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:48Z
Check the source to verify that this is the current version before use.

3 16 The nonfibrous material content, starch and protein, including chloroform-soluble and water-soluble materials, shall not exceed 5 0 percent when tested as specified in Table II

3 17 The fiber identification for each bedspread shall be labeled or ticketed for fiber content in accordance with the Rules and Regulations under the Textile Fiber Products Identification Act

3 18 The bedspreads shall meet the following test requirements as specified in Table II The methods of testing specified in Table II shall be followed The physical and chemical values specified apply to the average of the determinations made on the sample unit

Table II - Test methods

Characteristic	Requirement	Test method
Yarn identification	Material/cotton	FED-STD-191 1200 1/ AATCC-20
	Material/cotton-rayon	FED-STD-191 1200 and 1500 1/
	Material/cotton-poly	FED-STD-191 1200 and 1600 1/
	Material/poly-rayon	FED-STD-191 1500 and 1600 1/
	Material/polyester	1600/1/
Fiber content	Material/cotton-rayon	AATCC-20A
	Material/cotton-poly	1/ AATCC-20A
	Material/poly-rayon	1/ or ASTM-629
Size after laundering	Table I	FED-STD-191 5550 2/AATCC-96
Weight per bedspread	Table I	3/
Yarns per inch	Table I	FED-STD-191 5050 ASTM-D-3775
Breaking strength	Table I	FED-STD-191 5100 4/ ASTM-D-5034
Nonfibrous materials	Page 5	FED-STD-191 2611 ASTM-D-629-205
Weave	Page 4	Visual 5/
Colorfastness to		
Light	Page 4	FED-STD-191 5660 6/ 7/AATCC-16
Laundering	Page 4	FED-STD-191 5612 6/ AATCC-61
Bleaching	Page 4	FED-STD-191 5600 6/ AATCC-3

1/ Unless otherwise specified a supplier's certificate of compliance shall be accepted for this characteristic The certificate of conformance shall be based on actual test results dated no more than 2 years from the initial date of the contract These test results shall be available for inspection when requested by the Government

2 Except the test specimens shall be one full bedspread and a commercial-type mangler shall be used for pressing The average of three measurements taken from the full width and length directions respectively shall be reported

3/ One full bedspread shall be weighed and the results reported to the nearest 0 1 ounce The weight shall be recorded prior to the laundering test and shall be obtained in a nonconditioned basis

4/ Front jaws shall be centered on ground threads

5/ One determination per unit with result reported as "pass" or "fail

6/ Not applicable to undyed bedspreads

7/ The calibration of the fadeometer and the definition of AATCC Fading Units shall be according to AATCC Test Method 16 Using the formula below 16 to 22 AFU's are acceptable as 20 SFUs

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:48Z
Check the source to verify that this is the current version before use.

$$\text{AATCC Fading Units} = \frac{(\Delta E^*)(20)}{17}$$

where (ΔE^*) is the color difference in CIELAB* units of color difference

3.19 The cotton/rayon blend fabric shall contain the specified fiber percentages when tested in accordance with test method 20A-1971 (chemical method No. 4-59 5 percent sulfuric acid test) listed in the Technical Manual of the American Association of Textile Chemists and Colorists. Two specimens shall be tested from each sample unit. When the weights of both the original sample and the residue have been found, the fiber percentages on a conditioned basis shall be calculated by the following formula and shall be reported to the nearest 0.1 percent.

Percentage of cotton fiber (based on dry weight) $c = \frac{R(100)}{DW}$

Percentage of rayon fiber (based on dry weight) $v = 100 - c$

Percentage of corrected (regain) rayon fiber $CW = \frac{c(100)}{100 - 0.075}$

Percentage of corrected (regain) fiber $VW = \frac{v(100)}{100 - 0.110}$

Percentage of cotton on a conditioned basis $C = \frac{CW(100)}{CW + VW}$

Percentage of rayon on conditioned basis $V = 100 - CW$

Where:
- R = Weight of residue (ovendry)
- DW = Weight of original specimen (ovendry)
- c = Percentage of cotton (ovendry)
- v = Percentage of rayon (ovendry)
- CW = Corrected (regain) cotton
- C = Percentage of cotton on conditioned basis
- V = Percentage of rayon on conditioned basis

3.20 The fiber content for the cotton/polyester and polyester/rayon blend fabrics shall follow the general procedure of method 2100 and the fiber content percentage calculated as follows:

$$\frac{\text{Weight of dry residual fiber} \times 100}{\text{Weight of dry desized specimen}} = \text{percent polyester}$$

100 - percent polyester = percent cotton or rayon

3.21 Labels. A commercial-type label is acceptable, provided that an additional printed cloth label containing the contractor's name, contract number, size and National Stock Number (NSN) is caught

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:48Z
Check the source to verify that this is the current version before use.

on the stitching of the commercial label The commercial label shall include fiber and laundering information

3.22 Label/tag Each item shall be individually bar-coded with a paper tag The paper tag shall be standard bleached sulfate having a basis weight of 100 pounds The paper used for the tags shall have a smooth finish to accept thermal transfer and direct printing The tags shall have a hole and shall be attached to each item by a fastener, clearly legible and readable by a scanner The bar coding element shall be a 13 digit national stock number (NSN) The bar code type shall be a medium to high code density and shall be located so that it is completely visible on the item when it is folded and/or packaged as specified and so that it causes no damage to the item

4 REGULATORY REQUIREMENTS The offeror/contractor is encouraged to use recovered materials to the maximum extent practicable, in accordance with paragraph 23 403 of the Federal Acquisition Regulation (FAR)

5 QUALITY ASSURANCE PROVISIONS

5 1 Certification The contractor shall certify and maintain substantiating evidence that the product offered meets the salient characteristics of this commercial item description and conforms to the producer's own drawings specifications standards, and quality assurance practices The Government reserves the right to require proof of such conformance prior to the first delivery and thereafter as may be otherwise provided for under the provisions of the contract

5 2 Market acceptance criteria The item offered, or a generic equivalent must have been sold to the commercial market or to the Government for at least two years

5 3 Warranty The item offered shall include the standard warranty given to the commercial market beginning with the date of delivery of the individual items

5 4 Visual examination Each bedspread shall be examined for the defects listed below

Defects Any hole, cut, or tear, color not as specified, any part shaded, any spot or stain (outside), raw edges open seams thread ends not removed or loose tension resulting in loose seams any material defects distorted parts or poor workmanship any component part omitted label missing incorrect or illegible measurement of item not as specified bar code omitted or not readable by scanner human-readable interpretation (HRI) omitted or illegible bar code not visible on folded packaged item, bar code causes damage to the item In addition, the bedspread shall be examined for the following defects

1 Fabric
- a Weave not as specified
- b Broken or missing yarns
- c Excess yarns
- d Any smash
- e Any float or skip

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:48Z
Check the source to verify that this is the current version before use.

f Tight or pulled yarn
g Uneven weaving
h Cords not uniform (where applicable)
i Temple cuts or abrasion marks
j Selvage (when edges are not hemmed)
1 Rolled, folded, doubled, scalloped, loose
2 Tight (puckered or wavy)
3 Cut or torn
4 Tenter pin or tenter marks
2 Pattern or design not as specified
3 Any cut, hole, or tear, including selvages
4 Any spot, stain, or streak
5 Embedded crease or wrinkle (cannot be removed by manual pressure)
6 Measurement of item not as specified
7 Any corner not square cut
9 Wrong seam or stitch type
10 Hem
a Varies in width by more than 1/4 inch
b Badly twisted, pleated, or puckered
c Needle chews
d Stitching less than 1/16 or more than 1/8 inch from turned edge
e Raw edge
f Any required hem omitted

5.5 Acceptance criteria Acceptance criteria shall be as specified in the contract or purchase order

6 PACKAGING The preservation, packing, and marking shall be as specified in the contract or order

7 NOTES

7.1 Source of Government documents Copies of military and Federal documents are available from

Standardization Documents Order Desk
Bldg 4D
700 Robbins Avenue
Philadelphia PA 19111-5094

7.2 Sources of non-Government documents Copies of non-Government documents are available from

AATCC Test Methods

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:48Z
Check the source to verify that this is the current version before use.

(Applications for copies should be addressed to American Association of Textile Chemists and Colorists (AATCC), P O Box 12215, Triangle Park, NC 27709-2215)

Rules and Regulations Under The Textile Fiber Products Identification Act

(Applications for copies should be addressed to Federal Trade Commission, Washington, DC 20580)

ASTM Test Methods

(Applications for copies should be addressed to American Society For Testing and Materials, 100 Barr Harbor Drive, West Conshohocken, PA 19428)

INTERNATIONAL ORGANIZATION FOR STANDARDIZATION (ISO)

ISO 4915 - Textiles - Stitch Types - Classification and Terminology

ISO 4916 - Textiles - Seam Types - Classification and Terminology

(Application for copies should be addressed to the International Organization for Standardization, Case Postale 58 CH-1211 Geneve 20 Switzerland)

MILITARY INTERESTS

CUSTODIANS
Army - MD
Navy - NU
Air Force - 99

REVIEW ACTIVITY
Air Force - 82

CIVIL AGENCY COORDINATING ACTIVITY
GSA - FSS

PREPARING ACTIVITY
DLA - CT

Project Number 7210-0318

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:48Z
Check the source to verify that this is the current version before use.