ANA BULLETIN NO. 166e
15 OCTOBER 1964

Superseding
ANA Bulletin No. 166d
11 March 1959

AIR FORCE-NAVY AERONAUTICAL BULLETIN

COLORS; LIST OF STANDARD AIRCRAFT GLOSSY

1. Contents.- This bulletin contains the list of names and numerical designations of the Air Force-Navy standard colors for glossy finishes (see 4).

Color name	Color standard to be employed		Superseded
	Fed. Std. No. 595	ANA color No.	ANA color standard
Light Blue	15102	---	501
Insignia Blue	15044	---	502
Light Green	14187	---	503
Olive Drab	1/X14087	---	504
Light Yellow	13655	---	505
Orange Yellow	13538	---	506
Aircraft Cream	13594	---	507
International Orange	12197	---	508
Insignia Red	11136	---	509
Maroon	10049	---	510
Insignia White	17875	---	511
Aircraft Gray	16473	---	512
Engine Gray	16081	---	513
Gloss Black	17038	---	515
Strata-Blue	15045	---	516
Jet	17038	---	622
Glossy Sea Blue	15042	---	623
Fluorescent Red-Orange	-----	633	---
Fluorescent Yellow-Orange	-----	634	---

1/ X Chips for this color may be obtained from the Coatings and Chemical Laboratory, Aberdeen Proving Ground, Aberdeen, Md.

2. Color standards.- The applicable color standard listed in Section 1 should be employed as standards for matching purposes. When ANA Color Standards are required, application should be made to either the Commander, USAF, Engineering Specifications and Drawing Branch, Attention: EWBFE, Wright-Patterson Air Force Base, Ohio; or to the Director, Aeronautical Materials Laboratory, Naval Air Engineering Center, Philadelphia, Pennsylvania 19112. Requests for noe or more standard colors should include reference to each color name and number.

The Federal Standard No. 595 color chips may be purchased from Business Service Center, Region 3, Seventh and D Streets, S. W., Washington, D.C. 20407.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T14:03Z
Check the source to verify that this is the current version before use.

2.1 The Air Force-Navy Aircraft Glossy Color Standards have been distributed to all manufacturers of Air Force-Navy aeronautical paint materials. Users of these materials may obtain from the paint manufacturers the color required by referring to the specification, color name, and color number.

3. Color match.- In order to determine color match, the applicable standard shall be compared with the dry paint film under test by viewing both panels placed adjacently and under identical conditions at a north window illuminated by a fairly light overcast sky, or equivalent conditions.

3.1 If necessary to compare finishes of different degrees of gloss, wet down both panels with distilled water (if water does not wet use a heavy water-white mineral oil) and make comparison as above.

4. Glossy finishes.- Standard glossy finishes are defined as those finishes having a specular gloss of 60 or more, when determined in accordance with Method 6101 of Federal Test Method Standard No. 141.

5. Marginal indicia.- The margins of this bulletin are marked to indicate where changes, deletions, or additions to the previous issue have been made. This is done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content as written, irrespective of the marginal notations and relationship to the last previous issue.

6. Sources.- Copies of specifications, standards, drawings, and publications required by suppliers in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.

oOo

Source: https://assist.dla.mil -- Downloaded: 20260-26T14:03Z
Check the source to verify that this is the current version before use.