**Fed. Std. No. 4b**
**SECTIONS I, II, and III**
**July 29, 1964**

SUPERSEDING
Fed. Std. No. 4a
Sections I and II
August 29, 1963

## FEDERAL STANDARD

# GLOSSARY OF FABRIC IMPERFECTIONS

**Authority.** *This standard is issued pursuant to the Federal Property and Administrative Services Act of 1949, as amended, and its application to the purchase of commodities referred to herein is mandatory on all Federal agencies.*

This standard consists of:
Section I—Woven Cotton Fabrics.
Section II—Woven Woolen and Worsted Fabrics.
Section III—Woven Synthetic Fabrics.

## SECTION I—WOVEN COTTON FABRICS

### 1. PURPOSE AND SCOPE

1.1 This section consists of a complete listing of woven cotton fabric imperfections, with definitions, arranged according to whether they are the result of the spinning, weaving, or finishing operations. The purpose is to bring together in one publication the general information on woven cotton fabric imperfections.

### 2. ALPHABETICAL INDEX OF FABRIC IMPERFECTIONS

2.1 Imperfections and glossary numbers.

ALPHABETICAL INDEX

| Imperfection Commercial terminology | Glossary No. |
|---|---|
| Abrasion mark | 79 |
| Bad mend | 34A |
| Bad odor | 80 |
| Bad set mark (heavy side) | 2 |
| Bad set mark (light side) | 9 |
| Baggy cloth | 93 |
| Balling up | 45 |
| Barré mark | 18 |
| Beaded selvage | 54 |
| Bias filling | 88 |
| Blanket mark | 58 |
| Bowed filling | 88 |
| Box mark | 19 and 20 |
| Breakout | 78 |
| Broken or missing end | 33 |
| Broken pick | 11 |

ALPHABETICAL INDEX—Continued

| Imperfection Commercial terminology | Glossary No. |
|---|---|
| Broken selvage | 55 |
| Bruise | 79 |
| Bunch | 5 and 27 |
| Burrs | 82 |
| Calendar mark | 57 |
| Chafe mark | 79 |
| Change-in filling | 14 |
| Cleaning place | 23 |
| Clip marks | 73 |
| Coarse end | 26 |
| Coarse or heavy filling | 1 |
| Coarse or heavy pick | 1 |
| Corded selvage | 54 |
| Crack | 12 |
| Crease | 59 |
| Crooked cloth | 93 |
| Crowsfeet | 67 |
| Crushed pile | 95 |
| Curl | 6 |
| Curled selvage | 48 |
| Cut | 91 |
| Cut selvage | 55 |
| Dirty filling | 24 |
| Doctor streak | 66 |
| Double pick | 4 |
| Doubles | 48 |
| Drawback | 35 |
| Drop-ply | 82 |
| Dye stain | 69 |
| Dye streak | 70 |
| End out | 33 |
| Filling float | 13 |
| Fine end | 31 |



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:52Z
Check the source to verify that this is the current version before use.

## ALPHABETICAL INDEX—Continued

| Imperfection Commercial terminology | Glossary No. |
|---|---|
| Fine filling bar | 9 |
| Fine or light filling | 8 |
| Fine or light pick | 8 |
| Finger mark | 22 |
| Finishing bar | 57 |
| Flat | 4 |
| Flyers, loom fly | 77, 81 and 83 |
| Folded selvage | 48 |
| Fuzz balls | 45 |
| Gout | 77, 81 and 83 |
| Hang pick | 17 |
| Hang shot | 17 |
| Hang or loose threads | 30 |
| Hard crease | 59 |
| Hard size | 43 |
| Harness drop | 13 and 34 |
| Harness skips | 34 |
| Heavy filling bar | 2 |
| Heavy place | 2 |
| Hitchback | 35 |
| Hole | 90 |
| Jerked-in filling | 3 |
| Kink | 28 and 6 |
| Knot | 29 and 7 |
| Lashed-in filling | 3 |
| Light filling bar | 9 |
| Light place | 9 |
| Loop | 28 and 6 |
| Loopy selvage | 54 |
| Lump | 5 |
| Mill wrinkle | 59 |
| Mispick | 10 |
| Misply | 14 and 36 |
| Misprint | 65 |
| Missing pick | 11 |
| Mixed end | 36 |
| Mixed filling | 14 |
| Mottled | 71 |
| Neps | 84 and 85 |
| Neppiness | 86 |
| Objectionable odor | 80 |
| Off-register printing | 63 |
| Off-shade | 61A |
| Oily-filling | 24 |
| Overshot | 13 |
| Pick-out mark | 23 |
| Pile improperly formed | 96 |
| Pile missing | 94 |
| Pilling | 45 |
| Pin marks | 73 |
| Pressure mark | 22 |
| Puckering | 93 |

## ALPHABETICAL INDEX—Continued

| Imperfection Commercial terminology | Glossary No. |
|---|---|
| Pull-down | 9 |
| Pull-in filling | 8 |
| Reed mark | 41 |
| Ridgy cloth | 93 |
| Rip out | 23 |
| Rolled selvage | 48 |
| Rope marks | 68 |
| Ropy filling | 5A |
| Rough selvage | 54 |
| Sand roll mark | 79 |
| Sanforizing mark | 58 |
| Scalloped selvage | 51 |
| Seam mark | 61 |
| Selvage mark | 60 |
| Shade bar | 14 |
| Shell-off | 5A |
| Shift mark | 87 |
| Shuttle mark | 19 and 20 |
| Shyer (Shirer) | 12 |
| Skip | 13 |
| Slack end | 38 |
| Slack pick or filling | 16 |
| Slack selvage | 49 |
| Slack warp | 39 |
| Slough-off | 5A |
| Slub | 5 and 27 |
| Slug | 5 and 27 |
| Smash | 78 |
| Snap | 70 |
| Snarl | 6 |
| Soiled end | 46 |
| Soiled pick | 24 |
| Spot | 74 and 75 |
| Stain | 74 and 75 |
| Starch lumps | 43 |
| Starting mark (heavy side) | 2 |
| Starting mark (light side) | 9 |
| Sticker | 35 and 43 |
| Stop mark | 2 and 9 |
| Streak | 76 |
| Stretched filling | 15 |
| Stringy selvage | 53 |
| Tear | 92 |
| Tear drop or teariness | 21 |
| Temple marks | 42 |
| Tender spots | 89 |
| Tentering marks | 73 |
| Thin place | 9 and 12 |
| Tie back | 35 |
| Tight end | 37 |
| Tight pick or filling | 15 |
| Tight selvage | 50 |



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:52Z
Check the source to verify that this is the current version before use.

ALPHABETICAL INDEX—Continued

| Imperfection Commercial terminology | Glossary No. |
|---|---|
| Torn selvage | 56 |
| Uncut pile | 97 |
| Uneven dyeing | 62 |
| Uneven end | 47 |
| Uneven filling | 25 |
| Uneven finish | 63A |
| Uneven napping | 64 |
| Uneven shade | 62 |
| Uneven shrinkage | 72 |
| Uneven tension | 93 |
| Uneven weaving | 35A |
| Warp float | 34 |
| Warp holding place | 35 |
| Warp streak | 44 |
| Wavy cloth | 93 |
| Wavy selvage | 52 |

ALPHABETICAL INDEX—Continued

| Imperfection Commercial terminology | Glossary No. |
|---|---|
| Weak spots | 89 |
| Woven in waste | 77, 81 and 83 |
| Wrinkle mark | 61 |
| Wrong draw | 40 |

## 3. IMPERFECTIONS AND DEFINITIONS

### 3.1 Imperfections in filling direction.

3.1.1 *Thick places.* Imperfections which cause places in the cloth to be thicker than normal.

| Glossary No. | Imperfection Commercial Terminology | Definition |
|---|---|---|
| 1 | Coarse or heavy filling<br>Coarse or heavy pick | A yarn larger in diameter than normally being used in the cloth. |
| 2 | Heavy place<br>Heavy filling bar<br>Bad set mark (heavy side)<br>Stop mark<br>Starting mark (heavy side) | A fillingwise band or bar either across the full width of the cloth or a portion of it, containing picks of larger diameter than normally being used in the cloth or containing more than the normal number of picks. |
| 3 | Jerked-in filling<br>Lashed-in filling<br>Pull-in filling | An extra thread dragged into the shed with a proper pick and extending only a part of the way across the cloth. |
| 4 | Double pick<br>Flat | Two or more picks in the same shed across the full width of the cloth. |
| 5 | Slub or slug<br>Bunch<br>Lump | An abruptly thickened place in the yarn. |
| 5A | Slough-off<br>Shell-off<br>Ropy Filling | Filling which has slipped off bobbin and has been woven into the cloth along with the required pick. |
| 6 | Kink<br>Loop<br>Snarl<br>Curl | A place in the cloth where a short length of yarn has spontaneously doubled on itself. |



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:52Z
Check the source to verify that this is the current version before use.

| Glossary No. | Imperfection Commercial Terminology | Definition |
|---|---|---|
| 7 | Knot | Self-descriptive. |

3.1.2 *Thin places.* Imperfections which cause places in the cloth to be thinner than normal.

| Glossary No. | Imperfection Commercial Terminology | Definition |
|---|---|---|
| 8 | Fine or light filling<br>Fine or light pick | A yarn smaller in diameter than normally being used in the cloth. |
| 9 | Light place<br>Fine filling bar<br>Light filling bar<br>Pull down<br>Bad set mark (light side)<br>Stop mark<br>Starting mark (light side)<br>Thin place | A fillingwise band or bar either across the full width of the cloth or a portion of it, containing picks of smaller diameter than normally being used in the cloth or containing less than the normal number of picks. |

3.1.3 *Misweaves.* Imperfections in weave usually found in the filling direction.

| Glossary No. | Imperfection Commercial Terminology | Definition |
|---|---|---|
| 10 | Mispick | A pick woven in improper order. |
| 11 | Broken pick<br>Missing pick | A pick wholly or partially missing. |
| 12 | Crack<br>Shyer (Shirer)<br>Thin place | An open streak parallel with the filling and extending partly or entirely across the cloth. |
| 13 | Filling float<br>Skip<br>Overshot<br>Harness drop | A place in the cloth where a filling yarn extends unbound over the end (s) with which it should be interlaced. |
| 14 | Mixed filling<br>Change in filling<br>Shade bar<br>Misply | Filling yarn which differs from that normally being used in the cloth, such as wrong twist, wrong number of plies, wrong color, mixed yarn lots. |



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:52Z
Check the source to verify that this is the current version before use.

| Glossary No. | Imperfection Commercial Terminology | Definition |
|---|---|---|
| 15 | Tight pick or filling<br>Stretched filling | Self-descriptive. |
| 16 | Slack pick or filling | Self-descriptive. |
| 17 | Hang pick<br>Hang shot | A pick which is pulled out of line for a short distance producing a small triangular shaped hole in the cloth. |

3.1.4 *Miscellaneous fillingwise imperfections.*

| Glossary No. | Imperfection Commercial Terminology | Definition |
|---|---|---|
| 18 | Barré mark | One or more picks in the cloth characterized by an apparent difference in shade from adjoining picks. |
| 19 and 20 | Box mark<br>Shuttle mark | A fine line parallel with the filling. |
| 21 | Tear drop or teariness | A fabric condition characterized by short elliptical distortions of one or more adjoining picks. |
| 22 | Finger mark<br>Pressure mark | An irregular spot showing variations in picks per inch for a limited width. |
| 23 | Pick-out mark<br>Cleaning place<br>Rip out | A fillingwise band or bar characterized by a chafed or fuzzy appearance. |
| 24 | Soiled pick<br>Dirty filling<br>Oily filling | Self-descriptive. |
| 25 | Uneven filling | Self-descriptive. |

3.2 Imperfections in the warp direction.

3.2.1 *Thick places.* Imperfections which cause places in the cloth to be thicker than normal.



Source: https://assist.dla.mil -- Downloaded: 202640-26T12:52Z
Check the source to verify that this is the current version before use.

| Glossary No. | Imperfection Commercial Terminology | Definition |
|---|---|---|
| 26 | Coarse end | A yarn larger in diameter or containing more plies than normally being used in the cloth. |
| 27 | Slub or slug<br>Bunch | An abruptly thickened place in the yarn. |
| 28 | Kink<br>Loop | A place in the cloth where a short length of yarn has spontaneously doubled on itself. |
| 29 | Knot | Self-descriptive. |
| 30 | Hang or loose threads | Self-descriptive. |

3.2.2 *Thin places.* Imperfections which cause places in the cloth to be thinner than normal.

| Glossary No. | Imperfection Commercial Terminology | Definition |
|---|---|---|
| 31 | Fine end | A warp yarn smaller in diameter than normally used in the cloth. |
| 32 | Drop-ply | A yarn containing fewer plies than normally used in the cloth. |
| 33 | Broken or missing end<br>End out | A warp yarn missing for a portion or the entire length of the cloth. |

3.2.3 *Misweaves.* Imperfections in weave usually found in the warp direction.

| Glossary No. | Imperfection Commercial Terminology | Definition |
|---|---|---|
| 34 | Warp float<br>Harness skips<br>Harness drop | A place in the cloth where a warp yarn extends unbound over the pick(s) with which it should be interlaced. |
| 34A | Bad mend | Self-descriptive. |
| 35 | Hitch-back<br>Draw-back<br>Tie-back<br>Warp holding place<br>Sticker | A distortion in the weave characterized by tight and slack places in the same warp yarns. |
| 35A | Uneven weaving | Self-descriptive. |



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:52Z
Check the source to verify that this is the current version before use.

3.2.4 *Miscellaneous warpwise imperfections.*

| Glossary No. | Imperfection Commercial Terminology | Definition |
|---|---|---|
| 36 | Mixed end<br>Misply | Warp yarn which differs from that normally being used in the cloth, such as wrong twist, wrong number of plies, wrong color, mixed yarn lots. |
| 37 | Tight end | Self-descriptive. |
| 38 | Slack end | Self-descriptive. |
| 39 | Slack warp | A cloth having an overall crimped or cockled appearance, woven under tension less than proper. |
| 40 | Wrong draw | A place in the cloth where one or more ends have been drawn through the wrong heddle, or dent. |
| 41 | Reed mark | A mark running warpwise in the cloth. |
| 42 | Temple marks | Small holes, impressions, or marks adjacent to the edge of the cloth. |
| 43 | Hard size<br>Sticker<br>Starch lumps | Spots or bars in the cloth containing an excessive quantity of sizing. |
| 44 | Warp streak | A narrow warpwise band or an overall warpwise striation characterized by apparent differences in color from adjoining ends. |
| 45 | Fuzz balls<br>Balling up<br>Pilling | Loose or frayed fibers which have formed into a ball. |
| 46 | Soiled end | Self-descriptive. |
| 47 | Uneven end | Self-descriptive. |

3.3 Bad selvages.

| Glossary No. | Imperfection Commercial Terminology | Definition |
|---|---|---|
| 48 | Curled selvage<br>Folded selvage<br>Rolled selvage<br>Doubles | Self-descriptive. |
| 49 | Slack selvage | Self-descriptive. |



Source: https://assist.dla.mil -- Downloaded: 2026l0-26T12:52Z
Check the source to verify that this is the currentversion before use.

| Glossary No. | Imperfection Commercial Terminology | Definition |
|---|---|---|
| 50 | Tight selvage | Self-descriptive. |
| 51 | Scalloped selvage | Self-descriptive. |
| 52 | Wavy selvage | Self-descriptive. |
| 53 | Stringy selvage | Self-descriptive. |
| 54 | Corded selvage<br>Beaded selvage<br>Rough selvage<br>Loopy selvage | An improperly woven selvage of excessive thickness or a selvage containing irregular filling loops extending beyond the outside selvages. |
| 55 | Cut selvage<br>Broken selvage | Cuts or breaks that occur in the selvage only and do not extend into the body of the cloth. |
| 56 | Torn selvage | Self-descriptive. |

3.4 Finishing imperfections.

| Glossary No. | Imperfection Commercial Terminology | Definition |
|---|---|---|
| 57 | Finishing bar<br>Calendar mark | Uneven appearance extending partly or entirely across the cloth. |
| 58 | Blanket mark<br>Sanforizing mark | A crimped, rippled, wavy, pebbled, or cockled place in the cloth showing distortion of the weave. |
| 59 | Crease<br>Mill wrinkle<br>Hard crease | Self-descriptive. |
| 60 | Selvage mark | A more or less regular mark in the finished cloth along the selvage produced by folded or doubled selvage during finishing operations. |
| 61 | Wrinkle mark<br>Seam mark | A more or less regular mark in the finished cloth produced by pressure during finishing operations. |
| 61A | Off shade | Not within established shade tolerance, shaded side to side, side to center or end to end. |
| 62 | Uneven shade<br>Uneven dyeing | Color is not uniform throughout the cloth. |
| 63 | Off-register printing | Pattern displacement caused by improper alignment of printing rolls. |



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:52Z
Check the source to verify that this is the current version before use.

| Glossary No. | Imperfection Commercial Terminology | Definition |
|---|---|---|
| 63A | Uneven finish | Cloth does not have the same degree and character of finish throughout. |
| 64 | Uneven napping | Cloth in which the nap is not raised uniformly. |
| 65 | Misprint | Self-descriptive. |
| 66 | Doctor streak | A wavy white or colored streak in the warp direction on printed cloth. |
| 67 | Crowsfeet | Short indistinct markings on dyed or finished goods. |
| 68 | Rope marks | Long irregular indistinct markings on dyed or finished goods. |
| 69 | Dye stain | An area of discoloration in the cloth. |
| 70 | Dye streak<br>Snap | A dye stain extended as an irregular stripe in the cloth. |
| 71 | Mottled | A blotchy or spotted appearance of the cloth. |
| 72 | Uneven shrinkage | A wavy warpwise condition in the cloth, which prevents it from lying flat on a horizontal surface. This condition may appear along one selvage or both selvages or through sections in the center of the cloth. |
| 73 | Tentering marks<br>Clip marks<br>Pin marks | Enlarged pinholes, tears, or shift marks along the edge of the cloth. |

## 3.5 General imperfections.

| Glossary No. | Imperfection Commercial terminology | Definition |
|---|---|---|
| 74 and 75 | Spot<br>Stain | An area of discoloration on the surface of the cloth. |
| 76 | Streak | A spot or stain extended as an irregular stripe in the cloth. |
| 77, 81, and 83 | Woven in waste<br>Gout<br>Flyers, loom fly | Waste that has been woven into the cloth, or spun into the yarn. |
| 78 | Smash<br>Breakout | A damaged area where the texture has been ruptured by the breaking of a group of yarns, principally the warp. |



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:52Z
Check the source to verify that this is the current version before use.

| Glossary No. | Imperfection<br>*Commercial terminology* | Definition |
|---|---|---|
| 79 | Abrasion mark<br>Chafe mark<br>Bruise<br>Sand roll mark | A place where the surface of the cloth has been damaged by friction. |
| 80 | Objectionable odor<br>Bad odor | Self-descriptive. |
| 82 | Burrs | Seed fragments with bristles projecting from them. |
| 84 and 85 | Neps | All definite fiber tangles. |
| 86 | Neppiness | A speckled condition of the cloth characterized by a number of neps. |
| 87 | Shift mark | A place in the cloth where warp ends have shifted on the filling picks or vice versa, causing adjacent light and heavy spots. |
| 88 | Bias filling<br>Bowed filling | Cloth in which the filling yarn does not run at right angle to the warp. |
| 89 | Weak spots<br>Tender spots | Places in the cloth which have been abnormally weakened during any of the operations through which it has passed. |
| 90 | Hole | Self-descriptive. |
| 91 | Cut | Self-descriptive. |
| 92 | Tear | Self-descriptive. |
| 93 | Uneven tension<br>Ridgy cloth<br>Crooked cloth<br>Baggy cloth<br>Wavy cloth<br>Puckering | A wavy or ridgy cloth that will not lie flat. |
| 94 | Pile missing | Self-descriptive. |
| 95 | Crushed pile | Self-descriptive. |
| 96 | Pile improperly formed | Self-descriptive. |
| 97 | Uncut pile | Self-descriptive. |



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:52Z
Check the source to verify that this is the current version before use.

# SECTION II—WOVEN WOOLEN AND WORSTED FABRICS

## 1. PURPOSE AND SCOPE

1.1 This section consists of a complete listing of woven woolen and worsted fabric imperfections, with definitions, arranged according to whether they are the result of the spinning, weaving, or finishing operations. The purpose is to bring together in one publication the general information on woven woolen and worsted fabric imperfections.

## 2. ALPHABETICAL INDEX OF FABRIC IMPERFECTIONS

### 2.1 Imperfections and glossary numbers.

ALPHABETICAL INDEX

| Imperfection Commercial terminology | Glossary No. |
|---|---|
| Abrasion mark | 74 |
| Bad mend | 35 |
| Bad set mark (heavy side) | 2 |
| Bad set mark (light side) | 10 |
| Baggy cloth | 86 |
| Balling up | 45 |
| Barré mark | 20 |
| Beaded selvage | 54 |
| Bias filling | 83 |
| Bowed filling | 83 |
| Box mark | 21 |
| Breakout | 73 |
| Broken end | 33 |
| Broken pick | 12 |
| Broken selvage | 55 |
| Bruise | 74 |
| Bunch | 5 and 27 |
| Burrs | 78 |
| Chafe mark | 74 |
| Change-in-filling | 15 |
| Cleaning place | 23 |
| Clip marks | 70 |
| Coarse end | 26 |
| Coarse filling | 1 |
| Coarse pick | 1 |
| Corded selvage | 54 |
| Crack | 14 |
| Crease | 57 |
| Crooked cloth | 86 |

ALPHABETICAL INDEX—Continued

| Imperfection Commercial terminology | Glossary No. |
|---|---|
| Crowsfeet | 67 |
| Crushed pile | 88 |
| Curl | 7 |
| Curled selvage | 48 |
| Cut | 85 |
| Cut selvage | 55 |
| Dark hairs | 91 |
| Decating mark | 62 |
| Dirty filling | 24 |
| Double pick | 4 |
| Doubles | 48 |
| Draw-back | 34 |
| Drop-ply | 15 and 32 |
| End out | 33 |
| Extended tuck | 19 |
| Fine end | 31 |
| Fine filling | 9 |
| Fine filling bar | 10 |
| Fine pick | 9 |
| Finger mark | 22 |
| Finishing bar | 56 |
| Flat | 41 |
| Float | 77 |
| Folded selvage | 48 |
| Fuller rub | 74 |
| Fuzz balls | 45 |
| Hang pick | 18 |
| Hang shot | 18 |
| Hang thread | 30 |
| Heavy filling | 1 |
| Heavy filling bar | 2 |
| Heavy pick | 1 |
| Heavy place | 2 |
| Hitch-back | 34 |
| Hole | 85 |
| Jerked-in filling | 3 |
| Kink | 7 and 28 |
| Knot | 8 and 29 |
| Lashed-in filling | 3 |
| Light filling | 9 |
| Light filling bar | 10 |
| Light pick | 9 |
| Light place | 10 |
| Loop | 7 and 28 |
| Loopy selvage | 54 |
| Loose threads | 30 |
| Lump | 5 |
| Mill wrinkle | 60 |
| Mispick | 11 |



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:52Z
Check the source to verify that this is the current version before use.

ALPHABETICAL INDEX—Continued

| Imperfection Commercial terminology | Glossary No. |
|---|---|
| Misply | 15 and 37 |
| Misreed | 41 |
| Missing end | 33 |
| Missing pick | 13 |
| Mixed end | 37 |
| Mixed filling | 15 |
| Mottled | 69 |
| Neps | 80 |
| Neppiness | 81 |
| Objectionable odor | 75 |
| Off shade | 61 |
| Oily filling | 24 |
| Overall uncleanness | 84 |
| Overshot | 77 |
| Pick-out mark | 23 |
| Pile improperly formed | 89 |
| Pile missing | 87 |
| Pilling | 45 |
| Pin marks | 70 |
| Pressure mark | 22 |
| Puckering | 86 |
| Pull down | 10 |
| Pull-in filling | 3 |
| Reed mark | 42 |
| Ridgy cloth | 86 |
| Rip out | 23 |
| Rolled selvage | 48 |
| Rope marks | 68 |
| Roped filling | 6 |
| Rough selvage | 54 |
| Sand roll mark | 74 |
| Scalloped selvage | 51 |
| Seam mark | 59 |
| Selvage mark | 58 |
| Shade bar | 15 |
| Shell-off | 6 |
| Shift mark | 82 |
| Shiner | 16 |
| Shive | 79 |
| Shuttle mark | 21 |
| Shyer (Shirer) | 14 |
| Sidelines | 3 |
| Sisal | 79 |
| Skip | 77 |
| Slack end | 39 |
| Slack filling | 17 |
| Slack pick | 17 |
| Slack selvage | 49 |
| Slack warp | 40 |
| Slough-off | 6 |
| Slub | 5 and 27 |

ALPHABETICAL INDEX—Continued

| Imperfection Commercial terminology | Glossary No. |
|---|---|
| Slug | 5 and 27 |
| Smash | 73 |
| Snarl | 7 |
| Soiled end | 46 |
| Soiled pick | 24 |
| Speck | 79 |
| Spot | 71 |
| Stain | 71 |
| Starting mark (heavy side) | 2 |
| Starting mark (light side) | 10 |
| Sticker | 34 |
| Stop mark | 2 and 10 |
| Streak | 72 |
| Stretched filling | 16 |
| Tear | 85 |
| Temple marks | 43 |
| Tentering marks | 70 |
| Thick selvage | 53 |
| Thin place | 10 |
| Tie-back | 34 |
| Tight end | 38 |
| Tight filling | 16 |
| Tight pick | 16 |
| Tight selvage | 50 |
| Torn selvage | 55 |
| Uncut pile | 90 |
| Uneven end | 47 |
| Uneven filling | 25 |
| Uneven finish | 63 |
| Uneven napping | 64 |
| Uneven shade | 66 |
| Uneven shearing | 65 |
| Uneven tension | 86 |
| Uneven weaving | 36 |
| Warp holding place | 34 |
| Warp streak | 44 |
| Washer break | 60 |
| Washer rub | 74 |
| Washer wrinkle | 60 |
| Wavy cloth | 86 |
| Wavy selvage | 52 |
| Woven-in waste | 76 |
| Wrinkle mark | 59 |
| Wrong draw | 41 |

## 3. IMPERFECTIONS AND DEFINITIONS

### 3.1 Imperfections in filling direction.



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:52Z
Check the source to verify that this is the current version before use.

3.1.1 *Thick places.* Imperfections which cause places in the cloth to be thicker than normal.

| Glossary No. | Imperfection Commercial terminology | Definition |
|---|---|---|
| 1 | Coarse or heavy filling<br>Coarse or heavy pick | A yarn larger in diameter than normally being used in the cloth. |
| 2 | Heavy place<br>Heavy filling bar<br>Bad set mark (heavy side)<br>Stop mark<br>Starting mark (heavy side) | A fillingwise band or bar either across the full width of the cloth or a portion of it, containing picks of larger diameter than normally being used in the cloth or containing more than the normal number of picks. |
| 3 | Jerked-in filling<br>Lashed-in filling<br>Pull-in filling<br>Sidelines | Extra yarn or yarns dragged into the shed with a proper pick and extending only a part of the way across the cloth. |
| 4 | Double pick | Two or more picks in the same shed across the full width of the cloth. |
| 5 | Slub or slug<br>Bunch<br>Lump | An abruptly thickened place in the yarn. |
| 6 | Slough-off<br>Shell-off<br>Roped filling | Excess filling which has slipped off the bobbin and has been woven into the cloth along with the required pick. |
| 7 | Kink<br>Loop<br>Snarl<br>Curl | A place in the cloth where a short length of yarn has spontaneously doubled on itself. |
| 8 | Knot | Self-descriptive. |

3.1.2 *Thin places.* Imperfections which cause places in the cloth to be thinner than normal.

| Glossary No. | Imperfection Commercial terminology | Definition |
|---|---|---|
| 9 | Fine or light filling<br>Fine or light pick | A yarn smaller in diameter than normally being used in the cloth. |
| 10 | Light place<br>Fine filling bar<br>Light filling bar | A fillingwise band or bar either across the full width of the cloth or a portion of it, containing picks of smaller diameter than normally being used in the |



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:52Z
Check the source to verify that this is the current version before use.

| Glossary No. | Imperfection Commercial terminology | Definition |
|---|---|---|
| | Pull down<br>Bad set mark (light side)<br>Stop mark<br>Starting mark (light side)<br>Thin place | cloth or containing less than the normal number of picks. |

3.1.3 *Misweaves.* Imperfections in weave usually found in the filling direction.

| Glossary No. | Imperfection Commercial terminology | Definition |
|---|---|---|
| 11 | Mispick | A pick woven in improper order. |
| 12 | Broken pick | A pick partially missing. |
| 13 | Missing pick | A pick missing the entire width of the cloth. |
| 14 | Crack<br>Shyer (Shirer) | An open streak parallel with the filling and extending partly or entirely across the cloth. |
| 15 | Mixed filling<br>Change-in-filling<br>Shade bar<br>Drop-ply<br>Misply | Filling yarn which differs from that normally being used in the cloth, such as wrong twist, wrong number of plies, wrong color, mixed yarn lots. |
| 16 | Tight pick or filling<br>Stretched filling<br>Shiner | Self-descriptive. |
| 17 | Slack pick or filling | Self-descriptive. |
| 18 | Hang pick<br>Hang shot | A pick which is pulled out of line for a short distance producing a small triangular shaped hole in the cloth. |
| 19 | Extended tuck | Tuck in pick of cloth woven on shuttleless looms extended into body of cloth beyond selvage resulting in a nap (fuzziness) adjacent to the selvage in body of cloth. |

3.1.4 *Miscellaneous filling defects.*



Source: https://assist.dla.mil -- Downloaded: 202610-26T12:52Z
Check the source to verify that this is the current version before use.

| Glossary No. | Imperfection Commercial terminology | Definition |
|---|---|---|
| 20 | Barré mark | One or more picks in the cloth characterized by an apparent difference in shade from adjoining picks. |
| 21 | Shuttle mark<br>Box mark | A line parallel with the filling usually darker or lighter in color than normal shade. |
| 22 | Finger mark<br>Pressure mark | An irregular spot showing variations in picks per inch for a limited width. |
| 23 | Pick-out mark<br>Cleaning place<br>Rip out | A fillingwise band or bar characterized by a chafed or fuzzy appearance. |
| 24 | Soiled pick<br>Dirty filling<br>Oily filling | Self-descriptive. |
| 25 | Uneven filling | Self-descriptive. |

3.2 **Imperfections in the warp direction.**

3.2.1 *Thick places.* Imperfections which cause places in the cloth to be thicker than normal.

| Glossary No. | Imperfection Commercial terminology | Definition |
|---|---|---|
| 26 | Coarse end | A yarn larger in diameter or containing more plies than normally being used in the cloth. |
| 27 | Slub or slug<br>Bunch | An abruptly thickened place in the yarn. |
| 28 | Kink<br>Loop | A place in the cloth where a short length of yarn has spontaneously doubled on itself. |
| 29 | Knot | Self-descriptive. |
| 30 | Hang or loose threads | Self-descriptive. |

3.2.2 *Thin places.* Imperfections which cause places in the cloth to be thinner than normal.



Source: https://assist.dla.mil -- Downloaded: 202640-26T12:52Z
Check the source to verify that this is the currentversion before use.

| Glossary No. | Imperfection Commercial terminology | Definition |
|---|---|---|
| 31 | Fine end | A warp yarn smaller in diameter than normally used in the cloth. |
| 32 | Drop-ply | A warp yarn containing fewer plies than normally used in the cloth. |
| 33 | Broken or missing end<br>End out | A warp yarn missing for a portion of or the entire length of the cloth. |

3.2.3 *Misweaves.* Imperfections in weave usually found in the warp direction.

| Glossary No. | Imperfection Commercial terminology | Definition |
|---|---|---|
| 34 | Hitch-back<br>Draw-back<br>Tie-back<br>Warp holding place<br>Sticker | A distortion in the weave characterized by tight and slack places in the same warp yarns. |
| 35 | Bad mend | Self-descriptive. |
| 36 | Uneven weaving | Self-descriptive. |

3.2.4 *Miscellaneous warpwise imperfections.*

| Glossary No. | Imperfection Commercial terminology | Definition |
|---|---|---|
| 37 | Mixed end<br>Misply | Warp yarn which differs from that normally being used in the cloth, such as wrong twist, wrong number of plies, wrong color, mixed yarn lots. |
| 38 | Tight end | Self-descriptive. |
| 39 | Slack end | Self-descriptive. |
| 40 | Slack warp | A cloth having an overall crimped or cockled appearance, woven under tension less than proper. |
| 41 | Wrong draw<br>Flat<br>Misreed | A place in the cloth where one or more ends have been drawn through the wrong heddle or reed. |



Source: https://assist.dla.mil -- Downloaded: 202640-26T12:52Z
Check the source to verify that this is the currentversion before use.

| Glossary No. | Imperfection Commercial terminology | Definition |
|---|---|---|
| 42 | Reed mark | Thick or thin lines or both running warpwise in the cloth. |
| 43 | Temple marks | Small holes, impressions, or marks adjacent to the edge of the cloth. |
| 44 | Warp streak | A warpwise band characterized by apparent differences in the color from adjoining ends. |
| 45 | Fuzz balls<br>Balling up<br>Pilling | Loose or frayed fibers which have formed into a ball. |
| 46 | Soiled end | Self-descriptive. |
| 47 | Uneven end | Self-descriptive. |

3.3 Bad selvages.

| Glossary No. | Imperfection Commercial terminology | Definition |
|---|---|---|
| 48 | Curled selvage<br>Folded selvage<br>Rolled selvage<br>Doubles | Self-descriptive. |
| 49 | Slack selvage | Self-descriptive. |
| 50 | Tight selvage | Self-descriptive. |
| 51 | Scalloped selvage | Self-descriptive. |
| 52 | Wavy selvage | The selvage will not lies flat when the cloth is laid out. |
| 53 | Thick selvage | An improperly constructed selvage resulting in greater diameter roll at selvage than body of cloth. |
| 54 | Corded selvage<br>Beaded selvage<br>Rough selvage<br>Loopy selvage | An improperly woven selvage of excessive thickness or a selvage containing irregular filling loops extending beyond the outside selvages. |
| 55 | Cut selvage<br>Broken selvage<br>Torn selvage | Cuts, tears or breaks that occur in the selvage only and do not extend into the body of the cloth. |



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:52Z
Check the source to verify that this is the current version before use.

## 3.4 Finishing imperfections.

| Glossary No. | Imperfection Commercial terminology | Definition |
|---|---|---|
| 56 | Finishing bar | Uneven appearance across entire width of cloth. |
| 57 | Crease | Self-descriptive. |
| 58 | Selvage mark | A more or less regular mark in the finished cloth along the selvage. |
| 59 | Wrinkle mark<br>Seam mark | A more or less regular mark in the finished cloth. |
| 60 | Washer break<br>Washer wrinkle<br>Mill wrinkle | Warpwise indistinct streaks which may alternately appear as wrinkles, abrasions, shifting of yarns or excess or absence of felting cover. |
| 61 | Off shade | Not within established shade tolerance. |
| 62 | Decating mark | A crease mark or impression extending fillingwise across the cloth. |
| 63 | Uneven finish | Cloth does not have the same degree and character of finish throughout. |
| 64 | Uneven napping | Cloth in which the nap is not raised uniformly. |
| 65 | Uneven shearing | Cloth which has not been uniformly sheared. |
| 66 | Uneven shade | Color is not uniform throughout the cloth. |
| 67 | Crowsfeet | Short indistinct markings on dyed or finished goods. |
| 68 | Rope marks | Long irregular indistinct markings on dyed or finished cloth. |
| 69 | Mottled | A general blotchy or spotted appearance of the cloth. |
| 70 | Tentering marks<br>Clip marks<br>Pin marks | Enlarged pinholes or marks along the edge of the cloth. |

## 3.5 General imperfections.

| Glossary No. | Imperfection Commercial terminology | Definition |
|---|---|---|
| 71 | Spot<br>Stain | An area of discoloration on or in the cloth. |



Source: https://assist.dla.mil -- Downloaded: 202610-26T12:52Z
Check the source to verify that this is the current version before use.

| Glossary No. | Imperfection<br>Commercial terminology | Definition |
|---|---|---|
| 72 | Streak | A spot, stain or an off-shade area extended as an irregular stripe in the cloth. |
| 73 | Smash<br>Breakout | A damaged area where the texture has been ruptured by the breaking of a group of yarns, principally the warp. |
| 74 | Abrasion mark<br>Chafe mark<br>Bruise<br>Sand roll mark<br>Fuller rub<br>Washer rub | A place where the surface of the cloth has been damaged by friction. |
| 75 | Objectionable odor | Self-descriptive. |
| 76 | Woven-in waste | Waste or extraneous material that has been woven into the cloth, or spun into the yarn. |
| 77 | Float<br>Skip<br>Overshot | A place in the cloth where a filling or warp yarn extends unbound over the end or pick with which it should be interlaced. |
| 78 | Burrs | Seed fragments with bristles projecting from them. |
| 79 | Shive<br>Sisal<br>Speck | Vegetable matter other than burrs. |
| 80 | Neps | All definite fiber tangles. |
| 81 | Neppiness | A speckled condition of the cloth characterized by a number of neps. |
| 82 | Shift mark | A place in the cloth where warp ends have shifted on the filling picks or vice versa, causing adjacent light and heavy spots. |
| 83 | Bias filling<br>Bowed filling | Cloth in which the filling yarn does not run at right angle to the warp. |
| 84 | Overall uncleanness | Self-descriptive. |
| 85 | Hole<br>Tear<br>Cut | Self-descriptive. |
| 86 | Uneven tension<br>Ridgy cloth<br>Crooked cloth<br>Baggy cloth<br>Wavy cloth<br>Puckering | A wavy or ridgy cloth that will not lie flat when laid on a cutting table. |



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:52Z
Check the source to verify that this is the current version before use.

| Glossary No. | Imperfection Commercial terminology | Definition |
|---|---|---|
| 87 | Pile missing | Self-descriptive. |
| 88 | Crushed pile | Self-descriptive. |
| 89 | Pile improperly formed | Self-descriptive. |
| 90 | Uncut pile | Self-descriptive. |
| 91 | Dark hairs | Black or dark-brown hairs in light-colored cloth. |



Source: https://assist.dla.mil -- Downloaded: 202640-26T12:52Z
Check the source to verify that this is the currentversion before use.

# SECTION III—WOVEN SYNTHETIC FABRICS

## 1. PURPOSE AND SCOPE

1.1 This section consists of a complete listing of woven synthetic fabric imperfections, with definitions, arranged according to whether they are the result of the spinning, weaving, or finishing operations. The purpose is to bring together in one publication the general information on woven synthetic fabric imperfections.

## 2. ALPHABETICAL INDEX OF FABRIC IMPERFECTIONS

2.1 Imperfections and glossary numbers.

### ALPHABETICAL INDEX


| Imperfection Commercial terminology | Glossary No. |
|---|---|
| Abrasion mark | 77 |
| Bad mend | 35 |
| Bad odor | 78 |
| Bad set mark (heavy side) | 2 |
| Bad set mark (light side) | 10 |
| Baggy cloth | 85 |
| Balling up | 46 |
| Barré mark | 19 |
| Beaded selvage | 55 |
| Bias filling | 80 |
| Bowed filling | 80 |
| Box mark | 20 |
| Breakout | 76 |
| Broken filament | 90 |
| Broken or missing end | 33 |
| Broken pick | 12 |
| Broken selvage | 56 |
| Bruise | 77 |
| Bunch | 5 and 27 |
| Calendar mark | 58 |
| Chafe mark | 77 |
| Change-in filling | 15 |
| Cleaning place | 23 |
| Clip marks | 72 |
| Coarse end | 26 |
| Coarse or heavy filling | 1 |
| Coarse or heavy pick | 1 |
| Corded selvage | 55 |


### ALPHABETICAL INDEX—Continued


| Imperfection Commercial terminology | Glossary No. |
|---|---|
| Crack | 13 |
| Crease | 59 |
| Crooked cloth | 85 |
| Crowsfeet | 66 |
| Crushed pile | 87 |
| Curl | 7 |
| Curled selvage | 49 |
| Cut | 83 |
| Cut selvage | 56 |
| Dirty filling | 24 |
| Double pick | 4 |
| Doubles | 49 |
| Drawback | 36 |
| Drop-ply | 32 |
| Dye stain | 68 |
| Dye streak | 69 |
| End out | 33 |
| Filling float | 14 |
| Fine end | 31 |
| Fine filling bar | 10 |
| Fine or light filling | 9 |
| Fine or light pick | 9 |
| Finger mark | 22 |
| Finishing bar | 58 |
| Flat | 4 and 42 |
| Flyers, loom fly | 75 |
| Folded selvage | 49 |
| Fuzz balls | 46 |
| Gout | 75 |
| Hang pick | 18 |
| Hang shot | 18 |
| Hang or loose threads | 30 |
| Hard crease | 59 |
| Harness drop | 14 and 34 |
| Harness skips | 34 |
| Heavy filling bar | 2 |
| Heavy place | 2 |
| Hitchback | 36 |
| Hole | 82 |
| Jerked-in filling | 3 |
| Kink | 7 and 28 |
| Knot | 8 and 29 |
| Lashed in filling | 3 |
| Light filling bar | 10 |
| Light place | 10 |
| Loop | 7 and 28 |
| Loopy selvage | 55 |
| Lump | 5 |




Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:52Z
Check the source to verify that this is the current version before use.

ALPHABETICAL INDEX—Continued

| Imperfection Commercial terminology | Glossary No. |
|---|---|
| Mill wrinkle | 59 |
| Mispick | 11 |
| Misply | 15 and 38 |
| Missing pick | 12 |
| Mixed end | 38 |
| Mixed filling | 15 |
| Mottled | 70 |
| Objectionable odor | 78 |
| Off-shade | 62 |
| Oily filling | 24 |
| Overshot | 14 |
| Pick-out mark | 23 |
| Pile improperly formed | 88 |
| Pile missing | 86 |
| Pilling | 46 |
| Pin marks | 72 |
| Pressure mark | 22 |
| Puckering | 85 |
| Pull-down | 10 |
| Pull-in filling | 3 |
| Reed mark | 43 |
| Ridgy cloth | 85 |
| Rip out | 23 |
| Rolled selvage | 49 |
| Rope marks | 67 |
| Ropy filling | 6 |
| Rough selvage | 55 |
| Sand roll mark | 77 |
| Scalloped selvage | 52 |
| Seam mark | 61 |
| Selvage mark | 60 |
| Shade bar | 15 |
| Shell-off | 6 |
| Shift mark | 79 |
| Shiner | 91 |
| Shuttle mark | 20 |
| Shyer (Shirer) | 13 |
| Skip | 14 |
| Slack end | 40 |
| Slack pick or filling | 17 |
| Slack selvage | 50 |
| Slack warp | 41 |
| Slough-off | 6 |
| Slub | 5 and 27 |
| Slug | 5 and 27 |
| Smash | 76 |
| Snap | 69 |
| Snarl | 7 |
| Soiled end | 47 |

ALPHABETICAL INDEX—Continued

| Imperfection Commercial terminology | Glossary No. |
|---|---|
| Soiled pick | 24 |
| Split end | 90 |
| Split filament | 90 |
| Spot | 73 |
| Stain | 73 |
| Starting mark (heavy side) | 2 |
| Starting mark (light side) | 10 |
| Sticker | 36 |
| Stop mark | 2 and 10 |
| Streak | 74 |
| Stretched filling | 16 |
| Stringy selvage | 54 |
| Stripback | 90 |
| Tails | 81 |
| Tear | 84 |
| Tear drop or teariness | 21 |
| Temple mark | 44 |
| Tentering marks | 72 |
| Thin place | 10 and 13 |
| Tie back | 36 |
| Tight end | 39 |
| Tight pick or filling | 16 |
| Tight selvage | 51 |
| Torn selvage | 57 |
| Uncut pile | 89 |
| Uneven dyeing | 63 |
| Uneven finish | 64 |
| Uneven end | 48 |
| Uneven filling | 25 |
| Uneven napping | 65 |
| Uneven shade | 63 |
| Uneven shrinkage | 71 |
| Uneven tension | 85 |
| Uneven weaving | 37 |
| Warp float | 34 |
| Warp holding place | 38 |
| Warp streak | 45 |
| Wavy cloth | 86 |
| Wavy selvage | 53 |
| Whip-in | 3 |
| Woven-in waste | 75 |
| Wrinkle mark | 61 |
| Wrong draw | 42 |

## 3. IMPERFECTIONS AND DEFINITIONS

### 3.1 Imperfections in filling direction.



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:52Z
Check the source to verify that this is the current version before use.

3.1.1 *Thick places.* Imperfections which cause places in the cloth to be thicker than normal.

| Glossary No. | Imperfection<br>Commercial terminology | Definition |
|---|---|---|
| 1 | Coarse or heavy filling<br>Coarse or heavy pick | A yarn larger in diameter than normally being used in the cloth. |
| 2 | Heavy place<br>Heavy filling bar<br>Bad set mark (heavy side)<br>Stop mark<br>Starting mark (heavy side) | A fillingwise band or bar either across the full width of the cloth or a portion of it, containing picks of larger diameter than normally being used in the cloth or containing more than the normal number of picks. |
| 3 | Jerked-in filling<br>Lashed-in filling<br>Pull-in filling<br>Whip-in | An extra thread dragged into the shed with a proper pick and extending only a part of the way across the cloth. |
| 4 | Double pick<br>Flat | Two or more picks in the same shed across the full width of the cloth. |
| 5 | Slub or slug<br>Bunch<br>Lump | An abruptly thickened place in the yarn. |
| 6 | Slough-off<br>Shell-off<br>Ropy-filling | Filling which has slipped off bobbin and has been woven into the cloth along with the required pick. |
| 7 | Klink<br>Loop<br>Snarl<br>Curl | A place in the cloth where a short length of yarn has spontaneously doubled on itself. |
| 8 | Knot | Self-descriptive. |

3.1.2 *Thin places.* Imperfections which cause places in the cloth to be thinner than normal.

| Glossary No. | Imperfection<br>Commercial terminology | Definition |
|---|---|---|
| 9 | Fine or light filling<br>Fine or light pick | A yarn smaller in diameter than normally being used in the cloth. |
| 10 | Light place<br>Fine filling bar<br>Light filling bar<br>Pull down<br>Bad set mark (light side)<br>Stop mark<br>Starting mark (light side)<br>Thin place | A fillingwise band or bar either across the full width of the cloth or a portion of it, containing picks of smaller diameter than normally being used in the cloth or containing less than the normal number of picks. |



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:52Z
Check the source to verify that this is the current version before use.

3.1.3 *Misweaves.* Imperfections in weave usually found in the filling direction.

| Glossary No. | Imperfection Commercial terminology | Definition |
|---|---|---|
| 11 | Mispick | A pick woven in improper order. |
| 12 | Broken pick<br>Missing pick | A pick wholly or partially missing. |
| 13 | Crack<br>Shyer (Shirer)<br>Thin place | An open streak parallel with the filling and extending partly or entirely across the cloth. |
| 14 | Filling float<br>Skip<br>Overshot<br>Harness drop | A place in the cloth where a filling yarn extends unbound over the ends(s) with which it should be interlaced. |
| 15 | Mixed filling<br>Change in filling<br>Shade bar<br>Misply | Filling yarn which differs from that normally being used in the cloth, such as wrong twist, wrong number of plies, wrong color, mixed yarn lots. |
| 16 | Tight pick or filling<br>Stretched filling | Self-descriptive. |
| 17 | Slack pick or filling | Self-descriptive. |
| 18 | Hang pick<br>Hang shot | A pick which is pulled out of line for a short distance producing a small triangular shaped hole in the cloth. |

3.1.4 *Miscellaneous fillingwise imperfections.*

| Glossary No. | Imperfection Commercial terminology | Definition |
|---|---|---|
| 19 | Barré mark | One or more picks in the cloth characterized by an apparent difference in shade or lustre from adjoining picks. |
| 20 | Box mark<br>Shuttle mark | A fine line parallel with the filling. |
| 21 | Tear drop or teariness | A fabric condition characterized by short elliptical distortions on one or more adjoining picks. |
| 22 | Finger mark<br>Pressure mark | An irregular spot showing variations in picks per inch for a limited width. |
| 23 | Pick-out mark<br>Cleaning place<br>Rip out | A fillingwise band or bar characterized by a chafed or fuzzy appearance. |



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:52Z
Check the source to verify that this is the current version before use.

| Glossary No. | Imperfection Commercial terminology | Definition |
|---|---|---|
| 24 | Soiled pick<br>Dirty filling<br>Oily filling | Self-descriptive. |
| 25 | Uneven filling | Self-descriptive. |

3.2 **Imperfections in the warp direction.**

3.2.1 *Thick places.* Imperfections which cause places in the cloth to be thicker than normal.

| Glossary No. | Imperfection Commercial terminology | Definition |
|---|---|---|
| 26 | Coarse end | A yarn larger in diameter or containing more plies than normally being used in the cloth. |
| 27 | Slub or slug<br>Bunch | An abruptly thickened place in the yarn. |
| 28 | Kink<br>Loop | A place in the cloth where a short length of yarn has spontaneously doubled on itself. |
| 29 | Knot | Self-descriptive. |
| 30 | Hang or loose threads | Self-descriptive. |

3.2.2 *Thin places.* Imperfections which cause places in the cloth to be thinner than normal.

| Glossary No. | Imperfection Commercial terminology | Definition |
|---|---|---|
| 31 | Fine end | A warp yarn smaller in diameter than normally used in the cloth. |
| 32 — | Drop-ply | A yarn containing fewer plies than normally used in the cloth. |
| 33 | Broken or missing end<br>End out | A warp yarn missing for a portion or the entire length of the cloth. |



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:52Z
Check the source to verify that this is the current version before use.

3.2.3 *Misweaves.* Imperfections in weave usually found in the warp direction.

| Glossary No. | Imperfection Commercial terminology | Definition |
|---|---|---|
| 34 | Warp float<br>Harness skips<br>Harness drop | A place in the cloth where a warp yarn extends unbound over the pick(s) with which it should be interlaced. |
| 35 | Bad mend | Self-descriptive. |
| 36 | Hitch-back<br>Draw-back<br>Tie-back<br>Warp holding place<br>Sticker | A distortion in the weave characterized by tight and slack places in the same warp yarns. |
| 37 | Uneven weaving | Self-descriptive. |

3.2.4 *Miscellaneous warpwise imperfections.*

| Glossary No. | Imperfection Commercial terminology | Definition |
|---|---|---|
| 38 | Mixed end<br>Misply | Warp yarn which differs from that normally being used in the cloth, such as wrong twist, wrong number of plies, wrong color, mixed yarn lots. |
| 39 | Tight end | Self-descriptive. |
| 40 | Slack end | Self-descriptive. |
| 41 | Slack warp | A cloth having an overall crimped or cockled appearance, woven under tension less than proper. |
| 42 | Wrong draw<br>Flat | A place in the cloth where one or more ends have been drawn through the wrong heddle, or dent. |
| 43 | Reed mark | A mark running warpwise in the cloth. |
| 44 | Temple marks | Small holes, impressions, or marks adjacent to the edge of the cloth. |
| 45 | Warp streak | A narrow warpwise band or an overall warpwise striation characterized by apparent differences in color or lustre from adjoining ends. |
| 46 | Fuzz balls<br>Balling up<br>Pilling | Loose or frayed fibers which have formed into a ball. |
| 47 | Soiled end | Self-descriptive. |
| 48 | Uneven end | Self-descriptive. |



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:52Z
Check the source to verify that this is the current version before use.

### 3.3 Bad selvages.

| Glossary No. | Imperfection Commercial terminology | Definition |
|---|---|---|
| 49 | Curled selvage<br>Folded selvage<br>Rolled selvage<br>Doubles | Self-descriptive. |
| 50 | Slack selvage | Self-descriptive. |
| 51 | Tight selvage | Self-descriptive. |
| 52 | Scalloped selvage | Self-descriptive. |
| 53 | Wavy selvage | Self-descriptive. |
| 54 | Stringy selvage | Self-descriptive. |
| 55 | Corded selvage<br>Beaded selvage<br>Rough selvage<br>Loopy selvage | An improperly woven selvage of excessive thickness or a selvage containing irregular filling loops extending beyond the outside selvages. |
| 56 | Cut selvage<br>Broken selvage | Cuts or breaks that occur in the selvage only and do not extend into the body of the cloth. |
| 57 | Torn selvage | Self-descriptive. |

### 3.4 Finishing imperfections.

| Glossary No. | Imperfection Commercial terminology | Definition |
|---|---|---|
| 58 | Finishing bar<br>Calendar mark | Uneven appearance extending partly or entirely across the cloth. |
| 59 | Crease<br>Mill wrinkle<br>Hard crease | Self-descriptive. |
| 60 | Selvage mark | A more or less regular mark in the finished cloth along the selvage produced by folded or doubled selvage during finishing operations. |
| 61 | Wrinkle mark<br>Seam mark | A more or less regular mark in the finished cloth produced by pressure during finishing operations. |
| 62 | Off shade | Not within established shade tolerance, shaded side to side, side to center or end to end. |



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:52Z
Check the source to verify that this is the current version before use.

| Glossary No. | Imperfection Commercial terminology | Definition |
|---|---|---|
| 63 | Uneven shade<br>Uneven dyeing | Color is not uniform throughout the cloth. |
| 64 | Uneven finish | Cloth does not have the same degree and character of finish throughout. |
| 65 | Uneven napping | Cloth in which the nap is not raised uniformly. |
| 66 | Crowsfeet | Short indistinct markings on dyed or finished goods. |
| 67 | Rope marks | Long irregular indistinct markings on dyed or finished goods. |
| 68 | Dyestain | An area of discoloration in the cloth. |
| 69 | Dye streak<br>Snap | A dye stain extended as an irregular stripe in the cloth. |
| 70 | Mottled | A blotchy or spotted appearance of the cloth. |
| 71 | Uneven shrinkage | A wavy warpwise condition in the cloth, which prevents it from lying flat on a horizontal surface. This condition may appear along one selvage or both selvages or through sections in the center of the cloth. |
| 72 | Tentering marks<br>Clip marks<br>Pin marks | Enlarged pinholes, tears, or shift marks along the edge of the cloth. |

## 3.5 General imperfections.

| Glossary No. | Imperfection Commercial terminology | Definition |
|---|---|---|
| 73 | Spot<br>Stain | An area of discoloration on the surface of the cloth. |
| 74 | Streak | A spot or stain extended as an irregular stripe in the cloth. |
| 75 | Woven-in waste<br>Gout<br>Flyers<br>Loom fly | Waste that has been woven into the cloth, or spun into the yarn. |
| 76 | Smash<br>Breakout | A damaged area where the texture has been ruptured by the breaking of a group of yarns, principally the warp. |



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:52Z
Check the source to verify that this is the current version before use.

| Glossary No. | Imperfection<br>Commercial terminology | Definition |
|---|---|---|
| 77 | Abrasion mark<br>Chafe mark<br>Bruise<br>Sand roll mark | A place where the surface of the cloth has been damaged by friction. |
| 78 | Objectionable odor<br>Bad odor | Self-descriptive. |
| 79 | Shift mark | A place in the cloth where warp ends have shifted on the filling picks or vice versa, causing adjacent light and heavy spots. |
| 80 | Bias filling<br>Bowed filling | Cloth in which the filling yarn does not run at right angle to the warp. |
| 81 | Tails | A mend in which ends protrude from the cloth. |
| 82 | Hole | Self-descriptive. |
| 83 | Cut | Self-descriptive. |
| 84 | Tear | Self-descriptive. |
| 85 | Uneven tension<br>Ridgy cloth<br>Crooked cloth<br>Baggy cloth<br>Wavy cloth<br>Puckering | A wavy or ridgy cloth that will not lie flat. |
| 86 | Pile missing | Self-descriptive. |
| 87 | Crushed pile | Self-descriptive. |
| 88 | Pile improperly formed | Self-descriptive. |
| 89 | Uncut pile | Self-descriptive. |
| 90 | Stripback<br>Broken filament<br>Split filament<br>Split end | Self-descriptive. |
| 91 | Shiner | A streak caused by a lustrous section of a filament yarn. |

**4. Changes.** When a Federal agency considers that this standard does not provide for its essential needs, written request for changing or adding to the standard, supported by adequate justification, shall be sent to the Administration. This justification shall explain wherein the standard does not provide for essential needs. The request shall be sent in duplicate to the General Services Administration Federal Supply



Source: https://assist.dla.mil -- Downloaded: 202640-26T12:52Z
Check the source to verify that this is the currentversion before use.

Service, Standardization Division, Washington, D. C. 20402. The Administration will determine the appropriate action to be taken and will notify the agency.

MILITARY CUSTODIANS:

Army—GL

Navy—SA

Air Force—11

Interested activities:

*Review:*

Army—GL

Navy—SA, MC, YD

Air Force—11, 67

*User:*

Army—MO, MD

Navy—SH

Preparing activity:

Preparing activity:

Army—GL

Reviewer and User information is current as of the date of this document. For future coordination of changes to this document, draft circulation should be based on the information in the current Federal Supply Classification Listing of DOD Documents.

☆ U.S. GOVERNMENT PRINTING OFFICE: 1968—703329/502

Single copies of this standard are available without charge at the GSA Regional Offices in Boston, New York, Atlanta, Washington, D. C., Chicago, Kansas City, Mo., Dallas, Denver, San Francisco, Los Angeles, and Seattle, Wash. Additional copies may be purchased for cents each from the General Services Administration, Business Service Center, Washington, D.C. 20407.



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:52Z
Check the source to verify that this is the current version before use.

**INSTRUCTIONS:** In a continuing effort to make our standardization documents better, the DoD provides this form for use in submitting comments and suggestions for improvements. All users of military standardization documents are invited to provide suggestions. This form may be detached, folded along the lines indicated, taped along the loose edge *(DO NOT STAPLE)*, and mailed. In block 5, be as specific as possible about particular problem areas such as wording which required interpretation, was too rigid, restrictive, loose, ambiguous, or was incompatible, and give proposed wording changes which would alleviate the problems. Enter in block 6 any remarks not related to a specific paragraph of the document. If block 7 is filled out, an acknowledgement will be mailed to you within 30 days to let you know that your comments were received and are being considered.

*NOTE:* This form may not be used to request copies of documents, nor to request waivers, deviations, or clarification of specification requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document*(s)* or to amend contractual requirements.

*(Fold along this line)*

*(Fold along this line)*

DEPARTMENT OF THE ARMY

NO POSTAGE NECESSARY IF MAILED IN THE UNITED STATES

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300

**BUSINESS REPLY MAIL**
FIRST CLASS PERMIT NO. 12062 WASHINGTON D. C.
POSTAGE WILL BE PAID BY THE DEPARTMENT OF THE ARMY

Commander
US Army Natick Research and Development
Laboratories
ATTN: DRDNA-ES (Mr. D. Juppino)
Natick, MA 01760

Source: https://assist.dla.mil -- Downloaded: 202640-26T12:52Z
Check the source to verify that this is the current version before use.

(TO DETACH THIS FORM, CUT ALONG THIS LINE.)

# STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

*(See Instructions – Reverse Side)*

| 1. DOCUMENT NUMBER | 2. DOCUMENT TITLE |
|---|---|
| | |

| 3a. NAME OF SUBMITTING ORGANIZATION | 4. TYPE OF ORGANIZATION *(Mark one)* |
|---|---|
| | ☐ VENDOR |
| b. ADDRESS *(Street, City, State, ZIP Code)* | ☐ USER |
| | ☐ MANUFACTURER |
| | ☐ OTHER *(Specify)*: _____ |

5. PROBLEM AREAS

a. Paragraph Number and Wording:

b. Recommended Wording:

c. Reason/Rationale for Recommendation:

6. REMARKS

| 7a. NAME OF SUBMITTER *(Last, First, MI)* – Optional | b. WORK TELEPHONE NUMBER *(Include Area Code)* – Optional |
|---|---|
| c. MAILING ADDRESS *(Street, City, State, ZIP Code)* – Optional | 8. DATE OF SUBMISSION *(YYMMDD)* |

DD FORM 82 MAR 1426 PREVIOUS EDITION IS OBSOLETE.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:52Z
Check the source to verify that this is the current version before use.