LLL-B-568F
January 10, 1975
SUPERSEDING
Fed. Spec. LLL-B-568E
February 1, 1971

FEDERAL SPECIFICATION

BOARDS, FOOD SLICING

This specification was approved by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal agencies.

1. SCOPE AND CLASSIFICATION

1.1 Scope. This specification covers modified rubber and plastic food slicing boards.

1.2 Classification. Boards shall be of the following sizes, as specified (see 6.2):

Size 1 - 15 inches wide by 20 inches long by 3/4 inch thick
Size 2 - 18 inches wide by 24 inches long by 3/4 inch thick

2. APPLICABLE DOCUMENTS

2.1 The following documents, of the issue in effect on date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein.

Federal Specifications:

L-P-390	-	Plastic, Molding and Extrusion Material, Polyethylene and Copolymers (Low, Medium, and High Density)
L-P-394	-	Plastic Molding Material, (Propylene Plastics, Injection and Extrusion)
PPP-B-636	-	Boxes, Shipping, Fiberboard

Federal Standard:

Fed. Std. No. 123 - Marking for Domestic Shipping (Civil Agencies).

FSC 7330

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:47Z
Check the source to verify that this is the current version before use.

(Activities outside the Federal Government may obtain copies of Federal Specifications, Standards, and Handbooks as outlined under General Information in the Index of Federal Specifications and Standards and at the prices indicated in the Index. The Index, which includes cumulative monthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, U.S. Government Printing Office, Washington, DC 20402.

(Single copies of this specification and other Federal specifications required by activities outside the Federal Government for bidding purposes are available without charge from Business Service Centers at the General Services Administration Regional Offices in Boston, New York, Washington, DC, Atlanta, Chicago, Kansas City, MO, Fort Worth, Denver, San Francisco, Los Angeles, and Seattle, WA.

(Federal Government activities may obtain copies of Federal Specifications, Standards, and Handbooks and the Index of Federal Specifications and Standards from established distribution points in their agencies.)

Military Standards:

MIL-STD-105	-	Sampling Procedures and Tables for Inspection by Attributes
MIL-STD-129	-	Marking for Shipment and Storage
MIL-STD-147	-	Palletized Unit Loads For 40" x 48" Pallets

(Copies of Military Specifications and Standards required by contractors in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

LAWS AND REGULATIONS

U.S. Postal Service Manual

(Copies of the manual may be obtained from the Superintendent of Documents, U.S. Government Printing Office, Washington, DC 20402.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless a specific issue is identified, the issue in effect on date of invitation for bids or request for proposal shall apply:

American Society for Testing and Materials (ASTM)

D2240-64T - Indentation Hardness of Rubber and Plastics by means of a Durometer

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.)

Source: https://assist.dla.mil -- Downloaded: 202610-26T12:47Z
Check the source to verify that this is the current version before use.

National Motor Freight Traffic Association, Inc., Agent

National Motor Freight Classification

(Application for copies should be addressed to the American Trucking Associations, Inc., Tariff Order Section, 1616 P Street, N.W., Washington, DC 20036.)

Uniform Classification Committee, Agent

Uniform Freight Classification

(Application for copies should be addressed to the Uniform Classification Committee, Room 1106, 222 South Riverside Plaza, Chicago, IL 60606.)

National Sanitation Foundation (NSF)

Basic Criteria C2

Listing of Food Service Equipment

(Application for copies should be addressed to the National Sanitation Foundation, P.O. Box 1468, Ann Arbor, Michigan 48105.)

(Technical society and technical association specifications and standards are generally available for reference from libraries. They are also distributed among technical groups and using Federal agencies.)

3. REQUIREMENTS

3.1 Standard product. Slicing boards delivered under this specification shall be the manufacturer's standard commercial product, except for any design modifications and additional requirements specified herein.

3.2 NSF. Slicing boards shall conform to applicable requirements of NSF Basic Criteria C2 and shall be:

(1) A listing in the current edition of NSF "Listing of Food Service Equipment" or display of the NSF seal on the finished food slicing boards, or

(2) A certification for the food slicing boards issued by NSF under their special one-time contract evaluation/certification service, or

(3) A certified test report from a recognized independent testing laboratory acceptable to the medical department of the service for which the food slicing boards are being procured, indicating that the slicing boards have been tested and conform to NSF Basic Criteria C2.

Source: https://assist.dla.mil -- Downloaded: 202610-26T12:47Z
Check the source to verify that this is the current version before use.

3.3 Materials. Materials shall be as specified herein. Materials not definitely specified shall be of the quality normally used by the manufacturer in his standard commercial food slicing boards provided the completed item complies with provisions of this specification.

3.3.1 Modified rubber composition. Modified rubber composition boards shall be a styrene-butadiene rubber (SBR) high styrene rubber compound or an acrylonitrile-butadiene rubber compound and shall be buff in color.

3.3.1.1 Styrene-butadiene rubber. Styrene-butadiene rubber shall have a Shore D Durometer hardness reading of not less than 55 nor more than 75 and shall weigh not less than 4.5 nor more than 5.0 pounds per square foot per 3/4-inch of thickness when tested as specified in 4.3.2 and 4.3.3, respectively.

3.3.1.2 Acrylonitrile-butadiene rubber. Acrylonitrile-butadiene rubber shall have a Shore D Durometer hardness reading of not less than 55 nor more than 75 and shall weigh not less than 4.0 nor more than 5.0 pounds per square foot per 3/4-inch of thickness when tested as specified in 4.3.2 and 4.3.3, respectively.

3.3.2 Plastic. The plastic for the slicing board shall be a virgin high density ethylene copolymer material conforming to type I, class H of L-P-390 or type I or III B of L-P-394. Clean, unburned plastic material in the form of imperfect parts of the same composition as the virgin material, and produced in the molding or finishing operation, may be reground and mixed with the virgin material. When reground is mixed with the virgin material, the reground shall not exceed a level of 15 percent by weight of the blended mixture. The plastic board shall have a Shore D Durometer hardness reading of not less than 55 nor more than 75 and shall weigh not less than 1.75 nor more than 3.5 pounds per square foot per 3/4-inch of thickness when tested as specified in 4.3.2 and 4.3.3, respectively.

3.4 Construction. Boards shall be capable of being used on either side for the intended purpose and shall be flat within 1/32 of an inch when tested as specified in 4.3.1 and shall conform to the dimensional requirements of table I.

TABLE I. Dimensions

Size	Dimensions		
	Width ± 1/8	Length ± 1/8	Thickness ± 1/16
	Inches	Inches	Inches
1	15	20	3/4
2	18	24	3/4

Source: https://assist.dla.mil -- Downloaded: 202610-26T12:47Z
Check the source to verify that this is the currentversion before use.

3.4.1 Fabrication. Slicing boards shall be of one piece construction and shall be fabricated of modified rubber material specified in 3.3.1.1 or 3.3.1.2, or of plastic material specified in 3.3.2. If cloth is used to obtain the finish specified in 3.5, for the modified rubber slicing board, the cloth may be left on for protection prior to use. Each finished slicing board, except modified rubber slicing boards protected with cloth, shall be provided with removable paper or fabric protective covering, adhered to both sides. Instructions for removing the protective covering shall be provided with each board.

3.5 Finish. The modified rubber composition slicing boards shall have a finish obtained by pressing a cloth sheet into the top and bottom surfaces or by simulating a cloth impression without the use of a cloth sheet. The plastic slicing boards shall have a non-skid finish and shall be white (natural color).

3.6 Identification marking. Boards shall be legibly marked in accordance with the manufacturer's standard practice and shall bear the manufacturer's name or trademark.

3.7 Workmanship. The finished boards shall be clean, and suitable for the intended use. Corners and edges of all boards shall be rounded and smooth and shall be free from voids, cracks, and dirt.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or order, the supplier may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.2 Inspection. Sampling for inspection shall be performed in accordance with MIL-STD-105, except where otherwise indicated hereinafter.

4.2.1 Component and material inspection. In accordance with 4.1 above, components and materials shall be inspected and tested in accordance with all the requirements of referenced specifications and standards unless otherwise excluded, amended, modified, or qualified in this specification or applicable purchase document.

4.2.2 Process inspection.

Source: https://assist.dla.mil -- Downloaded: 202610-26T12:47Z
Check the source to verify that this is the current version before use.

4.2.2.1 In-process examination. Examination shall be made of the following processes to establish conformance with specified requirements. Whenever non-conformance is noted, correction shall be made to the affected items and lot in process. Blended mixture process (see 3.3.2). When reground material exceeds a level of 15 percent by weight of the blended mixture, correction shall be made to the mixture in process.

4.2.3 End item inspection. The lot shall consist of all boards of one size offered for inspection at one time. The sample unit shall be one slicing board.

4.2.3.1 Visual examination. The end item shall be examined for defects in table II. The inspection level shall be level II with an acceptable quality level (AQL) of 2.5 for major defects and 6.5 for total defects, expressed in terms of defects per hundred units.

TABLE II. Classification of visual defects

Examine	Defect	Classification Major	Minor
Finish	Not as specified	X	
	Not natural color for plastic boards	X	
Construction and workmanship (general)	Modified rubber boards not provided with sheeting cloth finish or simulated impression	X	
	Edges or corners of boards not rounded and smooth		X
	Not finished on both sides	X	
	Not as specified	X	
	Not free from voids, cracks, dirt and sink marks	X	
	Not one piece construction	X	
	Not provided with protective covering if sheeting cloth is not provided	X	
Marking	Missing or not legible		X

4.2.3.2 Dimensional examination. Examination shall be made to determine compliance with the dimensional requirements of this specification. Any dimension not within specified requirements shall be classified a defect. The inspection level shall be S-2 with an AQL of 4.0 defects, expressed in terms of defects per hundred units.

4.2.3.3 Testing of the end item. Production units shall be tested as specified in 4.3.1, 4.3.2 and 4.3.3 using inspection level S-4 with an AQL of 4.0 defects, expressed in terms of defects per hundred units.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:47Z
Check the source to verify that this is the current version before use.

4.2.4 Examination of preparation for delivery requirements. An examination shall be made to determine whether the packaging, packing, and marking complies with the section 5 requirements. Defects shall be scored in accordance with the list below. The sample unit shall be one shipping container fully prepared for delivery except that it need not be closed. The lot size shall be the number of shipping containers in the end item inspection lot. The inspection level shall be S-2 and the AQL shall be 4.0 defects per hundred units.

TABLE III. Examination of preparation for delivery

Examine	Defect
Marking (exterior)	Omitted; incorrect; illegible; of improper size, location, sequence or method of application.
Materials	Any component missing, damaged or not as specified.
Workmanship	Bulged or distorted containers.
Content	Number of boards per shipping container is more or less than required.

4.2.4.1 Examination of shipping container. When shipping containers are required to comply with PPP-B-636, examination for defects in the closure, waterproofing and reinforcing shall be in accordance with the appendix of the box specification.

4.2.5 Examination for palletization. An examination shall be made to determine that the palletization complies with the section 5 requirements. Defects shall be scored in accordance with the list below. The sample unit shall be one palletized unit load fully prepared for delivery. The lot size shall be the number of palletized unit loads in the end item inspection lot. The inspection level shall be S-1 and the AQL shall be 6.5 defects per hundred units.

TABLE IV. Examination of palletization

Examine	Defect
Finished dimension	Length, width, or height exceeds specified maximum requirements.
Palletization	Not as specified. Pallet pattern not as specified. Interlocking of loads not as specified. Load not bonded with required straps specified.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:47Z
Check the source to verify that this is the current version before use.

TABLE IV. Examination of palletization (cont'd)

Examine	Defect
Weight	Exceeds maximum load limits.
Marking	Omitted; incorrect; illegible; of improper size, location, sequence or method of application.

4.2.6 NSF compliance. Proof of compliance with the requirements of 3.2 shall be submitted to the Government representative.

4.3 Tests.

4.3.1 Flatness. The boards shall be placed with one face up on a surface plate or other known level surface and manual pressure applied to each of the four corners in sequence. The board shall be turned over so the reverse side is up and the same procedure repeated. Neither side of the board shall be more than 1/32 inch out of flatness as required by 3.4. Inability to meet the requirements for flatness specified shall constitute failure of this test.

4.3.2 Cutting board material. Slicing boards shall be tested in accordance with ASTM D2240-64T to determine compliance with the requirements of 3.3.1 and 3.3.2. Four determinations shall be made on each sample unit and the average of the determinations shall be calculated. The determinations shall be made at least 1/2 inch in from each corner. Inability of the average to meet the requirements specified in 3.3.1.1, 3.3.1.2, or 3.3.2 as applicable shall constitute failure of this test.

4.3.3 Material weight. Slicing boards shall be weighed to determine compliance with the requirements of 3.3.1.1, 3.3.1.2, or 3.3.2 as applicable. Inability to meet the requirements shall constitute failure of this test.

5. PREPARATION FOR DELIVERY

5.1 Packing. Packing shall be level A, B, or C as specified (see 6.2).

5.1.1 Level A. Four size 1 or three size 2 boards shall be packed in a snug-fitting fiberboard shipping container conforming to style RSC or OPF, grade V3s or V2s of PPP-B-636. Each fiberboard container shall be closed in accordance with method III, waterproofed in accordance with method V and reinforced as specified in the appendix of PPP-B-636.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:47Z
Check the source to verify that this is the current version before use.

5.1.2 Level B. Four size 1 or three size 2 boards shall be packed in a snug-fitting fiberboard shipping container conforming to style RSC or OPF, type CF (variety SW) or SF, class domestic, grade 200 of PPP-B-636. Each fiberboard container shall be closed in accordance with method II as specified in the appendix of PPP-B-636.

5.1.2.1 When specified (see 6.2), the fiberboard shipping container shall be a grade V3c, V3s, or V4s fiberboard box fabricated in accordance with PPP-B-636 and closed in accordance with method III as specified in the appendix of the container specification.

5.1.3 Level C (commercial packing). Boards shall be packed in a manner to insure carrier acceptance and safe delivery at destination at the lowest transportation rate for such supplies. The quantity per shipping container shall be the same as that normally used by the supplier for retail distribution. Containers shall comply with the US Postal Service Manual, Uniform Freight Classification Rules or National Motor Freight Classification Rules, as applicable.

5.2 Palletization. When specified (see 6.2), boards packed as specified in 5.1, shall be palletized in accordance with load type I of MIL-STD-147. Each prepared load shall be bonded with primary and secondary straps in accordance with bonding means K and L. Pallet patterns shall be in accordance with the appendix of MIL-STD-147. Interlocking of loads shall be effected by reversing the pattern of each course. If the container is of a size which does not conform to any of the pallet patterns specified in MIL-STD-147, the pallet pattern used shall first be approved by the contracting officer.

5.3 Marking.

5.3.1 Civil agencies. In addition to any special marking required by the contract or order, shipping containers shall be marked in accordance with FED-STD-123.

5.3.2 Military requirements. In addition to any special marking required by the contract or order, shipping containers and palletized unit loads shall be marked in accordance with MIL-STD-129.

6. NOTES

6.1 Intended use. The slicing board is intended for use in the kitchen or galley for the slicing of bread and other food products.

6.2 Ordering data. Purchasers should select the preferred options permitted herein and include the following information in procurement documents:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:47Z
Check the source to verify that this is the current version before use.

(a) Title, number, and date of this specification.
(b) Size of board required (see 1.2).
(c) Selection of applicable levels of packing (see 5.1).
(d) When weather resistant grade fiberboard shipping containers are required for level B packing (see 5.1.2.1).
(e) When palletization is required (see 5.2).

6.3 Supersession data. Board, Food Chopping has been deleted from title and the requirements for type I removed from this specification. Type II, size 1 and 2 boards have been changed in this revision to size 1 and 2 boards.

Custodians:

Army - GL
Navy - SA
Air Force - 84

Review activities:

Army - MD
Navy - MC, MS, YD

User activity:

Navy - CG

Preparing activity:

Army - GL

Civil Agency Coordinating Activities:

GSA-FSS
VA

Project No. 7330-0434

Orders for this publication are to be placed with General Services Administration, acting as an agent for the Superintendent of Documents. See section 2 of this specification to obtain extra copies and other documents referenced herein. Price 35 cents each.

Source: https://assist.dla.mil -- Downloaded: 202610-26T12:47Z
Check the source to verify that this is the currentversion before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

OMB Approval
No. 22-R255

INSTRUCTIONS: The purpose of this form is to solicit beneficial comments which will help achieve procurement of suitable products at reasonable cost and minimum delay, or will otherwise enhance use of the document. DoD contractors, government activities, or manufacturers/vendors who are prospective suppliers of the product are invited to submit comments to the government. Fold on lines on reverse side, staple in corner, and send to preparing activity. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements. Attach any pertinent data which may be of use in improving this document. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity.

DOCUMENT IDENTIFIER AND TITLE LLL-B-568F
BOARDS, FOOD SLICING

NAME OF ORGANIZATION AND ADDRESS

CONTRACT NUMBER

MATERIAL PROCURED UNDER A
☐ DIRECT GOVERNMENT CONTRACT ☐ SUBCONTRACT

1. HAS ANY PART OF THE DOCUMENT CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE?
   A. GIVE PARAGRAPH NUMBER AND WORDING.

   B. RECOMMENDATIONS FOR CORRECTING THE DEFICIENCIES

2. COMMENTS ON ANY DOCUMENT REQUIREMENT CONSIDERED TOO RIGID

3. IS THE DOCUMENT RESTRICTIVE?
   ☐ YES ☐ NO *(If "Yes", in what way?)*

4. REMARKS

SUBMITTED BY *(Printed or typed name and address - Optional)*

TELEPHONE NO.

DATE

DD FORM 1 JAN 72 1426

REPLACES EDITION OF 1 JAN 66 WHICH MAY BE USED

Source: https://assist.dla.mil -- Downloaded: 202610-26T12:47Z
Check the source to verify that this is the current version before use.

FOLD

DEPARTMENT OF THE ARMY
US ARMY NATICK LABORATORIES
NATICK, MA 01760
OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300
STSNL-TDG

POSTAGE AND FEES PAID
DEPARTMENT OF THE ARMY
DOD – 314

Commander
US Army Natick Laboratories
ATTN: STSNL-TD
Natick, MA 01760

FOLD

Source: https://assist.dla.mil -- Downloaded: 202610-26T12:47Z
Check the source to verify that this is the current version before use.