NOTICE: When Government drawings, specifications, or other data are used for any purpose other than in connection with a definitely related Government procurement operation, the U. S. Government thereby incurs no responsibility, nor any obligation whatsoever; and the fact that the Government may have formulated, furnished, or in any way supplied the said drawings, specifications, or other data is not to be regarded by implication or otherwise as in any manner licensing the holder or any other person or corporation, or conveying any rights or permission to manufacture, use, or sell any patented invention that may be in any way related thereto. Referenced documents shall be the issue in effect on date of invitation for bids.

MIL-STD- 716 (NORD)

16 June 1959
Superseding
NAVORD OS 8728
13 May 1958

MILITARY STANDARD

FORMULA FOR ILLUMINANT COMPOSITION III

Ingredient	Magnesium	Sodium Nitrate	Binder Solution
Specification	JAN-M-382 Type III Granulation 18	MIL-S-322 Grade B Class 2	MIL-STD-708 Class 2
Percent by Weight	53.0 ± 0.5	38.5 ± 0.5	8.5 ± 0.25

The composition shall be blended thoroughly prior to use.

The moisture content of the sodium nitrate at the time of blending shall be less than 0.2 percent when tested as specified in MIL-S-322.

The processing of the ingredients and the blending operation should take place under conditions which do not permit the relative humidity to exceed 75 percent and with a temperature of 50 to 100°F.

The following blending procedure has been found satisfactory: Place the magnesium in a muller type blender, add the laminac mixture and operate the blender for about 5 minutes. Then add the sodium nitrate and operate the blender for about 10 minutes. Acetone has been found satisfactory for cleaning the blender after the blending of each batch.

CAUTION: For safety reasons, the blending of more than 100 pounds per batch is considered inadvisable. The blender should be operated remotely from a barricaded control station. The usual precautions for handling pyrotechnic mixtures must be observed in handling this composition. See section 6.7 of MIL-P-21355 for general safety precautions.

The composition is prepared at time of use. No storage is required. The Replacement Sample Powder Tank Mk 1 Mods, BuOrd Dwg 423038, has been found satisfactory for handling the mixture.

Copies of specifications, standards, drawings and publications required by contractors in connection with specific procurement functions should be obtained from the procuring agency or as directed by the contracting officer.

FSC 1375

Source: https://assist.dla.mil -- Downloaded: 202610-23T22:24Z
Check the source to verify that this is the current version before use.