NOTICE: When Government drawings, specifications, or other data are used for any purpose other than in connection with a definitely related Government procurement operation, the U. S. Government thereby incurs no responsibility, nor any obligation whatsoever; and the fact that the Government may have formulated, furnished, or in any way supplied the said drawings, specifications, or other data is not to be regarded by implication or otherwise as in any manner licensing the holder or any other person or corporation, or conveying any rights or permission to manufacture, use, or sell any patented invention that may be in any way related thereto. Referenced documents shall be the issue in effect on date of invitation for bids.

MIL-STD-717 (NORD)

16 June 1959
Superseding NAVORD OS 8727
dated 15 May 1958

MILITARY STANDARD

FORMULA FOR BINDER SOLUTION II

Ingredient	Binder, Cellulose Nitrate Camphor	Acetone
Specification	MIL-B-10854, Any Form	JAN-A-489
Percent by Weight	8.0 ± 0.1	92.0 ± 0.1

REQUIREMENT:

The binder ingredient shall be completely dissolved prior to use of the binder solution.

CAUTION: Due to its high volatility and ease of ignition, extreme caution should be exercised in handling acetone. See section 6.7 of MIL-P-21355 (NOrd) for general safety precautions.

Copies of *specifications, standards, drawings and publications* required by contractors in connection with specific procurement functions should be obtained from the procuring agency or as directed by the contracting officer.

☆U.S. GOVERNMENT PRINTING OFFICE: 1976-603-766/5723

FSC 1375

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T22:24Z
Check the source to verify that this is the current version before use.