MIL–P–46502B(MU)
5 DECEMBER 1962

SUPERSEDING
MIL–P–46502A(ORD)
17 AUGUST 1962
AMENDMENT 1
17 OCTOBER 1962

MILITARY SPECIFICATION

PROJECTILE BODY, METAL PARTS ASSEMBLY FOR CARTRIDGE, HE, 81MM M362A1

1. SCOPE

1.1 This specification covers Projectile Body, Metal Parts Assembly for Cartridge, HE, 81MM, M362A1.

2. APPLICABLE DOCUMENTS

2.1 The following documents of the issue in effect on date of invitation for bids or request for proposal, form a part of the specification to the extent specified herein.

SPECIFICATIONS

MILITARY

MIL–A–2550 —Ammunition and Special Weapons, General Specification for

MIL–P–10025 —Packing and Marking for Domestic Shipment of Inert Ammunition Components, General Specification for

MIL–I–45208 —Inspection Requirements, General Specification for

MIL–M–11472 —Magnetic — Particle Inspection; Processes for Ferromagnetic Materials

MIL–C–7701 —Certification of Magnetic Particle Inspection Personnel

STANDARDS

FEDERAL

Federal Test Method Standard No. 151—Metals; Test Methods

MILITARY

MIL–STD–105 —Sampling Procedures and Tables for Inspection by Attributes

MIL–STD–109 —Quality Assurance and Definitions

MIL–STD–414 —Sampling Procedures and Tables for Inspection by Variables for Percent Defective

MIL–STD–639 —Surface Roughness Values Preferred for Army Ordnance Materiel

DRAWINGS

MUNITIONS COMMAND

D8596986 —Body Assembly

IEL–D–8596986 —Inspection Equipment List for Projectile Body, Metal Parts Assembly for Cartridge, HE, 81-MM, Mortar, M36-2A1

FSC 1315

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T06:07Z
Check the source to verify that this is the current version before use.

PUBLICATIONS

MUNITIONS COMMAND

ORD–M608–11 —Ordnance Inspection Handbook on Procedures and Tables for Continuous Sampling by Attributes

PA–PD–792 —Equipment, Testing or Measuring, For Ammunition Items

FRANKFORT ARSENAL

10519685 —Operating Instruction Manual for the Ultrasonic Inspection of Body Casting for 81MM Projectile

(Copies of specifications, standards, drawings and publications required by contractors in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

3. REQUIREMENTS

3.1 General. Materials, parts and assemblies shall comply with requirements specified on the applicable drawing, referenced specifications, and the following:

3.2 Initial production sample. Unless otherwise directed by the contracting officer, an initial production sample shall be required.

3.3 Heat treatment. The heat treatment of the body casting shall be uniform throughout each lot and shall be so conducted as to produce in each body casting the physical properties specified on the applicable drawing.

3.4 Physical properties. The physical properties specified on the applicable component drawing shall apply throughout each component.

3.5 Metal defects. The body casting shall be free from cracks, cold shuts, hot tears, shrinkage, inclusions, blow holes, porosity or other defects which produce voids greater than those described as minimum acceptable standards in Manual 10519685.

3.5.1 *Base adapter.* The base adapter shall be free from cracks, splits, cold shuts, laminations, porosity or similar defects.

3.6 Strength of brazed joint. Brazing between the base adapter and the body shall withstand the stresses developed by the application of 5000 pounds, minimum, internal hydrostatic pressure for 5 seconds, without leakage or rupture.

3.6.1 *Air pressure test.* After hydrostatic testing, the body assembly shall withstand an internal air pressure of 150 pounds per square inch, for 15 seconds without evidence of leakage.

3.7 Brazed point. The braze metal shall be visible around the entire area where the base adapter joins the body wall. The braze metal shall also be visible for the full 360 degrees around the joint between the rear of the body and the base adapter flange.

3.7.1 *Quality of joint.* The aggregate area of defects plus inclusions shall not exceed 15 percent of the area of the faying surfaces of the respective joint; and the maximum extent of a defect shall not exceed 15 percent of the overlap distance (width) of the joint.

3.8 Protective coating. Protective coating shall be in accordance with the applicable drawing and the specifications referenced thereon.

3.9 Functional.

3.9.1 *Security.* There shall be no breakup of the body assembly in the gunbore or in flight.

3.10 Workmanship. The requirements for workmanship are as shown on the applicable drawings, in the applicable specifications and the following:

3.10.1 *Surface finish.* The requirements for surface finish are as detailed on the applicable drawing. The cavity of the body assembly shall be free of burs, scale, fins, deep seams, pits or other surface discontinuities.

3.10.2 *Threads.* Threads shall be full and undamaged for the entire minimum length or depth as required by the applicable draw-

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T06:07Z
Check the source to verify that this is the current version before use.

FILE COPY
DO NOT ISSUE

ings and shall be in accordance with the provisions of MIL–A–2550.

3.10.3 *Bur.* No part shall have a bur which might interfere with the assembly or the function of the round or which might be injurious to personnel handling the item.

3.10.4 *Foreign matter.* No part or assembly shall contain dirt, grease, chips, rust, corrosion, or other foreign matter. Particular attention shall be paid to the cavity of the body assembly, prior to painting, to insure that no grit, scale or other foreign matter remains therein after final cleaning.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified, the supplier may utilize his own facilities or any commercial laboratory acceptable to the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.1.1 *Quality assurance terms and definitions.* Reference shall be made to MIL–STD–109 to define the Quality Assurance terms used.

4.1.2 *Inspection.* Inspection shall be in accordance with MIL–A–2550 and MIL–I–45208, except as specified herein

4.2 Initial production sample. Prior to initiation of regular production the contractor shall submit an initial production sample to a Government approved facility for evaluation. The sample shall consist of 70 body assemblies as follows: 55 body assemblies complete including paint, 5 body assemblies complete except protective coating, and 10 sets of component parts unassembled less protective coating, for performance of examinations and tests specified in 4.3. The test procedure shall be in accordance with 4.4 except as provided in MIL–I–45208. The sample shall be subjected to the tests listed in 4.3.3. The Government will perform ballistic test on 50 of the above assemblies in accordance with 4.3.4 to determine compliance with 3.9. The sample shall be manufactured in the same manner, using the same materials, equipment, processes and procedures as will be used for regular production. All parts and materials, including packaging and packing must be the same as will be used for regular production and shall be obtained from the same source of supply. The contractor shall inspect the sample in accordance with his inspection system and other inspection requirements of MIL–I–45208. After inspection and provisional acceptance at source, the initial production sample shall be inspected at the Government approved facility for all requirements of the drawings and specifications. Fifty of the above 55 assemblies shall be forwarded to a designated proving ground by the contractor for ballistic testing. The Government reserves the right to require new initial production samples until such time as an acceptable sample has been submitted.

4.3 Inspection provisions.

4.3.1 *Lot.*

4.3.1.1 *Submittal of product.* The contractor shall submit the product in accordance with MIL–STD–105 or Handbook ORD–M608–11, as applicable.

4.3.2 *Examination.* One hundred percent examination shall be performed for all critical defects. Examination for major and minor defects shall be performed on a defect basis in accordance with the classification of defects contained herein, using the sampling plans contained in MIL–STD–105 or ORD–M608–11 as applicable. An AQL of 0.25 percent for each major defect and an AQL of 0.40 percent for each minor defect shall be used. All nonconforming material shall be rejected. Four power (4X) magnification may be used in performing visual examination for such defects as bur and foreign matter. The Ordnance Standard Finish Blocks prescribed by MIL–STD–639 shall be used as a basis of comparison for surface roughness determination.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T06:07Z
Check the source to verify that this is the current version before use.

4.3.2.1 *Classification of Defects.*

4.3.2.1.1 *Base, Adapter, Drawing C8596988, covering a detail of Drawing D8596986.*

	Defect	Method of Inspection
Critical		
	None defined	
Major		
101.	Diameter outside forward of shoulder	Gage
102.	Thickness of base	Gage
Minor		
201.	Thickness through shoulder	Gage
202.	Radius or chamfer missing or incorrect	Visual
203.	Surface finish, improper	Visual

4.3.2.1.2 *Metal Parts Assembly (Prior to Painting), Drawing D8596986.*

	Defect	Method of Inspection
Critical		
1.	Braze metal not visible for 360 degrees at juncture of adapter and wall inside	Visual
2.	Braze metal not visible for 360 degrees around joint between rear of adapter and adapter flange.	Visual
3.	Ultrasonic, hydrostatic or air pressure stamp missing	Visual
Major		
101.	Concentricity of pitch diameter of nose thread with bourrelet, including perpendicularity of front face.	Gage
102.	Concentricity of pitch diameter of base thread with bourrelet, including perpendicularity of shoulder in front of thread.	Gage
103.	Concentricity of ogive with bourrelet	Gage
104.	Concentricity at rear of body with bourrelet	Gage
105.	Diameter of bourrelet, min.	Gage
106.	Diameter at rear of body, outside	Gage
107.	Wall thickness at bourrelet	Gage
108.	Wall thickness at forward datum location	Gage
109.	Wall thickness at rear datum location	Gage
110.	Variation in wall thickness	Gage
111.	Thickness through base at juncture of thread boss and rear face of shoulder, min.	Gage
112.	Base cover weld or braze inadequate	Manual
113.	Surface finish of cavity, improper	Visual/Measure
114.	Foreign matter in cavity	Visual
Minor		
201.	Diameter of nose, outside	Gage
202.	Diameter of nose thread chamfer	Gage
203.	Diameter at ogive datum length	Gage
204.	Diameter at forward datum length on rear taper	Gage
205.	Diameter at rear datum length on rear taper	Gage
206.	Length from rear to shoulder	Gage
207.	Length total, max.	Gage
208.	Surface finish, improper except as otherwise classified	Visual/Measure
209.	Stamping missing, incorrect or illegible	Visual
210.	Bur	Visual
211.	Foreign matter	Visual

4.3.2.1.3 *Metal Parts Assembly (after painting) Drawing D8596986.*

	Defect	Method of Inspection
Critical		
	None defined	
Major		
101.	Weight	Approved Scale
102.	Pitch diameter of nose thread, max.	Gage

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T06:07Z
Check the source to verify that this is the current version before use.

Defect	Method of Inspection
103. Minor diameter of nose thread, max.	Gage
104. Pitch diameter of base thread, min.	Gage
105. Major diameter of base thread, min.	Gage
106. Diameter of bourrelet, max.	Gage
107. Length of effective nose thread, min.	Gage
108. Length of effective base thread, min.	Gage
109. Paint in cavity inadequate	Visual
110. Pool of paint in cavity	Visual
111. Thread(s) damaged or not full	Visual
112. Foreign matter	Visual
Minor	
201. Pitch diameter of nose threads, min.	Gage
202. Pitch diameter of base thread, max.	Gage
203. Silicone compound missing from threads	Visual
204. Paint on thread(s)	Visual
205. Exterior paint, inadequate or damaged	Visual
206. Paint not dry	Visual/Manual

4.3.2.1.4 *Packed carton, prior to sealing.*

Defect	Method of Inspection
Critical	
None defined	
Major	
None defined	
Minor	
201. Support missing or damaged	Visual
202. Separator missing or damaged	Visual
203. Improper assembly	Visual
204. Incorrect number in carton	Visual

4.3.2.1.5 *Packed carton, after sealing.*

Defect	Method of Inspection
Critical	
None defined	
Major	
None defined	
Minor	
201. Carton damaged, cut or gouged through all layers	Visual
202. Carton not completely sealed	Visual
203. Contents loose	Visual/Manual
204. Marking missings, incorrect or illegible	Visual

4.3.3 *Inspection testing.* The following tests shall be performed in accordance with the provisions of 4.4, except as provided in MIL–I–45208.

4.3.3.1 *Physical properties.*

4.3.3.1.1 *Hardness.* In order to insure uniformity of heat-treatment, each body casting shall be subjected to a hardness test with a Brinell Hardness Tester, using a 5 seconds minimum dwell or by any other method of hardness testing approved by the procuring activity. For identification purposes, any quantity of body castings but not to exceed 4 hours production of the final heat treatment furnace, that have been subjected to final heat treatment in the same furnace, at the same temperature, for the same length of time or conveyor speed shall be considered as a heat treatment lot. The heat treatment lot thus constituted shall form the basis for selecting sample body castings for the tension test herein after prescribed.

4.3.3.1.2 *Tension test.* Two body castings, one of the hardest and one of the softest from each heat treated lot shall be subjected to this test. If all specimens comply with the

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T06:07Z
Check the source to verify that this is the current version before use.

yield strength and elongation requirements of the body drawing, the hardness range for the lot will have been established. Failure of one or more tension test specimens to comply with the requirements shall be cause for rejection of the heat treatment lot represented by the specimen.

4.3.3.1.3 *Retest.* When one or more tension test specimens fail to comply with the yield strength or elongation requirements of the body casting drawing, the rejected lot may at the discretion of the contractor be reheat treated or new samples of a higher or lower hardness value or both may be selected to establish a new hardness range. When the hardness range has been established, all castings whose hardness values fall outside the range shall be rejected, subject to reheat treatment.

4.3.3.1.4 *Alternate hardness testing.* A direct reading Brinell Hardness Testing Machine may be substituted for the Brinell Scope Method, provided the same diameter ball is used and the same load is applied as is used in Standard Brinell Testing, and provided that at least 2000 castings are tested by both methods to establish correlation. After correlation has been established, the diameter of the indentation in every tenth casting shall be measured with the Brinell Scope to assure continued correlation.

4.3.3.1.4.1 When the body castings are heat treated by a continuous process in conveyor type furnaces with automatic quench and temper cycle which has proven capable of consistently producing in the castings the physical properties required by the body casting drawing, the contractor may at the discretion of the contracting officer perform the hardness test on a sampling basis using a range type sampling plan selected from MIL–STD–414 inspection level 2 with an AQL of 0.25 percent. One of the hardest and one of the softest castings tested shall be selected for the tension test prescribed by 4.3.3.1.2. Failure of any test specimen to comply with the yield strength and elongation requirements of the applicable drawing shall be cause for rejection of the lot.

4.3.3.2 *Metal defects.*

4.3.3.2.1 *Ultrasonic inspection.* Each body casting, after rough machining of the outside surface, shall be subjected to an automatic ultrasonic inspection in accordance with Manual 10519685. Rejection of any body casting, by the ultrasonic testing machine shall be considered as failure to comply with the requirements of 3.5 and shall be cause for rejection of that body casting. To identify accepted body casting as a result of this inspection, the letter "U" shall be indented thereon by a metal stamp.

4.3.3.2.2 *Magnetic particle inspection.*

4.3.3.2.2.1 Upon initiation of production, the contractor shall perform a minimum of two 100 percent magnaglo inspections on all body castings that have been accepted by the ultrasonic inspection machine. Each individual magnaglo inspection shall be performed in accordance with the contractor's approved procedure and shall proceed through each cycle: i.e., magnetize apply suspensoid, drain, visually inspect, demagnetize (if residual method is used) and clean.

4.3.3.2.2.1.1 If one or more defects such as spike, cracks, or other disqualifying defects as defined in paragraph 3.5 are found the two 100 percent magnaglo inspections shall be continued until the defect has been removed from the process as indicated by 2500 consecutive castings having been magnaglo inspected two successive times without exhibiting a single magnaglo indication which reveals a disqualifying defect.

4.3.3.2.2.1.2 When a defect as defined in 3.5 is found during the second or last magnaglo inspection, the contractor shall be required to: (a) Screen the lot to remove all disqualifying defects therefrom (b) Then the lot shall be reinspected 100 percent to determine that all disqualifying defects have been removed.

4.3.3.2.2.1.3 When 2500 consecutive body castings have been subjected to two 100 percent magnaglo inspections and found free of disqualifying defects as defined in 3.5, the contractor will have qualified to perform the inspection on a sampling basis in accordance

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T06:07Z
Check the source to verify that this is the current version before use.

with the provisions of MIL–STD–105 using an AQL of .015 percent.

4.3.3.2.2.1.4 When performing the magnaglo inspection on the sampling basis and a defect is found, the contractor shall be required to take the action indicated in paragraph 4.3.3.2.2.1.2.

4.3.3.2.2.1.5 If at any time a magnaglo indication is present and the contractor is in doubt as to whether it is a true indication or not, he will be permitted to demagnetize the casting and reinspect it.

4.3.3.2.2.1.6 All body castings containing magnaglo indications shall be rejected and the Government reserves the right to have such castings examined by whatever means necessary to determine compliance or noncompliance with paragraph 3.5.

4.3.3.3 *Strength of brazed joint.* After assembly of the base adapter, but prior to gaging each body assembly, the body of which has passed the ultrasonic and magnetic particle inspections as indicated by the letters "U" and "M" stamped thereon, shall be subjected to an internal hydrostatic pressure to determine compliance with 3.6. Failure of any assembly to comply shall be cause for rejection of the assembly. Body assemblies which comply with 3.6 shall be stamped with the letter "H" as indicated on the assembly drawing.

4.3.3.4 *Air pressure.* Each body assembly that has passed the hydrostatic pressure test, as indicated by the letter "H" stamped on the body, shall after completion of the drying cycle be subjected to a submerged air pressure test. Any body assembly failing to comply with the requirements of 3.6.1 as evidenced by air bubbles, in the vicinity of the brazed joint or rising to the surface of the water shall be rejected. Body assemblies which comply with 3.6.1 shall be stamped with the letter "A" as indicated on the assembly drawing.

4.3.3.5 *Quality of joint.* Two body assemblies from each lot shall be selected and sectionalized to determine compliance with 3.7.1. Failure of any specimen to comply shall be cause for rejection of the lot.

4.3.3.6 *Protective coating.* The sample size and acceptance criteria shall be as specified in the applicable specification. Failure to comply with the requirements shall be cause for taking the corrective action recommended therein.

4.3.4 *Functional.* The following proving ground tests will be performed by the Government.

4.3.4.1 *Initial production sample.* The quantities listed in table I will be ballistically tested in the phase indicated.

TABLE I.

Phase	*Quantity*
Security	25
Velocity and Accuracy	25

4.3.4.2 *Production sample.* The quantities listed in table II will be ballistically tested in the phases indicated.

TABLE II.

Phase	*Quantity*
Security	10 each lot
Velocity and Accuracy	10 each lot

Failure of any round fired for security to comply with 3.9.1 shall be cause for rejection of the lot. Velocity-accuracy will be recorded for informational purposes only (see 6.1).

4.3.5 *Inspection equipment.* The examination and tests shall be made using equipment listed on IEL–D–8596986 except as provided in MIL–I–45208.

4.4 Test methods and procedures.

4.4.1 *Mechanical properties.*

4.4.1.1 *Hardness.* After final heat treatment and before machining, the hardness test shall be performed on the bourrelet of the body casting, using the procedures for this test prescribed by Federal Test Method No. 151.

4.4.1.2 *Yield strength and elongation.* From the bodies selected in accordance with 4.3.3.1.2, two tension test specimens conforming to a standard "R" type specimen as prescribed by Federal Test Method Standard No. 151 shall be taken longitudinally from each side of the body 180 degrees apart. The

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T06:07Z
Check the source to verify that this is the current version before use.

criteria for determining yield strength and elongation shall be as prescribed by Federal Test Method Standard No. 151.

4.4.2 *Metal defects.*

4.4.2.1 *Ultrasonic inspection.* The body castings shall be examined using ultrasonic equipment of the type and model approved by the cognizant technical agency. Procedures for operation of the unit shall be as prescribed by Manual 10519685. Prior to start of production, the contractor shall submit a copy of his proposed procedure for complying with the requirements of the manual to Commanding Officer, Frankford Arsenal, Philadelphia 37, ATTN: SMUFA–6130 for written approval. After approval, no change in procedure shall be made without prior approval of the above organization.

4.4.2.2 *Magnetic particle test procedure.* The procedures for performing this test shall be as specified in MIL–M–11472, for indirect magnetization by either the continuous method or the residual method. The solid content of the suspension shall be maintained at 0.2 to 0.4 milliliters (ml) of solids per 100 ml of suspension when oil is used, or 0.15 to 0.35 ml of solids per 100 ml of suspension when water is used. The suspension shall be checked at the start of each day's production and at intervals of not over 4 hours of continuous operation, utilizing the procedures and equipment prescribed by section 4 of MIL–M–11472. When performing the test for solid content of the suspension, if it is determined that it does not comply, all body castings that have been tested and accepted since the last satisfactory test was performed shall be retested after the suspension has been brought to the proper level. The magnetic particle test shall be performed on equipment that complies with the requirements of PA–PD–792. The operator(s) of the equipment and the inspector(s) making the determinations shall be certified in accordance with MIL–C–7701.

4.4.3 *Strength of brazed point.* The body assembly shall be hydrostatically tested using equipment capable of performing the test accurately and consistently. In performing the test the pressure will be applied gradually until the required minimum pressure is reached, after which the pressure will be held for a minimum of 5 seconds. The equipment shall be calibrated prior to the start of each day's operation and at intervals of not over 2 hours of continuous operation, it shall also be calibrated prior to restarting the operation after lay off of 1 hour or more.

4.4.4 *Air pressure test.* Body assemblies that have passed the hydrostatic test shall be mounted in an approved fixture in such manner that the body assembly will be completely submerged in water, the air pressure shall be applied and held for a minimum of 15 seconds.

4.4.5 *Quality of joint.* The samples selected in accordance with 4.3.3.5 shall be sectionalized as follows: (a) The rear portion of the projectile assembly forward of the base adapter shall be removed in such a manner that no portion of the brazed joint will be damaged; (b) the rear portion of the body containing the base adapter shall then be cut vertically through the center of the base adapter; (c) each portion of the body casting shall be peeled from the base adapter section. After sectioning, the brazed area of both pieces of the base adapter and both pieces of the body casting that have been peeled therefrom, shall be visually examined to determine compliance with 3.7.1.

4.4.6 *Base cover weld or braze.* The test of the base cover weld or braze shall be performed as follows: visually inspect the base shield and select the area that appears to have the weakest weld; insert a 5/8" chisel in this area and apply force by use of a 1 lb. steel hammer and an approximately 1 foot stroke. If the weld breaks loose after 2 strokes, the body assembly will be classed defective. If the weld is found to be secure, the bur made by the chisel may be knocked back into position and accepted.

4.4.7 *Functional.*

4.4.7.1 *Security.* The samples furnished in accordance with 4.3.4.1 or 4.3.4.2, inert loaded to the service weight, will be assem-

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T06:07Z
Check the source to verify that this is the current version before use.

bled into complete rounds and fired in a mortar for which the round is standard. The propellant charge will be adjusted to obtain 112 percent of the maximum rated pressure of the round in a new mortar.

4.4.7.2 *Velocity-accuracy.* The samples furnished in accordance with 4.3.4.1 or 4.3.4.2 inert loaded will be assembled into complete rounds utilizing the service charge and fired in a mortar, for which the round is standard, for comparison with an equal number from a reference lot. The sample round and reference rounds will be fired alternately. Horizontal and vertical distances will be recorded for each round fired for determination of horizontal and vertical probable error (PE) in mils to assess accuracy. Data obtained will be recorded for information only and forwarded to the cognizant technical agency.

5. PREPARATION FOR DELIVERY

5.1 Packing.

5.1.1 *Level A.* Not applicable

5.1.2 *Level B.* Not applicable

5.1.3 *Level C.* Bodies shall be packed in accordance with the requirements of MIL–P–10025.

5.2 Labeling and marking. Labeling and marking for shipment shall be in accordance with MIL–P–10025.

5.3 Data card. Data card information shall be as specified in MIL–A–2550.

6. NOTES

6.1 *Ballistic test.* Rounds fired for velocity-accuracy are not acceptance tests, but the results will be carefully analyzed by the Munitions Command to determine quality of ammunition produced. Evidence of excessive variation in either phase of the proving ground tests will result in immediate investigation by the Munitions Command.

Notice. When Government drawings, specifications or other data are used for any purpose other than in connection with a definitely related Government procurement operation, the United States Government thereby incurs no responsibility nor any obligation whatsoever; and the fact that the Government may have formulated, furnished, or in any way supplied the said drawings, specifications, or other data is not to be regarded by implication or otherwise as in any manner licensing the holder or any other person or corporation, or conveying any rights or permission to manufacture, use or sell any patented invention that may in any way be related thereto.

Custodian:
Army—MU

Preparing activity:
Army—MU
Project No. 1315–A275

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T06:07Z
Check the source to verify that this is the current version before use.