MILITARY SPECIFICATION SHEET

SHEET, PRINTED WIRING BOARD, LAMINATED, BASE MATERIAL GF
(WOVEN E-GLASS REINFORCEMENT, MAJORITY DIFUNCTIONAL EPOXY RESIN,
FLAME RESISTANT, METAL CLAD OR UNCLAD)

This amendment forms a part of MIL-S-13949/4D, dated 16 August 1993, and is approved for use by all Departments and Agencies of the Department of Defense.

PAGE 2

After "Peel strength values for copper foil: See table I", add "or II, as applicable".

TABLE I, delete title in its entirety and substitute the following:

"TABLE I. Standard profile foil peel strength values, minimum pounds per inch of width 1/"

Table I, add new footnote as follows:

"1/ Standard foil profile is described by IPC-MF-150 "

Add new TABLE II as follows:

"TABLE II. Low and very low profile foil peel strength values, minimum pounds per inch of width 1/

Test/copper foil weight	Base material thickness	
	Less than .020 inch	.020 inch and over
After thermal stress All copper foil weights	4.0	4.0
At elevated temperature of 125°C: All copper foil weights	4.0	4.0
After exposure to processing solutions: All copper foil weights	4.0	4.0

1/ Low and very low foil profile are described by IPC-MF-150 "

CONCLUDING MATERIAL

Custodians.
Army - ER
Navy - EC
Air Force - 85

Review activities:
Army - AR, AT, ME, MI
Navy - AS, MC, OS, SH
Air Force - 11, 19, 99
NSA - NS

Preparing activity:
DLA - ES

(Project 5998-0071)

DISTRIBUTION STATEMENT A Approved for public release; distribution is unlimited

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T02:38Z
Check the source to verify that this is the current version before use.