GGG–I–671a
21 APRIL 1953
SUPERSEDING
Fed. Spec. GGG–I–671
October 14, 1942

FEDERAL SPECIFICATION

IRONS: CALKING, WOOD

This specification was approved by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal Agencies.

1. SCOPE AND CLASSIFICATION

1.1 Scope.—This specification covers forged hardened steel calking irons designed for ship calking and making purposes.

1.1.1. *Federal specification coverage.*—This specification does not include all types, classes, grades, sizes, etc., of the commodities indicated by the title of the specification or which are commercially available, but is intended to cover the types, etc., which are generally used by the Federal Government.

1.2 Classification.—The calking irons covered by this specification shall be of the following types and classes, as specified (see 6.1):

Type I.—Calking iron, single crook.
  Class A.—Sharp.
  Class B.—Without crease.
Type II.—Calking iron, straight, without crease.
  Class A.—Narrow.
  Class B.—Wide.
Type III.—Deck and dumb iron, without crease.
Type IV.—Dumb iron, crooked, without crease.
Type V.—Making iron, straight, with one crease.
  Class A.—Light.
  Class B.—Heavy.
Type VI.—Making iron, straight, with two creases.
Type VII.—Making iron, single crook.
  Class A.—Without crease.
  Class B.—With double crease.
Type VIII.—Reefing hook, without crease.
Type IX.—Reefing iron, without crease.
  Class A.—Short.
  Class B.—Long.
Type X.—Spike iron, bent, without crease.
Type XI.—Spike iron, straight, without crease.
Type XII.—Boot iron, without crease.
  Class A.—Stub nose.
  Class B.—Sharp nose.

2. APPLICABLE SPECIFICATIONS AND STANDARD

2.1 Specifications.—There are no other specifications applicable to this specification except those referenced in section 7 by individual departments.

(Copies of Federal specifications and the Federal Specification Index may be obtained upon application, accompanied by check, money order, cash, or Government Printing Office coupons, to the General Services Administration, Business Service Center, Region 3, Seventh and D Streets, S. W., Washington 25, D. C. This office will also honor deposit numbers issued by the Government Printing Office. Single copies of product specifications required for bidding purposes are available without charge at the GSA Regional Offices in Boston, New York, Atlanta, Chicago, Kansas City, Mo., Dallas, Denver, San Francisco, Los Angeles, Seattle, and Washington 25, D. C. Prices of additional copies may be obtained from the GSA Regional Offices.)

2.2 Standards.—The following Military Standard, of the issue in effect on date of invitation for bids, forms a part of this specification:

MIL–STD–105—Sampling Procedures and Tables for Inspection by Attributes.

(Copies of Military Standard referenced above, required by contractors in connection with specific procurement functions should be obtained from the procuring agency or as directed by the contracting officer.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:41Z
Check the source to verify that this is the current version before use.

3. REQUIREMENTS

3.1 Material.—The material used in the manufacture of calking irons shall be a good grade of carbon tool steel possessing qualities which will assure tough and high performance tools.

3.2 Hardness.—The hardness of the working edge and for a distance of not less than one-quarter inch therefrom shall be Rockwell C 30–48.

3.3 Marking.—Each iron shall be stamped or otherwise permanently marked in a plain and legible manner with the manufacturer's name or trade-mark of such known character that the source of manufacture may be readily determined.

3.4 Finish.—Each iron shall be coated with black enamel over a smooth finish, except the blade and its edge which shall be ground.

3.5 Creases. — Creases, where specified herein, shall consist of approximately semicircular grooves in the end of the tool centrally located between the faces or sides and extending the full width of the tool.

3.6 Shanks.—Shanks shall be not less than $^{15}/_{32}$ and not more than $^{9}/_{16}$ inch in diameter. The head of the shank shall be slightly convex and not less than $^{7}/_{8}$ nor more than 1 inch in diameter.

3.7 Shape and dimensions. — Each iron shall comply with the requirements of table I for type and class and also shall be in substantial agreement with the figure for that type and class as shown in figures 1 to 13 inclusive.

TABLE I.

Type	Class	Width of blade			Thickness end of blade			Length overall		
		Nominal	Minimum	Maximum	Nominal	Minimum	Maximum	Nominal	Minimum	Maximum
		Inches	*Inches*	*Inches*	*Inches*	*Inches*	*Inches*	*Inches*	*Inches*	*Inches*
I	*A	2-7/16	2-5/16	2-9/16	*1/8	7/64	9/64	8-1/4	8	8-1/2
	B	2-7/16	2-5/16	2-9/16	1/16	3/64	5/64	8	7-3/4	8-1/4
II	A	2	1-7/8	2-1/8	1/16	3/64	5/64	5-1/8	4-7/8	5-3/8
	B	2-1/2	2-3/8	2-5/8	1/16	3/64	5/64	5-3/4	5-1/2	5-7/8
III		2	1-7/8	2-1/8				6-1/2	6-1/4	6-3/4
IV		2	1-7/8	2-1/8				7-1/2	7	8-1/2
V	A	2-1/2	2-3/8	2-5/8	1/8	7/64	9/64	5-1/2	5-1/4	5-3/64
	B	2-3/8	2-1/4	2-1/2	3/16	11/64	13/64	6	5-3/4	6-1/4
VI		2-1/2	2-3/8	2-5/8	3/16	11/16	13/16	5-1/2	5-1/4	5-3/4
VII	A	2-1/2	2-3/8	2-5/8	1/16	3/64	5/64	7	6-3/4	7-1/4
	B	2-3/16	2-1/16	2-5/16	3/16	11/64	13/64	7-1/4	7	7-1/2
VIII		4	3-7/8	4-1/8	3/16	11/64	13/64	14	13-3/4	14-1/4
IX	A	1-1/16	1	1-1/8	7/32	13/64	15/64	11	10-3/4	11-1/4
	B	1-1/4	1-3/16	1-5/16	3/16	11/64	13/64	14-1/2	14-1/4	14-3/4
X		9/16	1/2	5/8	1/8	7/64	9/64	8-1/2	8-1/4	8-3/4
XI		9/16	1/2	5/8	3/32	5/64	7/64	8-3/4	8-1/2	9
XII	A	5	4-7/8	5-1/8	3/32	5/64	7/64	12-1/4	12	12-1/2
	*B	4-7/8	4-3/4	5	3/32	5/64	7/64	12-1/4	12	12-1/2

* Thickness of sharp-nose irons shall be taken just above the point.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:41Z
Check the source to verify that this is the current version before use.

3.8 Illustrations.—The illustrations are included for the convenience of those interested, and are not intended to preclude the purchase of calking irons which are otherwise in accordance with the requirements of this specification.




FIGURE 1.—Type I, calking iron, single crook.
Class A.—Sharp nose.
Class B.—Without crease.




FIGURE 2.—Type II, calking iron, straight, without crease.
Class A.—Narrow.
Class B.—Wide.




FIGURE 3.—Type III, deck and dumb iron, without crease.




FIGURE 4.—Type IV, dumb iron, crooked, without crease.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:41Z
Check the source to verify that this is the current version before use.




FIGURE 5.—Type V, making iron, straight with one crease.
Class A.—Light.
Class B.—Heavy.




FIGURE 6.—Type VI, making iron, straight, with two creases.




FIGURE 7.—Type VII, class A, making iron, single crook, without crease.

Source: https://assist.dla.mil -- Downloaded: 202640-26T12:41Z
Check the source to verify that this is the current version before use.




FIGURE 8.—Type VII, class B, making iron, single crook, with double crease.





FIGURE 9.—Type VIII, reefing hook, without crease.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:41Z
Check the source to verify that this is the current version before use.



CLASS	DIM. "A"
A	11"
B	14 1/2"

FIGURE 10.—Type IX, reefing iron, without crease.
Class A.—Short.
Class B.—Long.




FIGURE 11.—Type X, spike iron, bent, without crease.




FIGURE 12.—Type XI, spike iron, straight, without crease.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:41Z
Check the source to verify that this is the current version before use.




FIGURE 13.—Type XII, boot iron, without crease.
Class A.—Stub nose.
Class B.—Sharp nose.

4. SAMPLING, INSPECTION, AND TEST PROCEDURES

4.1 Inspection lot.—All tools of the same type, class, and size presented at one time shall be considered a lot for purposes of acceptance, inspection and tests.

4.2 Sampling for lot acceptance. — Sampling requirements shall be in accordance with Military Standard MIL–STD–105, (for Navy, Bureau of Ships, see 7.2.5).

4.2.1 *Visual and dimensional inspection.*— Each of the sample irons selected shall be visually and dimensionally inspected by the Government inspector to verify compliance with the requirements of this specification. Any iron in the sample containing one or more visual or dimensional defects shall be rejected, and if the number of defective irons in any sample exceeds the acceptance number for that sample, the lot represented by the sample shall be rejected.

4.3 Sampling for tests. — From each lot which has passed the inspection of 4.2, the Government inspector shall select the number of samples in accordance with Military Standard MIL–STD–105.

4.4 Test procedures. — Each sample selected in accordance with 4.3 shall be subjected to the hardness test. The hardness shall be measured to determine compliance with the requirements of 3.2. All values shall be within the limits specified in 3.2.

4.5 Rejected lots.—Rejected lots may be offered again for Government inspection provided the contractor has repaired or removed all nonconforming irons. The Government inspector shall again select and examine samples from such resubmitted lots to verify

Source: https://assist.dla.mil -- Downloaded: 202610-26T12:41Z
Check the source to verify that this is the current version before use.

compliance with the specification requirements.

5. PREPARATION FOR DELIVERY

5.1 Packaging. — Unless otherwise specified in the invitation for bids, commercial packaging is acceptable under this specification for irons, calking. Packages shall contain irons of the same type and class.

5.2 Unless otherwise specified, irons, calking, shall be packed in substantial containers of the type, size and kind commonly used for the purpose, so constructed as to insure acceptance and safe delivery by common or other carriers, at the lowest rate, to point of delivery called for in the contract or purchase order.

5.3 Marking.

5.3.1 *Boxes and packages.*—Each box or package shall be plainly marked with the name of the article, the type, quantity contained therein and the name of the manufacturer.

5.3.2 *Shipping containers.*—Unless otherwise specified, shipping containers shall be marked with the name of the article, the type as defined in the contract or order under which shipment is made, the quantity contained therein, the name of the contractor and the number of the contract or order.

6. NOTES

6.1 Purchasers should specify the type, class and size of each iron and exercise any desired options offered herein. (See 1.2, 5.1, 5.2, 7.)

6.2 The illustrations are included for the convenience of those interested, and are not intended to preclude the purchase of calking irons which are otherwise in accordance with this specification.

6.3 Transportation description. — Transportation description applicable to these items is:

Tools, not otherwise indexed by name.
Carload weight 30,000 pounds.
Truckload weight 30,000 pounds.

Patent notice.—When Government drawings, specifications, or other data are used for any purpose other than in connection with a definitely related Government procurement operation, the United States Government thereby incurs no responsibility nor any obligation whatsoever; and the fact that the Government may have formulated, furnished, or in any way supplied the said drawings, specifications, or other data, is not to be regarded, by implication or otherwise, as in any manner licensing the holder or any other person or corporation, or conveying any rights or permission to manufacture, use, or sell any patented invention that may in any way be related thereto.

7. DEPARTMENTAL REQUIREMENTS

7.1 The following specifications and standards of the issues in effect on date of invitation for bids, form a part of this specification for purchases made under this specification by the respective departments:

7.2 Army, Navy, and Air Force.

7.2.1 *Applicable specifications and standard:*

Military Specification:
MIL–P–15424—Packaging of Hand Tools; General Specification for Domestic and Overseas Preservation.

Navy Department Specification:
General Specifications for Inspection of Material[1].

Military Standard:
MIL–STD–105 — Sampling Procedures and Tables for Inspection by Attributes.

(Copies of specifications and standards required by contractors in connection with specific procurement functions should be obtained from the procuring agency or as directed by the contracting officer.)

[1] Applicable to Navy purchases only.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:41Z
Check the source to verify that this is the current version before use.

7.2.2 *Preparation for delivery.* — Irons shall be cleaned, preserved, packaged, packed, and marked in accordance with Military Specification MIL-P-15424.

7.2.3 *Inspection procedures.* — For Naval purchases, the general inspection procedures shall be in accordance with General Specification for Inspection of Material.

7.2.4 *Sampling procedures.*—For Military purchases, the sampling procedures will be in accordance with Military Standard MIL-STD-105 (see 4.2 and 4.3).

7.2.5 *Sampling for Navy, Bureau of Ships.*

7.2.5.1. *Sampling for visual and dimensional inspection.*—A random sample of irons as specified in table II shall be taken from each inspection lot of material offered for Government inspection of visual and dimensional characteristics with lot acceptance based on the sampling inspection requirements in accordance with Military Standard MIL-STD-105.

TABLE II.—*Sampling for visual and dimensional inspection A.Q.L. (approx.) = 2.5 percent defective*

Number of irons in inspection lot	Number of irons in sample	Acceptance number (defectives)	Rejection number (defectives)
40 or under	10	0	1
41 to 110	15	1	2
111 to 300	25	1	2
301 to 500	35	2	3
501 to 800	50	3	4
801 to 1300	75	4	5
1301 and over	110	6	7

7.2.5.2. *Sampling for tests.* — A random sample of irons shall be taken from each inspection lot in accordance with table III and shall be subjected to the tests of 4.4.

TABLE III.

Lot size	Sample size
Under 200	3
201 - 500	5
Over 500	10

NAVY INTEREST: *MC* Sh S

This specification is a part of Section IV, Part 5, of the Federal Standard Stock Catalog.

Copies of this specification can be purchased for 10 cents each from the General Services Administration, Business Service Center, Region 3, Seventh and D Streets, S. W., Washington 25, D. C. Single copies required for bidding purposes are available without charge at the nearest GSA Regional Office.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:41Z
Check the source to verify that this is the current version before use.