UU-B-00344(GSA-FSS)
AMENDMENT-2
October 15, 1972
SUPERSEDING
Amendment-1
December 10, 1971

AMENDMENT

TO

INTERIM FEDERAL SPECIFICATION

BINDER, LOOSE-LEAF: MULTIPLE RING TYPE

This amendment was developed by Standardization Division, Federal Supply Service, General Services Administration, Washington, DC 20406, based upon currently available technical information. The General Services Administration has authorized this amendment as a part of Interim Federal Specification UU-B-00344(GSA-FSS) dated June 22, 1970.

PAGE 1

Paragraph 2.1, under "Federal Specifications", delete: "UU-B-623 - Book Cover Board".

PAGE 2

Paragraph 2.2, under Technical Association of the Pulp and Paper Industry (TAPPI) Publications, add: "T807 - Bursting Strength of Paperboard and Linerboard."

PAGE 3

Table II, delete and substitute the following:

TABLE II. Rubber bonded cellulose fiber requirements

Requirement	Thickness	
	0.025-inch	0.030-inch
BASIS WEIGHT (24 inch, by 36 inch, 500 sheets), MINIMUM	315 lbs.	350 lbs.
TENSILE BREAKING STRENGTH, MINIMUM		
Machine direction	160 lbs./in. of width	180 lbs./in. of width
Cross direction	50 lbs./in. of width	60 lbs./in. of width

PAGE 4

Delete paragraph 3.1.3 and substitute:

"3.1.3 Paperboard. Paperboard used to fabricate the covers of the class 2 binders with a capacity over 1-5/8 inch shall be not less than 0.117 inch thick with a bursting strength of not less than 435 points, and for binders up to and including 1-5/8 inch capacity the paperboard shall be not less than 0.095 inch thick with a bursting strength of not less than 375 points."

PAGE 5

Delete paragraph 3.3.2.2 and substitute:

"3.3.2.2 Class 2 binders. Cover material for class 2 binders shall be vinyl specified in 3.1.2.1 over both sides of paperboard specified in 3.1.3. The vinyl shall be 0.014 ± 0.001-inch, or 0.016 ± 0.001-inch in thickness, as specified (see 6.2). The vinyl shall overlap the paperboard to permit sealing, and shall encompass the backbone area to provide housing for the backbone support and backplate (when applicable), and to provide front and back cover hinges. The overlapped edges and area established for hinges shall be welded or sealed by the high frequency electronic method. The vinyl covering shall be fitted to the paperboard in such a manner that no wrinkling or loosening is evident when the binder is in the opened or closed position. Binder covers shall be sufficiently larger than the sheet size as specified in 3.3.2.1 and outside corners shall be rounded. When specified (see 6.2), the entire inner area of the hinges for the front and back cover shall be reinforced with vinyl-impregnated nylon cloth."

FSC 7510

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:20Z
Check the source to verify that this is the current version before use.

PAGE 7

At the end of paragraph 4.1.1, add new test paragraph as follows:

Paperboard. The thickness and bursting strength of paperboard shall be determined as described in TAPPI Test Method T411, and T807, respectively (see 3.1.3).

PAGE 9

Paragraph 5.3, delete in its entirety and substitute:

"5.3 Marking.

5.3.1 Civil agencies. In addition to any special marking required by the contract or order (see 6.2), all interior packages and shipping containers shall be marked in accordance with Fed. Std. No. 123.

5.3.2 Military agencies. In addition to any special marking required by the contract or order (see 6.2), all interior packages and shipping containers shall be marked in accordance with MIL-STD-129."

GSA GC 78-5703

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:20Z
Check the source to verify that this is the current version before use.