UU-B-00366B(GSA-FSS)
AMENDMENT-2
October 15, 1972
SUPERSEDING
Amendment-1
December 10, 1971

AMENDMENT

TO

INTERIM FEDERAL SPECIFICATION

BINDER, LOOSE-LEAF, SECTIONAL-POST-TYPE

This amendment was developed by Standardization Division, Federal Supply Service, General Services Administration, Washington, DC 20406, based upon currently, available technical information. The General Services Administration has authorized this amendment as a part of Interim Federal Specification UU-B-00366B(GSA-FSS) dated August 30, 1966.

PAGE 2

Paragraph 2.1, under "Federal Specifications", delete: "UU-B-623 - Book Cover Board", and "CCC-T-191 - Textile Test Methods".

Paragraph 2.1, under "Federal Standards", delete "Federal Test Methods Std. No. 151 - Metals; Test Methods".

Paragraph 2.1, under "Federal Standards", add:

"Fed. Test Method Std. No. 191/GEN (General Provisions) - Textile Test Methods.
Fed. Test Method 191/5041 - Determination of Weight of Textile Materials: Small Specimen Method.
Fed. Test Method 191/5100 - Breaking Strength and Elongation, of Woven Cloth; Grab Method.
Fed. Test Method 191/5651 - Crocking of Woven and Knitted Cloth; Standard Sample Munsell Scale Method."

Add new paragraph 2.2, as follows:

"2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless a specific issue is identified, the issue in effect on date of invitation for bids or request for proposal shall apply.

American Society for Test and Materials (ASTM) Publications:

ASTM E 18 - Rockwell Hardness and Rockwell Superficial Hardness of Metallic Materials.

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.)

Technical Association of the Pulp and Paper Industry (TAPPI) Publications:

T410 - Weight Per Unit Area (Basis Weight or Substance) of Paper and Paperboard.
T411 - Thickness (Caliper) of Paper and Paperboard.
T807 - Bursting Strength of Paperboard and Linerboard.

(Application for copies should be addressed to the Technical Association of the Pulp and Paper Industry, 360 Lexington Avenue, New York, NY 10017.)"

PAGE 3

Delete paragraph 3.3 and substitute:

"3.3 Covers. Covers of binders shall be made from paperboard with a thickness of 0.220 inch plus or minus 5 percent, and a bursting strength of not less than 750 points. Covers shall be bound as specified in 3.4 and these, together with post assemblies, shall align evenly when locked. Corners of covers at the index edge shall be rounded."

FSC 7510

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:20Z
Check the source to verify that this is the current version before use.

PAGE 3 (con.)

Delete paragraph 3.4 and substitute:

"3.4 Binding. Covers and post housing shall be bound with a continuous piece of duck. The binding material shall be carried over the post housing and over the inside face of covers at least 5/8 inch beyond the edges. The binding material shall be securely glued in place. (See 3.6.1 and 3.7.)"

Delete paragraphs 3.4.1, 3.4.1.1 and 3.4.1.2 and substitute:

"3.4.1 Duck. The duck cloth shall be not less than 7.0 ounces per square yard. The duck shall have a colorfastness to crocking rating of at least "good", and the breaking strength shall be not less than 95 pounds in the warp direction and 57 pounds in the filling direction (see 4.3.1.1)."

Delete paragraph 3.4.2 and 3.4.2.1 through 3.4.2.5.

PAGE 4

Paragraph 3.7.1, 5th sentence, line 6, change "0.120-inch thick book cover board" to "0.117-inch thick paperboard".

PAGE 5

Paragraph 4.2.1, delete last sentence and substitute:

"Tests on duck shall be conducted in accordance with the test methods of Fed. Test Method Std. No. 191 specified in 4.3.1.1, test on paperboard and paper lining in accordance with TAPPI test methods specified in 4.3.1.2 and 4.3.1.3, and Rockwell hardness of steel posts in accordance with ASTM test method specified in 4.3.1.4."

PAGE 6

Table II, under defects of covers and binding, 2nd line, delete "or latex fiber".

PAGE 7

Table III (cont'd), under "examine" heading, delete "This operation shall be repeated a consecutive time" and substitute "This operation shall be repeated 10 consecutive times".

PAGE 8

Delete paragraphs 4.3.1.1 through 4.3.1.4.2 and substitute:

"4.3.1.1 Duck. Duck shall be tested in accordance with the following test methods of Fed. Test Method Std. No. 191 (see 3.4.1).

Weight	- method 5041
Colorfastness to crocking	- method 5651
Breaking strength	- method 5100

4.3.1.2 Paperboard. The thickness and bursting strength of paperboard shall be determined as described in TAPPI Test Method T411, and T807, respectively (see 3.3).

4.3.1.3 Paperlining. The basis weight of paper lining shall be determined in accordance with TAPPI Test Method T401 (see 3.5).

4.3.1.4 Rockwell hardness. Rockwell hardness of steel sectional posts shall be determined in accordance with ASTM E 18 (see 3.7.2)".

PAGE 9

Paragraphs 5.1.1, and 5.1.2, at the end of the paragraphs, add "The box shall be closed in accordance with the appendix to the box specification".

Paragraph 5.3.1, line 3, after "size", delete "etc)" and substitute "color.)".

GSA DC 73-5784

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:20Z
Check the source to verify that this is the current version before use.