UU-P-272C
December 22, 1972
SUPERSEDING
Int. Fed. Spec. UU-P-00272B(GSA-FSS)
April 16, 1971

FEDERAL SPECIFICATION

PAPER, WRAPPING, FREEZER (POLYETHYLENE COATED)

This specification was approved by the Commissioner, Federal Supply Service, General Services Administration for the use of all Federal agencies.

1. SCOPE AND CLASSIFICATION

1.1 Scope. This specification covers polyethylene coated wrapping paper for wrapping food.

1.2 Classification.

1.2.1 Types. Polyethylene coated wrapping paper covered by this specification shall be of one type only (see 6.3).

2. APPLICABLE DOCUMENTS

2.1 Specifications and standards. The specifications and standards of the issues in effect on date of invitation for bid or request for proposal shall apply.

Federal Specifications:

UU-P-268 - Paper, Kraft, Untreated, Wrapping.
MMM-A-260 - Adhesive, Water-Resistant (For Sealing Waterproofed Paper)
PPP-B-636 - Boxes, Shipping, Fiberboard.
PPP-B-640 - Boxes, Fiberboard, Corrugated, Triple Wall.
PPP-B-1055- Barrier Material, Waterproofed Flexible.

Federal Standards:

Fed. Std. No. 123 - Marking for Domestic Shipment (Civil Agencies).

(Activities outside the Federal Government may obtain copies of Federal Specifications, Standards, and Handbooks as outlined under General Information in the Index of Federal Specifications and Standards and at the prices indicated in the Index. The Index, which includes cumulative monthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, U.S. Government Printing Office, Washington, DC 20402.

(Single copies of this specification and other Federal Specifications required by activities outside the Federal Government for bidding purposes are available without charge from Business Service Centers at the General Services Administration Regional Office in Boston, New York, Washington, DC, Atlanta, Chicago, Kansas City, MO, Fort Worth, Denver, San Francisco, Los Angeles, and Seattle, WA.

(Federal Government activities may obtain copies of Federal Specifications, Standards, and Handbooks and the Index of Federal Specifications and Standards from established distribution point in their agencies.)

Military Standards:

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes.
MIL-STD-129 - Marking for Shipment and Storage.

(Copies of Military Specifications and Standards required by contractors in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:20Z
Check the source to verify that this is the current version before use.

Laws and Regulations:

U.S. Department of Health, Education and Welfare, 21 CFR 121 Federal Food, Drug and Cosmetic Act and Regulations Promulgated Thereunder. (The code of Federal Regulations (CFR) and the Federal Register are for sale on a subscription basis by the Superintendent of Documents, U.S. Government Printing Office, Washington, DC 20402. When indicated, reprints of certain regulations may be obtained from the Federal agency responsible for issurance thereof.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on the date of invitation for bids or request for proposal shall apply.

Technical Association of the Pulp and Paper Industry Standards (TAPPI):

T401 - Fiber Analysis of Paper and Paperboard.
T403 - Bursting Strength of Paper.
T404 - Tensile Breaking Strength of Paper and Paperboard.
T410 - Weight per unit area (Basis Weight or Substance) of Paper and Paperboard.
T414 - Internal Tearing Resistance of Paper.

(Application for copies should be addressed to the Technical Association of the Pulp and Paper Industry, One Dunwoody Park, Atlanta, GA 30341.)

National Motor Freight Traffic Association, Incorporated, Agent:

National Motor Freight Classification.

(Application for copies should be addressed to the American Trucking Association, Inc., Tariff Order Section, 1616 P Street N.W., Washington, DC 20036.)

Uniform Classification Committee Agent:

Uniform Freight Classification.

(Application for copies should be addressed to the Uniform Classification Committee, Room 1106, 222 South Riverside Plaza, Chicago, IL 60606.)

3. REQUIREMENTS

3.1 Materials. The materials used to manufacture this polyethylene coated paper shall conform to the requirements of Federal Food and Cosmetic Act and the regulations promulgated thereunder.

3.1.1 Paper. The paper shall consist of bleached chemical wood fiber and a minimum of 20 percent reclaimed fibers. Reclaimed fibers are those reclaimed from solid waste or waste collected as a result of a manufacturing process but shall not include those materials generated from that reused within a plant as part of its own paper making process. The paper shall comply with the basis weight, bursting strength tearing resistance and tensile strength requirements of table I.

3.1.2 Polyethylene. The polyethylene coating shall be that normally used for the product which is augmented with high density resins.

TABLE I. Physical requirements

Characteristic	Requirement
Basic paper	
Basis weight (24 by 36-500)	39.0 pounds ± 5%
Bursting strength	24.8 points, average minimum
Tearing resistance	
machine direction	48.0 grams, average minimum
Tensile strength (pounds per inch width)	
machine direction	20.4 average minimum
cross direction	12.2 average minimum
Polyethylene coating (24 by 36-500)	4.0 minimum pounds

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:20Z
Check the source to verify that this is the current version before use.

3.1.3 Roll plugs. The finished roll shall be fitted with wooden, metal or plastic plugs at each end and shall be of sufficient rigidity to prevent distortion of the roll under normal conditions of transportation and use.

3.2 End Item. The basic paper shall be uniformly coated on one side with polyethylene. The color of the coated paper shall be white. The coated paper shall be furnished in the width and length specified (see 6.2). The acceptable tolerance is ± 1/16 for the width and ± 1 percent for the length. The polyethylene coated wrapping paper shall be uniformly and smoothly wound on a 3 ± 1/16 inch paper core. There shall not be more than one splice per 1000 feet of coated paper. When a splice occurs, it shall be even and flagged at each end with colored markers. Each roll shall be restrained from unwinding. The finished roll shall be fitted with roll plugs (see 3.1.3)

3.3 Workmanship. The polyethylene coated wrapping paper shall be clean, free from objectionable odor and all imperfections which may impair its serviceability.

3.4 Certification.

3.4.1 The contractor shall certify in writing to the contracting officer or his representative that the material offered to the government contains the minimum percentage of reclaimed paper required by 3.1.1, in addition to certifying that the materials used comply with the requirements of 3.1.

3.4.2 When specified in the contract or purchase order (see 6.2), the contractor shall forward to the procuring agency for each order of freezer paper a statement with test data certifying that the material submitted conforms to the requirements of paragraph 3.1 and 3.3.

4. QUALITY ASSURANCE PROVISIONS

4.1 Inspection responsibility. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified, the supplier may utilize his own facilities or any commerical laboratory acceptable to the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure that supplies and services conform to prescribed requirements.

4.1.1 Sampling for inspection. Sampling for inspection and acceptance shall be performed in accordance with the provisions set forth in MIL-STD-105, except where otherwise indicated. For purposes of sampling, a lot shall consist of all material of the same type, form and weight submitted for inspection at one time.

4.2 Inspection of materials and components. The supplier is responsible for insuring that materials and components used were manufactured, tested and inspected in accordance with the requirements of referenced subsidiary specifications and standards to the extent specified, or, if none, in accordance with this specification.

4.2.1 Inspection records. Inspection records of the examination and tests for the certification as specified in the contract or order shall be complete and made available to the government.

4.3 Inspection of the end item.

4.3.1 Examination of the end item. The end item shall be examined in accordance with the classification of defects and acceptable quality levels (AQL's), set forth below. The lot size, for purpose of determining sample size in accordance with MIL-STD-105, shall be expressed in units of rolls.

4.3.1.1 Examination of the end item for defects. The sample unit for this examination shall be one roll. The inspection level shall be S-2 with an AQL of 4.0 expressed in terms of defects per hundred units.

Source: https://assist.dla.mil -- Downloaded: 202610-26T12:20Z
Check the source to verify that this is the current version before use.

TABLE II. Examination of end item

Examination	Defects
Coating	Not uniformly coated
Width	More or less than 1/16 inch of width specified.
Splice	More than 1 splice per 1000 feet. Separates while unwinding. Not neat. Not flagged at each end with colored markers.
Roll plugs	One or both plugs missing. Plugs not made of wood, plastic, or metal.
Roll-wind	Not uniformly and smoothly wound.
Length per roll	More or less than 1 percent of length specified.

4.3.1.2 Examination of preparation for delivery. An examination shall be made to determine whether the packaging, packing and marking comply with the requirements to section 5. Defects shall be scored as specified in table III. Sampling shall be in accordance with MIL-STD-105. The sample unit shall be one container fully prepared for delivery. The lot shall be the number of containers offered for inspection at one time. The inspection level shall be S-2 with an AQL of 4.0 expressed in terms of defects per hundred units.

Container	Not as specified.
Contents	Not as specified.
Markings	Omitted; incorrect; illegible; improper size, location, sequence, or method of application.
Materials	Component missing or damaged.
Workmanship	Bulging or distortion of containers. Cushioning inadequate, improper of missing.

4.3.1.2.1 Examination of closure and reinforcement of containers. When shipping containers are required to comply with PPP-B-636, examination to defects in closure and reinforcement shall be in accordance with the appendix of that specification.

4.4 Tests. Test procedures and controls which differ from those specified herein, may be used by the supplier if they provide a quality assurance equivalent to that specified. If the Government inspection activities determines that such procedure and controls do not provide as a minimum, such quality assurance the supplier will use the test procedures set forth herein. In case of dispute as to test results, the test methods specified herein will govern. Unless otherwise indicated, the tests shall be performed at and the samples conditioned to standard conditions of 73 + 3.5°F. and 50 + 2% relative humidity. The results of the tests shall be reported as indicated in table IV.

4.4.1 Tests. The following tests shall be determined in accordance with the indicated TAPPI Methods.

Test	TAPPI Method
Fiber Analysis of Paper and Paperboard	T 401
Basis Weight of Paper and Paperboard	T 410
Bursting Strength of Paper	T 403
Internal Tearing Resistance of Paper	T 414
Tensile Strength	T 404

4.4.2 Polyethylene coating. The polyethylene coating shall be determined using the following apparatus and procedures.

4.4.2.1 Apparatus. The apparatus shall consist of a Thwing-Albert Basis weight scale or equal, Type 63-20, steel template (1 square foot area) and a knife.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:20Z
Check the source to verify that this is the current version before use.

4.4.2.2 Procedure. Using the 1 square foot template, cut out both a coated and uncoated speciman of the paper. Using the Thwing-Albert Scale, note the weight of both specimens. NOTE: The Thwing-Albert scale expresses the weight of 1 square foot specimens directly in pounds per ream.) Substract the weight of the uncoated paper from that of the coated paper. The weight difference expresses the basis weight of the coating in pounds per ream.

TABLE IV. Instructions for testing

Characteristics	Basic requirement		Requirement [1] applicable to: Individual unit	Requirement [1] applicable to: Lot average[2]	Number determinations per unit [3]	Result reported to nearest	Inspection level
Stock	3.1	T 401	X		2 (composite)	Pass or fail	S-1
Basic weight	Table 1	T 410		X	1 (composite)	0.1 pound	S-1
Bursting strength	Table 1	T 403		X	5	Point	S-1
Tearing resistance	Table 1	T 414		X	5	Gram	S-1
Tensile strength	Table 1	T 404		X	10	0.1 lb/ inch width	S-1

[1]The composite when applicable shall consist of small pieces taken from each of the sample units. When more than one numerical result determination is required on the composite sample, the numerical observations shall be averaged to obtain the test results for the composite sample; when more than one pass or fail observation is made, all the observations shall meet the applicable requirements for the composite sample to be considered satisfactory for the characteristic being tested.

[2]Test reports shall include all values on which average results are based.

[3]For the characteristics on which multiple determinations are specified per unit, the determinations shall be randomly distributed to the extent possible among all the sheets comprising the sample unit. For each characteristic the results of determination on each sample unit shall be averaged to obtain the test result for that for that sample unit.

5. PREPARATION FOR DELIVERY

5.1 Packaging. Packaging shall be level A, B or C, as specified (see 6.2).

5.1.1 Level A. Each roll of wrapping paper shall be completely and compactly wrapped in material conforming to PPP-B-1055. The wrap shall be sealed with a header on the inside and outside of each end. The headers and the seams of the wrap shall be sealed with an adhesive conforming to MMM-A-260.

5.1.2 Level B. Each roll of wrapping paper shall be completely and compactly wrapped in material conforming to UU-P-268. The wrap shall be closed with a header on the inside and outside of each end. The headers and the seams of the wrap shall be sealed in a manner normally used by industry.

5.1.3 Level C. Each roll of wrapping paper shall be packaged to afford adequate protection against damage during shipment from the supply source to the first receiving activity.

5.2 Packing. Packing shall be level A, B or C, as specified (see 6.2).

5.2.1 Level A. Each roll of wrapping paper, packaged as specified in 5.1, shall be packed in one of the following containers at the option of the contractor.

Specifications	Type and Class
PPP-B-636	Class weather-resistant, V2s
PPP-B-640	Class weather-resistant, Grade A.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:20Z
Check the source to verify that this is the current version before use.

The box shall be closed and reinforced in accordance with the appendix of the box specification.

5.2.2 Level B. Each roll of wrapping paper, packaged as specified in 5.1, shall be packed in a box conforming to PPP-B-636, class domestic. The box shall be closed in accordance with the appendix to the box specification.

5.2.3 Level C. Rolls packaged as specified in 5.1, in quantities as specified (see 6.2) shall be packed in containers to assure carrier acceptance and safe arrival at destination. Containers shall be in compliance with Uniform Freight Classification Rules or National Motor Freight Classification Rules, as applicable.

5.3 Marking. In addition to any special markings required in the procurement document, marking of the interior packages and exterior shipping container shall be in accordance with Fed. Std. No. 123 for civil agencies or MIL-STD-129 for military agencies, as applicable (see 6.2).

6. NOTES

6.1 Intended use. The polyethylene coated wrapping paper is intended as an initial wrap for meat, fish, poultry and other similar items to be frozen and stored in a freezer.

6.2 Ordering data. Purchasers should select the preferred options permitted herein and include the following information in procurement documents:

a. Title, number and date of this specification.
b. Length and width required (see 3.2).
c. Selection of applicable levels of packaging and packing required (see 5.1 and 5.2).
d. Marking document required (see 5.3).
e. Quantities required (see 5.2.3).
f. When certification (see 3.4.2) is required.

6.3 This revision deletes Type II and Type III since there is no supply demand.

Review Agencies
GPO

Custodians
Army - GL
Navy - SA
Air Force - 84

Preparing Activity:
GSA-FSS

Orders for this publication are to be placed with the General Services Administration, acting as an agent for the Superintendent of Documents. See section 2 of this specification to obtain extra copies and other documents referenced herein. Price 10 cents each.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:20Z
Check the source to verify that this is the current version before use.