UU-P-288J
May 5, 1973
SUPERSEDING
Int. Fed. Spec. UU-P-00288H(GSA-FSS)
August 24, 1971 and
Fed. Spec. UU-P-288G
December 8, 1965

FEDERAL SPECIFICATION

PAPER, LEDGER, UNRULED

This specification was approved by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal agencies.

1. SCOPE AND CLASSIFICATION

1.1 Scope. This specification covers cotton or linen white ledger paper and white and colored ledger paper, and reflects item requirements parallel to the specifications of the Joint Committee on Printing (JCP).

1.2 Classification.

1.2.1 Types. Ledger paper in accordance with this specification shall be furnished in the following types as specified (see 6.2).

Type I - 100 percent, white, ledger (JCP J30).
Type II - 25 percent, white, ledger (JCP J20).
Type III - Ledger, white and colored (JCP J10).

2. APPLICABLE DOCUMENTS

2.1 The following documents, of the issues in effect on date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein.

Federal Specification:

PPP-P-25 - Printing and Stationery Paper, Packaging and Packing of.

(Activities outside the Federal Government may obtain copies of Federal Specifications, Standards, and Handbooks as outlined under General Information in the Index of Federal Specifications and Standards and at the prices indicated in the Index. The Index, which includes cumulative monthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, U.S. Government Printing Office, Washington, DC 20402.

(Single copies of this specification and other Federal Specifications required by activities outside the Federal Government for bidding purposes are available without charge from Business Service Centers at the General Services Administration Regional Offices in Boston, New York, Washington, DC, Atlanta, Chicago, Kansas City, MO, Fort Worth, Denver, San Francisco, Los Angeles, and Seattle, WA.

(Federal Government activities may obtain copies of Federal Specifications, Standards, and Handbooks and the Index of Federal Specifications and Standards from established distribution points in their agencies.)

Military Standards:

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes.

(Copies of Military Specifications and Standards required by contractors in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

FSC 7530

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:20Z
Check the source to verify that this is the current version before use.

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless a specific issue is identified, the issue in effect on date of invitation for bids or request for proposal shall apply.

Joint Committee on Printing Publications

Government Paper Specification Standards

(Application for copies should be addressed to the Superintendent of Documents, U.S. Government Printing Office, Washington, DC 20402.)

3. REQUIREMENTS

3.1 Standard sample. The color, formation, finish, and cleanliness, as applicable, shall conform to the standard sample as adopted by the Joint Committee on Printing and as furnished by the contracting officer.

3.2 Material.

3.2.1 Type I. Type I bond paper shall conform to the requirements of J30, "100 percent, white, ledger", set forth in the Government Paper Specification Standards for the applicable basis weight.

3.2.2 Type II. Type II bond paper shall conform to the requirements of J20, "25 percent, white, ledger", set forth in the Government Paper Specification Standards for the applicable basis weight.

3.2.3 Type III. Type III bond paper shall conform to the requirements of J10, "Ledger, white and colored", set forth in the Government Paper Specification Standards for the applicable basis weight.

3.3 Size and trim. Paper shall be furnished in the size(s) ordered (see 6.2) and must be flat, trimmed square on four sides with clean, smooth edges, and evenly jogged. Size and trim tolerance shall conform to the requirements set forth in the Government Paper Specification Standards.

3.4 Basis weight. The basis weight (or substance) of the ledger paper shall be 48, 64, or 88 pounds per 1000 sheets of a 17 by 22 inches basic size, as specified (see 6.2).

3.5 Grain. Direction of the grain on flat paper shall be as ordered (see 6.2).

3.6 Color. All types of paper in accordance with this specification shall be furnished in white. Type III paper shall also be blue, buff, green, pink, salmon, or yellow in substance 64 and 88, as specified (see 6.2).

3.7 Workmanship. All types of paper covered by this specification shall be clean, free from dirt spots, oil spots, shives, foreign matter, and shall be uniform in color. The sheets shall be free from holes, tears, cuts, folds, scuff marks, lint, fuzz, or any particles that will fluff or pile on the blanket under normal press conditions. There shall be no splices within a sheet and there shall be no partial sheets.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified, the supplier may use his own facilities or any commercial laboratory acceptable to the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure that supplies and services conform to prescribed requirements.

4.1.1 Inspection. Sampling for inspection shall be performed in accordance with MIL-STD-105, except where otherwise indicated.

4.2 Components and material inspection. In accordance with 4.1 above, components and materials shall be tested in accordance with all the requirements of referenced specifications, drawings and standards unless otherwise excluded, amended, modified, or qualified in this specification or applicable purchase documents.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:20Z
Check the source to verify that this is the current version before use.

4.3 Inspection of the end item.

4.3.1 Examination of the end item. The end item shall be examined for the defects set forth in the applicable subparagraphs at the inspection levels and acceptable quality level (AQLs) shown in table I. Each inspection lot sampled shall consist of one type, size, weight, and color of ledger paper.

TABLE I. Sampling procedure

Examination paragraph	Lot size units	Sample unit	Inspection level	AQL percent defective
4.3.1.1	Shipping container	Shipping container	S-2	1/
4.3.1.2	Ream	Ream	S-2	---
4.3.1.3	Sheets	Sheet	S-4	1.5
4.3.1.4	As specified in paragraph 4.3.1.4			

1/ Acceptable quality level shall be as specified in PPP-P-25.

4.3.1.1 Examination of preparation for delivery. An examination shall be made to determine that the packaging, packing, and marking requirements comply with PPP-P-25, except that the inspection level shall be S-2.

4.3.1.2 Examination of the end item for average count (sheets), as applicable. The average number of sheets per ream, or between markers when skid packed, of all sample units examined shall be not less than the specified quantity.

4.3.1.3 Examination of the end item for dimensional defects. The sample unit for this examination shall be one sheet. The number of sheets comprising the sample size, as specified in table I for this examination shall be made up by taking two consecutive sheets from one ream or 500 sheet unit, when skid packed, (to count as two sample units). Examine each sheet.

Examine	Defect
Sheet size	Less than specified in length or width.
Sheet 8-1/2 by 14 inches or less	Oversize by more than 1/16 inch along any edge, from size specified.
Sheets over 8-1/2 by 14 inches	Oversize by more than 1/8 inch along any edge, from size specified.
Squareness	Diagonal variation exceeds 1/32 inch for sheets 32 inches or less in length or exceeds 1/16 inch for sheets over 32 inches in length.
Consecutive sheets 8-1/2 by 14 inches or less	Successive sheets differ from each other by more than 1/64 inch in in either dimension.

4.3.1.4 Examination of the end item for visual defects.

4.3.1.4.1 Reams. An examination shall be made for the defects listed in table II, applicable to reams. The lot size for this examination shall be expressed in units of reams of paper and the sample size shall be selected in accordance with level S-2. The acceptable quality level (AQL) for ream defects shall be 2.5 defects per hundred reams. Approximately an equal number of sample reams shall be taken from each of the shipping containers selected in accordance with 4.3.1.1. Sample reams shall be selected from not less than 5 shipping containers.

4.3.1.4.2 Skids. An examination shall be made for the defects listed in table II, applicable to skids. The lot size shall be expressed in units of skids and the sample size shall be selected in accordance with level S-2. The acceptable quality level shall be 2.5 defects per hundred skids.

4.3.1.4.3 Sheets. An examination shall be made for the defects listed in table II, applicable to sheets. The lot size for this examination shall be expressed in units of sheets and the sample size shall be selected in accordance with level S-4. The sheets for this examination shall be accumulated by taking approximately an equal number of sheets, in consecutive order, from each of the

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:20Z
Check the source to verify that this is the current version before use.

mple unit shall be two stenographer's notebooks. The and in accordance with the referenced TAPPI test methods. The sa

reams selected in accordance with 4.3.1.4.1 or the skids selected in accordance with 4.3.1.4.2. The acceptable quality level (AQL) shall be 2.5 defects per hundred sheets for major defects, all types of ledger paper and the AQL for minor defects shall be 25 defects per hundred sheets for types I and II paper and 40 defects per hundred sheets for type III paper.

TABLE II. Classification of defects

Examine	Defect
Reams or skids, as applicable	
Color and finish	Variation within ream or skid. Variation between reams or skids.
Workmanship, reams and skids only	Wavy, edges, uneven, ragged or crushed edges. Torn or partial sheets; spliced sheets.
Sheets	
Major	
Appearance	Presence of creases, wrinkles, tears, or holes larger than 1.5 mm in area.
Color, finish, and formation	Does not compare favorably with the standard sample.
Watermark (types I and II)	Watermark missing; indistinct; incomplete; date missing.
Minor	
Cleanliness	Does not compare favorably with the standard sample with respect to dirt specks larger than 0.5 mm in area; oil, size, color, or slime spots; foreign matter; lumps; fuzz or loose particles, scabs, or scale.

4.3.2 Testing of the end item. The end item shall be tested for the applicable characteristics as specified in section 3 for each lot presented for examination for each type, weight, size, or color of paper. The characteristics tested and methods of testing shall be as specified in the Government Paper Specification Standards. The lot size shall be expressed in units of shipping containers and the inspection level for determining the sample size shall be S-2. The sample unit shall consist of not less than 3000 square inches of paper and not more than one sample unit shall be taken from any one ream or skid. The stock determination shall be performed in duplicate on a composite sample consisting of equal portions of paper from all of the sample units in the sample size. All other determinations shall be applicable to the sample unit. The test report shall include all values upon which the results are based and there shall be no failure to meet the lot average, sample unit, or composite average.

5. PREPARATION FOR DELIVERY

5.1 Packaging, packing and marking. Packaging, packing and marking shall be level A, B, or C, as specified (see 6.2), and shall be in accordance with PPP-P-25.

6. NOTES

6.1 Intended use. The intended use for each type of paper shall be as specified in the Government Paper Specification Standards for the applicable type and weight.

6.2 Ordering data. Purchasers should select the preferred options permitted herein and include the following information in procurement documents:

(a) Title, number, and date of this specification.
(b) Type and size required (see 1.2.1 and 3.3).
(c) Basis weight, as specified (see 3.4).
(d) Grain direction (see 3.5).
(e) Color (see 3.6).
(f) Pressroom conditions (see 6.3).
(g) Preparation for delivery, (see ordering data in PPP-P-25).

6.3 When paper will be used in air-conditioned pressrooms the level of temperature and relative humidity maintained shall be stated in the invitation to bid (see 6.2).

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:20Z
Check the source to verify that this is the current version before use.

6.4 Copies of full size watermark design will be supplied upon request to the Joint Committee on Printing.

6.5 The Department of Defense has waived coordination of this specification.

Military Interest:

User - Army GL

Preparing Activity:

GSA-FSS

Orders for this publication are to be placed with General Services Administration, acting as an agent for the Superintendent of Documents. See Section 2 of this specification to obtain extra copies and other documents reference herein. Price 10 cents each.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:20Z
Check the source to verify that this is the current version before use.