UU-P-322F
March 19, 1976
SUPERSEDING
Fed. Spec. UU-P-322E
June 30, 1964

FEDERAL SPECIFICATION

PAPER, SHORTHAND MACHINE

This specification was approved by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal agencies.

1. SCOPE AND CLASSIFICATION

1.1 Scope. This specification covers shorthand machine paper for use in stenotyping machines.

1.2 Classification. Shorthand machine paper shall be furnished in one type and grade.

2. APPLICABLE DOCUMENTS

2.1 The following documents, of the issues in effect on date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein.

Federal Specifications:

DDD-R-271 - Ribbons, Computing and Recording Machines.
PPP-B-636 - Boxes, Shipping, Fiberboard.

Federal Standard:

Fed. Std. No. 123 - Marking for Shipment (Civil Agencies).

(Activities outside the Federal Government may obtain copies of Federal Specifications, Standards, and Handbooks as outlined under General Information in the Index of Federal Specifications and Standards and at the prices indicated in the Index. The Index, which includes cumulative monthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, U.S. Government Printing Office, Washington, DC 20402.

(Single copies of this specification and other Federal Specifications required by activities outside the Federal Government for bidding purposes are available without charge from Business Service Centers at the General Services Administration Regional Offices in Boston, New York, Washington, DC, Atlanta, Chicago, Kansas City, MO, Fort Worth, Denver, San Francisco, Los Angeles, and Seattle, WA.

(Federal Government activities may obtain copies of Federal Specifications, Standards, and Handbooks and the Index of Federal Specifications and Standards from established distribution points in their agencies.)

Military Standards:

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes.
MIL-STD-129 - Marking for Shipment and Storage.

(Copies of Military Specifications and Standards required by suppliers in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless a specific issue is identified, the issue in effect on date of invitation for bids or request for proposal shall apply.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:20Z
Check the source to verify that this is the current version before use.

Technical Association of the Pulp and Paper Industry (TAPPI) Test Methods:

T402 - Standard Conditioning and Testing Atmosphere for Paper, Board, Pulp Handsheets, and Related Products.
T403 - Bursting Strength of Paper.
T404 - Tensile Breaking Strength of Paper and Paperboard.
T410 - Weight per Unit Area (Basis Weight or Substance) of Paper and Paperboard.
T411 - Thickness (Caliper) of Paper and Paperboard.
T452 - Brightness of Paper and Paperboard.

(Application for copies should be addressed to the Technical Association of the Pulp and Paper Industry, One Dunwoody Park, Atlanta, GA 30341.)

National Motor Freight Traffic Association, Inc., Agent:

National Motor Freight Classification.

(Application for copies should be addressed to the American Trucking Associations, Inc., Tariff Order Section, 1616 P Street, N.W., Washington, DC 20036.)

Uniform Classification Committee, Agent:

Uniform Freight Classification.

(Application for copies should be addressed to the Uniform Classification Committee, Room 1106, 222 South Riverside Plaza., Chicago, IL 60606.)

3. REQUIREMENTS

3.1 Material.

3.1.1 Paper. The stenotype paper shall be made from fibrous cellulosic material, which may include reclaimed fibers.

3.1.2 Printing quality. When printed by means of a shorthand machine ribbon, the ink shall be quickly absorbed without smearing or blurring of the printed figures when tested in accordance with 4.3.1.3.1.

3.2 Physical Properties. The physical properties of the stenotype paper shall be as specified in table I when tested in accordance with 4.2.

TABLE I. Physical properties

Basis Weight, pounds, (24 x 36 - 500) ± 5%	30
Thickness, inch, average ± 0.0005	0.0028
Tensile strength, kg/15mm width (min.)	
Machine Direction	2.5
Cross Direction	1.0
Bursting strength, points (min.)	7.5
Brightness, % (min.)	55

3.3 Form. Shorthand machine paper shall be in the form of bundles, consisting of one continuous strip in accordion-folded form. The folding joints shall be pronounced to the extent that nonassisting refold will occur during use.

3.3.1 Fold lines. The fold lines shall be at right angles to the edge of the paper to the extent that the assembled bundle has uniformly even edges with no folds protruding more than 1/16 inch along the edges of the bundle. The folds per bundle shall be 300.

Source: https://assist.dla.mil -- Downloaded: 202640-26T12:20Z
Check the source to verify that this is the currentversion before use.

3.4 Dimensions. The length between folds shall be 8-1/2 inches and the width of the bundle shall be 2-3/8 inches, with a ± 1/32 inch tolerance in all dimensions.

3.5 Workmanship. The paper shall be free from dirt, nicks, wrinkles, tears, holes, and splices. When formed the bundle shall be flat with uniform, clean-cut dust-free edges. The quality shall conform to the acceptable quality levels established in section 4.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or order, the supplier may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure that supplies and services conform to prescribed requirements.

4.1.1 Inspection. Sampling for inspection shall be performed in accordance with MIL-STD-105, except where otherwise indicated.

4.1.2 Inspection of components and materials. The supplier is responsible for insuring that components and materials used were manufactured, examined, and tested in accordance with this specification or referenced subsidiary specifications and standards.

4.1.3 Evidence of compliance. In lieu of using his own facilities, the contractor may submit a report of analysis of component materials from a laboratory acceptable to the Government, whether an independent test facility or the laboratory of the raw material supplier, as evidence of compliance with the specification requirements. The report of analysis shall include, in addition to the actual test data, the manufacturer's name, name and address of the testing laboratory, date of test, and quantity of material represented by the test report. Where certificates of compliance or reports of analysis are submitted, the Government reserves the right to check test such items to determine the validity of the certificate or analysis.

4.2 Sampling and testing of components. The paper shall be tested for the applicable characteristics in table II. The sample unit shall be a minimum of 3000 square inches of paper. Three randomly selected sample units shall be tested from each lot. The lot shall consist of one shipment of paper received at one time from one source of supply. All samples shall be conditioned under uniform atmospheric conditions as specified in TAPPI method T402 and tested according to TAPPI methods listed in table II. Composite samples shall consist of representative portions of small pieces selected from all sample units and combined in a single sample.

TABLE II. Instructions for testing components

Characteristic	Requirement paragraph	TAPPI test method	Requirement applicable to	Results reported to nearest
Atmospheric conditions	4.2	T402	All tests	-
Basis weight	Table I	T410	Lot average	0.1 pound
Thickness	Table I	T411	Lot average	.0001 inch
Tensile strength	Table I	T404	Lot average	0.1 kg/15mm width
Bursting strength	Table I	T403	Lot average	1 point
Brightness	Table I	T452	Lot average	1 percent

4.3 Inspection of the end item.

4.3.1 Sampling. The end item shall be examined for the defects set forth in the applicable subparagraphs at the inspection levels and acceptable quality levels (AQLs) specified. The lot size for purposes of determining the sample size in accordance with MIL-STD-105 shall be expressed in units of the end item for examination under 4.3.1.2 and in units of shipping containers for examination under 4.3.1.1.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:20Z
Check the source to verify that this is the current version before use.

4.3.1.1 Examination of preparation for delivery. An examination shall be made to determine whether the packaging, packing and marking comply with the requirements of sections 5. Defects shall be scored as specified in table III. Sampling shall be in accordance with MIL-STD-105. The sample unit shall be one container fully prepared for delivery. The lot shall be the number of containers offered for inspection at one time. The inspection level shall be S-2 with an AQL of 4.0 expressed in terms of percent defective.

TABLE III. Examination of preparation for delivery

Examine	Defects
Contents	Not as specified.
Containers	Not as specified.
Markings	Omitted; incorrect; illegible; improper size, location, sequence or method of application.
Material	Component missing or damaged.
Workmanship	Packaging adhesive on the end item. Bulging or distortion of container. Cushioning inadequate, improper or missing.

4.3.1.1.1 Examination of closure, waterproofing and banding. When shipping containers are required to comply with PPP-B-636, examination for defects in closure, waterproofing and banding shall be in accordance with the appendix of PPP-B-636.

4.3.1.2 Examination of the end item. The sample unit shall be one banded bundle randomly selected. The lot shall be the number of banded bundles offered for inspection at one time. The inspection level shall be S-2 with an AQL of 4.0 expressed in terms of percent defective. No more than two (2) bundles shall be selected from any one container.

Examine	Defect
Assembly	Not banded individually. Edges not clean cut; nicked, crushed. Not flat.
Folds	Protruding edges more than 1/16 inch. Fold joints not properly made. Less than 300 folds to a bundle.
Dimensions	Vary by more than ± 1/32 inch from specified dimension.
Workmanship	Surfaces not clean, spots, dust or foreign material. Tear, cut, splice, hole, wrinkles.

4.3.1.3 Testing of end item. Packages of shorthand machine paper shall be selected from containers in 4.3.1.1 from each lot in accordance with inspection level S-2. The lot size shall be expressed in units of packages. Acceptance or rejection shall be based upon lot average of the selected samples. If any package fails the test in 4.3.1.3.1, the lot shall be rejected.

4.3.1.3.1 Printing quality. Print number on the sample bundles of shorthand machine paper using a shorthand machine with a ribbon conforming to the requirements of DDD-R-271. The paper shall be examined for ink smearing or blurring.

5. PREPARATION FOR DELIVERY

5.1 Packaging. Packaging shall be level A, B or C, as specified (see 6.2).

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:20Z
Check the source to verify that this is the current version before use.

5.1.1 Level A and B. Unit container. The paper bundles as specified in 3.3 shall be banded with a kraft paper not less than six (6) inches in width. Alternatively, the bundle shall be packaged with plastic film. The paper band or plastic film shall be secured to prevent accidental opening.

5.1.2 Level C. Shorthand-machine paper in 300-fold bundles shall be packaged in accordance with the industry's practice.

5.2 Packing. Packing shall be level A, B, or C, as specified (see 6.2).

5.2.1 Level A. Shipping container. Fifty (50) bundles with three-hundred (300) folds shall be packed in a box conforming to PPP-B-636, grade V2s. The box shall be closed in accordance with method III, waterproofed and banded in accordance with the appendix to PPP-B-636.

5.2.2 Level B. Shipping container. Fifty (50) bundles with three hundred (300) folds shall be packed in a box conforming to PPP-B-636, class domestic. The box shall be closed in accordance with the appendix to PPP-B-636.

5.2.2.1 Weather-Resistance. When specified (see 6.2), the shipping container shall be a box conforming to PPP-B-636, V3c, V3s or V4s and closed in accordance with method III of the appendix to PPP-B-636.

5.2.3 Level C. The paper bundles in the quantity, as specified (see 6.2), shall be packed in a container complying with the Uniform Freight Classification, or National Motor Freight Classification, as applicable. The containers shall be packed to assure carrier acceptance and safe arrival at destination.

5.3 Marking. Marking of interior packages and shipping containers shall be in accordance with Fed. Std. No. 123 for civil agencies or MIL-STD-129 for military agencies, as applicable (see 6.2).

6. NOTES

6.1 Intended use. Shorthand-machine paper is used in shorthand typing on stenotype machines.

6.2 Ordering data. Purchasers should select the preferred options permitted herein, and include the following information in procurement documents:

(a) Title, number, and date of this specification.
(b) Selection of applicable levels of packaging and packing (see 5.1 and 5.2).
(c) When weather resistant grade fiberboard shipping containers are required for level B packing (see 5.2.2.1).

MILITARY INTEREST:

User interest:

Army - GL

Preparing activity:

GSA-FSS

Civil Agency Coordinating Activities:

GSA-FSS

Orders for this publication are to be placed with General Services Administration, acting as an agent for the Superintendent of Documents. See Section 2 of this specification to obtain extra copies and other documents referenced herein. Price 30 cents each.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:20Z
Check the source to verify that this is the current version before use.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:20Z
Check the source to verify that this is the current version before use.