UU-P-00328K (GSA-FSS)
February 21, 1978
Interim Revision of
Fed. Spec. UU-P-328J
March 20, 1973

INTERIM FEDERAL SPECIFICATION

PAPER, MANIFOLD

This Interim Federal Specification was developed by the General Services Administration, Federal Supply Service, Washington, DC 20406, based upon currently available technical information. It is recommended that Federal agencies use it in procurement and forward recommendations for changes to the preparing activity at the address shown above.

The General Services Administration has authorized the use of this Interim Federal Specification as a valid exception to Federal Specification UU-P-328J, dated March 20, 1973.

1. SCOPE AND CLASSIFICATION

1.1 Scope. This specification covers 25 percent white manifold paper, 25 percent white glazed manifold paper, and white and colored chemical wood manifold paper (see 6.1).

1.2 Classification. The manifold papers covered by this specification shall be of the following types, as specified (see 6.2).

Type IV - 25 percent white manifold.
Type V - Manifold, white and colored.
Type VI - 25 percent white glazed manifold.

2. APPLICABLE DOCUMENTS

2.1 The following documents, of the issues in effect on date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein.

Federal Specification:

PPP-B-636 - Boxes, Shipping, Fiberboard.

(Activities outside the Federal Government may obtain copies of Federal Specifications, Standards, and Handbooks as outlined under General Information in the Index of Federal Specifications and Standards and at the prices indicated in the Index. The Index, which includes cumulative monthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, U.S. Government Printing Office, Washington, DC 20402.

(Single copies of this specification and other Federal Specifications required by activities outside the Federal Government for bidding purposes are available without charge from Business Service Centers at the General Services Administration Regional Offices in Boston, New York, Philadelphia, Washington, DC, Atlanta, Chicago, Kansas City, MO, Fort Worth, Houston, Denver, San Francisco, Los Angeles, and Seattle, WA.

(Federal Government activities may obtain copies of Federal Specifications, Standards, and Handbooks and the Index of Federal Specifications and Standards from established distribution points in their agencies.)

Military Standard:

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:20Z
Check the source to verify that this is the current version before use.

(Copies of Military Specifications and Standards required by contractors in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless a specific issue is identified, the issue in effect on date of invitation for bids or request for proposal shall apply.

National Motor Freight Traffic Association, Inc., Agent:

National Motor Freight Classification.

(Application for copies should be addressed to the American Trucking Associations, Inc., Traffic Department, 1616 P Street, N.W., Washington, DC 20036.)

Uniform Classification Committee, Agent:

Uniform Freight Classification.

(Application for copies should be addressed to the Uniform Classification Committee, Room 1106, 222 South Riverside Plaza, Chicago, IL 60606.)

Technical Association of the Pulp and Paper Industry (TAPPI) Standards:

T 401 - Fiber Analysis of Paper and Paperboard.
T 403 - Bursting Strength of Paper.
T 408 - Rosin in Paper and Paperboard.
T 410 - Weight per Unit Area (Basis Weight or Substance) of Paper and Paperboard.
T 435 - Hydrogen Ion Concentration (pH) of Paper Extracts - Hot Extraction Method.

(Application for copies should be addressed to the Technical Association of the Pulp and Paper Industry, One Dunwoody Park, Atlanta, GA 30341.)

3. REQUIREMENTS

3.1 Material.

3.1.1 Types IV and VI. The paper shall contain not less than 25 percent cotton or linen fibers when tested in accordance with 4.3. The remainder shall be bleached chemical wood pulp.

3.1.2 Type V. The paper shall be made of bleached chemical pulp, free from ground wood when tested in accordance with 4.3.

3.1.3 Recovered material. The material offered (all types) shall contain not less than 10 percent of recovered materials. Recovered materials are defined as material which has been collected or recovered from solid waste. Solid waste is defined as any garbage, refuse, sludge from a waste treatment plant, water supply treatment plant, or air pollution control facility and other discarded material, including solid, liquid, semisolid, or contained gaseous material resulting from industrial, commercial, mining, and agricultural operations, and from community activities, but does not include solid or dissolved material in domestic sewage, or solid or dissolved materials in irrigation return flows or industrial discharges.

3.2 Physical properties. The paper shall conform to the applicable requirements of table I when tested in accordance with 4.3.

TABLE I. Physical Properties

	Type		
	IV	V	VI
Acidity (pH), minimum	4.8	4.5	4.8
Rosin, maximum percent	2.5	NA	2.5
Basis weight, 17 x 22 inches - 1000 sheets, pounds, (± 5 pct)	18	18	16
Bursting strength, minimum, pounds per square inch	15	7	15

Source: https://assist.dla.mil -- Downloaded: 202640-26T12:20Z
Check the source to verify that this is the current version before use.

3.3 Grain. Unless otherwise specified (see 6.2), the grain (machine direction) of the paper shall parallel the long dimension.

3.4 Color. The paper shall be white, blue, green, pink, or yellow, as specified (see 6.2).

3.5 Workmanship. The paper shall be clean, free from dirt spots, oil spots, shives, slivers, and foreign matter. It shall be uniform in color and formation. The sheets shall be free from holes, tears, cuts, folds, scuff marks, lint, and fuzz. There shall be no partial sheets or splices within a sheet.

3.6 Standard sample. The color, formation, finish, and cleanliness, as applicable, shall conform to the standard sample as furnished by the contracting officer.

3.7 Size and trim. The paper shall be furnished in the size(s) specified (see 6.2). It shall be flat, trimmed square on four sides with clean smooth edges, and evenly jogged. A tolerance of ± 1/16 inch (1.588 mm) shall be allowed for sheets larger than 8-1/2 x 14 inches (216 x 356 mm). A tolerance of ± 1/32 inch (0.794 mm) shall apply to sheets 8-1/2 x 14 inches or smaller. Successive sheets within any package shall not differ from each other by more than 1/64 inch (0.397 mm). Paper with the long dimension 32 inches (813 mm) or less shall be considered square if the difference between diagonals does not exceed 1/32 inch; over 32 inches, the difference shall not exceed 1/16 inch.

3.8 Sizing. The paper shall be surface- and internal- sized so that, when tested in accordance with 4.4, all characters drawn shall be clear cut, without feathering or spreading.

3.9 Quantities. Unless otherwise specified (see 6.2), there shall be 1000 sheets per package (see 5.1) or between markers (see 5.2.1.2).

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or order, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government.

4.1.1 Inspection. Sampling for inspection shall be performed in accordance with MIL-STD-105, except where otherwise indicated.

4.1.2 Certification. A certificate shall be submitted with each bid specifying that the material to be supplied will contain the percentage of recovered material required herein.

4.2 End item inspection.

4.2.1 Examination of preparation for delivery. The sample unit shall be one package, shipping container, skid, or palletized load, as applicable. An examination shall be made to determine conformance with the weight and dimensions (palletized load), marking, materials, workmanship, and content requirements of section 5. The inspection level shall be S-4, with an AQL of 4.0 percent defective.

4.2.2 Examination of count. Five packages, or five units between markers in the case of skid packs, shall be randomly selected from the shipping containers or skids selected in accordance with 4.2.1, and examined for count. The average number of sheets per package, or between markers shall be not less than 1,000, and there shall be not less than 960 sheets in any one package, or between one pair of markers.

4.2.3 Examination for dimensional defects. The sample unit shall be one sheet. The inspection level shall be S-4, with an AQL of 1.5 percent defective. Two consecutive sheets (to count as two sample units) shall be taken from each package or skid sampled. Defects are as indicated.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:20Z
Check the source to verify that this is the current version before use.

Examine	Defect
Size	Not as specified; not within tolerance (see 3.7).
Squareness	Diagonal variation out of tolerance (see 3.7).
Consecutive sheets	Variation between sheets out of tolerance (see 3.7).
Grain	Not long; or not as specified.

4.2.4 Examination for visual defects.

4.2.4.1 Packages or skids. Packages or skids, as applicable, shall be examined for the defects listed below. The sample unit shall be one package or skid. The inspection level and AQL shall be S-2 and 4.0 percent defective.

Examine	Defect
Color and finish	Varies within or between packages or skids.
Workmanship	Edges wavy, unevenly jogged, ragged or crushed.

4.2.4.2 Sheets. Sheets shall be examined for the defects listed below. The sample shall consist of 25 sheets from each of the packages or skids selected in accordance with 4.2.4.1. The AQL shall be 3 percent defective for major defects, and 6 percent defective for major and minor defects combined.

Examine	Defect
Major:	
Appearance	Creases, wrinkles or tears.
Color, finish, and formation	Not comparable to the standard sample.
Workmanship	Torn or partial sheets; spliced sheets.
Minor:	
Cleanliness	Does not meet or exceed the standard sample with respect to dirt or oil spots, holes, slime spots, foreign matter, and fuzz or loose particles.

4.3 End item testing. Each lot of paper shall be tested for the applicable characteristics in table II. The sample unit shall be 50 sheets. The inspection level shall be S-1 with an AQL of 2.5 percent defective.

TABLE II. Instructions for testing

Characteristics	Requirement	Test Method 1/
Fiber analysis	3.1.1 or 3.1.2	T 401
Bursting strength	Table I	T 403
Rosin content	Table I	T 408
Basis weight	Table I	T 410
Acidity	Table I	T 435
Sizing	3.8	4.4

1/ Numbers preceded by "T" refer to TAPPI test methods.

4.4 Sizing. Draw the letters A through M in capitals on both sides of one sheet from each sample unit. A pen with a firm medium point (Esterbrook point number 9668 or equal), and a 1 percent aqueous solution of either C.I. Acid Red 1 (Color Index No. 18050) or C.I. Acid Green 3 (Color Index No. 42085) shall be used. The letters shall be drawn to produce good, consistent line quality. The letters so drawn shall be clear-cut and legible without feathering or spreading.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:20Z
Check the source to verify that this is the current version before use.

5. PREPARATION FOR DELIVERY

5.1 Packaging. The paper shall be wrapped and sealed to provide moisture resistant protection. The package shall be designed to protect the paper against damage during shipment, handling, and storage. Packaging is not required for skid packing.

5.2 Packing. Packing shall be level A, or Commercial, as specified (see 6.2).

5.2.1 Level A.

5.2.1.1 Boxes. The packaged paper of one type, form, and size only, shall be packed in a box conforming to PPP-B-636, class weather-resistant. The box shall be closed, waterproof sealed, and banded in accordance with the appendix to PPP-B-636.

5.2.1.2 Skid packing. The skid load of paper shall be packed to provide product protection against loss and damage during multiple shipments, handling, and storage. The load shall have markers (see 3.9) which project beyond the edge of the paper. The load shall be completely wrapped with a waterproof wrapper or shrink film. The skid shall have runners not less than 28 inches nor more than 38 inches apart. The skid load shall be in accordance with the National Motor Freight Classification or Uniform Freight Classification.

5.2.2 Commercial.

5.2.2.1 Boxes. The packaged paper of one type, form, and size only, shall be packed in fiberboard boxes to insure delivery at destination, to provide for redistribution by the initial receiving activity, and shall be acceptable by common carrier under the National Motor Freight Classification and Uniform Freight Classification.

5.2.2.2 Skid packing. Skid packing shall be in accordance with 5.2.1.2.

5.3 Palletization. When shipments to Government depots are full car or truckload, the shipping containers shall be palletized on expendable wooden pallets, 2 or 4-way entry design, to facilitate handling in accordance with normal commercial practice. The palletized load shall not exceed 2,500 pounds in weight, 63 inches in height, 56 inches in length, and 45 inches in width. Skid packs shall not be palletized.

5.4 Marking. Marking shall be as specified in the contract or purchase order (see 6.2).

6. NOTES

6.1 Intended use. Manifold paper is a light weight, low bulk, low opacity paper for use in making multiple copies of correspondence. Type V paper is intended for temporary records. Types IV and VI are intended for semipermanent records.

6.2 Ordering data. Purchasers should select the preferred options permitted herein, and include the following information in procurement documents:

(a) Title, number, and date of this specification.
(b) Type and size required (see 1.2 and 3.7).
(c) Color (type V only) (see 3.4).
(d) Grain direction (will be grain long unless otherwise specified) (see 3.3).
(e) Packing required (see 5.2).
(f) Marking required (see 5.4).
(g) Quantity required (see 5.1 and 5.2). Quantity per package, or between markers (skid pack) shall be 1000 sheets, unless otherwise specified.

GSA DC 78-3448

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:20Z
Check the source to verify that this is the current version before use.