UU-P-381B
October 23, 1969
SUPERSEDING
Fed. Spec. UU-P-381a
May 25, 1964

FEDERAL SPECIFICATION

PAPER, MASKING, PHOTOLITHOGRAPHIC (COATED)

This specification was approved by the Commissioner, Federal Supply Services, General Services Administration, for the use of all Federal agencies.

1. SCOPE AND CLASSIFICATION

1.1 Scope. This specification covers Paper, Masking, Photolithographic, Coated, and reflects item requirements parallel to the specifications of the Joint Committee on Printing (JCP 0-50).

1.2 Classification.

1.2.1 Type and grade. Masking paper in accordance with this specification shall be one type and grade, as hereinafter specified..

2. APPLICABLE DOCUMENTS

2.1 Specifications and standards. The following specifications and standards, of the issues in effect on date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein:

Federal Specification:

PPP-P-25 - Printing and Stationery Paper, Packaging and Packing of.

(Activities outside the Federal Government may obtain copies of Federal Specifications, Standards, and Handbooks as outlined under General Information in the Index of Federal Specifications and Standards and at the prices indicated in the Index. The Index, which includes cumulative monthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, U. S. Government Printing Office, Washington, D.C. 20402.

FSC 3610

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:20Z
Check the source to verify that this is the current version before use.

(Single copies of this specification and other product specifications required by activities outside the Federal Government for bidding purposes are available without charge at the General Services Administration Regional Offices in Boston, New York, Washington, D. C., Atlanta, Chicago, Kansas City, Mo., Fort Worth, Denver, San Francisco, Los Angeles, and Seattle, Washington.

(Federal Government activities may obtain copies of Federal Specifications, Standards, and Handbooks and the Index of Federal Specifications and Standards from established distribution points in their agencies.)

Military Standard:

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes.

(Copies of Military Specifications and Standards required by contractors in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitation for bids or request for proposal, shall apply.

Joint Committee on Printing

Government Paper Specification Standards.

(Copies may be obtained from the Superintendent of Documents, U. S. Government Printing Office, Washington, D. C. 20402.)

American Society for Testing and Materials Publication:

E 308-66 - Recommended Practices for Spectrometry and Description of Color in C.I.E. 1931 System

(Application for copies should be addressed to American Society for Testing and Materials, 1916 Race Street, Philadelphia, Pennsylvania 19103.)

Technical Association of the Pulp and Paper Industry Publications:

T 401 m-60 - Fiber Analysis of Paper and Paperboard

T 402 m-49 - Conditioning Paper and Paperboard for Testing

T 410 os-61 - Basis Weight of Paper and Paperboard

T 403 ts-63 - Bursting Strength of Paper

T 442 m-45 - Spectral Reflectivity and Color of Paper

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:20Z
Check the source to verify that this is the current version before use.

(Copies of TAPPI testing methods may be obtained from the Technical Association of the Pulp and Paper Industry, 360 Lexington Avenue, New York, New York 10017.

(Technical society and technical association specifications and standards are generally available for reference from libraries. They are also distributed among technical groups and using Federal agencies.)

3. REQUIREMENTS

3.1 Standard sample. The color, finish, formation and cleanliness of the masking paper must conform to the standard sample as adopted by the Joint Committee on Printing and as furnished by the contracting officer.

3.2 Masking paper. Masking paper shall be made from such material as to comply with the requirements set forth in the Government Paper Specification Standards for JCP 0-50, Paper, Masking, Photolithograph (Coated), of the Joint Committee on Printing.

3.3 Size. Paper shall be furnished in the size(s) ordered (see 6.2), and must be flat, trimmed square on four sides with clean, smooth edges, and evenly jogged. Size and trim tolerance shall conform to the requirements set forth in the Government Paper Specification Standards.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or order, the supplier may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.1.1 Certificates of compliance. Where certificates of compliance are submitted, the Government reserves the right to check test such items to determine the validity of the certification.

4.2 Inspection. Sampling for inspection shall be performed in accordance with MIL-STD-105, except where otherwise indicated hereinafter.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:20Z
Check the source to verify that this is the current version before use.

4.2.1 Inspection of materials and components. In accordance with 4.1 above, components and materials shall be tested in accordance with the requirements of referenced specifications, drawings and standards unless otherwise excluded, amended, modified or qualified in this specification or applicable purchase documents.

4.2.2 Inspection of the end item.

4.2.2.1 Examination of the end item. The end item shall be examined for the defects set forth in the applicable subparagraphs at the inspection levels and acceptable quality levels (AQL's) in 4.2.2.1.5. The lot size, for the purposes of determining the sample size in accordance with MIL-STD-105, shall be expressed in units of packages or reams for examination in 4.2.2.1.1, 4.2.2.1.2 and 4.2.2.1.3, and in units of shipping containers in 4.2.2.1.4.

4.2.2.1.1 Examination for visual defects. The sample unit for this examination shall be one sheet. No more than one sample unit shall be taken from any one package of sheets or reams of sheets. Examine both sides.

Examine	Defects
Color and formation	Does not compare favorably with standard sample. Variation in color between sheets, between reams, or within order. Finish not uniform on both sides.
Coating	Coating not uniform between areas of same sheet. Coating gritty, stippled, mottled, or ribbed.
Cleanliness	Presence of shives, dirt specks, oil, grease, iron, oil or coal spots or any other extraneous matter in excess of that displayed by the standard.
Workmanship	Presence of wrinkles, creases, calendar cuts, tears, uneven or ragged edges or crushed corners.

4.2.2.1.2 Examination of dimensions. The masking paper shall be examined for defects in dimension. The sample unit shall be one sheet.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:20Z
Check the source to verify that this is the current version before use.

Examine	Defects
Dimensions	Long or short dimension of sheet less than specified. Long or short dimension of sheet more than 1/8 inch oversize.

4.2.2.1.3 Examination for count per package. The packaged masking paper shall be examined for determining the average count of sheets per package. The sample unit shall be one package of sheets or one ream as applicable.

Examine	Defects
Count	Number of sheets in any individual package or ream less than 95 percent of required count. Average number of sheets per ream or package (for all packages examined) less than specified.

4.2.2.1.4 Examination of preparation for delivery. An examination shall be made to determine that markings, materials and workmanship, comply with the requirements of Section 5 of this specification. The sample unit shall be one shipping container, fully packed, selected just prior to the closing operation. Shipping containers fully prepared for delivery shall be examined for closure defects.

Examine	Defects
Markings (exterior and interior)	Incorrect incomplete illegible omitted of improper size, location, sequence or method of application.
Materials	Any nonconforming component component missing, damaged, or otherwise defective.
Workmanship	Inadequate application of components, such as: incomplete closure of case liners, container flaps, loose or inadequate sealing, strapping or stapling. Bulged or distorted container.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:20Z
Check the source to verify that this is the current version before use.

4.2.2.1.5 Inspection levels and acceptable quality levels (AQL's) for examination. The inspection levels, for determining the sample size and acceptable quality levels (AQL's), expressed in defects per 100 units, shall be as follows:

Examination paragraph	Inspection levels	AQL's
4.2.2.1.1	I	2.5
4.2.2.1.2	S-2	2.5
4.2.2.1.3	S-2	N/A
4.2.2.1.4	S-2	2.5

4.3.2 Testing of the end item. The end item shall be tested for the characteristics in table II. The lot size for determining the sample size shall be expressed in reams. The sample unit shall consist of 1000 square inches of paper and no more than one sample unit shall be taken from any ream. The samples shall be conditioned in accordance with procedure specified in TAPPI standard T 402 before testing. Test reports shall include all values on which the results are based, and there shall be no failure to meet the composite, sample unit, or lot average requirements.

Lot size (reams)	Sample size (number of sampling units)	Ac	Re
0 - 50	2	0	1
51 - 500	3	0	1
501 - 35,000	5	0	1
35,001 or more	8	0	1

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:20Z
Check the source to verify that this is the current version before use.

TABLE II. Instructions for testing

CHARACTERISTIC	Specification Reference		Requirements Applicable To		Number Determinations Per Unit	Results Reported As		Inspect Level	AQL
	Requirement	Test Method 1/ 3/ 4/	Individ Unit	Lot Aver		Pass or Fail	Numerically to Nearest		
Atmospheric conditions	3.2	T402 m-49	--	-	All testing				
Stock	3.2	T401 m-60	-	-	2 on composite 2/		5 percent		
Basis weight, pounds, 25 x 38 - 500			X						
Sheet basis	3.2	T410 os-61	X		5 per sample unit		pound		
Bursting strength	3.2	T403 ts-63	X		10, 5 per side		point		
Light transmission, percent, maximum									
Below 540 millimicron wave length	3.2	E 308-66			5		0.1 percent		
From 540-700 millimicron wave length	3.2	E 308-66			5		0.1 percent		
Chromaticity coordinates and luminance value	3.2.	T442 m-45			5		0.01 chromaticity unit and 1.0 percent luminance		

1/ Refers to TAPPI Standard Number.

2/ The composite shall consist of small pieces of paper, of equal size, taken from each sample unit.

3/ Denotes ASTM Standard Number.

4/ Suppliers certificate of compliance shall satisfy this requirement.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:20Z
Check the source to verify that this is the current version before use.

5. PREPARATION FOR DELIVERY

5.1 Packaging. Packaging shall be level A or C as specified (see 6.2).

5.1.1 Level A. The masking paper shall be packaged in accordance with the applicable level A requirements for printing papers as specified in PPP-P-25.

5.1.2 Level C. The masking paper shall be packaged in accordance with the applicable level C requirements for printing papers as specified in PPP-P-25.

5.2 Packing. Packing shall be level A, B, or C as specified (see 6.2).

5.2.1 Level A. Masking paper, packaged as specified in 5.1, shall be packed in accordance with the level A requirements for printing papers as specified in PPP-P-25.

5.2.2 Level B. Masking paper, packaged as specified in 5.1, shall be packed in accordance with the applicable level B requirements for printing papers as specified in PPP-P-25.

5.2.3 Level C. Masking paper packaged as specified in 5.1, shall be packed in accordance with the applicable level C requirements for printing papers as specified in PPP-P-25.

5.3 Marking. In addition to any special marking required by the contract or order, interior packages, shipping containers and skids of paper, (when applicable) shall be marked in accordance with the applicable marking requirements of PPP-P-25.

6. NOTES

6.1 Intended use. This paper is intended for photographic masking use incidental to the offset printing process.

6.2 Ordering data. Purchasers should select the preferred options permitted herein and include the following information in procurement documents:

(a) Title, number, and date of this specification.
(b) Size (see 3.3).
(c) Packaging, packing, and marking required (see 5.1, 5.2, and 5.3).

6.3 Standard comparison samples may be obtained upon application to the procuring agency issuing the invitation for bids.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:20Z
Check the source to verify that this is the current version before use.

MILITARY CUSTODIANS:

Army - GL
Navy - SA
Air Force - 84

Review activities:

Army - MD, ME
Navy - SA
Air Force - 84

Preparing activity:

Army - GL

CIVIL AGENCY INTEREST:

AGR	JUS
COM	JUS-FPI
DC	PO
GSA	TR
HEW	VA

Project No. 3610-0156

Order for this publication are to be placed with General Services Administration, acting as an agent for the Superintendent of Documents. See Section 2 of this specification to obtain extra copies and other documents reference herein. Price 15 cents each.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:20Z
Check the source to verify that this is the current version before use.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:20Z
Check the source to verify that this is the current version before use.

SPECIFICATION ANALYSIS SHEET

Form Approved
Budget Bureau No. 22-R255

INSTRUCTIONS: This sheet is to be filled out by personnel, either Government or contractor, involved in the use of the specification in procurement of products for ultimate use by the Department of Defense. This sheet is provided for obtaining information on the use of this specification which will insure that suitable products can be procured with a minimum amount of delay and at the least cost. Comments and the return of this form will be appreciated. Fold on lines on reverse side, staple in corner, and send to preparing activity. Comments and suggestions submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or serve to amend contractual requirements.

SPECIFICATION

Paper, Masking, Photolithographic (Coated) UU-P-381B

ORGANIZATION

CITY AND STATE

CONTRACT NUMBER

MATERIAL PROCURED UNDER A

☐ DIRECT GOVERNMENT CONTRACT ☐ SUBCONTRACT

1. HAS ANY PART OF THE SPECIFICATION CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE?

A. GIVE PARAGRAPH NUMBER AND WORDING.

B. RECOMMENDATIONS FOR CORRECTING THE DEFICIENCIES

2. COMMENTS ON ANY SPECIFICATION REQUIREMENT CONSIDERED TOO RIGID

3. IS THE SPECIFICATION RESTRICTIVE?

☐ YES ☐ NO *(If "yes", in what way?)*

4. REMARKS *(Attach any pertinent data which may be of use in improving this specification. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity)*

SUBMITTED BY *(Printed or typed name and activity - Optional)*

DATE

DD FORM 1 JAN 66 1426

REPLACES EDITION OF 1 OCT 64 WHICH MAY BE USED.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:20Z
Check the source to verify that this is the current version before use.