UU-P-388M
March 30, 1973
SUPERSEDING
Int. Fed. Spec. UU-P-00388L (GSA-FSS)
June 8, 1970 and
Fed. Spec. UU-P-388K
December 8, 1965

FEDERAL SPECIFICATION

PAPER, MIMEOGRAPH

This specification was approved by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal agencies.

1. SCOPE AND CLASSIFICATION

1.1 Scope. This specification covers cotton or linen, white mimeograph paper, white mimeograph bond paper, and white and colored memeograph paper and reflects item requirements parallel to the specifications of the Joint Committee on Printing (JCP).

1.2 Classification.

1.2.1 Types. Mimeograph paper, in accordance with this specification, shall be furnished in the following types, as specified (see 6.2).

Types:

I - 25 percent white mimeograph (JCP B 20).
II - White mimeograph bond (JCP G 30).
III - Mimeograph, white and colored (JCP B 10).

2. APPLICABLE DOCUMENTS

2.1 The following documents of the issue in effect on date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein.

Federal Specification:

PPP-P-25 - Printing and Stationery Paper, Packaging and Packing of.

(Activities outside the Federal Government may obtain copies of Federal Specifications, Standards, and Handbooks as outlined under General Information in the Index of Federal Specifications and Standards and at the prices indicated in the Index. The Index, which includes cumulative monthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, U.S. Government Printing Office, Washington, DC 20402.

(Single copies of this specification and other Federal Specifications required by activities outside the Federal Government for bidding purposes are available without charge from Business Service Centers at the General Services Administration Regional Offices in Boston, New York, Washington, DC, Atlanta, Chicago, Kansas City, MO, Fort Worth, Denver, San Francisco, Los Angeles, and Seattle, WA.

(Federal Government activities may obtain copies of Federal Specifications, Standards, and Handbooks and the Index of Federal Specifications and Standards from established distribution points in their agencies.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:20Z
Check the source to verify that this is the current version before use.

Military Standard:

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes.

(Copies of Military Specifications and Standards required by contractors in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publications. The following document forms a part of this specification to the extent specified herein. Unless a specific issue is identified, the issue in effect on date of invitation for bids or request for proposal shall apply.

Joint Committee on Printing Publications.

Government Paper Specification Standards.

(Application for copies should be addressed to the Superintendent of Documents, U.S. Government Printing Office, Washington, D.C. 20402.)

3. REQUIREMENTS.

3.1 Standard sample. The color, formation, and cleanliness, as applicable, shall conform to the standard sample as adopted by the Joint Committee on Printing and as furnished by the contracting officer.

3.2 Material.

3.2.1 Type I. Type I mimeograph paper shall conform to the requirements of B 20, "25 percent White Mimeograph" set forth in the Government Paper Specification Standards.

3.2.2 Type II. Type II mimeograph paper shall conform to the requirements of G 30, "White Mimeograph Bond" set forth in the Government Paper Specification Standards.

3.2.3 Type III. Type III mimeograph paper shall conform to the requirements of B-10, "Mimeograph White and Colored" set forth in the Government Paper Specification Standards.

3.3 Size and trim. Mimeograph paper shall be furnished in the size(s) ordered (see 6.2), and must be flat, trimmed square on four sides with clean, smooth edges, and evenly jogged. Size and trim tolerances shall conform to the requirements set forth in the Government Paper Specification Standards.

3.4 Grain. Direction of the grain on flat paper shall be as ordered (see 6.2).

3.5 Color. Type I and II paper shall be white. Type III shall be white, blue, buff, green, pink, or yellow, as specified (see 6.2).

3.6 Workmanship. All types of paper covered by this specification shall be clean, free from dirt spots, oil spots, shives, foreign matter, and shall be uniform in color. The sheets shall be free from holes, tears, cuts, folds, scuff marks, lint, or loose particles. There shall be no splices within a sheet and there shall be no partial sheets.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsiblity for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified, the supplier may utilize his own facilities or any commercial laboratory acceptable to the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure that supplies and services conform to prescribed requirements.

4.1.1 Inspection. Sampling for inspection shall be performed in accordance with MIL-STD-105, except where otherwise indicated.

4.2 Component and material inspection. In accordance with 4.1 above, components and materials shall be tested in accordance with all the requirements of referenced specifications, drawings, and standards unless otherwise excluded, amended, modified or qualified in this specification or applicable purchase documents.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:20Z
Check the source to verify that this is the current version before use.

4.3 Inspection of the end item.

4.3.1 Sampling. Samples of shipping containers, skids, reams, and sheets of mimeograph paper shall be examined for the defects set forth in the applicable subparagraphs. The inspection levels and acceptable quality levels (AQLs), shall be as indicated below. Each inspection lot sample shall consist of one type, size, and color of mimeograph paper presented for inspection at one time.

TABLE I. Sampling procedure

Examination paragraph	Lot size units	Sample units	Inspection level	AQL percent defective
4.3.1.1	Shipping containers	Shipping container	S-2	1/
4.3.1.2	Reams or 500 sheet units	Reams or 500 sheet units	S-1	--
4.3.1.3	Sheets	Sheet	S-4	1.5
4.3.1.4	As specified in paragraph 4.3.1.4			

1/ Acceptable quality level shall be as specified in PPP-P-25.

4.3.1.1 Examination of preparation for delivery. An examination shall be made to determine that packaging, packing, and marking requirements comply with PPP-P-25, except that the inspection level shall be S-2.

4.3.1.2 Examination of the end item for average count. The average number of sheets per ream, or between markers when skid packed, of all sample units examined shall be not less than the specified quantity. No ream shall be more than 5 percent below the specified quantity.

4.3.1.3 Examination of the end item for dimensional defects. The sample unit for this examination shall be one sheet. The number of sheets comprising the sample size, as specified in table I, for this examination shall be made up by taking two consecutive sheets from one ream or 500 sheet unit when skid packed (to count as two sample units). Examine each sheet.

Examine	Defect
Sheet size	Less than specified in length or width.
Sheet 8-1/2 by 14 inches or less	Oversize by more than 1/16 inch along any edge, from size specified.
Sheets over 8-1/2 by 14 inches	Oversize by more than 1/8 inch along any edge, from size specified.
Squareness	Diagonal variation exceeds 1/32 inch for sheets 32 inches or less in length or exceeds 1/16 inch for sheets over 32 inches in length.
Consecutive sheets 8-1/2 by 14 inches or less	Successive sheets differ from each other by more than 1/64 inch in either dimension.

Source: https://assist.dla.mil -- Downloaded: 2026l0-26T12:20Z
Check the source to verify that this is the currentversion before use.

4.3.1.4 Examination of the end item for visual defects.

4.3.1.4.1 Reams. An examination shall be made for the defects listed in table II, applicable to reams. The lot size for this examination shall be expressed in units of reams of paper and the sample size shall be selected in accordance with level S-2. The acceptable quality level (AQL), for ream defects shall be 2.5 defects per hundred reams. Approximately an equal number of sample reams shall be taken from each of the shipping containers selected in accordance with 4.3.1.1. Sample reams shall be selected from not less than 5 shipping containers.

4.3.1.4.2 Skids. An examination shall be made for the defects listed in table II, applicable to skids. The lot size shall be expressed in units of skids and the sample size shall be selected in accordance with level S-2. The acceptable quality level shall be 2.5 defects per hundred skids.

4.3.1.4.3 Sheets. An examination shall be made for the defects listed in table II, applicable to sheets. The lot size for this examination shall be expressed in units of sheets and the sample size shall be selected in accordance with level S-4. The sheets for this examination shall be accumulated by taking approximately an equal number of sheets, in consecutive order, from each of the reams selected in accordance with 4.3.1.4.1, or the skids selected in accordance with 4.3.1.4.2. The acceptable quality level (AQL), shall be 2.5 defects per hundred sheets for major defects, all types of mimeograph paper and the AQL for minor defects shall be 25 defects per hundred sheets for type I, and 40 defects per hundred sheets for types II and III paper.

TABLE II. Classification of defects

Examination	Defects
Reams or skids, as applicable	
Color and finish	Variation within ream or skid. Variation between reams or skids.
Workmanship, reams and skids only	Wavy edges, uneven, ragged or crushed edges. Torn or partial sheets; spliced sheets.
Sheets	
Major	
Appearance	Presence of creases, wrinkles, tears, or holes larger than 1.5 mm. in area.
Color, finish and formation	Does not compare favorably with the standard sample.
Minor	
Cleanliness	Does not compare favorably with the standard sample with respect to dirt specks larger than 0.5 mm. in area; oil, size, color, or slime spots; foreign matter; lumps; fuzz or loose particles, scabs or scale.

4.3.2 Testing of the end item. The end item shall be tested for the applicable characteristics as specified in section 3 for each lot presented for examination for each type, size, or color of paper. The characteristics tested and methods of testing shall be as specified in the Government Paper Specification Standards. The lot size shall be expressed in units of shipping containers and the inspection level for determining the sample size shall be S-2. The sample unit shall consist of not less than 3000 square inches of paper and not more than one sample unit shall be taken from any one ream or skid. The stock determination shall be performed in duplicate on a composite sample consisting of equal portions of paper from all of the sample units in the sample size. All other determinations shall be applicable to the sample unit. The test report shall include all values upon which the results are based and there shall be no failure to meet the composite or sample unit requirements.

5. PREPARATION FOR DELIVERY

5.1 Packaging, packing and marking. Packaging, packing, and marking shall be level A, B, or C, as specified (see 6.2), and shall be in accordance with PPP-P-25.

Source: https://assist.dla.mil -- Downloaded: 202610-26T12:20Z
Check the source to verify that this is the current version before use.

6. NOTES

6.1 Intended use. The intended use for each type of paper shall be as specified in the Government Paper Specification Standards for the applicable type.

6.2 Ordering data. Purchasers should select the preferred options permitted herein and include the following information in procurement documents.

(a) Title, number, and date of this specification.
(b) Type and size required (see 1.2.1 and 3.3).
(c) Grain direction (see 3.4).
(d) Color (see 3.5).
(e) Pressroom conditions (see 6.3).
(f) Selection of applicable levels of packaging and packing (see 5.1).

6.3 When paper will be used in air-conditioned pressrooms the level of temperature and relative humidity maintained shall be stated in the invitation to bid (see 6.2).

6.4 The Department of Defense has waived coordination of this specification.

MILITARY INTEREST:

User activity:

Army-GL

Preparing Activity:

GSA-FSS

CIVIL AGENCY COORDINATING ACTIVITIES:

COMMERCE-NBS
GSA-FSS
GPO-GPO

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:20Z
Check the source to verify that this is the current version before use.