UU-P-510B
May 17, 1976
SUPERSEDING
Int.Fed.Spec.UU-P-00510a(DSA-DM)
February 2, 1971 and
Fed.Spec. UU-P-510
March 24, 1959

FEDERAL SPECIFICATION

PAPER SHEETING, EXAMINATION-TREATMENT TABLES

This specification was approved by the Commissioner, Federal Supply Service, General Services Administration for the use of all Federal agencies.

1. SCOPE

1.1 This specification covers one type of paper sheeting that is furnished in rolls (see 6.1).

2. APPLICABLE DOCUMENTS

2.1 The following documents, of the issue in effect on date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein:

Federal Specifications:

PPP-B-585 - Boxes, Wood, Wirebound.
PPP-B-601 - Boxes, Wood, Cleated-Plywood.
PPP-B-621 - Boxes, Wood, Nailed and Lock-Corner.
PPP-B-636 - Boxes, Shipping, Fiberboard.

Federal Standards:

Fed. Std. No. 123 - Marking for Shipment (Civil Agencies).

(Activities outside the Federal Government may obtain copies of Federal Specifications, Standards, and Handbooks as outlined under General Information in the Index of Federal Specifications and Standards and at the prices indicated in the Index. The Index, which includes cumulative monthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, US Government Printing Office Washington, DC 20402.

FSC 6530

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:21Z
Check the source to verify that this is the current version before use.

(Single copies of this specification and other Federal Specifications required by activities outside the Federal Government for bidding purposes are available without charge from Business Service Centers at the General Services Administration Regional Offices in Boston, New York, Washington, DC, Atlanta, Chicago, Kansas City, MO, Forth Worth, Denver, San Francisco, Los Angeles, and Seattle, WA.

(Federal Government activities may obtain copies of Federal Specifications, Standards, and Handbooks and the Index of Federal Specifications and Standards from established distribution points in their agencies.

Military Specifications:

MIL-L-10547	Liners, Case, and Sheet, Overwrap; Water-Vaporproof, or Waterproof, Flexible.

Military Standards:

MIL-STD-105	Sampling Procedures and Tables for Inspection by Attributes.
MIL-STD-129	Marking for Shipment and Storage.

(Copies of Military Specifications and Standards required by suppliers in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitation for bids or request for proposal shall apply.

Technical Association of the Pulp and Paper Industry (TAPPI)

T-400 - Sampling a Lot of Paper.
T-403 - Bursting Strength of Paper.
T-404 - Tensile Breaking Strength of Paper and Paperboard.
T-410 - Basis Weight of Paper and Paperboard.
T-411 - Thickness of Paper.
T-414 - Interval Tearing Resistance of Paper.
T-432 - Water Absorption of Bibulous Paper.
T-452 - Brightness of Paper.
T-456 - Wet Tensile Breaking Strength of Paper and Paperboard.
T-457 - Stretch of Paper.

(Application for copies should be addressed to the Technical Association of the Pulp and Paper Industry, 1 Dunwoody Park, Atlanta, GA 30341.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:21Z
Check the source to verify that this is the current version before use.

3. REQUIREMENTS

3.1 First article. When specified in the procurement document, the contractor shall furnish sample unit(s) for first article inspection and approval (see 4.1.2.1 and 6.3).

3.2 Material. The paper sheeting shall be a white, absorbent, 100 percent bleached, kraft paper having a creped or stippled surface.

3.2.1 Physical properties. The paper sheeting shall conform to the following properties, when tested as specified in 4.4.1:

Basis weight, pounds per 500 sheets, 24 by 36 inches; minimum	20
Bursting strength (dry), pounds per square inch (p.s.i.), minimum	7.9
Tearing resistance, grams, minimum:	
Machine direction	25
Cross direction	30
Stretch, Percent	10.5 ± 1.0
Tensile, breaking strength (dry), pounds per inch width, minimum:	
Machine direction	4.5
Cross direction	3.0
Thickness, inch, minimum	0.0040
Tensile breaking strength (wet), machine direction, pounds per inch width, minimum	1.0
Water absorptiveness, 0.1 milliliters of water, seconds, maximum	20
Brightness, points, minimum	80

3.3 Description. The paper sheeting shall be furnished in rolls not more than 3-1/4 inches in diameter. The rolls shall be tightly wound at even tension. The average length of paper contained in the roll shall be 150 feet, ± 1 percent when measured as required in 4.3.2. The paper shall be wound, without breaks, on a suitable cardboard or metal core having an inside diameter sufficiently large to accommodate a 5/8 inch dowel, but not exceeding 1-9/16 inches inside diameter. The width of the roll, including paper and core shall be 17-7/8 +3/16, -0 inches.

3.4 Workmanship. Workmanship shall be first class throughout. Rolls of paper shall be free from defects which detract from their appearance or may impair their serviceability.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:21Z
Check the source to verify that this is the current version before use.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure that supplies and services conform to prescribed requirements.

4.1.1 Records. Records of examinations and tests performed by or for the contractor shall be maintained by the contractor and made available to the Government, upon the Government's request, at any time, or from time to time, during the performance of the contract and for a period of three years after delivery of the supplies to which such records relate.

4.1.2 Inspection. Inspection, as used in this specification, is defined as both examination (such as visual and auditory investigation without the use of special laboratory appliances or procedures) and testing (determination by technical means of physical and chemical properties) of the item.

4.1.2.1 Classification of inspection. The inspection requirements specified herein are classified as follows:

a. First article inspection
b. Quality conformance inspection

4.1.2.1.1 First article inspection. First article inspection shall be performed on six rolls when a first article sample is required (see 3.1). This inspection shall include examination of 4.3, 4.3.1 and 4.3.2 and tests of 4.4.1.

4.1.2.1.2 Quality conformance inspection. Quality conformance inspection shall include the examination of 4.3, 4.3.1 and 4.3.2 and tests of 4.4.1.

4.1.3 Certificates of quality. Certificates of quality, supplied by the manufacturer of the paper sheeting may be furnished in lieu of actual performance of such testing by the contractor, provided lot identity has been maintained and can be demonstrated to the Government. The certificate shall include the name of the contractor, the contract number, the name of the manufacturer or supplier, the NSN, the Item Identification, the name of the component or material, the lot number, the lot size, the sample size, the date of testing, the test method, individual test results, and the specification requirements.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:21Z
Check the source to verify that this is the current version before use.

4.2 Sampling. Unless otherwise specified, unit of inspection shall be one roll of paper.

4.2.1 For examination. Sampling for examination shall be conducted in accordance with MIL-STD-105, and table I.

TABLE I. Sampling for examination

	Inspection level	AQL (percent defective)
For visual examination		
Major defects	S-4	1.0
Total (Major and Minor combined)	S-4	4.0
For dimensional examination	S-3	2.5
Paper length	S-2	(see 4.3.2)

4.2.2 For tests. Not less than 5 percent of the mill-rolls of paper shall be sampled. Sampling shall be in accordance with TAPPI Method T-400. Testing for conformance to the physical properties of 3.2.1 shall be performed in accordance with 4.4.1. Acceptance number shall be zero.

4.3 Examination. The paper sheeting shall be examined to determine compliance with all requirements contained in this specification. Excessive glue on the first or the last foot of paper in the roll shall not be scored in determining acceptance/rejection criteria for the particular lot; but shall not impair use of the remaining paper in the roll. Tears less than 1/4 inch in length and glue spots no larger than 1/4 inch in diameter shall not be considered defects.

4.3.1 Classification of defects. Examination shall be conducted in accordance with the following classification of defects, as shown in table II. Examination shall not be restricted to the classified possible defects listed below.

TABLE II. Classification of defects

Categories	Defects
Major	
101	Not color specified
102	Core not furnished.
Minor	
201	Paper not free of holes, cuts or tears, or glue spots (see 4.3).
202	Paper not supplied in one continuous piece.
203	Paper or core not clean.
204	Rolls not tightly wound.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:21Z
Check the source to verify that this is the current version before use.

4.3.2 Length of paper. The length of paper in the sample rolls shall be measured and shall be averaged. The average shall be 150 feet, ± 1 percent.

4.3.3 Dimensional examination. The paper sheeting shall be examined for defects in dimensions. Any dimension not within the tolerances specified herein shall be classified as a defect.

4.4 Tests. Tests shall be conducted to determine compliance with all requirements contained in this specification.

4.4.1 Physical tests. Physical tests shall be conducted in accordance with standard TAPPI procedures as listed below:

Property	TAPPI Method
Brightness	T-452
Basis Weight	T-410
Bursting Strength	T-403
Tearing Resistance	T-414
Tensile Breaking Strength - Dry	T-404
Tensile Breaking Strength - Wet	T-456
Water Absorptiveness	T-432
Thickness	T-411
Stretch	T-457

4.5 Examination of preparation for delivery. An examination shall be made to determine compliance with the packaging, packing and marking requirements of section 5. Defects shall be scored as specified in table III. Sampling shall be in accordance with MIL-STD-105. The sample unit shall be one container fully prepared for delivery. The lot shall be the number of containers offered for inspection at one time. The inspection level shall be S-2 with AQL of 4.0 expressed in terms of percent defective.

TABLE III. Examination of preparation for delivery

Examine	Defect
Contents	not as specified.
Container	not as specified.
Marking	Omitted; incorrect; illegible; improper size, location, sequence or method of application.
Material	Component missing or damaged.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:21Z
Check the source to verify that this is the current version before use.

4.5.1 Examination of closure, waterproofing and banding of container. When the shipping container is required to comply with PPP-B-636, the examination for defects in closure, waterproofing or banding shall be in accordance with the appendix of the box specification.

5. PREPARATION FOR DELIVERY

5.1 Packaging. Packaging shall be level A or C as specified (see 6.2).

5.1.1 Level A. Each unit, one roll, shall be wrapped in one thickness of paper sheeting and secured by adhesive or tape. As an alternate to the paper wrap, each roll may be furnished in sufficient extra length to permit securing on the end of the roll by adhesive or pressure sensitive tape. When adhesive is used, the adhesive shall not penetrate more than one (1) thickness of paper. Each roll shall be further overwrapped in kraft paper or placed in a paper bag, or polyethylene bag of appropriate size and weight. Wrapper shall be adequately secured to prevent accidental opening and to prevent entrance of dust or other foreign matter. Closure of bag shall be adequate to prevent spilling of contents during normal handling.

5.1.2 Level C. Units shall be packaged in standard commercial containers of the size and kind commonly used, which will afford the degree of protection required for shipment and use of the product for its intended purpose.

5.2 Packing. Packing shall be level A, B, or C as specified (see 6.2).

5.2.1 Level A. Twelve units, packaged as specified in 5.1.1, shall be packed in an exterior container designed for a type 2 load and constructed in accordance with PPP-B-585, class 3, style 3; PPP-B-601, overseas type; PPP-B-621, class 2; or PPP-B-636, class weather-resistant. Closure and strapping shall be as specified in the appendix of the applicable box specification.

5.2.1.1 Case liner. Each level A wood box shall be lined with a waterproof case liner conforming to MIL-L-10547. Closure and sealing shall conform to applicable paragraphs of appendix thereto. Case liner shall not be required for fiberboard boxes. Each fiberboard box shall be waterproofed as specified in the appendix of PPP-B-636.

5.2.2 Level B. Twelve units, packed as specified in 5.1.1, shall be packed in an exterior container designed for a type 2 load and constructed in accordance with PPP-B-585, class 1, style 3; PPP-B-601, domestic type; PPP-B-621, class 1; or PPP-B-636, class domestic. Closure shall be as specified in the appendix of the applicable box specification.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:21Z
Check the source to verify that this is the current version before use.

5.2.3 Level C. The subject commodity shall be packed in substantial commercial containers of the type, size, and kind commonly used for the purpose, so constructed as to insure acceptance and safe delivery by common or other carriers, at the lowest rate, to point of delivery called for in the contract or purchase order.

5.3 Marking.

5.3.1 Civil agencies. Marking for shipment shall be in accordance with FED-STD-123.

5.3.2 Military activities.

5.3.2.1 Interior packages. Each interior package shall be marked in accordance with MIL-STD-129. Contract or purchase order number and name of contractor shall be shown.

5.3.2.2 Exterior container. Exterior container shall be marked in accordance with MIL-STD-129.

6. NOTES

6.1 Intended use. The paper covered by this specification is intended for use with cabinet type examining tables to provide a clean surface for patients.

6.2 Ordering data. Purchasers should select the preferred options permitted herein and include the following information in procurement documents.

a. Title, number and date of this specification.
b. Selection of applicable levels of packaging and packing (see 5.1 and 5.2).
c. When first article is required (see 3.1); all Department of Defense activities, see 6.3.
d. When specific test facilities are required (see 4.1).

6.3 First article. When a first article is required, it shall be tested and approved under the appropriate provisions of 7-104.55 of the Armed Services Procurement Regulation. The contract or purchase order specifies the quantity, procedure for delivery and other specific instructions for inspection and approval of the first article.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:21Z
Check the source to verify that this is the current version before use.

6.4 This specification covers the following item appearing in the Federal Supply Catalog:

National Stock Number	Item Identification
6530-00-786-4790	PAPER SHEETING, EXAMINATION-TREATMENT TABLES, 18 inch, 50 yards.

MILITARY CUSTODIANS:
Army - MD
Navy - MS
Air Force - 03

Preparing activity:
DSA-DM

Civil Agency Coordinating Activities:
VA-DMS
GSA-FSS
COM-NBS
Project No. 6530-1343

Orders for this publication are to be placed with General Services Administration, acting as an agent for the Superintendent of Documents. See section 2 of this specification to obtain extra copies and other documents referenced herein. Price 35 cents each.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:21Z
Check the source to verify that this is the current version before use.

FOLD

Defense Personnel Support Center
2800 South 20th Street
Philadelphia, PA 19101

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300

POSTAGE AND FEES PAID
DEFENSE SUPPLY AGENCY
DoD - 304



Defense Personnel Support Center
Directorate of Medical Materiel
ATTN: DPSC-ATT
2800 South 20th Stteet
Philadelphia, PA 19101

FOLD

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:21Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

OMB Approval
No. 22-R255

INSTRUCTIONS: The purpose of this form is to solicit beneficial comments which will help achieve procurement of suitable products at reasonable cost and minimum delay, or will otherwise enhance use of the document. DoD contractors, government activities, or manufacturers/ vendors who are prospective suppliers of the product are invited to submit comments to the government. Fold on lines on reverse side, staple in corner, and send to preparing activity. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements. Attach any pertinent data which may be of use in improving this document. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity.

DOCUMENT IDENTIFIER AND TITLE

UU-P-510B PAPER SHEETING, EXAMINATION-TREATMENT TABLES

NAME OF ORGANIZATION AND ADDRESS

CONTRACT NUMBER

MATERIAL PROCURED UNDER A

☐ DIRECT GOVERNMENT CONTRACT ☐ SUBCONTRACT

1. HAS ANY PART OF THE DOCUMENT CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE?

A. GIVE PARAGRAPH NUMBER AND WORDING.

B. RECOMMENDATIONS FOR CORRECTING THE DEFICIENCIES

2. COMMENTS ON ANY DOCUMENT REQUIREMENT CONSIDERED TOO RIGID

3. IS THE DOCUMENT RESTRICTIVE?

☐ YES ☐ NO *(If "Yes", in what way?)*

4. REMARKS

SUBMITTED BY *(Printed or typed name and address - Optional)*

TELEPHONE NO.

DATE

DD FORM 1 JAN 72 1426

REPLACES EDITION OF 1 JAN 66 WHICH MAY BE USED

☆ GPO 1974—603-680/6126 2-1

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:21Z
Check the source to verify that this is the current version before use.