UU-P-547J
Amendment-4
April 30, 1977
SUPERSEDING
Amendment-3
May 23, 1975

FEDERAL SPECIFICATION

PAPER, TELETYPEWRITER, ROLL

This amendment, which forms a part of Federal Specification UU-P-547J, dated July 17, 1972, was approved by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal agencies.

PAGE 2

Paragraph 3.1, delete and substitute:

"3.1 Material. Materials used shall conform to the requirements specified herein. Materials not definitely specified shall be of a quality used for the purpose in commercial practice. No polychlorinated biphenyls (PCB's) shall be added or used during the manufacture of the paper or in any coating operation on the base paper. As evidence of compliance, the contractor shall submit a certificate stating that no polychlorinated biphenyls have been added or used during the manufacturing or converting operations (see 4.1.2.2)."

PAGE 3

Delete Table I and substitute:

TABLE I. Physical requirements

Types	Classes	Grades, Styles and Plies	Basis weight, (pounds, 17x22-1000, ± 5 percent)	Caliper or thickness, (inches)	Tear strength, average, grams, not less than: Machine direction	Tear strength, average, grams, not less than: Cross direction
I and II	1	Grade A, all plies	36	0.0030-0.0044	28	36
I and II	1	Grade B, all plies	36	.0030- .0044	26	34
I	2	Grade A	32	.0030- .0038	24	32
I	2	Grade B	32	.0030- .0038	24	30
I	3	Top sheet	32	.0030- .0038	20	22
I	3	Auto-copy sheets	26	.0015- .0025	18	18
I	4	First sheet	32	.0030- .0038	20	20
I	4	Inner plies	18	----------	--	--
I	5	Grade A, first sheet	24.6-35.7 1/	.0026- .0042	18	21
I	5	Grade A, inner plies	24.6-38.9 1/	.0025- .0042	15	20
I	5	Grade A, bottom sheet	26.6-36.0 1/	.0022- .0035	18	21
I	5	Grade B, first sheet	28	.0031- .0038	18	22
I	5	Grade B, inner plies	32	.0031- .0038	18	22
I	5	Grade B, bottom sheet	30	.0022- .0035	18	22
I	6	Style A, first sheet white	28.4-33.6 1/	.0027- .0035	20	25
I	6	Style A, first sheet colored	28.4-33.6 1/	.0027- .0035	20	20
I	6	Style A, inner plies	20.8-30.0 1/	.0023- .0041	14	16
I	6	Style B, all plies	20.9-28.0 1/	.0023- .0041	14	16

1/ Tolerance does not apply.

PAGE 4

Paragraph 3.5, last sentence, delete and substitute: "The signal shall be not less than 1/4 inch wide and shall start within five feet of the core and continue for an additional length of five to ten feet. The signal shall not impair the legibility of the copy printed on the paper."

FSC 7530

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:21Z
Check the source to verify that this is the current version before use.

PAGE 5

Delete Table II and substitute:

TABLE II. Length (in feet) of paper on 5-inch diameter rolls

Copies	Class 1	Class 2	Class 3	Class 4	Class 5	Class 6	
						Style A	Style B
1	325	---	---	---	---	---	368
2	---	165	240	209	195	198	179
3	---	100	172	130	125	128	122
4	---	70	134	95	93	94	91
5	---	---	109	75	73	75	72
6	---	---	92	---	60	62	60
7	---	---	80	---	51	52	51
8	---	---	71	---	45	46	45
9	---	---	63	---	39	40	40

Paragraph 3.5.2.1, delete and substitute:

3.5.2.1 Type II. The 12-1/2 inch width type II roll shall have a diameter of not less than 15 inches and not more than 15-1/8 inches. The 8-25/64 inch width type II roll shall have a length of not less than 325 feet and a diameter of not more than 5 inches.

PAGE 8

In table IV, in the "Test methods" column, change "4.4.3" to "4.4.2" and change "4.4.3.2" to "4.4.2.3".

PAGE 9

Paragraph 4.4.2.3, delete and substitute:

4.4.2.3 Copyability. After examination of the message copy in accordance with 4.4.2 and 4.4.2.1, prepare a copy of the original and all copies of the message on Xerox model 7000 copier, in good operating condition. All letters and words on all of the xerographic copies shall be readily distinguishable for the lot to be considered acceptable.

Paragraph 5.3, delete last sentence, and substitute:

'When specified, the shipping container shall be marked "Store in cool place".'

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:21Z
Check the source to verify that this is the current version before use.