MIL-C-40129B(GL)
28 April 1970
SUPERSEDING
MIL-C-40129A(GL)
24 September 1963

MILITARY SPECIFICATION

CLOTH, BATISTE, COTTON, POLISHING

1. SCOPE

1.1 Scope.- This specification covers the requirements for bleached cotton batiste cloth.

1.2 Classification.- The cloth shall be of one type and the following classes as specified (see 6.2):

Class 1 - Rolls

Class 2 - Cut pieces

2. APPLICABLE DOCUMENTS

* 2.1 The following documents of the issue in effect on date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein.

SPECIFICATIONS

FEDERAL

PPP-B-636 - Box, Fiberboard
PPP-P-1134 - Packaging and Packing of Cotton and Cotton-Synthetic Fiber Blend Fabrics (Excluding Duck Fabrics)

STANDARDS

FEDERAL

FED-STD-4 - Glossary of Fabric Imperfections
FED-STD-191 - Textile Test Methods

FSC 8305

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T19:18Z
Check the source to verify that this is the current version before use.

MILITARY

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes
MIL-STD-129 - Marking for Shipment and Storage

(Copies of specifications and standards required by suppliers in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting office.)

2.2 Other publications.- The following documents form a part of this specification to the extent specified herein. Unless otherwise specified, the issue in effect on date of invitation for bids or request for proposal shall apply.

Rules and Regulations Under the Textile Fiber Products Identification Act

(Copies may be obtained without charge from the Federal Trade Commission, Washington, D.C. 20580.)

NATIONAL MOTOR FREIGHT TRAFFIC ASSOCIATION, INC.

National Motor Freight Classification

(Application for copies should be addressed to American Trucking Associations, ATTN: Tariff Order Section, 1616 P Street, N.W., Washington, D.C. 20036.)

UNIFORM CLASSIFICATION COMMITTEE

Uniform Freight Classification

(Application for copies should be addressed to the Uniform Classification Committee, Room 202 Union Station, 516 W. Jackson Blvd., Chicago, Illinois 60606.)

3. REQUIREMENTS

3.1 Yarn.- The cotton used in the manufacture of the yarn shall be combed and spun into singles yarn for both the warp and filling.

* 3.2 Physical requirements.- The finished cloth shall conform to the requirements shown in table I when tested as specified in 4.4.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T19:18Z
Check the source to verify that this is the current version before use.

TABLE I.- Physical requirements

Weight per square yard	Yarns per inch (minimum)		Breaking strength (minimum)	
Maximum, ounces	Warp	Filling	Warp	Filling
			Pounds	Pounds
1.9	75	70	32	20

3.2.1 Weave.- The weave shall be plain: one up and one down.

3.2.2 Width (class 1 only).- Unless otherwise specified, the finished cloth shall be a minimum of 39-1/2 inches inclusive of selvages (see 6.2).

3.3 Finish.- The cloth shall be closely singed on both sides, desized, bleached white and mercerized.

* 3.3.1 Nonfibrous material content.- The starch and protein content including chloroform-soluble and water-soluble material of the finished cloth shall not exceed 2.0 percent when tested as specified in 4.4.

* 3.3.2 pH.- The pH value of the finished cloth shall be no less than 5.5 nor more than 8.5 when tested as specified in 4.4.

3.4 Length, class 1, rolls.- Unless otherwise specified (see 6.2), the cloth shall be in one continuous length of not less than 50 yards and shall be put up on rolls as specified in PPP-P-1134 (see 5.1).

3.5 Class 2, cut pieces.- The cloth shall be cut into 4 by 6 inch pieces (± 1/4 inch tolerance) with the four edges pinked. Pinking of selvage edge is not required. The measurement to be from the extreme outside point on one side to the opposing indentation on the other side.

* 3.6 Fiber identification.- Each roll (class 1) or set-up box (class 2) shall be labeled, ticketed, or invoiced for fiber content in accordance with the Rules and Regulations Under the Textile Fiber Products Identification Act.

* 3.7 Workmanship.- The finished cloth shall conform to the quality and grade of product established by this specification. For class 1 cloth, the points per 100 square yards shall not exceed the established point value. The occurrence of defects for class 2 cloth shall not exceed the acceptable quality levels (AQLs) specified.

4. QUALITY ASSURANCE PROVISIONS

* 4.1 Responsibility for inspection.- Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or order, the supplier may use his own or any other

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T19:18Z
Check the source to verify that this is the current version before use.

facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.1.1 Certificate of compliance.- Where certificates of compliance are submitted, the Government reserves the right to check test such items to determine the validity of the certification.

4.2 Inspection.- Sampling for inspection shall be performed in accordance with MIL-STD-105, except when otherwise indicated hereinafter.

* 4.2.1 Component and material inspection.- In accordance with 4.1 above, components and materials shall be tested in accordance with all the requirements of referenced specifications, drawings and standards unless otherwise excluded, amended, modified or qualified in this specification or applicable procurement documents.

4.2.2 Examination of the end item.- Examination of the end item shall be in accordance with 4.2.2.1 through 4.2.3.

* 4.2.2.1 Yard-by-yard examination (class 1).- Each roll in the sample shall be examined on one side only. When the total yardage in the roll does not exceed 100 yards, the entire yardage in the roll shall be examined. When the total yardage in the roll exceeds 100 yards, only 100 yards shall be examined. All defects, as defined in Section I of FED-STD-4, which are clearly noticeable at normal inspection distance (3 feet) shall be scored and assigned demerit points as listed in 4.2.2.1.1 except that only those slubs and knots which exceed the limits shown on figure 3 of FED-STD-4 shall be scored. No linear yard (increments of 1 yard on the measuring device of the inspection machine) from any one roll within the sample shall be penalized more than 4 points. The sample size shall be 20 rolls selected from 20 containers. The lot shall be unacceptable if the points per 100 square yards of the total yardage examined exceeds 30 points. The lot shall be unacceptable if the points per 100 square yards of two or more individual rolls exceeds 45 points. If one roll exceeds 45 points per 100 square yards, a second sample of 20 rolls shall be examined only for individual roll quality examination. The lot shall be unacceptable if one or more rolls in the second sample exceeds 45 points per 100 square yards. Point computation for lot quality and individual roll quality shall be as follows:

$$\frac{\text{Total points scored in sample} \times 3600}{\text{Contracted width of cloth (inches)} \times \text{total yards inspected}} = \text{Points per 100 square yards}$$

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T19:18Z
Check the source to verify that this is the current version before use.

4.2.2.1.1 Demerit points.- Demerit points shall be assigned as follows:

For defects up to 3 inches in any dimension	- one point
For defects exceeding 3 inches, but not exceeding 6 inches in any dimemsion	- two points
For defects exceeding 6 inches, but not exceeding 9 inches in any dimemsion	- three points
For defects exceeding 9 inches in any dimemsion	- four points

The following defects, when present, shall be scored four points for each yard in which they occur:

Overall uncleanness
Width less than specified
Not closely singed on both sides
Excessive neppiness

4.2.2.2 Examination for length.-

4.2.2.2.1 Individual rolls.- During the yard-by-yard examination, each roll in the sample shall be examined for length. Any length found to be less than the minimum specified or more than two yards less than the length marked on the ticket shall be considered a defect with respect to length. The lot shall be unacceptable if two or more rolls in the sample are defective in respect to length.

4.2.2.2.2 Total yardage in sample.- The lot shall be unacceptable if the total of the actual lengths of rolls in the sample is less than the total of the lengths marked on the ticket.

4.2.2.3 Examination for compliance with the Rules and Regulations Under the Textile Fiber Products Identification Act.- During the yard-by-yard examination, each roll in the sample shall be examined for compliance with the Textile Fiber Products Identification Act. Each roll not labeled in accordance with this act shall be a defect. The lot shall be unacceptable if two or more of these defects occur.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T19:18Z
Check the source to verify that this is the current version before use.

4.2.3 Class 2, cut pieces.- The sample unit for this examination shall be one piece and shall be inspected on one side. The acceptable quality level shall be 6.5 percent defective. The sample size shall be based upon level II of MIL-STD-105. The number of bags from which the sample is to be selected shall be in accordance with table II. An approximate equal number of pieces shall be examined from each bag in the sample. The required number of pieces shall be inspected and the visual defects classified as follows:

Hole, cut or tear
Smash
Multiple broken yarns
Hitch-back, 1/2 inch or more in combined warp and filling direction
Kink or knot
Edges not pinked
Spot, stain*
Float or skips - Multiple, 1/2 inch or more in combined directions
Slub, slug or gouts - Exceeding the maximum acceptable limits shown in figure 3 of FED-STD-4
Any rough raised surface*
Any dimension less than specified

* Clearly visible at normal inspection distance (approximately 3 feet).

TABLE II.- Sample size

Lot size in cut pieces	Sample size bags
1300 or less	7
1301 up to and including 3200	10
3201 up to and including 8000	15
8001 up to and including 22,000	25
22,001 up to and including 110,000	35
110,001 and over	50

4.3 Examination of preparation for delivery requirements.-

4.3.1 Rolls.- An examination shall be made in accordance with the provisions of PPP-P-1134 to determine that packaging, packing and marking complies with the section 5 requirements of this specification.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T19:18Z
Check the source to verify that this is the current version before use.

4.3.2 Cut pieces (class 2).- An examination shall be made to determine that packaging, packing and marking complies with the requirements of the applicable specification. Defects shall be scored in accordance with the list below. The sample unit shall be one shipping container fully prepared for delivery with the exception that it need not be sealed. Defects of closure listed below shall be examined on shipping containers fully prepared for delivery. The lot size shall be the number of shipping containers in the end item inspection lot. The inspection level shall be S-2 and the AQL shall be 2.5 defects per hundred units.

Examine	Defect
Marking (exterior and interior)	Omitted, incorrect, illegible, of improper size, location, sequence or method of application.
Material	Any component missing. Any component damaged, affecting serviceability.
Workmanship	Inadequate application of components, such as: incomplete closure of container flaps; improper taping; loose strapping; inadequate stapling. Bulging or distortion of containers. Open and noncontinuous heat sealed seams and closure of polyethylene bag.
Contents	Number of boxes per container is more or less than specified. 1/ Number of bags per box is more or less than specified. 1/ Number of cut pieces per bag is more or less than specified. 1/

1/ For these defects, four boxes shall be examined from each shipping container in the sample and one bag shall be examined from each box.

* 4.4 Testing.- The methods of testing specified in FED-STD-191 wherever applicable and as listed in table III shall be followed. The physical and chemical values specified in section 3 apply to the result of the determinations made on a sample unit for test purposes as specified in the applicable test methods. The sample unit shall be 1 yard, full width of the finished cloth. The sample size (number of sample units) shall be as shown in the list below. The lot shall be unacceptable if one or more sample units fail to meet any test requirement specified. All test reports shall contain the individual values utilized in expressing the final result.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T19:18Z
Check the source to verify that this is the current version before use.

Lot size (yard and cut pieces)	Sample size
800 or less	2
801 up to and including 22,000	3
22,001 and over	5

TABLE III.- Test methods

Characteristic	Requirement paragraph	Test method
Material (cotton yarn)	3.1	1/
Yarn ply:		
Warp	3.1	Visual 2/
Filling	3.1	Visual 2/
Weight	3.2	5041
Yarns per inch:		
Warp	3.2	5050
Filling	3.2	5050
Breaking strength:		
Warp	3.2	5100
Filling	3.2	5100
Weave	3.2.1	Visual 2/
Mercerization	3.3	Microscopic examination for swelling of cotton 1/
Nonfibrous material	3.3.1	2611
pH	3.3.2	2811

1/ Unless otherwise specified, a certificate of compliance shall be submitted and will be acceptable for the stated requirement.

2/ One determination shall be made from each sample unit and the results reported as "pass" or "fail".

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T19:18Z
Check the source to verify that this is the current version before use.

5. PREPARATION FOR DELIVERY

5.1 Rolls of cloth.-

5.1.1 Put-up and packaging.- Put-up and packaging shall be level A or C as specified (see 6.2).

5.1.1.1 Levels A and C.- The cloth shall be put-up and packaged in accordance with the applicable requirements of PPP-P-1134.

5.1.2 Packing.- Packing shall be level A, B, or C as specified (see 6.2).

5.1.2.1 Levels A, B and C.- The cloth shall be packed in accordance with the applicable requirements of PPP-P-1134.

5.1.3 Marking.- In addition to any special marking required by the contract or order, interior packages and shipping containers shall be marked in accordance with PPP-P-1134.

5.2 Cut pieces of cloth.-

5.2.1 Packaging.- Packaging shall be level A or C as specified (see 6.2).

5.2.1.1 Level A.- One hundred cloth pieces shall be evenly stacked one on another and inserted in a snug fitting clear polyethylene film bag of 0.0015 inch thickness (± 20 percent tolerance). The polyethylene bag shall be formed with heat sealed seams that are straight and continuous and parallel to each other and the formed edges of the bag. Prior to or during the heat sealing closure operation, excess air within the bag shall be expelled. Five bags shall then be packaged in a snug-fitting folding or set-up paperboard box, and the box secured with gummed paper tape.

5.2.1.2 Level C.- Cloth pieces shall be packaged to afford adequate protection against physical damage during shipment from the supply source to the first receiving activity. The supplier may use his standard practice when it meets this requirement.

5.2.2 Packing.- Packing shall be level A, B, or C, as specified (see 6.2).

5.2.2.1 Level A.- Eighteen thousand cloth pieces, packaged as specified in 5.2.1, shall be packed in a snug-fitting fiberboard shipping container conforming to style RSC, grade V2s of PPP-B-636. Level A boxes shall be packed flat, three in length, four in width and three in depth, with the length of the boxes parallel to the length of the shipping container. Each shipping container shall be closed, waterproofed and reinforced in accordance with the appendix of the container specification.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T19:18Z
Check the source to verify that this is the current version before use.

5.2.2.2 Level B.- Eighteen thousand cloth pieces, packaged as specified in 5.2.1, shall be packed in a snug-fitting fiberboard shipping container conforming to style RSC, type CF (variety SW) or SF, class domestic, grade 275 of PPP-B-636. Level A boxes shall be packed flat, three in length, four in width, and three in depth, with the length of the boxes parallel to the length of the shipping container. Each shipping container shall be closed in accordance with method II as specified in the appendix of the container specification.

5.2.2.2.1 When specified (see 6.2), the shipping container shall be a grade V3c, V3s or V4s fiberboard box fabricated in accordance with PPP-B-636 and closed in accordance with the appendix of the container specification.

5.2.2.3 Level C.- Cloth pieces, packaged as specified in 5.2.1, shall be packed in a manner to insure carrier acceptance and safe delivery at destination at the lowest transportation rate for such supplies. Containers shall be in accordance with Uniform Freight Classification Rules or National Motor Freight Classification Rules, as applicable.

5.2.3 Marking.- In addition to any special marking required by the contract or order, interior packages and shipping containers shall be marked in accordance with MIL-STD-129.

5.2.3.1 Polyethylene bagged packages.- Polyethylene bagged packages shall have the required information legibly printed or stamped in black directly on the bag across the center face or on a white paper label inserted within the bag so as to permit ready identification. The bag or label shall indicate the following information:

STOCK NUMBER
ITEM DESCRIPTION
QUANTITY

6. NOTES

6.1 Intended use.- The cloth covered by this specification is intended to be used for cleaning and polishing coated optics.

6.2 Ordering data.- Procurement documents should specify the following:

(a) Title, number, and date of this specification.
(b) Class required.
(c) Width of class 1, if other than specified (see 3.2.2).

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T19:18Z
Check the source to verify that this is the current version before use.

(d) When minimum length or roll put-up is other than specified (see 3.4).
(e) Selection of applicable levels of put-up packaging and packing (see 5.1.1, 5.1.2, 5.2.1 and 5.2.2).
(f) When weather-resistant grade fiberboard shipping containers are required for level B packing (see 5.2.2.2.1).

6.3 .The margins of this specification are marked with an asterisk to indicate where changes (additions, modifications, corrections, deletions) from the previous issue were made. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and suppliers are cautioned to evaluate the requirements of this document based on the entire content irrespective of the marginal notations and relationship to the last previous issue.

Custodian:

Army - GL

Preparing activity:

Army - GL

Project No. 8305-A955

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T19:18Z
Check the source to verify that this is the current version before use.

FOLD

DEPARTMENT OF THE ARMY
U. S. Army Natick Laboratories
Natick, Massachusetts 01760

POSTAGE AND FEES PAID
DEPARTMENT OF THE ARMY

OFFICIAL BUSINESS

Commanding General
U. S. Army Natick Laboratories
ATTN: AMXRES-EQS
Natick, Massachusetts 01760

FOLD

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T19:18Z
Check the source to verify that this is the current version before use.

SPECIFICATION ANALYSIS SHEET

Form Approved
Budget Bureau No. 22-R255

INSTRUCTIONS: This sheet is to be filled out by personnel, either Government or contractor, involved in the use of the specification in procurement of products for ultimate use by the Department of Defense. This sheet is provided for obtaining information on the use of this specification which will insure that suitable products can be procured with a minimum amount of delay and at the least cost. Comments and the return of this form will be appreciated. Fold on lines on reverse side, staple in corner, and send to preparing activity. Comments and suggestions submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or serve to amend contractual requirements.

SPECIFICATION
Cloth, Batiste, Cotton, Polishing MIL-C-40129B(GL)

ORGANIZATION

CITY AND STATE

CONTRACT NUMBER

MATERIAL PROCURED UNDER A
☐ DIRECT GOVERNMENT CONTRACT ☐ SUBCONTRACT

1. HAS ANY PART OF THE SPECIFICATION CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE?
   A. GIVE PARAGRAPH NUMBER AND WORDING.

   B. RECOMMENDATIONS FOR CORRECTING THE DEFICIENCIES

2. COMMENTS ON ANY SPECIFICATION REQUIREMENT CONSIDERED TOO RIGID

3. IS THE SPECIFICATION RESTRICTIVE?
   ☐ YES ☐ NO *(If "yes", in what way?)*

4. REMARKS *(Attach any pertinent data which may be of use in improving this specification. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity)*

SUBMITTED BY *(Printed or typed name and activity - Optional)*

DATE

DD FORM 1 JAN 66 1426 REPLACES EDITION OF 1 OCT 64 WHICH MAY BE USED.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T19:18Z
Check the source to verify that this is the current version before use.