MIL-F-40132G
30 September 1985
SUPERSEDING
MIL-F-40132F
13 June 1974

MILITARY SPECIFICATION

FRAME SECTIONS, TENT, MAINTENANCE, MEDIUM, LIGHT METAL

This specification is approved for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This document covers the sections of the medium, light metal, maintenance tent frame with auxiliary lighting and guying equipment. The end section provides for 8 feet (two end bays each 4 feet) in length and each intermediate section provides for an additional 8 feet in length of frame.

1.2 Classification. Sections of the frame shall be classified as follows (see 6.2):

End section.
Door section.
Intermediate section.

2. APPLICABLE DOCUMENTS

* 2.1 Government documents. Unless otherwise specified, the following documents of the issue in effect on date of invitation for bids or request for proposal form a part of this document to the extent specified herein.

Beneficial comments (recommendations, additions, deletions) and any pertinent data that may be of use in improving this document should be addressed to U.S. Army Natick Research and Development Center, Natick, MA 01760-5014, by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

FSC 8340

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T19:19Z
Check the source to verify that this is the current version before use.

SPECIFICATIONS

FEDERAL

L-P-410	- Plastic, Polyamide (Nylon), Rigid: Rods, Tubes, Flats, Molded and Cast Parts
W-C-440	- Clip, Electrical, General Specification For
QQ-B-654	- Brazing Alloys, Silver
QQ-M-31	- Magnesium Alloy, Bars, Rods, and Special Shaped Sections, Extruded
QQ-M-38	- Magnesium Alloy Die Castings (AZ91A)
QQ-M-44	- Magnesium Alloy Plate and Sheet (AZ31B)
QQ-M-55	- Magnesium Alloy, Permanent and Semi-Permanent Mold Castings
QQ-M-56	- Magnesium Alloy, Sand Castings
QQ-P-35	- Passivation Treatments for Corrosion-Resisting Steel
QQ-S-571	- Solder, Tin Alloy: Tin-Lead Alloy; and Lead Alloy
QQ-S-698	- Steel, Sheet and Strip, Low-Carbon
QQ-S-763	- Steel Bar Wire, Shape and Forging, Corrosion-Resisting
QQ-W-423	- Wire, Steel, Corrosion-Resisting
QQ-W-470	- Wire, Steel, Carbon, Spring, Music
TT-E-529	- Enamel, Alkyd, Semigloss
TT-P-1757	- Primer Coating, Zinc Chromate, Low Moisture Sensitivity
WW-T-825	- Tube, Magnesium-Alloy, Extruded
PPP-B-601	- Boxes, Wood, Cleated-Plywood
PPP-B-621	- Boxes, Wood, Nailed and Lock-Corner
PPP-B-636	- Boxes, Shipping, Fiberboard
PPP-B-640	- Boxes, Fiberboard, Corrugated, Triple-Wall
PPP-S-760	- Strapping, Nonmetallic (and Connectors)
PPP-T-60	- Tape: Packaging, Waterproof

MILITARY

MIL-P-116	- Preservation, Methods Of
MIL-M-3171	- Magnesium Alloy, Processes for Pretreatment and Prevention of Corrosion On
MIL-T-7928	- Terminals, Lug: Splice, Conductor: Crimp Style, Copper, General Specification For
MIL-R-17343	- Rope, Nylon
MIL-C-26074	- Coatings, Electroless Nickel, Requirement For
MIL-C-52950	- Crates, Wood, Open and Covered

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T19:19Z
Check the source to verify that this is the current version before use.

STANDARDS

FEDERAL

FED-STD-151 - Metals: Test Methods

MILITARY

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes
MIL-STD-129 - Marking for Shipment and Storage
MIL-STD-1186 - Cushioning, Anchoring, Bracing, Blocking and Waterproofing; with Appropriate Test Methods

DRAWINGS

U.S. ARMY NATICK RESEARCH AND DEVELOPMENT CENTER

5-4-581 - Frame Sections, Tent, Maintenance, Medium, Light Metal; Assembly, Complete
5-4-582 - Arch Assemblies and Details
5-4-583 - Door Post Assemblies and Details
5-4-584 - Purlin and End Arch Purlin Assemblies and Details and Anchor Castings
5-4-585 - Door Winch and Transom Chord Assemblies and Details
5-4-586 - Door Spar and Bracket Assemblies and Details
5-4-587 - Captive End Fittings, Eyebolt and Chain, and Guy Assemblies and Details
5-4-588 - Wiring Harness Assembly, Details and Illustration
5-4-957 - Alternate Purlin Assembly
5-4-1213 - Miscellaneous Alternate Castings
5-4-1239 - Alternate Arch Joint Castings

(Copies of documents required by manufacturers in connection with specific acquisition functions should be obtained from the contracting activity or as directed by the contracting officer.)

* 2.2 Other publications. Unless otherwise specified, the following documents of the issue in effect on date of invitation for bids or request for proposal form a part of this document to the extent specified herein.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T19:19Z
Check the source to verify that this is the current version before use.

UNDERWRITERS' LABORATORIES, INC. (UL)

Standard No. 62 - Flexible Cord and Fixture Wire

(Application for copies should be addressed to the Underwriters' Laboratories, Inc., 333 Pfingsten Road, Northbrook, IL 60062.)

NATIONAL FIRE PROTECTION ASSOCIATION (NFPA)

Standard No. 70 - National Electric Code

(Application for copies should be addressed to the National Fire Protection Association, 60 Batterymarch Street, Boston, MA 02269.)

AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM)

A 108 - Steel Bars, Carbon, Cold Finished, Standard Quality
A 575 - Merchant Quality Hot Rolled Carbon Steel Bars
A 582 - Free-Machining Stainless and Heat-Resisting Steel Bars, Hot-Rolled or Cold-Finished
E 8 - Tension Testing of Metallic Materials
E 9 - Compression Testing of Metallic Materials At Room Temperature
E 18 - Rockwell Hardness and Rockwell Superficial Hardness of Metallic Materials
D 3951 - Standard Practice for Commercial Packaging

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.)

(Technical society and technical association documents are generally available for reference from libraries. They are also distributed among technical groups and using Federal agencies.)

2.3 Order of precedence. In the event of conflict between the text of this document and the references cited herein, the text of this document shall take precedence.

3. REQUIREMENTS

3.1 First article. When specified, a sample shall be subjected to first article inspection (see 4.3, 6.2, and 6.3).

3.2 Standards. Flexible cords and fixture wire shall comply with the applicable requirements of UL Standard No. 62.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T19:19Z
Check the source to verify that this is the current version before use.

3.2.1 Compliance. Prior to approval of the first article, if one is submitted, or prior to commencing production, the contractor shall submit to the contracting officer or his authorized representative satisfactory evidence that all flexible cords and fixture wire he proposes to furnish under this document meet the applicable requirements of UL Standard No. 62.

3.2.1.1 UL. Acceptable evidence of meeting the requirements of UL shall be a UL listing mark or a certified test report from a recognized independent testing laboratory acceptable to the Government, indicating that the flexible cords and fixture wire have been tested and conform to UL Standard No. 62.

* 3.3 Materials and components. Materials and components shall be as specified herein and on applicable drawings. Materials not definitely specified shall be of the quality normally used by the manufacturer, provided the completed item complies with all provisions of this document. Recycled material may be used (see 6.4).

3.3.1 Carbon steel.

3.3.1.1 Sheet and strip. Carbon steel sheet and strip shall conform to any quality, temper, and finish of QQ-S-698.

3.3.1.2 Bar.

* 3.3.1.2.1 Hot rolled. Hot rolled carbon steel bar shall conform to ASTM A 575.

* 3.3.1.2.2 Cold finished. Cold finished carbon steel bar shall conform to ASTM A 108.

3.3.1.3 Wire, spring. Carbon steel spring wire shall conform to QQ-W-470.

3.3.2 Corrosion-resisting steel.

* 3.3.2.1 Bar. Corrosion-resisting steel shall conform to class 304 or 410 (as shown on applicable drawing), condition A, round form, and any finish of QQ-S-763 or to type 303 or 416 (as shown on applicable drawing), any condition, round form, and any finish of ASTM A 582.

3.3.2.2 Wire. Corrosion-resisting steel wire shall conform to type I, composition 302 or 304, condition A of QQ-W-423.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T19:19Z
Check the source to verify that this is the current version before use.

3.3.3 Magnesium alloy.

3.3.3.1 Castings. Identification marking of castings is not required.

a. Die castings (AZ91A) shall conform to QQ-M-38.

b. Permanent and semipermanent mold castings shall conform to composition AZ63A or AZ91C, temper T4, of QQ-M-55.

c. Sand castings shall conform to alloys AZ63A or AZ91C, temper T4, of QQ-M-56.

3.3.3.2 Bar, rod and special shaped section, extruded. Magnesium alloy extruded bar, rod and special shaped section shall conform to composition AZ31B or ZK60A-T5 of QQ-M-31 as specified on applicable drawing.

3.3.3.3 Plate and sheet. Magnesium alloy plate and sheet shall conform to composition AZ31B, condition O or H24, of QQ-M-44 as specified on applicable drawing.

* 3.3.3.4 Tube, extruded. Extruded magnesium alloy tube shall conform to the composition and condition specified in the applicable drawings. Where tube is required to conform as extruded alloy AZ31B, it shall conform to composition AZ31B of WW-T-825. Where tube is required to be extruded and cold worked commercial AZ31B-H26, it shall conform to the chemical requirements of table I when tested as specified in 4.6.1 and the mechanical requirements of table II when tested as specified in 4.6.2 and 4.6.3. At the option of the contractor, extruded commercial ZK40B-T5 magnesium alloy may be used as an equivalent for the extruded and cold worked AZ31B-H26 magnesium alloy, provided items that require forming be processed in the following sequence: Forming is to be done at room temperature; within 12 hours after forming, the components are to be loaded into a temperature controlled oven and raised to a temperature of 350°F, then held at that temperature for a minimum of one hour. After removing the heat source, the oven is to remain closed for not less than two hours before opening for product removal. This stress relief procedure is necessary to reestablish the T5 condition. The chemical composition of extruded ZK40B-T5 magnesium alloy items shall conform to the percentages specified in table I when tested as specified in 4.6.1, and the minimum mechanical properties shall conform to table II when tested as specified in 4.6.2 and 4.6.3.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T19:19Z
Check the source to verify that this is the current version before use.

TABLE I. Chemical requirements

Ingredient	Composition (percent)	
	AZ31B-H26	ZK40B-T5
Aluminum	2.5 - 3.5	---
Manganese	0.20 (minimum)	---
Zinc	0.7 - 1.3	3.5 - 4.5
Silicon	0.05 (maximum)	---
Copper	0.05 (maximum)	---
Nickel	0.005 (maximum)	---
Iron	0.005 (maximum)	---
Calcium	0.04 (maximum)	---
Zirconium	---	0.45 (minimum)
Other impurities	0.30 (maximum)	0.30 (maximum)
Magnesium	Remainder	Remainder

TABLE II. Mechanical requirements

Criteria	Requirement
Ultimate tensile strength	36,000 psi
Tensile yield strength	34,000 psi
Elongation in 2 inches	4%
Compressive yield strength	20,000 psi

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T19:19Z
Check the source to verify that this is the current version before use.

3.3.4 Solder, tin alloy. Tin alloy solder shall conform to composition Sn60 of QQ-S-571.

3.3.5 Brazing alloy, silver-base. Silver-base brazing alloy shall conform to grade IV or VI of QQ-B-654.

3.3.6 Clip, electrical, jaw grip. Jaw grip electrical clip shall conform to type PC, item No. 2, of W-C-440.

3.3.7 Rollers, nylon. Nylon rollers shall conform to composition polyhexamethylene adipamide (nylon 6/6) and natural without fillers as specified in L-P-410 except that the material need only meet the specific gravity, melting point, and tensile strength requirements.

3.3.8 Rope, nylon. Nylon rope shall conform to MIL-R-17343 except that only the circumference and breaking strength tests shall be required.

3.3.9 Bolts, nuts, rivets, threaded inserts, and washers. The bolts, nuts, rivets, threaded inserts, and washers shall be of the materials, type, and size specified on the drawings. Where steel is specified, the part shall be cadmium plated in accordance with the manufacturer's standard practice for commercial items. Where corrosion-resisting steel threaded components are specified (i.e., items 2-10, 5-20, 5-28, 7-2, 7-3, 8-2, 8-3, 11-2, 11-8, 14-2, 15-1, 16-1, 28-2, 32-2, stud and threaded insert of Drawing 5-4-957), the components shall be passivated in accordance with QQ-P-35.

3.3.10 Primer. Primer shall conform to composition G or L, as applicable, color Y, of TT-P-1757.

3.3.11 Enamel. Enamel shall conform to class A or B, composition G or L, as applicable, olive drab color No. 24087 of TT-E-529. Identification bands shall be of colors and location identified on drawings.

3.3.12 Alternate components. Components offered as equivalent to components specified herein and on the referenced drawings as specific manufacturer's part number or equal shall be functionally equal, of equal or better quality, with the manufacturer's part number identified. The incorporation and inclusion of such a component in the design of the specified end product shall not require modification or change to any other specified component and shall not reduce ease of maintenance to it or any other components, unless such modification or change is specifically approved by the contracting officer. Prior to manufacture of the preproduction first article or, if none is required, prior to commencing production, the contractor shall submit for the contracting officer's approval a list identifying each proposed

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T19:19Z
Check the source to verify that this is the current version before use.

alternate component, together with proof that each listed component complies with requirements specified herein. The contracting officer, at his written option, may require a physical sample of the proposed substitution. Approval of the submitted listing, together with necessary supporting data, authorizes the commencement of first article or production manufacture as applicable and does not relieve the contractor of the responsibility that these components perform in accordance with specified requirements when incorporated into the end product.

3.4 Design. The frame sections are designed to provide a 20-foot wide by 14-foot high tent frame. The frame is expandable up to 64 feet in length overall by increasing the number of intermediate sections. The end section provides for 8 feet (two end bays each of 4 feet) in length, and each intermediate section provides for an additional 8 feet in length of frame.

3.5 Construction. The construction of the frame sections shall conform to Drawings 5-4-581 through 5-4-588, 5-4-957, 5-4-1213, and 5-4-1239, and as specified herein. A single magnesium casting may be used at the option of the contractor for the following, providing that casting design, material, and dimensions are submitted and approved by the contracting officer or his authorized representative prior to fabrication of the first article (when one is required) or the initial production unit:

a. Diecasting for item 4-7 of Drawing 5-4-582, items 5-7, 6-7, 5-25 and 6-25 of Drawing 5-4-583, items 12-1 and 13-1 of Drawing 5-4-584.

b. Combined items 12-1 with 12-2 or items 13-1 with 13-2 of Drawing 5-4-584 and items 20-7 with 20-16 of Drawing 5-4-585.

c. Casting of items 18-2 and 19-2 of Drawing 5-4-586.

3.5.1 Sections.

3.5.1.1 End. Each end section provides for 8 feet (two end bays each 4 feet) in length of frame. The end section shall consist of the following:

a. Two (2) end arch assemblies complete with RH and LH anchor assemblies, captive end fitting assemblies, eye-nut and chain assemblies, RH and LH bracket assemblies, slotted end arch joints, long and short arch fillers, safety bolt, ring and chain assemblies.

b. One (1) intermediate arch assembly.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T19:19Z
Check the source to verify that this is the current version before use.

c. Four (4) end arch purlin assemblies.

d. Thirteen (13) purlin assemblies, short (4 feet) with male and female ends.

e. Thirteen (13) purlin assemblies, short (4 feet) with female ends.

f. One (1) wiring harness assembly consisting of a circuit breaker assembly and a lighting and outlet assembly.

g. Six (6) guy assemblies.

h. One (1) arch spacer assembly.

i. Two (2) wrenches.

3.5.1.2 Door. The door section shall consist of the following:

a. Door post assemblies, 2 right and 2 left.

b. Two (2) door winch and transom chord assemblies, including 2 door winch shaft assemblies with 4 cable and toggle pin assemblies.

c. Eight (8) door spar assemblies.

The door spar, transom chord, and door winch assemblies shall be capable of operation with an applied pull of 35 pounds or less without any binding when tested as specified in 4.6.4. Chain assembly shall not be permanently kinked.

3.5.1.3 Intermediate. Each intermediate section provides for 8 feet in length of frame. The intermediate section shall consist of the following:

a. One (1) intermediate arch assembly complete with safety bolt, ring and chain assemblies, and plain end arch joints.

b. Thirteen (13) long (8 feet) purlin assemblies.

c. One (1) lighting and outlet assembly.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T19:19Z
Check the source to verify that this is the current version before use.

3.5.2 Wiring harness assembly. The wiring harness assembly shall conform to the applicable requirements of the National Electrical Code. The wiring harness assembly of the end section and the lighting and outlet assembly of the intermediate section, as applicable, shall be capable of conducting electrical power and shall have electrical continuity without any open circuit when tested as specified in 4.6.5.

3.5.2.1 Switch, circuit breaker. The switch shall be a double pole circuit breaker incorporating thermal magnetic operating mechanisms, rated at 15 amperes for use on 120 - 240 volts, alternating current. The switch shall be designed for manual resetting after tripping and shall be housed in a general purpose type I box, surface mounted enclosure, modified as shown on Drawing 5-4-588. The outer surface of the cover of the switch housing shall be plainly marked with the words "ALTERNATING CURRENT ONLY" by decal or by stencil, using a white or orange colored enamel. The letters shall be distinct and legible from a minimum distance of 8 feet.

3.5.2.2 Cord, electric. The electric cord shall consist of three rubber-covered copper wires, size No. 14 American Wire Gage (AWG) flexible standard conductors. The cord shall be rated 600 volts and shall conform to the Underwriters' Standard for type S.O.

3.5.2.3 Lighting and outlet assembly. The lighting and outlet assembly shall be in accordance with Drawing 5-4-588, fabricated with electric cord specified in 3.5.2.2, and of molded connectors, light and outlet sockets, and tie junctions. The molded composition of the connectors, light and outlet sockets, and tie junctions shall be polychloroprene. All molding shall be integral with and bonded to the cable. All cable molding shall be accomplished without cutting or splicing of the No. 14 AWG 3-conductor cable main feed line. The lamp and utility sockets, tie junctions, and connectors of the wiring harness shall be soldered with tin alloy solder as specified in 3.3.4 or crimp spliced in accordance with the tensile requirements of MIL-T-7928. All connection components shall be interchangeable as shown on applicable drawings.

3.5.3 Castings.

3.5.3.1 AZ91A. Where magnesium alloy AZ91A is specified for castings on applicable drawings, the castings shall conform to 3.3.3.1.a. Anchor die castings (items 4-7, 5-7, 6-7, 12-1 and 13-1 of Drawing 5-4-584), when applicable, shall be cast with the 7/8-inch diameter holes cast in place. The 0.312-inch diameter, 7/16-inch diameter and the 1/2-inch diameter holes shall be either cast in place or drilled at assembly. Reaming of holes will be

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T19:19Z
Check the source to verify that this is the current version before use.

allowed for tolerance control, where applicable. The anchor die casting shall weigh a minimum of 90 percent of its theoretical solid weight when tested as specified in 4.6.7.

3.5.3.2 AZ63A-T4. Where magnesium alloy AZ63A-T4 is specified for castings on applicable drawings, the castings shall conform to 3.3.3.1.b or 3.3.3.1.c.

3.5.3.3 AZ91C-T4. Where magnesium alloy AZ91C-T4 is specified for castings on applicable drawings, the castings shall conform to 3.3.3.1.b or 3.3.3.1.c.

3.5.4 Welding. All welding shall be complete, sound, smooth, uniform, and free from excess welding material, burn-through area, pits, slag inclusion, porosity, crack, fracture, weld spatter, flash, and excess flux deposit. On items requiring magnesium alloy ZK60A-T5 to be welded to either AZ31B, AZ31B-H26 or ZK40B-T5, a maximum of three cracked or fractured welds will be permitted because of the inherent difficulties that may be encountered. All other weldments not employing ZK60A-T5 shall be free of any cracks or fractures. Rough or projecting edges shall be ground smooth prior to finishing.

3.5.5 Soldering and brazing. All soldered and brazed joints shall be complete, sound, smooth, and clean, and shall be free from pin holes and flux residue.

3.5.6 Riveting. All rivets shall be securely and neatly set by heading, peening, or upsetting the ends.

* 3.6 Finish of frame sections. All burrs, rough and sharp edges shall be ground smooth or removed prior to finishing. The roller shaft and compression spring (items 10-4 and 10-6 of drawing 5-4-586) shall be electroless nickel coated in accordance with MIL-C-26074 as follows:

a. Roller shaft (10-4) shall be given a class 1, grade A coating.

b. Compression spring (10-6) shall be given a stress-relief heat treatment prior to cleaning and a class 2, grade A coating.

Prior to assembly, interior and exterior surfaces of magnesium alloy members shall be treated in accordance with type I or III of MIL-M-3171. All assembled arch joints, safety bolts, threads of studs, bolts, collars, adjustment shafts, and threaded inserts of arches, purlins, and door posts shall be protected from primer and paint by a protective covering or closure. All other exposed (exterior) surfaces shall be coated with primer as specified in 3.3.10. All primed surfaces shall be thoroughly coated with enamel as

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T19:19Z
Check the source to verify that this is the current version before use.

specified in 3.3.11. The coating shall level out to an adherent continuous uniform film and shall be free from blisters, peeling, flaking, area of no film or thin film, scratch, dig, abrasion, gouges, soft run, dirt or foreign matter imbedded in finish, and wet or tacky paint. The contractor shall touch up areas of finish damaged during examination, erection, and disassembly of the frame sections.

3.7 Marking for identification. The lower right segment of each end arch assembly, the lower segments of each intermediate arch assembly, and each right door post assembly shall be permanently and distinctly stamped or marked for identification. The letters "US" shall be in characters a minimum of one inch in height. The name of the manufacturer or brand or mark of such known character as to be identifiable with the manufacturer and the number and year of contract shall be in characters a minimum of 1/2 inch in height. Any other brands or marks identified on the frame sections shall be as specified on applicable drawings.

3.8 Workmanship. Components of the frame sections shall be free from split, puncture, malformation, deformation, and fracture and shall not be bent out of shape. The oval sleeves of the guy assembly and arch spacer assembly shall be securely compressed and free from looseness. The ends of wire in the cable shall not protrude beyond the compressed sleeve. Threads of studs, bolts, nuts, collars, adjustment shafts, and threaded inserts of arches, purlins, and door posts shall not be stripped or damaged. Screws, drive screws, and spring pins shall be secured and completely driven. Heads of bolts shall be pulled up tight to surfaces. Nuts shall be drawn up tightly. Chains shall be free of any permanent kink. All components of the frame shall be free of burrs, rough or sharp edges, and any nonspecified holes. The inside of components shall be free of any chips that could cause interference at assembly.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the document where such inspections are deemed necessary to ensure that supplies and services conform to prescribed requirements.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T19:19Z
Check the source to verify that this is the current version before use.

4.2 Classification of inspection. The inspection requirements specified herein are classified as follows:

a. First article inspection (see 4.3).
b. Quality conformance inspection (see 4.4).

4.3 First article inspection. When a first article is required, the frame sections shall be examined as specified in 4.4.3.1, 4.4.3.2, and 4.4.3.3 and tested as specified in 4.4.3.4. The presence of any visual defect, dimension not within specified requirements, erection defect, or any failure to pass applied tests shall be cause for rejection of the first article.

4.4 Quality conformance inspection. Unless otherwise specified, sampling for inspection shall be performed in accordance with MIL-STD-105.

4.4.1 Component and material inspection. In accordance with 4.1, components and materials shall be inspected in accordance with all the requirements of referenced documents unless otherwise excluded, amended, modified, or qualified in this document or applicable purchase documents.

4.4.1.1 Component testing. In addition to the quality assurance provisions of the referenced documents, testing shall be performed on components listed in table III for the test characteristics shown.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T19:19Z
Check the source to verify that this is the current version before use.

TABLE III. Component tests

Component and lot expressed in terms of	Characteristic	Requirement paragraph or drawing	Test method paragraph	No. det. per sample unit	Sample unit	Results reported as numerically
Magnesium tube, extruded and cold worked AZ31B-H26 or extruded ZK40B-T5 1/	Chemical composition	3.3.3.4	4.6.1	1 for each element (composite)	1/	To nearest 0.01%
2/	Ultimate tensile strength	3.3.3.4	4.6.2	1	2/	To nearest 100 psi
2/	Tensile yield strength 0.2% offset	3.3.3.4	4.6.2	1	2/	To nearest 100 psi
2/	Elongation in 2 inches	3.3.3.4	4.6.2	1	2/	To nearest 0.5%
2/	Compression yield strength 0.2% offset	3.3.3.4	4.6.3	1	2/	To nearest 100 psi
Shaft, adjustment, (item 11-2) 3/	Hardness Rockwell C26-33	5-4-584	4.6.6	3	1 shaft	Average of 3 determinations to nearest Rockwell scale reading

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T19:19Z
Check the source to verify that this is the current version before use.

TABLE III. Component tests - Continued

Component and lot expressed in terms of	Characteristic	Requirement paragraph or drawing	Test method paragraph	No. det. per sample unit	Sample unit	Results reported as numerically
Stud of captive end arch fitting assembly (item 14-2) 3/	Hardness Rockwell C26-33	5-4-587	4.6.6	3	1 stud	Average of 3 determinations to nearest Rockwell scale reading
Stud of captive doorpost fitting assembly (item 28-2) 3/	Hardness Rockwell C26-33	5-4-587	4.6.6	3	1 stud	Average of 3 determinations to nearest Rockwell scale reading
Stud of alternate purlin assembly 3/	Hardness Rockwell C26-33	5-4-957	4.6.6	3	1 stud	Average of 3 determinations to nearest Rockwell scale reading
Anchor die casting 4/	Porosity	3.5.3.1	4.6.7	1	1 anchor die casting	To nearest 0.5%

1/ A lot shall consist of each 4,000 pounds or less of extruded magnesium tube offered for inspection at one time. One test sample shall be selected from each lot for composition analysis inspection. The presence of any defect shall be cause for rejection of the lot represented by the sample.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T19:19Z
Check the source to verify that this is the current version before use.

TABLE III. Component tests - Continued

2/ For the purposes of mechanical properties inspection, the number of samples required shall be as follows:

a. For material having a nominal weight of less than 1 pound per linear foot, one test sample shall be selected from each lot of 500 pounds or less. For lots greater than 500 pounds, one additional sample shall be selected for each 1,000 pounds or fraction thereof in excess of the first 500 pounds.

b. For material having a nominal weight of 1 pound or more per linear foot, one test sample shall be selected from each lot of 500 feet or less. An additional sample shall be selected for each 1,000 feet or fraction thereof in excess of the first 500 feet.

The presence of any defect shall be cause for rejection of the lot represented by the sample.

3/ For the purposes of Rockwell Hardness inspection, a lot shall be the number of adjustment shafts of end arch purlin assembly, studs of captive end arch fitting assembly, studs of captive doorpost fitting assembly or studs of alternate purlin assembly, as applicable, offered for inspection at one time. The inspection level shall be S-2 and the AQL shall be 4.0.

4/ For the purposes of porosity inspection, a lot shall be the number of anchor die castings submitted for inspection at one time. The inspection level shall be S-2 and the AQL shall be 4.0.

4.4.2 In-process inspection.

* 4.4.2.1 Process examination. Examination shall be made of the fabrication processes in table IV to establish conformance with specified requirements. Whenever nonconformance is noted, correction shall be made to the process and all items processed.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T19:19Z
Check the source to verify that this is the current version before use.

TABLE IV. Fabrication process requirements

Requirement, operation, or assembly	Requirement reference
Wiring, harness assembly complies with the National Electric Code	3.5.2
The lamp and utility sockets, tie junctions, and connectors of the wiring harness are soldered or crimp spliced	3.5.2.3
Anchor die castings (4-7, 5-7, 6-7, 12-1, and 13-1), when applicable, are cast with the 7/8-inch diameter holes cast in place	3.5.3.1 and Drawing 5-4-584
Welds are complete, sound, smooth, uniform, and free from excess welding material, burn-through area, pits, slag inclusion, porosity, crack, fracture, weld spatter, flash, and excess flux deposit; a maximum of 3 cracked or fractured welds will be acceptable in the weldment of the Post Brace (5-38) to the Doorpost (5-37). Rough and projecting welded edges are ground smooth prior to finishing.	3.5.4 and Drawing 5-4-583
Burrs, rough and sharp edges are ground smooth or removed prior to finishing	3.6
Interior and exterior surfaces of magnesium alloy members are treated	3.6
Primer was applied before application of enamel	3.6

4.4.3 End item inspection. The inspection lot shall be all of end sections, door sections, or intermediate sections, as applicable, submitted for inspection at one time. The sample unit for this inspection shall be one end section, door section, or intermediate section, as applicable.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T19:19Z
Check the source to verify that this is the current version before use.

4.4.3.1 Visual examination. The frame sections shall be examined for the defects listed in table V. The inspection level shall be I, with an acceptable quality level (AQL) of 15 for major defects and 100 for major and minor defects combined, expressed in terms of defects per hundred units.

TABLE V. Classification of visual defects

Examine	Defect	Category	
		Major	Minor
Finish of exposed (exterior) surfaces (except protected surfaces) 1/	Not finished		201
	Color of finish is not as specified		202
	Coating is not adherent or not uniform (e.g., is blistered, peeled, or flaky)		203
	Area of no film:		
	a. bare metal showing in area greater than 1 square inch	101	
	b. bare metal showing in area 1 square inch or less		204
	Primer shows through (area of thin film)		205
	Scratch, dig, abrasion or gouge exposing bare metal:		
	a. greater than 2 inches in length	102	
	b. 2 inches or less in length		206
	Scratch, dig, abrasion, or gouge exposing primer		207
	Soft run		208
	Dirt or foreign matter imbedded in finish		209
	Finish is not dry (i.e., wet or tacky to touch)		210

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T19:19Z
Check the source to verify that this is the current version before use.

TABLE V. Classification of visual defects - Continued

Examine	Defect	Category	
		Major	Minor
Construction and workmanship	Component missing	103	
	Component is not specified type or size		211
	Any part or component not fabricated of applicable referenced material		212
	Component is split, punctured, malformed, deformed, fractured, or bent out of shape:		
	a. affecting serviceability	104	
	b. not affecting serviceability		213
	Oval sleeve is loose or not securely compressed (end section only):		
	a. guy assembly	105	
	b. arch spacer		214
	Ends of wire in cable protrude beyond the compressed sleeve (end section only)		215
	Threads of stud, bolt, nut collor, adjustment shaft, or threaded insert of purlin or doorpost are stripped or damaged		216
	Screw, drive screw, or spring pin not secure or not completely driven		217
	Head of bolt not pulled up tight to surface		218
	Nut not drawn up tightly (e.g., can be removed by hand		219
	Permanent kink in chain (door section only)		220
	Burrs, rough or sharp edges, or non-specified hole on any component		221
	Chain contains more or less than the required number of links		222
	Inside of components are not free of chips which could cause interference at assembly		223

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T19:19Z
Check the source to verify that this is the current version before use.

TABLE V. Classification of visual defects - Continued

Examine	Defect	Category	
		Major	Minor
Construction and workmanship (continued)	Corners not rounded where required		224
	Polychloroprene molding not integral with or not bonded to the cable		225
	Main feed line cable is cut or spliced	106	
	Lighting and outlet assembly connection components are not interchangeabe		226
Protected surfaces	Assembled arch joints, safety bolts, threads of studs, bolts, collars, adjustments shafts, and threaded inserts of purlins and doorposts not protected with covering or closure (e.g., evidence of primer or enamel)		227
Welding	Missing where required	107	
	Not type specified	108	
	Incomplete or not sound		228
	Not smooth or not uniform		229
	Excess welding material not removed		230
	Burn-through area, pits, or porous		231
	Slag inclusion but weld is sound		232
	Crack, fracture or otherwise not fused (except a maximum of 3 cracked or fractured welds will be acceptable in the weldment of the Post Brace (5-38) to the Doorpost (5-37))		233
	Weld spatter		234
	Flash or excess flux deposit has not been removed		235
Soldering and brazing	Missing where required	109	
	Incomplete		236
	Not sound, not smooth, or not clean		237
	Pin holes or flux residue		238

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T19:19Z
Check the source to verify that this is the current version before use.

TABLE V. Classification of visual defects - Continued

Examine	Defect	Category	
		Major	Minor
Riveting	Rivet not securely set		239
	Rivet not neatly set		240
Marking (including identification, color, and other special markings)	Missing, illegible, misspelled, misplaced, incorrect, or not applied in specified manner		241
	Not specified size or color		242
	Cover of switch housing marking is not distinct and legible from a minimum distance of eight feet		243

1/ Defects in finish attributable to flexing of movable joints during examination will not be scored as a defect. However, the contractor shall touch up areas of finish damaged during examination.

4.4.3.2 Dimensional examination. The frame sections shall be examined for compliance with dimensions specified. Any dimension not within the specified requirements shall be classified as a defect. The inspection level shall be S-1 with an AQL of 15, expressed in terms of defects per hundred units.

4.4.3.3 Examination of frame sections for defects in erection. Erection examination shall be made of the frame sections for the defects listed in table VI. The inspection level shall be S-1 with an AQL of 6.5, expressed in terms of defects per hundred units.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T19:19Z
Check the source to verify that this is the current version before use.

TABLE VI. Examination for defects in erection.

Examine	Defect
Assembly 1/	Any assembly that cannot be connected or joined with companion assembly (i.e., assembling requires realignment of parts, drilling or enlargement of holes, use of drift pin or other mechanical means) Special tool is required to effect assembly Component is too loose or does not fit properly in mating components Component is out of alignment

1/ The contractor shall touch up areas of finish damaged during erection and disassembly of the frame sections.

4.4.3.4 Testing of the end item. The door spar, transom chord, and door winch assemblies of the door section shall be tested as specified in 4.6.4. The wiring harness assembly of the end section and the lighting and outlet assembly of the intermediate section, as applicable, shall be tested as specified in 4.6.5. The inspection level shall be S-2 with an AQL of 4.0 expressed in terms of defects per hundred units.

4.4.4 Packaging inspection. An inspection shall be made to determine that preservation, packing, and markings are in compliance with section 5 of this document. Defects shall be as specified in table VII. The sample unit for this inspection shall be one shipping container fully packaged. The lot shall be the number of containers offered for inspection at one time. The inspection level shall be S-2 with an AQL of 25, expressed in terms of defects per hundred units.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T19:19Z
Check the source to verify that this is the current version before use.

TABLE VII. Packaging inspection

Examine	Defect
Markings (exterior and interior)	Missing; incorrect; incomplete; illegible; of improper size, location, sequence, or method of application
Materials	Any nonconforming component, component missing, damaged, or otherwise defective
Preservation	Frame section not cleaned and dried as specified Preservative on roller chain missing or not properly applied
Workmanship	Thread protection missing Eye-bolts, eye-nuts, safety bolts, or eye-pins not secured to the arch as specified Doorpost assembly not locked in the closed position Door control arm and door control arm diagonal not folded folded together and secured as specified Door cable not coiled on winch and secured as specified Endless chain not coiled and secured as specified Strut on door winch and transom chord assembly not positioned as specified and nuts resecured Guy or arch spacer assembly not coiled and secured as specified Cords of the circuit breaker assembly not coiled as specified Lighting and outlet assembly not coiled as specified Skids missing, when applicable Inadequate cushioning and anchoring Bulged or distorted container
Packing	Number of components per container is more or less than required
Fiberboard container, as applicable.	Not class or style specified Skids or base missing Skid or base lumber not size specified Skids not grooved when required Skid not secured to box or base boards as specified Washers missing under nail head when required Strapping size and application not as specified Buckles used

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T19:19Z
Check the source to verify that this is the current version before use.

4.5 Certificate examination. Certificates of compliance, certified test reports, approval labels, or listing marks for codes and standards, as applicable, that are submitted as proof of compliance with the document requirements shall be examined and validated.

4.6 Tests.

4.6.1 Composition analysis of extruded and cold worked commercial AZ31B-H26 magnesium alloy tube or extruded commercial ZK40B-T5 magnesium alloy tube. The composition analysis of extruded and cold worked commercial AZ31B-H26 magnesium alloy tube or extruded commercial ZK40B-T5 magnesium alloy tube shall be determined in accordance with Method 111 or 112 of FED-STD-151. Any failure to meet the composition analysis requirements as specified in 3.3.3.4 shall be classified as a defect.

4.6.2 Tension tests. The ultimate tensile strength, tensile yield strength, and elongation of the extruded and cold worked commercial AZ31B-H26 magnesium alloy tube or extruded commercial ZK40B-T5 magnesium alloy tube shall be tested in accordance with ASTM E 8. Tensile yield strength shall be measured at 0.2 percent offset. Failure to meet either the ultimate tensile strength, tensile yield strength, or elongation test requirements as specified in 3.3.3.4 shall be classified as a defect.

4.6.3 Compression test. The compressive yield strength of the extruded and cold worked commercial AZ31B-H26 magnesium alloy tube or extruded commercial ZK40B-T5 magnesium alloy tube shall be tested in accordance with ASTM E 9. Compressive yield strength shall be measured at 0.2 percent offset. Failure to meet the compressive yield strength test requirement as specified in 3.3.3.4 shall be classified as a defect.

4.6.4 Operational test. The operation of the door spar, transom chord, and door winch assemblies of the door section shall be tested by applying a pull on the chain of no more than 35 pounds. Any door spar, transom chord, or door winch assembly binding or not capable of operation with a pull of 35 pounds or less as specified in 3.5.1.2 shall be classified as a defect.

4.6.5 Electrical continuity test. The wiring harness assembly of the end section, and the lighting and outlet assembly of the intermediate section shall be tested for electrical continuity by means of bulbs, bells, or voltmeter. Any circuit breaker assembly or lighting and outlet assembly not capable of conducting electrical power or one that has an open circuit as specified in 3.5.2 shall be classified as a defect.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T19:19Z
Check the source to verify that this is the current version before use.

4.6.6 Hardness test. The Rockwell hardness of the adjustment shaft of end arch purlin assembly, stud of captive end arch fitting assembly, stud of captive doorpost fitting assembly, and stud of alternate purlin assembly shall be tested in accordance with ASTM E 18. Any average of the three hardness readings not meeting the hardness requirements specified on Drawings 5-4-584, 5-4-587, and 5-4-957 shall be classified as a defect.

4.6.7 Porosity test. Weigh the die casting test specimen in air to determine its actual weight and record to the nearest 0.1 gram. Immerse the die casting test specimen into a container of water capable of measuring the volume of the die casting test specimen by the water displacement method. Determine the volume of the die casting test specimen and record to the nearest cubic centimeter. Multiply the volume in cubic centimeters by 1.81 (specific gravity of AZ91A) to calculate the theoretical solid weight in grams. Divide the actual weight of the die casting test specimen in air by the calculated theoretical solid weight. Record the result to the nearest 0.1 percent. Any die casting test specimen weighing less than 90 percent of its theoretical solid weight shall be classified as a defect.

5. PACKAGING

5.1 Preservation. Preservation shall be level A or Commercial as specified (see 6.2).

5.1.1 Level A.

5.1.1.1 Disassembly. Each frame section shall be unit packed knocked down (KD). Disassembly shall be such as to facilitate reassembly in the field.

* 5.1.1.2 Preservation application.

a. Each frame section shall be cleaned in accordance with process C-1 and dried in accordance with any drying procedure of MIL-P-116.

b. Each roller chain of the hoist assembly shall be coated with type P-2 or P-6 preservative in accordance with MIL-P-116.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T19:19Z
Check the source to verify that this is the current version before use.

5.1.1.3 Unit packing.

5.1.1.3.1 Arches. The threads of the eye bolts and projecting screws shall be protected by commercial thread protectors or by means of cushioning material secured with minimum one-inch tape conforming to either type III or IV, class I of PPP-T-60. The eye-bolts, eye-nuts, safety bolts, and eye-pins shall be secured to the arch with jute, sisal, manila or cotton twine.

5.1.1.3.2 Doorpost assembly. Each doorpost top assembly shall be locked in the closed position. Each door control arm shall be disassembled from the top post gusset. The door control arm and the door control arm diagonal shall then be folded together down against the doorpost into the door control arm lock and secured to the doorpost by wrapping and tying with the control arm rope. Exposed threads of the captive doorpost fitting shall be protected by thread protectors or cushioning as specified in 5.1.1.3.1.

5.1.1.3.3 Door winch and transom chord assembly. The door cables shall be coiled onto their respective winch shafts and secured with annealed wire minimum 0.06 inch diameter (16 gage). Each endless chain shall be coiled and secured in place with annealed wire specified herein. The two struts on the door winch and transom chord assembly shall be positioned parallel to the transom chord and the nuts resecured.

5.1.1.3.4 Guy assemblies, arch spacer assembly, and wrenches. Each guy assembly and arch spacer assembly shall be compactly coiled and secured with tape, specified in 5.1.1.3.1; or jute, sisal, manila, and cotton twine; or paper or plastic and metal wire; or placed in a minimum 0.001 inch thick polyethylene bag. The bag shall be securely closed with a paper or plastic and metal wire tie. Six guy assemblies, one arch spacer assembly, and the two wrenches, shall then be unit packed in a fiberboard box conforming to W5c or W5s, style RSC of PPP-B-636, and the box waterproofed with tape in accordance with the appendix thereto.

5.1.1.3.5 Circuit breaker assembly. The attached cords of the circuit breaker assembly shall be compactly coiled. One circuit breaker assembly shall be unit packed in a fiberboard box and the box waterproofed as specified in 5.1.1.3.4.

5.1.1.3.6 Lighting and outlet assembly. Each lighting and outlet assembly shall be compactly coiled and unit packed in a fiberboard box, and the box waterproofed as specified in 5.1.1.3.4.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T19:19Z
Check the source to verify that this is the current version before use.

* 5.1.2 Commercial. Components of each frame section shall be preserved in accordance with ASTM D 3951.

5.2 Packing. Packing shall be level A or B as specified (see 6.2).

5.2.1 Level A packing.

* 5.2.1.1 End section. Components of each end section (see 3.5.1.1), preserved as specified in 5.1, shall be packed in one or two shipping containers conforming to either overseas type, style A or B, type 3 load of PPP-B-601; or class 2, style 2 or 4, type 3 load of PPP-B-621; or type II, style A of MIL-C-52950. When two containers are used, two end arch assemblies and one intermediate arch assembly shall be packed in one of the shipping containers and the remaining components of the end section shall be packed in the other shipping container. Each shipping container having a gross weight of over 250 pounds shall be provided with skids as specified in the applicable container document. The contents of each container shall be cushioned and anchored in accordance with MIL-STD-1186. Nonmetallic strapping may be used to secure components. Each shipping container shall be closed and strapped in accordance with the appendix of the applicable container document.

5.2.1.2 Door section. Components of each door section (see 3.5.1.2), preserved as specified in 5.1, shall be packed in a shipping container conforming to either overseas type, style A or B, type 3 load of PPP-B-601, or class 2, style 2 or 4, type 3 load of PPP-B-621. The contents shall be cushioned and anchored as specified in 5.2.1.1. Each shipping container shall be provided with skids as specified in the applicable container document. Closure and strapping of the shipping container shall be in accordance with the appendix of the applicable container document.

5.2.1.3 Intermediate section. Components of each intermediate section (see 3.5.1.3), preserved as specified in 5.1, shall be packed in a shipping container, closed, strapped, and provided with skids as specified in 5.2.1.1. The contents of each shipping container shall be cushioned and anchored as specified in 5.2.1.1.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T19:19Z
Check the source to verify that this is the current version before use.

* 5.2.2 Level B packing. Components of each section (see 3.5.1), preserved as specified in 5.1, shall be packed as specified in 5.2.2.1 and 5.2.2.2 for the respective section. Alternatively, shipping containers conforming to domestic type, style A, B, or I, type 3 load of PPP-B-601; type II, style A of MIL-C-52950; or class 1, style 2 or 4, type 3 load of PPP-B-621 may be used. The alternate containers shall be provided with skids.

5.2.2.1 End and door section. Components of each end or door section shall be packed in one shipping container conforming to class 2, style C of PPP-B-640 and be provided with a wood base. The contents of each container shall be cushioned and anchored as specified in 5.2.1.1. The base shall be made with a minimum of 4 nominal 1 by 4 inch members equally spaced under and full length of the container and secured to 4 nominal 3 by 4 inch cross skids, 2 skids spaced not more than 6 inches and not less than 4 from each end of the container and the third and fourth equidistant. Nailing of the 1 by 4's to the skids shall be with not less than two 8d common nails diagonally at each intersection of the base boards with the skids. The fiberboard box bottom shall be secured to the base with not less than 8 nails uniformly spaced and fitted with minimum 1-inch diameter flat metal washers. The base shall be of sufficient width to support the top when in place. The top shall be secured to the container and the base by a minimum of 4 nonmetallic straps encircling the container and base with one placed adjacent to the outer edge of each outer skid and one adjacent to each of the other skids. The straps shall be tightened to indent the fiberboard without cutting into the edge. The nonmetallic strap shall have a minimum thickness of 0.025 inch, breaking strength of 900 lb, and shall conform to type II or III of PPP-S-760. Buckles shall not be used on strapping.

5.2.2.2 Intermediate section. Components of each intermediate section shall be packed in one shipping container conforming to class 2, style C of PPP-B-640 and provided with 5 cross skids. The contents of each container shall be cushioned and anchored as specified in 5.2.1.1. The skids shall be placed one at each end of the bottom of the box and three equidistant between the end skids. The skids shall be nominal 3 by 4 inch lumber grooved full length along the bottom of the skid to accept strapping. The skids shall be the full width of the containers with the top in place. The skids shall be secured to the bottom of the box by nailing through a minimum 1-inch diameter flat metal washer. The top shall be secured to the container and skids by 5 encircling bands of minimum 0.025 inch thick nonmetallic strapping conforming to PPP-S-760 and having a minimum break strength of 900 lb. The straps shall be tightened to indent the fiberboard without cutting into the edge. Buckles shall not be used on strapping.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T19:19Z
Check the source to verify that this is the current version before use.

* 5.3 Marking. In addition to any special marking (see 6.2), shipping containers shall be marked in accordance with MIL-STD-129. Set marking requirements shall apply to containers for end sections when two containers are used. In addition, containers shall be marked "END SECTION," "DOOR SECTION," or "INTERMEDIATE SECTION," as applicable. Shipping containers shall be marked "TRANSPORT AND STORE IN A DRY AREA."

6. NOTES

6.1 Intended use. The frame sections are intended to be used to support and attach the outer tent covering and the insulated tent liner, when applicable. When the tent frame sections are intended to be used for housing wheeled and tracked motor vehicles undergoing repair in cold climates, the Military characteristics require a 64-foot overall length frame consisting of one (1) end section, one (1) door section, and seven (7) intermediate sections.

6.2 Ordering data. Acquisition documents should specify the following:

a. Title, number, and date of this document.

b. Section required, as applicable (see 1.2).

c. When a first article is required (see 3.1, 4.3, and 6.3).

d. Selection of a plicable levels of preservation and packing (see 5.1 and 5.2).

e. When additional marking is not required (see 5.3).

* 6.3 First article. When a first article is required, it shall be inspected and approved under the appropriate provisions of FAR 52.209. The first article should be a preproduction sample. The contracting officer should specify the appropriate type of first article and the number of units to be furnished. The contracting officer should include specific instructions in all acquisition instruments regarding arrangements for inspection and approval of the first article.

* 6.4 Recycled material. The contractor is encouraged to use recycled material when practical, provided that it meets the requirement of this document (see 3.3).

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T19:19Z
Check the source to verify that this is the current version before use.

6.5 International interest. Certain provisions of this document are the subject of international standardization agreement (ABC Army Standard No. 110). When amendment, revision, or cancellation of this document is proposed that affects or violates the international agreement concerned, the preparing activity will take appropriate reconciliation action through international standardization channels including departmental standardization officers, if required.

6.6 Changes from previous issue. The margins of this document are marked with an asterisk (*) to indicate where changes (additions, modifications, corrections, deletions) from the previous issue were made. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content irrespective of the marginal notations and relationship to the last previous issue.

Custodians:

Army - GL
Air Force - 99

Preparing activity:

Army - GL

Project No. 8340-0466

Review activities:

Army - MD
Air Force - 82
DLA-CT

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T19:19Z
Check the source to verify that this is the current version before use.

INSTRUCTIONS: In a continuing effort to make our standardization documents better, the DoD provides this form for use in submitting comments and suggestions for improvements. All users of military standardization documents are invited to provide suggestions. This form may be detached, folded along the lines indicated, taped along the loose edge *(DO NOT STAPLE)*, and mailed. In block 5, be as specific as possible about particular problem areas such as wording which required interpretation, was too rigid, restrictive, loose, ambiguous, or was incompatible, and give proposed wording changes which would alleviate the problems. Enter in block 6 any remarks not related to a specific paragraph of the document. If block 7 is filled out, an acknowledgement will be mailed to you within 30 days to let you know that your comments were received and are being considered.

NOTE: This form may not be used to request copies of documents, nor to request waivers, deviations, or clarification of specification requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

(Fold along this line)

(Fold along this line)

DEPARTMENT OF THE ARMY
US Army Natick Research and Development Center
Natick, Massachusetts 01760-5014

NO POSTAGE NECESSARY IF MAILED IN THE UNITED STATES

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300
STRNC-ES

BUSINESS REPLY MAIL
FIRST CLASS PERMIT NO. 12062 WASHINGTON D. C.
POSTAGE WILL BE PAID BY THE DEPARTMENT OF THE ARMY

Commander
US Army Natick Research and Development Center
ATTN: STRNC-ES
Natick, MA 01760-5014

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T19:19Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

(See Instructions – Reverse Side)

1. DOCUMENT NUMBER	2. DOCUMENT TITLE
MIL-F-40132G	Frame Sections, Tent, Maintenance, Medium, Light Metal

3a. NAME OF SUBMITTING ORGANIZATION	4. TYPE OF ORGANIZATION *(Mark one)*
	☐ VENDOR ☐ USER ☐ MANUFACTURER ☐ OTHER *(Specify)*: _____
b. ADDRESS *(Street, City, State, ZIP Code)*	

5. PROBLEM AREAS

a. Paragraph Number and Wording:

b. Recommended Wording:

c. Reason/Rationale for Recommendation:

6. REMARKS

7a. NAME OF SUBMITTER *(Last, First, MI)* – Optional	b. WORK TELEPHONE NUMBER *(Include Area Code)* – Optional
c. MAILING ADDRESS *(Street, City, State, ZIP Code)* – Optional	8. DATE OF SUBMISSION *(YYMMDD)*

DD FORM 82 MAR 1426 PREVIOUS EDITION IS OBSOLETE.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T19:19Z
Check the source to verify that this is the current version before use.