MIL-P-40148F
9 January 1987
SUPERSEDING
MIL-P-40148E
31 January 1984

MILITARY SPECIFICATION

POLES, TENT, TELESCOPIC, ADJUSTABLE, ALUMINUM

This specification is approved for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This document covers aluminum telescopic tent poles of one type and two sizes. One pole is adjustable to lengths of 3 feet, 5 feet, and 7 feet; and the other pole is adjustable to lengths of 8 feet, 6 inches and 10 feet, 6 inches.

1.2 Classification. The aluminum telescopic poles shall be of the following sizes as specified (see 6.2):

Size - 7 feet, maximum length
Size - 10 feet, 6 inches, maximum length

2. APPLICABLE DOCUMENTS

2.1 Government documents.

* 2.1.1 Documents. The following documents form a part of this document to the extent specified herein. Unless otherwise specified, the issues of these documents shall be those listed in the issue of the Department of Defense Index of Specifications and Standards (DODISS) and supplement thereto, cited in the solicitation.

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: U.S. Army Natick Research, Development and Engineering Center, Natick, MA 01760-5014 by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

AMSC N/A FSC 8340

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T19:21Z
Check the source to verify that this is the current version before use.

SPECIFICATIONS

FEDERAL

QQ-A-200/8 - Aluminum Alloy 6061, Bar, Rod, Shapes, Tube and Wire, Extruded
QQ-A-200/9 - Aluminum Alloy 6063, Bar, Rod, Shapes, Tube and Wire, Extruded
QQ-A-225/8 - Aluminum Alloy 6061, Bar, Rod, Wire, and Special Shapes; Rolled, Drawn, or Cold Finished
QQ-A-591 - Aluminum Alloy Die Castings
TT-C-542 - Coating, Polyurethane, Oil-Free, Moisture Curing
TT-E-529 - Enamel, Alkyd, Semigloss
TT-P-1757 - Primer Coating, Zinc Chromate, Low-Moisture-Sensitivity
WW-T-700/6 - Tube, Aluminum Alloy, Drawn, Seamless, 6061
PPP-B-621 - Boxes, Wood, Nailed and Lock-Corner

MILITARY

MIL-C-5541 - Chemical Conversion Coatings on Aluminum and Aluminum Alloys

STANDARDS

MILITARY

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes
MIL-STD-129 - Marking for Shipment and Storage
MIL-STD-147 - Palletized Unit Loads

DRAWINGS

US ARMY NATICK RESEARCH, DEVELOPMENT, AND ENGINEERING CENTER

5-4-1091 - Poles, Tent, Telescopic, Adjustable, 3', 5', 7', Aluminum; Assembly Complete
5-4-1092 - Poles, Tent, Telescopic, Adjustable, 8'-6" and 10'-6", Aluminum; Assembly Complete
5-4-1093 - Poles, Tent, Telescopic, Adjustable, 3', 5', 7', 8'-6" and 10'-6", Aluminum; Details and Alternate Construction

(Copies of documents required by contractors in connection with specific acquisition functions should be obtained from the contracting activity or as directed by the contracting activity.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T19:21Z
Check the source to verify that this is the current version before use.

* 2.2 Other publications. The following documents form a part of this document to the extent specified herein. Unless otherwise specified, the issues of the documents which are DOD adopted shall be those listed in the issue of the DODISS specified in the solicitation. Unless otherwise specified, the issues of documents not listed in the DODISS shall be the issues of the nongovernment documents which are current on the date of the solicitation.

AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM)

B 210 - Aluminum Alloy Drawn Seamless Tubes
B 449 - Chromate Treatment on Aluminum
D 3951 - Standard Practice for Commercial Packaging

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.)

* (Technical society and technical association documents are generally available for reference from libraries. They also distributed among technical groups and using Federal agencies.)

2.3 Order of precedence. In the event of a conflict between the text of this document and the references cited herein, the text of this document shall take precedence. Nothing in this document however, shall supersede applicable laws and regulations unless a specific exemption has been obtained.

3. REQUIREMENTS

3.1 First article. When specified in the contract or purchase order, a sample shall be subjected to first article inspection (see 4.3, 6.2, and 6.3).

3.2 Materials and components. Materials (see 6.5) and components shall be as specified on the applicable drawings and as specified herein. For materials or components for which it is stated "or equal", if the contractor proposes to use an item considered to be equal to the material or component specified, prior to its use the contractor shall furnish a sample of the material or component, with supporting data to the contracting officer for subsequent evaluation by the responsible military agency.

3.2.1 Aluminum alloys.

3.2.1.1 Bar and rod. Aluminum alloy bar and rod shall conform to 6061-T6 of QQ-A-200/8 or QQ-A-225/8, or 6063-T6 of QQ-A-200/9.

3.2.1.2 Tube. Aluminum alloy tube shall conform to any of the following:

a. 6061-T6 of QQ-A-200/8
b. 6063-T832 of ASTM B 210
c. 6061-T6, type 1 of WW-T-700/6

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T19:21Z
Check the source to verify that this is the current version before use.

3.2.1.3 Castings. Aluminum alloy die castings shall conform to alloy number 360.0 or A 360.0 of QQ-A-591.

3.2.2 Wire rope. Wire rope shall be of the type and size as shown on Drawings 5-4-1091 and 5-4-1092.

3.2.3 Primer. Primer shall conform to composition G or L as applicable, color Y of TT-P-1757.

3.2.4 Enamel. Enamel shall conform to class A or B, composition G or L, Olive Drab No. 24087 of TT-E-529.

3.2.5 Epoxy coating. As an alternate to the primer and enamel specified above, the tent poles may be coated with standard Corvell ECA-1555-FC3 Epoxy Coating. The color shall be Olive Drab No. 24087.

3.2.6 Enamel acrylic. As an alternate to the coating requirements specified in 3.2.4 and 3.2.5, Duracon Super 600 acrylic enamel may be used to coat the tent pole. The color shall be Olive Drab No. 24087.

* 3.2.7 Enamel polyurethane. As an alternate to the coating requirements specified in 3.2.4, 3.2.5 and 3.2.6, polyurethane enamel conforming to type I, class A of TT-C-542 may be used. The color shall be Olive Drab No. 24087.

3.3 Construction. The construction of the poles shall conform to Drawings 5-4-1091 through 5-4-1093 and as specified herein. The poles shall be capable of extending and retracting by hand operation to the lengths specified without binding or having to use a tool to force the sections to extend or retract. Safety bolts shall be capable of function as intended, i.e., being readily inserted in safety bolt holes and locked in position by hand operation. Safety bolt holes shall be in alignment longitudinally in accordance with tolerance specified on applicable drawing when the pole is in its fully retracted condition, at each specified length and at its fully extended condition (prior to insertion of safety bolts).

* 3.3.1 Shaft, end plug and disc. Shaft, end plug, and disc shall be fabricated of aluminum bar or rod specified in 3.2.1.1 except die castings specified in 3.2.1.3 may be supplied as alternate construction as follows:

a. Disc and end plug of Drawing 5-4-1092
b. Shaft of Drawing 5-4-1092
c. Single die casting for the shaft and disc of Drawing 5-4-1093.

3.3.2 Tube segments and intermediate plug. Tube segments and intermediate plug shall be fabricated of aluminum specified in 3.2.1.2.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T19:21Z
Check the source to verify that this is the current version before use.

* 3.3.3 Wire rope and sleeve assembly. Wire rope and sleeve assembly shall be capable of withstanding a load of 180 pounds minimum in tension without fracture of sleeve or wire rope and with no evidence of wire rope pulling out of, or through, sleeve when tested as specified in 4.4.5. The loop of wire rope shall be 1 ± 1/4 inches in length between the sleeve and the lanced retainer or welded clip assembly, as applicable.

* 3.3.4 Lancing. The wall of the tube shall be lanced (see 6.4) as shown on Drawing 5-4-1093 to retain the wire rope as follows:

a. Lanced retainer shall be free of fracture or crack. Welding of fractured or cracked lanced retainer shall not be permitted.

b. Lanced retainer shall be capable of withstanding a load of 180 pounds minimum in tension without fracture, cracking, or bending out of shape when tested as specified in 4.4.5.

* 3.3.5 Clip. Clip as shown on Drawing 5-4-1093 may be used to retain the wire rope in lieu of lancing the wall of the tube (see 3.3.4) providing that the clip is welded with the deposited weld metal thoroughly fused with the base metal along all surfaces and edges of the union, except as shown on Drawing 5-4-1093. Welds shall be sound, smooth, and free from flash. The welded clip shall be cap-able of withstanding a load of 180 pounds minimum in tension without fracture, bending out of shape, or separating from the tube when tested as specified in 4.4.5.

* 3.4 Finish. Prior to finishing, all burrs, sharp edges, and rough spots shall be removed and all lancing or welding, as applicable, shall be completed. All aluminum surfaces to be primed shall be prepared for painting in accordance with class 1A treatment of MIL-C-5541 or class 1 or 2 treatment of ASTM B 449. After final assembly and with the pole fully extended, all exposed surfaces including wire rope retainers and safety bolts shall be coated with primer specified in 3.2.3. After drying, primed surfaces shall be coated with enamel specified in 3.2.4. The finish coating shall level out to produce a smooth, uniform, dry finish without blisters, peeling, chipping, or cracking. The finish shall be free from any area of no film, sag, run, drop, scratch, or pebbled finish. The crevice adjacent to the spring of the safety bolts shall be protected from build-up of finish coating to prevent malfunction of the spring action. Coating damaged during examination of the poles shall be touched up.

3.4.1 Epoxy coating or acrylic enamel. When the coating specified in 3.2.5, 3.2.6, or 3.2.7 is used as an alternate, the requirements in 3.4 shall apply, except priming is not required. The coatings shall be applied in accordance with the manufacturer's instructions.

3.5 Marking for identification. The letters "U.S." and the manufacturer's name or trade name, or trademark of such characters as to be identifiable with the manufacturer, shall be distinctly indented or raised on the side or bottom surface of the end plug and shall be not less than 1/8 inch in size.

Source: https://assist.dla.mil -- Downloaded: 202640-21T19:21Z
Check the source to verify that this is the current version before use.

3.6 Workmanship. Components shall be free from split, puncture, malformation, deformation, and fracture. The finished pole shall be clean and free of dirt and grease. All staked components shall be sound, tight, and free from looseness e.g., staked tube loose in countersink of hole in shaft or disc loose on shaft.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the document where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

* 4.1.1 Responsibility for compliance. All items must meet all requirements of sections 3 and 5. The inspection set forth in this document shall become a part of the contractor's overall inspection system or quality program. The absence of any inspection requirement in the document shall not relieve the contractor of the responsibility of assuring that all products or supplies submitted to the Government for acceptance comply with all requirements of the contract. Sampling in quality conformance does no authorize submission of known defective material, either indicated or actual, nor does it commit the Government to acceptance of defective material.

* 4.1.2 Responsibility for dimensional requirements. Unless otherwise specified in the contract or purchase order, the contractor is responsible for assuring that all specified dimensions have been met. When dimensions cannot be examined on the end item, inspection shall be made at any point, or at all points in the manufacturing process necessary to assure compliance with all dimensional requirements.

4.2 Classification of inspection. The inspection requirements specified herein are classified as follows:

a. First article inspection (see 4.3).
b. Quality conformance inspection (see 4.4).

4.3 First article inspection. When a first article is required (see 6.2), it shall be examined for the defects specified in table I and 4.4.4 and tested for the characteristics specified in table II. The presence of any defect or failure to pass any test shall be cause for rejection of the first article.

4.4 Quality conformance inspection. Unless otherwise specified, sampling for inspection shall be performed in accordance with MIL-STD-105.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T19:21Z
Check the source to verify that this is the current version before use.

4.4.1 Component and material inspection. In accordance with 4.1, components and materials shall be inspected in accordance with all the requirements of referenced documents unless otherwise excluded, amended, modified, or qualified in this document or applicable purchase document.

4.4.2 In-process examination. Examination shall be made of the following operations to establish conformance with the specified requirements. Whenever a nonconformance is noted, correction shall be made to items affected, the lot in process, and the operation. Parts which cannot be corrected shall be removed from production.

Requirement or operation	Requirement reference
Swaging the base of the shaft (1-7) and ends of tube segments (1-2 and 1-5)	Drawing 5-4-1091
Swaging ends of tube segments (1-2, 1-5, 1-8, and 1-10)	Drawing 5-4-1092
Lanced retainer to be free of fracture, crack, or weld	3.3.4
Indenting tube (1-5) into groove of intermediate plug (1-12)	Drawing 5-4-1092
Completion of lancing or welding, prior to finishing	3.4
Removal of burrs, sharp edges, and rough spots prior to finishing	3.4
Chemical treatment of aluminum components prior to priming	3.4
Priming of exposed surfaces of components prior to enameling except when priming is not required	3.4.1

4.4.3 End item visual examination. The end item shall be examined for the defects listed in table I. The lot size shall be expressed in units of poles of one size only. The sample unit shall be one pole. The inspection level shall be II and the acceptable quality level (AQL), expressed in terms of defects per hundred units, shall be 2.5 for major defects and 10.0 for total (major and minor combined) defects.

TABLE I. End item visual defects

Examine	Defect	Classification Major	Minor
Finish	Missing	X	
	Color of finish not as specified		X
	Coating not smooth and uniform		X
	Finish is not dry, i.e., wet or tacky to touch		X

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T19:21Z
Check the source to verify that this is the current version before use.

TABLE I. End item visual defects (cont'd)

Examine	Defect	Classification Major	Classification Minor
Finish (cont'd)	Blistered, peeled, chipped, or cracked		X
	Area of no film, sag, run, drop, scratch, or pebbled finish		X
	Finish coating has been allowed to build-up into crevices adjacent to spring of safety bolt causing malfunction of the spring action		X
	NOTE: Defects in finish attributable to extension during examination will not be scored as a defect. However, the contractor shall touch up areas of finish damaged during examination.		
Construction and workmanship	Any part not fabricated of the specified materials	X	
	Any operation omitted or improperly performed, e.g., lanced retainer repaired by welding	X	
	End of wire rope obviously not secured by the sleeve	X	
	End of wire rope protruding through sleeve		X
	Component part missing, e.g., end plug, wire sleeve, safety bolt, or intermediate plug		X
	Component part is split, punctured, malformed, deformed, fractured, or cracked		X
	Not clean, i.e., has dirt or grease		X
	Burr, sharp edge, or rough spot		X
	Staked component is loose, i.e., not sound and tight		X
	End plug vent hole missing		X
	Tube segment not indented into groove of end plug	X	
	Pole cannot be extended or retracted by hand operation to the specified lengths, e.g., binds or requires the use of a tool to force the sections to extend or retract	X	

Source: https://assist.dla.mil -- Downloaded: 202610-21T19:21Z
Check the source to verify that this is the current version before use.

DIMENSIONS:

TABLE I. End item visual defects (cont'd)

Examine	Defect	Classification Major	Minor
Construction and workmanship (cont'd)	Safety bolt cannot be readily inserted in safety bolt holes and locked into position by hand operation		X
	Safety bolt hole not in alignment longitudinally when the pole is in its fully retracted condition at each specified length and at its fully extended condition (prior to insertion of safety bolts)		X
Welding, when applicable	Missing or incomplete	X	
	Deposited weld metal not thoroughly fused with the base metal along all surfaces and edges of the union (except as shown on Drawing 5-4-1093)		X
	Weld not sound and smooth		X
	Evidence of flash		X
Identification marking	Missing, wrong location, wrong size, incomplete, illegible, incorrect, or not accomplished as specified		X

* 4.4.4 End item dimensional examination. The end item shall be examined for conformance to the dimensions, identified with an asterisk, specified on Drawings 5-4-1091, 5-4-1092, and 5-4-1093. Any dimension not within the specified tolerance shall be classified as a defect. The lot size shall be expressed in units of poles of one size only. The sample unit shall be one pole. The inspection level shall be S-2 and the AQL, expressed in terms of defects per hundred units, shall be 2.5.

* 4.4.5 End item testing. The end item shall be tested for the characteristics specified in table II. The lot size shall be expressed in units of tent poles of one size only. The sample unit shall be one tent pole. The inspection level shall be S-2 and the AQL, expressed in terms of defects per hundred units, shall be 2.5.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T19:21Z
Check the source to verify that this is the current version before use.

TABLE II. End item tests 1/

Characteristic	Requirement paragraph	Test method paragraph	Requirements applicable to	Number of determinations per sample unit	Results reported as
Strength of wire rope and sleeve assembly	3.3.3	4.5.1	Each individual wire rope and sleeve assembly of pole	One for each individual wire rope and sleeve assembly of the pole	Pass or fail
Strength of lanced retainer	3.3.4	4.5.2	Each individual lanced retainer of the pole	One for each individual lanced retainer of the pole	Pass or fail
Strength of welded clip assembly (if applicable)	3.3.5	4.5.3	Each individual welded clip assembly	One for each individual welded clip assembly	Pass or fail

1/ One pole may be used for both end item tests.

* 4.4.6 Packaging examination. The fully packaged end items shall be examined for the defects listed below. The lot size shall be expressed in units of shipping containers. The sample unit shall be one shipping container fully packaged. The inspection level shall be S-2 and the AQL, expressed in terms of defects per hundred units, shall be 4.0.

Examine	Defect
Marking, exterior	Omitted; incorrect; illegible; of improper size, location, sequence, or method of application.
Materials	Any component missing, damaged, or not as specified.
Workmanship	Improper nesting, inadequate blocking and bracing. Safety bolt not fully engaged in the safety bolt hole.
Content	Content is more or less than required.

* 4.4.7 Palletization examination. The fully packaged and palletized end items shall be examined for the defects listed below. The lot size shall be expressed in units of palletized unit loads. The sample unit shall be one palletized unit load fully packaged. The inspection level shall be S-1 and the AQL, expressed in terms of defects per hundred units, shall be 6.5.

Source: https://assist.dla.mil -- Downloaded: 202610-21T19:21Z
Check the source to verify that this is the current version before use.

Examine	Defect
Finished dimension	Length, width, or height exceeds specified maximum requirement.
Palletization	Pallet pattern not as specified. Interlocking of loads not as specified. Load not bonded as specified.
Weight	Exceeds maximum load limit.
Marking	Omitted; incorrect; illegible; of improper size, location, sequence, or method of application

4.5 Methods of inspection.

* 4.5.1 Wire rope and sleeve assembly strength test. The wire rope and sleeve assembly shall be placed in a tension testing machine in such a manner that a pull of 180 pounds minimum is exerted on the inside bearing surface of each wire rope loop. The pull shall be applied at a load rate not to exceed 500 pounds per minute. After the pull has been released, the wire rope and sleeve assembly shall be examined. Any wire rope and assembly having fracture of sleeve or wire rope, or evidence of wire rope pulling out of, or through, sleeve shall be classified as a defect.

4.5.2 Lanced retainer strength test. The lanced retainer shall be placed in a tension testing machine in such a manner that a pull of 180 pounds minimum is applied to the lanced retainer by the attached wire rope and sleeve assembly at a load rate not to exceed 500 pounds per minute. The load shall be applied at a 90 degree angle to the axis of the tube. After the pull has been released, the lanced retainer shall be examined. Any lanced retainer having evidence of fracture, cracking, or bening out of shape shall be classified as a defect.

* 4.5.3 Welded clip assembly strength test. The welded clip assembly shall be placed in a tension testing machine in such a manner that a pull of 180 pounds minimum is applied to the clip by the wire rope and sleeve assembly at a load rate not to exceed 500 pounds per minute. The load shall be applied at a 90 degree angle to the axis of the tube. After the pull has been released, the welded clip shall be examined. Any welded clip assembly having evidence of fracture, bending out of shape, or separation from the tube shall be classified as a defect.

Source: https://assist.dla.mil -- Downloaded: 202610-21T19:21Z
Check the source to verify that this is the current version before use.

5. PACKAGING

* 5.1 Packing. Packing shall be level A, B or Commercial as specified (see 6.2).

5.1.1 Level A packing.

5.1.1.1 Size 7 feet, maximum length. Thirty fully retracted tent poles shall be packed five layers of six each, within a snug-fitting nailed wood shipping container conforming to class 2, style 2, type 3 load of PPP-B-621, except that the minimum width of cleats shall be 2-5/8 inches and the requirements for additional battens shall not apply. The safety bolts shall be fully engaged in the safety bolt holes of the tent pole as shown on Drawing 5-4-1091. The tent poles shall be packed in a manner to allow close nesting of the tubular section of the tent poles by alternating each pole, end for end. A plug end shall abut the under side of the disc at the spindle end in each row and each layer, and the safety bolts shall be positioned at an angle to eliminate interference with the adjacent tent pole. Blocking and bracing shall be used, as necessary, to prevent movement and contact of the the tent poles within the shipping container. Closure and strapping of the shipping container shall be in accordance with the appendix of PPP-B-621.

5.1.1.2 Size 10 feet 6 inches, maximum length. Twenty fully retracted tent poles shall be packed four layers of five each, within a snug-fitting nailed wood shipping container conforming to class 2, style 2, type 3 load of PPP-B-621 except that minimum width of cleats shall be 2-5/8 inches, requirements for additional battens shall not apply, and minimum thickness of lumber shall be 3/4 inches. The shipping container shall be provided with three skids. The size and placement of the skids shall be in accordance with the requirements of PPP-B-621. The safety bolts shall be fully engaged in the safety bolt holes of the tent pole as shown on Drawing 5-4-1092. The tent poles shall be packed in a manner to allow close nesting of the tubular section of the tent poles by alternating each pole, end for end. A plug end shall be adjacent to a spindle end in each row and each layer, and the safety bolts shall be positioned at an angle to eliminate interference with the adjacent tent pole. Blocking and bracing shall be used, as necessary, to prevent movement and contact of the tent poles within the shipping container. Closure and strapping of the shipping container shall be in accordance with the appendix of PPP-B-621.

5.1.2 Commercial packing. Tent poles shall be packed in accordance with ASTM D 3951.

* 5.2 Palletization. When specified (see 6.2), the size 7 foot tent poles packed as specified in 5.1 shall be palletized on a 4-way entry pallet in accordance with load type I of MIL-STD-147. Each prepared load shall be bonded with primary and secondary straps in accordance with bonding means K and L or film binding means O. Pallet patterns shall be in accordance with the

Source: https://assist.dla.mil -- Downloaded: 202610-21T19:21Z
Check the source to verify that this is the current version before use.

appendix of MIL-STD-147. Interlocking of loads shall be affected by reversing the pattern of each course. If the container is of a size which does not conform to any of the pallet patterns specified in MIL-STD-147, the pallet pattern intended to be used shall first be approved by the contracting officer prior to its use.

5.3 Marking. In addition to any special marking required by the contract or purchase order, shipping containers and palletized loads shall be marked in accordance with MIL-STD-129, or ASTM D 3951, as applicable.

6. NOTES

6.1 Intended use. The aluminum telescopic tent poles covered by this document are intended to be used with the Tent, General Purpose, Small.

6.2 Ordering data. Acquisition documents should specify the following:

a. Title, number, and date of this document.
b. Size pole required (see 1.2).
c. When a first article is required (see 3.1, 4.3, and 6.3).
d. Selection of applicable levels of packing (see 5.1).
e. When palletization is required (see 5.2).

* 6.3 First article. When a first article is required, it shall be inspected and approved under the appropriate provisions of FAR 52.209. The first article should be a preproduction sample. The contracting officer should specify the appropriate type of first article and the number of units to be furnished. The contracting officer should include specific instructions in all acquisition instruments regarding arrangements for selection, inspection, and approval of the first article.

6.4 Lancing of extruded aluminum. The aluminum industry has indicated that lancing may be properly applied to drawn aluminum tube. No assurance can be given that extruded aluminum tube produced by the die and mandrel method can be properly lanced. Extruded aluminum tube produced by the bridge die method is not acceptable for lancing.

6.5 Recycled material. It is encouraged that recycled material be used when practical as long as it meets the requirements of the document (see 3.2).

* 6.6 Subject term (key word) listing.

Poles
Shelters
Tents

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T19:21Z
Check the source to verify that this is the current version before use.

6.7 International standardization agreements. Certain provisions of this document are the subject of international standardization agreement as cited in NATO, STANAG NO. 2882, relative to camouflage requirements for tents, shelters and subsidiary components. When amendment, revision, or cancellation of this document is proposed which will affect or violate the international agreement concerned, the preparing activity will take appropriate reconciliation action through international standardization channels including departmental standardization offices, if required.

6.8 Changes from previous issue. The margins of this document are marked with an asterisk to indicate where changes (additions, modifications, corrections, deletions) from the previous issue were made. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document bassed onthe entire content irrespective of the marginal notations and relationship to the last previous issue.

Custodians:

Army - GL
Navy - NU
Air Force - 99

Review activities:

Army - MD
Air Force - 82
DLA - CT

User activities:

Navy - YD
Air Force - 45

Preparing activity:

Army - GL

Project No. 8340-0467

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T19:21Z
Check the source to verify that this is the current version before use.

INSTRUCTIONS: In a continuing effort to make our standardization documents better, the DoD provides this form for use in submitting comments and suggestions for improvements. All users of military standardization documents are invited to provide suggestions. This form may be detached, folded along the lines indicated, taped along the loose edge *(DO NOT STAPLE)*, and mailed. In block 5, be as specific as possible about particular problem areas such as wording which required interpretation, was too rigid, restrictive, loose, ambiguous, or was incompatible, and give proposed wording changes which would alleviate the problems. Enter in block 6 any remarks not related to a specific paragraph of the document. If block 7 is filled out, an acknowledgement will be mailed to you within 30 days to let you know that your comments were received and are being considered.

NOTE: This form may not be used to request copies of documents, nor to request waivers, deviations, or clarification of specification requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document*(s)* or to amend contractual requirements.

(Fold along this line)

(Fold along this line)

DEPARTMENT OF THE ARMY

U.S. ARMY NATICK RESEARCH, DEVELOPMENT
and ENGINEERING CENTER
ATTN: STRNC-ES
Natick, MA 01760-5014

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300

NO POSTAGE
NECESSARY
IF MAILED
IN THE
UNITED STATES

BUSINESS REPLY MAIL
FIRST CLASS PERMIT NO. 12062 WASHINGTON D. C.

POSTAGE WILL BE PAID BY THE DEPARTMENT OF THE ARMY

Commander
U.S. Army Natick Research, Development
and Engineering Center
ATTN: STRNC-ES
Natick, MA 01760-5014

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T19:21Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

(See Instructions – Reverse Side)

1. DOCUMENT NUMBER	2. DOCUMENT TITLE
MIL-L-40148F	Poles, Tent, Telescopic, Adjustable, Aluminum

3a. NAME OF SUBMITTING ORGANIZATION	4. TYPE OF ORGANIZATION *(Mark one)*
	☐ VENDOR
	☐ USER
b. ADDRESS *(Street, City, State, ZIP Code)*	☐ MANUFACTURER
	☐ OTHER *(Specify)*: _____

5. PROBLEM AREAS

a. Paragraph Number and Wording:

b. Recommended Wording:

c. Reason/Rationale for Recommendation:

6. REMARKS

7a. NAME OF SUBMITTER *(Last, First, MI)* – Optional	b. WORK TELEPHONE NUMBER *(Include Area Code)* – Optional
c. MAILING ADDRESS *(Street, City, State, ZIP Code)* – Optional	8. DATE OF SUBMISSION *(YYMMDD)*

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T19:21Z
Check the source to verify that this is the current version before use.

FSC 4120 and sleeve assembly shall be specific