The documentation and process conversion measures necessary to comply with this revision shall be completed by 10 November 2017.

INCH-POUND

MIL-PRF-19500/756A
w/AMENDMENT 1
10 August 2017
SUPERSEDING
MIL-PRF-19500/756A
12 December 2014

PERFORMANCE SPECIFICATION SHEET

TRANSISTOR, FIELD EFFECT RADIATION HARDENED,
N-CHANNEL, SILICON, THROUGH HOLE AND SURFACE MOUNT, TYPES 2N7606 AND 2N7607
QUALITY LEVELS JANTXV AND JANS

This specification is approved for use by all Departments and Agencies of the Department of Defense.

The requirements for acquiring the product described herein shall consist of this specification sheet and MIL-PRF-19500.

1. SCOPE

1.1 Scope. This specification covers the performance requirements for a N-channel, enhancement-mode, radiation hardened (total dose and single event effects (SEE)), low-threshold logic level, MOSFET, transistor. Two levels of product assurance (JANTXV and JANS) are provided for each device type as specified in MIL-PRF-19500, with avalanche energy maximum rating ($E_{AS}$) and maximum avalanche current ($I_{AS}$).

1.2 Package outlines. The device packages for this specification sheet are the TO-257AA (T3) and TO-276AA (SMD.5, U3), in accordance with figures 1 and 2 for all packaged device types.

1.3 Maximum ratings. Unless otherwise specified, $T_A$ = +25°C.

| Type | $P_T$ (1) $T_C$ =+25°C | $P_T$ $T_A$ =+25°C | $R_{\theta JC}$ (2) | $V_{DS}$ | $V_{GS}$ | $I_{D1}$ $T_C$ =+25°C (3) (4) | $I_{D2}$ $T_C$ =+100°C (3) (4) | $I_S$ | $I_{DM}$ (5) | $T_J$ and $T_{STG}$ |
|---|---|---|---|---|---|---|---|---|---|---|
| | W | W | °C/W | V dc | V dc | A dc | A dc | A dc | A (pk) | °C |
| 2N7607T3 | 75 | 1.56 | 1.67 | 60 | ±10 | 20 | 20 | 20 | 80 | -55 to +150 |
| 2N7606U3 | 57 | 1.00 | 2.20 | 60 | ±10 | 22 | 20 | 22 | 88 | |

(1) Derate linearly by 0.60 mW/°C (T3) for $T_C$ > +25°C, 0.45mW/ºC (U3) for $T_C$ > +25°C.
(2) See figure 3, thermal impedance curves.
(3) The following formula derives the maximum theoretical $I_D$ limit: $I_D$ is limited by product design & construction (package, internal wires and pin diameter) to 20A (T3) and 22A (U3).

$$I_D = \sqrt{\frac{T_{JM} - T_C}{(R_{\theta JC}) \times (R_{DS}(on) \text{ at } T_{JM})}}$$

(4) See figure 4, maximum drain current graph.
(5) $I_{DM}$ = 4 X $I_{D1}$ as calculated in note (3).

Comments, suggestions, or questions on this document should be addressed to DLA Land and Maritime, ATTN: VAC, P.O. Box 3990, Columbus, OH 43218-3990, or emailed to Semiconductor@dla.mil. Since contact information can change, you may want to verify the currency of this address information using the ASSIST Online database at https://assist.dla.mil/.

AMSC N/A

FSC 5961

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T05:46Z
Check the source to verify that this is the current version before use.

1.3 Maximum ratings - Continued. Unless otherwise specified, $T_C$ = +25°C.

| Type | Min $V_{(BR)\ DSS}$ $V_{GS}$ = 0 V $I_D$ = 250 µA dc | $V_{GS\ (th)1}$ $V_{DS}$ = $V_{GS}$ $I_D$ = 250 µA dc | Max $I_{DSS1}$ $V_{GS}$ = 0 V $V_{DS}$ = 80% rated VDS | Max $r_{DS(on)}$ (1) $V_{GS}$ = 4.5 V dc | | $E_{AS}$ | $I_{AS}$ |
|---|---|---|---|---|---|---|---|
| | | | | at $I_{D2}$ $T_J$ = +25°C | $T_J$ = +150°C | | |
| | V dc | V dc | µA dc | Ohm | Ohm | mJ | A dc |
| | | Min Max | | | | | |
| 2N7607T3 | 60 | 1.0 2.0 | 1.0 | 0.045 | 0.076 | 98 | 20 |
| 2N7606U3 | 60 | 1.0 2.0 | 1.0 | 0.035 | 0.057 | 63 | 22 |

(1) Pulsed (see 4.5.1).

1.4 Part or Identifying Number (PIN). The PIN is in accordance with MIL-PRF-19500, and as specified herein. See 6.5 for PIN construction example and 6.6 for a list of available PINs.

1.4.1 JAN certification mark and quality level. The quality level designators for encapsulated devices that are applicable for this specification sheet from the lowest to the highest level are as follows: "TXV" and "S".

1.4.2 Radiation hardness assurance (RHA) designator. The RHA levels that are applicable for this specification sheet from lowest to highest are as follows: "R" and "F".

1.4.3 Device type. The designation system for the device types of transistors covered by this specification sheet are as follows.

1.4.3.1 First number and first letter symbols. The transistors of this specification sheet are identified by the first number and letter symbols "2N".

1.4.3.2 Second number symbols. The second number symbols for the transistors covered by this specification sheet are as follows: "7606" and "7607".

1.4.4 Suffix symbols. The following suffix symbols are incorporated in the PIN for this specification sheet:

| | |
|---|---|
| T3 | Indicates a through-hole mount package similar to a TO-257AA (see figure 1). |
| U3 | Indicates a 3 pad surface mount package similar to a TO-276AA (SMD-0.5) (see figure 2). |

1.4.5 Lead finish. The lead finishes applicable to this specification sheet are listed on QML-19500.



Source: https://assist.dla.mil -- Downloaded: 2026-10-19T05:46Z
Check the source to verify that this is the current version before use.

2. APPLICABLE DOCUMENTS

2.1 General. The documents listed in this section are specified in sections 3 and 4 of this specification. This section does not include documents cited in other sections of this specification or recommended for additional information or as examples. While every effort has been made to ensure the completeness of this list, document users are cautioned that they must meet all specified requirements of documents cited in sections 3 and 4 of this specification, whether or not they are listed.

2.2 Government documents.

2.2.1 Specifications, standards, and handbooks. The following specifications, standards, and handbooks form a part of this document to the extent specified herein. Unless otherwise specified, the issues of these documents are those cited in the solicitation or contract.

DEPARTMENT OF DEFENSE SPECIFICATIONS

MIL-PRF-19500 - Semiconductor Devices, General Specification for.

DEPARTMENT OF DEFENSE STANDARDS

MIL-STD-750 - Test Methods for Semiconductor Devices.

* (Copies of these documents are available online at http://quicksearch.dla.mil/).

2.3 Order of precedence. Unless otherwise noted herein or in the contract, in the event of a conflict between the text of this document and the references cited herein, the text of this document takes precedence. Nothing in this document, however, supersedes applicable laws and regulations unless a specific exemption has been obtained.

3. REQUIREMENTS

3.1 General. The individual item requirements shall be as specified in MIL-PRF-19500 and as modified herein.

3.2 Qualification. Devices furnished under this specification shall be products that are manufactured by a manufacturer authorized by the qualifying activity for listing on the applicable qualified manufacturer's list before contract award (see 4.2 and 6.3).

3.3 Abbreviations, symbols, and definitions. Abbreviations, symbols, and definitions used herein shall be as specified in MIL-PRF-19500.

3.4 Interface requirements and physical dimensions. The interface requirements and physical dimensions shall be as specified in MIL-PRF-19500 and herein. The device package style is either a TO-257AA or TO-276AA, in accordance with figure 1 (T3) and figure 2 (U3).

3.4.1 Lead finish. Unless otherwise specified, lead finish shall be solderable in accordance with MIL-PRF-19500, MIL-STD-750, and herein. Where a choice of lead finish is desired, it shall be specified in the acquisition document (see 6.2).


3.4.2 Pin-out. The pin-out of the device shall be as shown on figures 1 and 2.

3.4.3 Internal construction. Multiple chip construction shall not be permitted to meet the requirements of this specification.

3.5 Marking. Marking shall be in accordance with MIL-PRF-19500.



Source: https://assist.dla.mil -- Downloaded: 2026-10-19T05:46Z
Check the source to verify that this is the current version before use.





| Ltr | Inches | | Millimeters | |
|---|---|---|---|---|
| | Min | Max | Min | Max |
| BL | .410 | .430 | 10.41 | 10.92 |
| $BL_1$ | | .033 | | 0.84 |
| CH | .190 | .200 | 4.83 | 5.08 |
| LD | .025 | .035 | 0.64 | 0.89 |
| LL | .600 | .650 | 15.24 | 16.51 |
| LO | .120 BSC | | 3.05 BSC | |
| LS | .100 BSC | | 2.54 BSC | |
| MHD | .140 | .150 | 3.56 | 3.81 |
| MHO | .527 | .537 | 13.39 | 13.64 |
| TL | .645 | .665 | 16.38 | 16.89 |
| TT | .035 | .045 | 0.89 | 1.14 |
| TW | .410 | .420 | 10.41 | 10.67 |
| Term 1 | Drain | | | |
| Term 2 | Source | | | |
| Term 3 | Gate | | | |

NOTES:
1. Dimensions are in inches.
2. Millimeters are given for general information only.
3. All terminals are isolated from the case.
4. This area is for the lead feed-thru eyelets (configuration is optional, but will not extend beyond this zone).
5. In accordance with ASME Y14.5M, diameters are equivalent to ϕx symbology.

FIGURE 1. Dimensions and configuration, TO-257AA (T3).



Source: https://assist.dla.mil -- Downloaded: 2026-10-19T05:46Z
Check the source to verify that this is the current version before use.




| Symbol | Dimensions | | | |
|---|---|---|---|---|
| | Inches | | Millimeters | |
| | Min | Max | Min | Max |
| BL | .395 | .405 | 10.04 | 10.28 |
| BW | .291 | .301 | 7.40 | 7.64 |
| CH | | .124 | | 3.15 |
| LH | .010 | .020 | 0.25 | 0.51 |
| LW1 | .281 | .291 | 7.14 | 7.39 |
| LW2 | .090 | .100 | 2.29 | 2.54 |
| LL1 | .220 | .230 | 5.59 | 5.84 |
| LL2 | .115 | .125 | 2.93 | 3.17 |
| LS1 | .150 BSC | | 3.81 BSC | |
| LS2 | .075 BSC | | 1.91 BSC | |
| Q1 | .030 | | 0.762 | |
| Q2 | .030 | | 0.762 | |
| TERM 1 | Drain | | | |
| TERM 2 | Gate | | | |
| TERM 3 | Source | | | |

NOTES:
1. Dimension are in inches.
2. Millimeters are given for information only.
3. The lid shall be electrically isolated from the drain, gate and source.
4. In accordance with ASME Y14.5M, diameters are equivalent to $\phi$x symbology.

FIGURE 2. Dimensions and configuration TO-276AA, SMD-0.5 (U3).



Source: https://assist.dla.mil -- Downloaded: 2026-10-19T05:46Z
Check the source to verify that this is the current version before use.

3.6 Electrical performance characteristics. Unless otherwise specified herein, the electrical performance characteristics are as specified in 1.3 and table I.

3.7 Workmanship. Transistors shall be processed in such a manner as to be uniform in quality and shall be free from other defects that will affect life, serviceability, or appearance.

4. VERIFICATION

4.1 Classification of Inspections. The inspection requirements specified herein are classified as follows:

a. Qualification inspection (see 4.2).

b. Screening (see 4.3).

c. Conformance inspection (see 4.4).

4.2 Qualification inspection. Qualification inspection shall be in accordance with MIL-PRF-19500 and as specified herein.

4.2.1 SEE. Design capability shall be tested on the initial qualification and thereafter whenever a major die design or process change is introduced (see table II). End-point measurements shall be in accordance with table II.

4.2.2 Group E qualification. Group E inspection shall be performed for qualification or re-qualification only. In case qualification was awarded to a prior revision of the specification sheet that did not request the performance of table III tests, the tests specified in table III herein that were not performed in the prior revision shall be performed on the first inspection lot of this revision to maintain qualification.



Source: https://assist.dla.mil -- Downloaded: 2026-10-19T05:46Z
Check the source to verify that this is the current version before use.

4.3 Screening (JANS and JANTXV levels only). Screening shall be in accordance with table E-IV of MIL-PRF-19500 and as specified herein. The following measurements shall be made in accordance with table I herein. Devices that exceed the limits of table I herein shall not be acceptable.

| Screen (see table E-IV of MIL-PRF-19500) (1) (2) | Measurement | |
|---|---|---|
| | JANS | JANTXV |
| (3) | Gate stress test (see 4.3.1) | Gate stress test (see 4.3.1) |
| (3) | Method 3470 of MIL-STD-750, $E_{AS}$ (see 4.3.2) | Method 3470 of MIL-STD-750, $E_{AS}$ (see 4.3.2) |
| (3) 3c | Method 3161 of MIL-STD-750, thermal impedance, (see 4.3.3) | Method 3161 of MIL-STD-750, thermal impedance, (see 4.3.3) |
| 9 | Subgroup 2 of table I herein<br>$I_{DSS1}$, $I_{GSSF1}$, $I_{GSSR1}$ as minimum | Not applicable |
| 10 | Method 1042 of MIL-STD-750, test condition B | Method 1042 of MIL-STD-750, test condition B |
| 11 | $I_{GSSF1}$, $I_{GSSR1}$, $I_{DSS1}$, $r_{DS(ON)1}$, $V_{GS(TH)1}$<br>Subgroup 2 of table I herein.<br><br>$\Delta I_{GSSF1}$ = ±20 nA dc or ±100 percent of initial value, whichever is greater.<br>$\Delta I_{GSSR1}$ = ±20 nA dc or ±100 percent of initial value, whichever is greater.<br>$\Delta I_{DSS1}$ = ±0.2 µA dc or ±100 percent of initial value, whichever is greater. | $I_{GSSF1}$, $I_{GSSR1}$, $I_{DSS1}$, $r_{DS(ON)1}$, $V_{GS(TH)1}$<br>Subgroup 2 of table I herein. |
| 12 | Method 1042 of MIL-STD-750, test condition A | Method 1042 of MIL-STD-750, test condition A |
| 13 | Subgroups 2 and 3 of table I herein<br>$\Delta I_{GSSF1}$ = ±20 nA dc or ±100 percent of initial value, whichever is greater.<br>$\Delta I_{GSSR1}$ = ±20 nA dc or ±100 percent of initial value, whichever is greater.<br>$\Delta I_{DSS1}$ = ±0.2 µA dc or ±100 percent of initial value, whichever is greater.<br>$\Delta r_{DS(ON)1}$ = ±20 percent of initial value.<br>$\Delta V_{GS(TH)1}$ = ±20 percent of initial value. | Subgroup 2 of table I herein<br>$\Delta I_{GSSF1}$ = ±20 nA dc or ±100 percent of initial value, whichever is greater.<br>$\Delta I_{GSSR1}$ = ±20 nA dc or ±100 percent of initial value, whichever is greater.<br>$\Delta I_{DSS1}$ = ±0.2 µA dc or ±100 percent of initial value, whichever is greater.<br>$\Delta r_{DS(ON)1}$ = ±20 percent of initial value.<br>$\Delta V_{GS(TH)1}$ = ±20 percent of initial value. |
| 17 | For TO-257AA and U3 packages:<br>Method 1081 of MIL-STD-750 (see 4.3.4), Endpoints: Subgroup 2 of table I herein | For TO-257AA and U3 packages:<br>Method 1081 of MIL-STD-750 (see 4.3.4), Endpoints: Subgroup 2 of table I herein |

(1) At the end of the test program, $I_{GSSF1}$, $I_{GSSR1}$, and $I_{DSS1}$ are measured.
* (2) An out-of-family program to characterize $I_{GSSF1}$, $I_{GSSR1}$, $I_{DSS1}$, $V_{GS(th)1}$, and $r_{DS(ON)1}$ shall be invoked.
* (3) Shall be performed anytime after temperature cycling, screen 3a; JANTXV level does not need to be repeated in screening requirements.



Source: https://assist.dla.mil -- Downloaded: 2026-10-19T05:46Z
Check the source to verify that this is the current version before use.

4.3.1 Gate stress test. Apply $V_{GS}$ = 15 V minimum for t = 250 μs minimum.

4.3.2 Single pulse avalanche energy ($E_{AS}$).

a. Peak current ($I_{AS}$)..... $I_{D1}$.

b. Peak gate voltage ($V_{GS}$)..... 5 V dc (up to max rated $V_{GS}$).

c. Gate to source resistor ($R_{GS}$)..... $25 \leq R_{GS} \leq 200\ \Omega$.

d. Initial case temperature ..... +25°C, +10°C, -5°C.

e. Inductance: ..... $\left[\frac{2E_{AS}}{(I_{D1})^2}\right]\left[\frac{V_{BR} - V_{DD}}{V_{BR}}\right]$ mH minimum.

f. Number of pulses to be applied ..... 1 pulse minimum.

g. Supply voltage ($V_{DD}$)..... 25 V dc (up to max $V_{DS}$).

4.3.3 Thermal impedance. The thermal impedance measurements shall be performed in accordance with method 3161 of MIL-STD-750 using the guidelines in that method for determining $I_M$, $I_H$, $t_H$, $t_{SW}$, (and $V_H$ where appropriate). Measurement delay time ($t_{MD}$) = 70 μs max. See table III, group E, subgroup 4 herein.

4.3.4 Dielectric withstanding voltage.

a. Magnitude of test voltage..... 800 V dc (TO-257AA), 600V dc (U3).

b. Duration of application of test voltage..... 15 seconds (min).

c. Points of application of test voltage ..... All leads to case (bunch connection).

d. Method of connection ..... Mechanical.

e. Kilovolt-ampere rating of high voltage source ..... 1,200 V/1.0 mA (min).

f. Maximum leakage current..... 1.0 mA.

g. Voltage ramp up time..... 500 V/second

4.4 Conformance inspection. Conformance inspection shall be in accordance with MIL-PRF-19500. Alternate flow is allowed for quality conformance inspection in accordance with MIL-PRF-19500.

4.4.1 Group A inspection. Group A inspection shall be conducted in accordance with MIL-PRF-19500 and table I herein. Electrical measurements (end-points) shall be in accordance with the inspections of table I herein.



Source: https://assist.dla.mil -- Downloaded: 2026-10-19T05:46Z
Check the source to verify that this is the current version before use.

4.4.2 Group B inspection. Group B inspection shall be conducted in accordance with the conditions specified for subgroup testing in table E-VIA (JANS) and table E-VIB (JANTXV) of MIL-PRF-19500, and herein.

4.4.2.1 Quality level JANS (table E-VIA of MIL-PRF-19500).

| Subgroup | Method | Condition |
|---|---|---|
| B3 | 1051 | Test condition G, 100 cycles. |
| B5 | 1042 | Accelerated steady-state gate bias, condition B, $V_{GS}$ = rated $V_{GS}$; $T_A$ = +175°C, t = 24 hours minimum; or $T_A$ = +150°C, t = 48 hours minimum. |
| B5 | 1042 | Accelerated steady-state reverse bias, condition A, $V_{DS}$ = rated $V_{DS}$; $T_A$ = +175°C, t = 120 hours minimum; or $T_A$ = +150°C, t = 240 hours minimum. |

4.4.2.2 Quality level JANTXV (table E-VIB of MIL-PRF-19500).

| Subgroup | Method | Condition |
|---|---|---|
| B2 | 1051 | Test condition C, 25 cycles. |
| B3 | 1042 | Accelerated steady-state gate bias, condition B, $V_{GS}$ = rated $V_{GS}$; $T_A$ = +175°C, t = 24 hours minimum; or $T_A$ = +150°C, t = 48 hours minimum; and accelerated steady-state reverse bias, condition A, $V_{DS}$ = rated $V_{DS}$; $T_A$ = +175°C, t = 170 hours minimum; or $T_A$ = +150°C, t = 340 hours minimum. |

4.4.3 Group C inspection. Group C inspection shall be conducted in accordance with the conditions specified for subgroup testing in table E-VII of MIL-PRF-19500 and as follows.

| Subgroup | Method | Condition |
|---|---|---|
| C2 | 2036 | Test Condition A, weight = 10 lbs (4.54 Kg), t = 10 s (applicable to TO-257AA only). |
| C5 | 3161 | See 4.3.3, $R_{\theta JC}$ = (see 1.3). |
| C6 | 1042 | Accelerated steady-state gate bias, condition B, $V_{GS}$ = rated $V_{GS}$; $T_A$ = +175°C, t = 48 hours minimum; or $T_A$ = +150°C, t = 96 hours minimum. and accelerated steady-state reverse bias, condition A, $V_{DS}$ = rated $V_{DS}$; $T_A$ = +175°C, t = 500 hours minimum; or $T_A$ = +150°C, t = 1,000 hours minimum. |

4.4.4 Group D inspection. Group D inspection shall be conducted in accordance with table E-VIII of MIL-PRF-19500 and table II herein.

4.4.5 Group E inspection. Group E inspection shall be conducted in accordance with the conditions specified for subgroup testing in table E-IX of MIL-PRF-19500 and as specified in table III herein.

4.5 Methods of inspection. Methods of inspection shall be as specified in the appropriate tables and as follows.

4.5.1 Pulse measurements. Conditions for pulse measurement shall be as specified in section 4 of MIL-STD-750.



Source: https://assist.dla.mil -- Downloaded: 2026-10-19T05:46Z
Check the source to verify that this is the current version before use.

* TABLE I. Group A inspection.

| Inspection 1/ | MIL-STD-750 | | Symbol | Limits | | Unit |
|---|---|---|---|---|---|---|
| | Method | Condition | | Min | Max | |
| Subgroup 1 | | | | | | |
| Visual and mechanical inspection | 2071 | | | | | |
| Subgroup 2 | | | | | | |
| Thermal impedance 2/ | 3161 | See 4.3.3 | $Z_{\theta JA}$ | | | °C/W |
| Breakdown voltage drain to source | 3407 | $V_{GS}$ = 0, $I_D$ = 250 µA dc, bias condition C | $V_{(BR)DSS}$ | 60 | | V dc |
| Gate to source voltage (threshold) | 3403 | $V_{DS} \geq V_{GS}$, $I_D$ = 250 µA dc | $V_{GS(TH)1}$ | 1.0 | 2.0 | V dc |
| Gate current | 3411 | $V_{GS}$ = +10 V dc, bias condition C, $V_{DS}$ = 0 | $I_{GSSF1}$ | | +100 | nA dc |
| Gate current | 3411 | $V_{GS}$ = -10 V dc, bias condition C, $V_{DS}$ = 0 | $I_{GSSR1}$ | | -100 | nA dc |
| Drain current | 3413 | $V_{GS}$ = 0, bias condition C, $V_{DS}$ = 80% of rated $V_{DS}$ | $I_{DSS1}$ | | 1.0 | µA dc |
| Static drain to source on-state resistance | 3421 | $V_{GS}$ = 4.5 V dc, condition A, pulsed (see 4.5.1), $I_D$ = $I_{D2}$ | $r_{DS(ON)1}$ | | | |
| 2N7607T3 | | | | | 0.045 | Ω |
| 2N7606U3 | | | | | 0.035 | Ω |
| Forward voltage | 4011 | $V_{GS}$ = 0, condition B, pulsed (see 4.5.1), $I_D$ = $I_{D1}$ | $V_{SD}$ | | 1.2 | V (pk) |
| Subgroup 3 | | | | | | |
| High temperature operation: | | $T_C$ = $T_J$ = +125°C | | | | |
| Gate current | 3411 | $V_{GS}$ = ±10 V dc, bias condition C, $V_{DS}$ = 0 | $I_{GSS2}$ | | ±200 | nA dc |
| Drain current | 3413 | $V_{GS}$ = 0, bias condition C, $V_{DS}$ = 80 percent of rated $V_{DS}$ | $I_{DSS2}$ | | 10 | µA dc |
| Static drain to source on-state resistance | 3421 | $V_{GS}$ = 4.5 V dc, condition A, pulsed (see 4.5.1), $I_D$ = $I_{D2}$ | $r_{DS(ON)2}$ | | | |
| 2N7607T3 | | | | | 0.070 | Ω |
| 2N7606U3 | | | | | 0.055 | Ω |
| Gate to source voltage (threshold) | 3403 | $V_{DS}$ = $V_{GS}$, $I_D$ = 250 µA dc | $V_{GS(TH)2}$ | 0.5 | | V dc |
| Low temperature operation: | | $T_C$ = $T_J$ = -55°C | | | | |
| Gate to source voltage (threshold) | 3403 | $V_{DS} \geq V_{GS}$, $I_D$ = 250 µA dc | $V_{GS(TH)3}$ | | 2.5 | V dc |

See footnotes at end of table.



Source: https://assist.dla.mil -- Downloaded: 2026-10-19T05:46Z
Check the source to verify that this is the current version before use.

* TABLE I. Group A inspection - Continued.

| Inspection 1/ | MIL-STD-750 | | Symbol | Limits | | Unit |
|---|---|---|---|---|---|---|
| | Method | Condition | | Min | Max | |
| Subgroup 4 | | | | | | |
| Forward transconductance | 3475 | $V_{DS}$ = 10 V dc, $I_D = I_{D2}$, pulsed (see 4.5.1) | $g_{FS}$ | | | |
| 2N7607T3 | | | | 19 | | S |
| 2N7606U3 | | | | 24 | | S |
| * Switching time test | 3472 | $I_D = I_{D1}$, $V_{GS}$ = 5.0 V dc, $R_G$ = 7.5 Ω, $V_{DD}$ = 50 percent of rated $V_{DS}$ | | | | |
| Turn-on delay time | | | $t_{D(on)}$ | | 30 | ns |
| Rise time | | | $t_r$ | | 7 | ns |
| Turn-off delay time | | | $t_{D(off)}$ | | 60 | ns |
| Fall time | | | $t_f$ | | 20 | ns |
| Subgroup 5 | | | | | | |
| Safe operating area test | 3474 | $V_{DS}$ = 80 percent of rated $V_{DS}$ (see 1.3), $t_P$ = 10 ms, $I_D$ as specified in figure 5 | | | | |
| Electrical measurements | | See table I, subgroup 2 | | | | |
| Subgroups 6 | | | | | | |
| Not applicable | | | | | | |
| Subgroup 7 | | | | | | |
| Gate charge | 3471 | Condition B, $I_D = I_{D1}$ | | | | |
| On-state gate charge | | | $Q_{G(on)}$ | | 34 | nC |
| On Gate to source charge | | | $Q_{GS1}$ | | 8 | nC |
| On Gate to drain charge | | | $Q_{GD1}$ | | 13 | nC |
| Turn-off gate charge | | | $Q_{G(off)}$ | | 34 | nC |
| Off Gate to source charge | | | $Q_{GS2}$ | | 8 | nC |
| Off Gate to drain charge | | | $Q_{GD2}$ | | 13 | nC |
| Reverse recovery time | 3473 | di/dt = -100 A/µs, $V_{DD} \leq$ 50 V, $I_D = I_{D1}$ | $t_{rr}$ | | 200 | ns |

1/ For sampling plan, see MIL-PRF-19500.
2/ This test required for the following end-point measurements only:
Group B, subgroups 3 and 4 (JANS).
Group B, subgroups 2 and 3 (JANTXV).
Group C, subgroup 2 and 6.
Group E, subgroup 1.



Source: https://assist.dla.mil -- Downloaded: 2026-10-19T05:46Z
Check the source to verify that this is the current version before use.

TABLE II. Group D inspection.

| Inspection 1/ 2/ 3/ | MIL-STD-750 | | Symbol | Pre-irradiation limits | | Post-irradiation limits | | Post-irradiation limits | | Unit |
|---|---|---|---|---|---|---|---|---|---|---|
| | | | | R & F | | R | | F | | |
| | Method | Conditions | | Min | Max | Min | Max | Min | Max | |
| Subgroup 1 | | | | | | | | | | |
| Not applicable | | | | | | | | | | |
| Subgroup 2 | | $T_C$ = + 25°C | | | | | | | | |
| Steady-state total dose irradiation ($V_{GS}$ bias) 4/ | 1019 | $V_{GS}$ = 6 V; $V_{DS}$ = 0 | | | | | | | | |
| Steady-state total dose irradiation ($V_{DS}$ bias) 4/ | 1019 | $V_{GS}$ = 0; $V_{DS}$ = 80 percent of rated $V_{DS}$ (preirradiation) | | | | | | | | |
| End-point electricals: | | | | | | | | | | |
| Breakdown voltage, drain to source | 3407 | $V_{GS}$ = 0; $I_D$ = 250 µA; bias condition C | $V_{(BR)DSS}$ | 60 | | 60 | | 60 | | V dc |
| Gate to source voltage (threshold) | 3403 | $V_{DS} \geq V_{GS}$ $I_D$ = 250 µA | $V_{GS(th)1}$ | 1.0 | 2.0 | 1.0 | 2.0 | 1.0 | 2.0 | V dc |
| Gate current | 3411 | $V_{GS}$ = +10 V, $V_{DS}$ = 0, bias condition C | $I_{GSSF1}$ | | 100 | | 100 | | 100 | nA dc |
| Gate current | 3411 | $V_{GS}$ = -10 V, $V_{DS}$ = 0, bias condition C | $I_{GSSR1}$ | | -100 | | -100 | | -100 | nA dc |
| Drain current | 3413 | $V_{GS}$ = 0, bias condition C $V_{DS}$ = 80 percent of rated $V_{DS}$ (preirradiation) | $I_{DSS}$ | | 1.0 | | 1.0 | | 1.0 | µA dc |
| Static drain to source on-state voltage | 3405 | $V_{GS}$ = 4.5 V; condition A, pulsed (see 4.5.1), $I_{D1} = I_{D2}$ | $V_{DS(on)}$ | | | | | | | |
| 2N7607T3 | | | | | 0.900 | | 0.900 | | 0.900 | V dc |
| 2N7606U3 | | | | | 0.600 | | 0.600 | | 0.600 | V dc |
| Forward voltage source drain diode | 4011 | $V_{GS}$ = 0; $I_D = I_{D1}$ bias condition C | $V_{SD}$ | | 1.2 | | 1.2 | | 1.2 | V dc |

1/ For sampling plan see MIL-PRF-19500.
2/ Group D qualification may be performed prior to lot formation. Wafers qualified to these group D QCI requirements may be used for any other specification sheets utilizing the same die design.
3/ At the manufacturer's option, group D samples need not be subjected to the screening tests, and may be assembled in its qualified package or in any qualified package that the manufacturer has data to correlate the performance to the designated package.
4/ Separate samples shall be pulled for each bias.



Source: https://assist.dla.mil -- Downloaded: 2026-10-19T05:46Z
Check the source to verify that this is the current version before use.

* TABLE III. Group E inspection (all quality levels) - for qualification or re-qualification only.


| Inspection | MIL-STD-750 | | Sample plan |
|---|---|---|---|
| | Method | Conditions | |
| Subgroup 1 | | | 45 devices c = 0 |
| Temperature cycling | 1051 | Condition G, 500 cycles | |
| Hermetic seal<br>Fine leak<br>Gross leak | 1071 | As applicable | |
| Electrical measurements | | See table I, subgroup 2 | |
| Subgroup 2 1/ | | | 45 devices c = 0 |
| Steady-state gate bias | 1042 | Condition B, 1,000 hours | |
| Electrical measurements | | See table I, subgroup 2 | |
| Steady-state reverse bias | 1042 | Condition A, 1,000 hours | |
| Electrical measurements | | See table I, subgroup 2 | |
| Subgroup 4 | | | Sample size N/A |
| Thermal impedance curves | 3161 | See MIL-PRF-19500 | |
| Subgroup 5 | | Not applicable | |
| Subgroup 10 | | | 22 devices c = 0 |
| Commutating diode for safe operating area test procedure for measuring dv/dt during reverse recovery of power MOSFET transistors or insulated gate bipolar transistors | 3476 | Test conditions shall be derived by the manufacturer. | |

1/ A separate sample for each test shall be pulled.
2/ Group E qualification of SEE effect testing may be performed prior to lot formation. Qualification may be extended to other specification sheets utilizing the same structurally identical die design.
3/ The sampling plan applies to each bias condition.



Source: https://assist.dla.mil -- Downloaded: 2026-10-19T05:46Z
Check the source to verify that this is the current version before use.

2N7607T3




2N7606U3






FIGURE 3. Thermal impedance graph.



Source: https://assist.dla.mil -- Downloaded: 2026-10-19T05:46Z
Check the source to verify that this is the current version before use.

2N7607T3




2N7606U3






FIGURE 4. Maximum drain current vs case temperature graphs.



Source: https://assist.dla.mil -- Downloaded: 2026-10-19T05:46Z
Check the source to verify that this is the current version before use.

2N7607T3




2N7606U3





FIGURE 5. Safe-operating-area graph



Source: https://assist.dla.mil -- Downloaded: 2026-10-19T05:46Z
Check the source to verify that this is the current version before use.

5. PACKAGING

5.1 Packaging. For acquisition purposes, the packaging requirements shall be as specified in the contract or order (see 6.2). When packaging of materiel is to be performed by DoD or in-house contractor personnel, these personnel need to contact the responsible packaging activity to ascertain packaging requirements. Packaging requirements are maintained by the Inventory Control Point's packaging activities within the Military Service or Defense Agency, or within the Military Service's system commands. Packaging data retrieval is available from the managing Military Department's or Defense Agency's automated packaging files, CD-ROM products, or by contacting the responsible packaging activity.

6. NOTES

(This section contains information of a general or explanatory nature that may be helpful, but is not mandatory. The notes specified in MIL-PRF-19500 are applicable to this specification.)

6.1 Intended use. Semiconductors conforming to this specification are intended for original equipment design applications and logistic support of existing equipment.

6.2 Acquisition requirements. Acquisition documents should specify the following:

a. Title, number, and date of this specification.

b. Packaging requirements (see 5.1).

c. Lead finish (see 3.4.1).

* d. The complete PIN, see 1.4 and 6.5.

e. For acquisition of RHA designated devices, table II, subgroup 1 testing of group D herein is optional. If subgroup 1 is desired, it should be specified in the contract.

f. If SEE testing data is desired, it should be specified in the contract or order.

6.3 Qualification. With respect to products requiring qualification, awards will be made only for products which are, at the time of award of contract, qualified for inclusion in Qualified Manufacturers List (QML 19500) whether or not such products have actually been so listed by that date. The attention of the contractors is called to these requirements, and manufacturers are urged to arrange to have the products that they propose to offer to the Federal Government tested for qualification in order that they may be eligible to be awarded contracts or orders for the products covered by this specification. Information pertaining to qualification of products may be obtained from DLA Land and Maritime, ATTN: P.O. Box 3990, Columbus, OH 43218-3990 or e-mail vqe.chief@dla.mil. An online listing of products qualified to this specification may be found in the Qualified Products Database (QPD) at https://assist.dla.mil .


6.4 Cross-reference list. The following table shows the generic P/N and its associated military P/N (without JAN and RHA prefix).

| Generic P/N | Military P/N |
|---|---|
| IRHLYS77034CM | 2N7607T3 |
| IRHLNJ77034CM | 2N7606U3 |



Source: https://assist.dla.mil -- Downloaded: 2026-10-19T05:46Z
Check the source to verify that this is the current version before use.

6.5 PIN construction example. The PINs for encapsulated devices are constructed using the following form.




6.6 List of PINs. The following is a list of possible PINs available on this specification sheet.

| PINs for devices in a TO-276AA package | PINs for devices in a TO-257AA package |
|---|---|
| JANTXVR2N7606U3 | JANTXVR2N7607T3 |
| JANSR2N7606U3 | JANSR2N7607T3 |

* 6.7 Request for new types and configurations. Requests for new device types or configurations for inclusions in this specification sheet should be submitted to: DLA Land and Maritime, ATTN: VAC, Post Office Box 3990, Columbus, OH 43218-3990 or by electronic mail at Semiconductor@dla.mil or by facsimile (614) 692-6939 or DSN 850-6939.

* 6.8 Amendment notations. The margins of this specification are marked with asterisks to indicate modifications generated by this amendment. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content irrespective of the marginal notations.

Custodians:
Army - CR
Navy - EC
Air Force - 85
NASA - NA
DLA - CC

Review activity:
Air Force - 99

Preparing activity:
DLA - CC

(Project 5961-2017-057)

NOTE: The activities listed above were interested in this document as of the date of this document. Since organizations and responsibilities can change, you should verify the currency of the information above using the ASSIST Online database at https://assist.dla.mil.



Source: https://assist.dla.mil -- Downloaded: 2026-10-19T05:46Z
Check the source to verify that this is the current version before use.