# CCC–B–791a

**AUGUST 27, 1937**

SUPERSEDING
Fed. Spec. CCC–B–791
March 29, 1932

FEDERAL STANDARD STOCK CATALOG

## Section IV

(Part 5)

## FEDERAL SPECIFICATION

FOR

# BUNTING; COTTON, MERCERIZED

This specification was approved on the above date by the Director of Procurement, for the use of all departments and establishments of the Government, and shall become effective not later than April 1, 1938. It may be put into effect, however, at any earlier date after promulgation.

### A. APPLICABLE FEDERAL SPECIFICATIONS.

**A–1.** The following Federal specifications of the issue in effect on date of invitation for bids form a part of this specification:

CCC–T–191.—Textiles; Test Methods.
TT–C–591.—Colors; (for) Flag of the United States.

### B. TYPES AND GRADE.

**B–1.** Bunting shall be of the following types as specified:

Type A.—Light weight.
Type B.—Heavy weight.

**B–2.** The grade shall be "firsts."

### C. MATERIAL AND WORKMANSHIP.

~~**C–1.** *Material.*—The bunting shall be made of cotton. The cotton shall be thoroughly cleaned, well combed, evenly drawn, spun~~

**C–2.** *Workmanship.*—The workmanship shall be of good quality in all respects. The bunting shall be evenly constructed and free from defects or blemishes affecting its appearance or which might affect its serviceability, other than as allowed under paragraph D–8.

### D. GENERAL REQUIREMENTS.

**D–1.** *Weave.*—The weave shall be plain.

**D–2.** *Mercerization.*—The bunting shall be fully mercerized.

~~**D–3.** *Singeing.*—The bunting shall not be singed.~~

**D–4.** *Selvages.*—The bunting shall be made with two nonraveling edges.

**D–5.** *Tolerances.*—

**D–5a.** *Width.*—A tolerance of plus ¾ inch and a minus tolerance of 1 percent will be permitted.



Source: https://assist.dla.mil -- Down
Check the source to verify that this is t

D–6. *Length of bolt.*—Any commercial length over 35 yards will be acceptable.

D–7. *Color.*—The color shall conform in hue and fastness to the standard sample where available, otherwise it shall have good color fastness when tested according to CCC–T–191. The bunting shall be evenly dyed, and shall show the above prescribed fastness to crocking, light, salt water, and soap. Bleeding of color shall not occur during salt water and soap test.

D–8. *Defects.*—The contractor shall indicate by a string at the nearest selvage, each stain, hole, small, filling yarn missing, damaged selvage, variation in shade, or other defect of equivalent importance, and shall make an allowance of ¼ yard for each such defect. Bunting shall not have any two such defects closer together than 10 yards, nor shall such defects occur at an average of more than one defect to every 5 yards. No single defect shall involve more than ¼ yard.

**E. DETAIL REQUIREMENTS.**

E–1. *Physical requirements.*—The physical requirements of the bunting shall be as shown in table I.

TABLE I

| Type | Width (inches) | Weight per sq. yd. (minimum ounces) | Ends per inch (minimum) | Picks per inch (minimum) | Breaking strength (minimum) | |
|---|---|---|---|---|---|---|
| | | | | | Warp (pounds) | Filling (pounds) |
| A | 18-inch, 36 inch, or as specified | 3.2 | 32 | 31 | 38 | 37 |
| B | 18-inch, 36-inch, or as specified | 4.5 | 31 | 30 | 50 | 50 |

E–2. The yarns shall be two-ply warp and filling.

**F. METHODS OF SAMPLING, INSPECTION, AND TESTS.**

F–1. *Sampling.*—

F–1a. *Sampling for tests.*—Not less than one sample, at least 1 yard by the width of the material, shall be taken at random from each 1,000 yards, or fraction thereof, except when the lot offered for inspection is over 10,000 yards, in which case a sample shall be taken at random from each one-tenth of the lot.

F–1b. *Sampling for defects.*—Not less than one bolt shall be taken at random from each 500 yards, or fraction thereof, except when the lot offered for inspection is over 2,500 yards, in which case a bolt shall be taken from each one-fifth of the lot. The presence of defects in excess of those allowed in paragraph D–8, or of defects not indicated by a string, shall be cause for rejection of the bolt in which they occur, and for inspection of the entire lot.

F–2. *Testing.*—Federal specification CCC–T–191 referred to in section A shall be used wherever applicable.

Source: https://assist.dla.mil -- Dow
Check the source to verify that this is

F–2a. *Strength.*—Strength shall be determined by the grab method.

F–2b. *Fastness to light.*—Fastness to light shall be determined by test no. 1 or test no. 2 of CCC–T–191 as specified.

F–2c. *Matching of color.*—Color shall be matched with standard samples by the method described in Federal specification TT–C–591, referred to in section A.

G. PACKAGING, PACKING, AND MARKING.

G–1. *Packaging.*—Unless otherwise specified, commercial packages will be acceptable under this specification.

G–2. *Packing.*—Unless otherwise specified, the subject commodity shall be delivered in standard commercial containers so constructed as to insure acceptance by common or other carrier for safe transportation at the lowest rate to the point of delivery.

G–3. *Marking.*—

G–3a. *Bolts or rolls.*—Unless otherwise specified, each bolt or roll shall have a ticket attached with the name of the material, the color, the width, the type, the quantity of each bolt or roll, the name of the contractor, and the number of the contract or order.

G–3b. *Shipping containers.*—Unless otherwise specified, shipping containers shall be marked with the name of the material, the color, the width, the type, the quantity contained therein, as defined by the contract or order under which shipment is made, the name of the contractor, and the number of contract or order.

H. REQUIREMENTS APPLICABLE TO INDIVIDUAL DEPARTMENTS.

H–1. The following departmental specifications of the issue in effect on date of invitation for bids and other special requirements form a part of this specification.

H–1a. *War Department.*—United States Army Specification No. 100–2, Standard Specifications for Marking Shipments.

H–1b. *Navy Department.*—General Specifications for Inspection of Material (copies of which may be obtained, without cost, upon application to the Bureau of Supplies and Accounts, Navy Department, Washington, D. C.).

H–2. *For War Department purchases.*—

H–2a. Blue bunting shall be dyed with vat colors; red bunting shall be dyed with vat or naphthol colors.

H–2b. Bunting shall show fastness equal to that of the standard sample when exposed to weather for 10, 20, and 30 days.

H–3. *Navy Department purchases.*—Standard samples of cotton bunting, in the shades purchased by the Navy Department, may be seen upon application to any of the following, or a portion thereof may be obtained upon application to the Commandant, Navy Yard, Mare Island, Calif., or the Commandant, Navy Yard, New York, N. Y.:

Commandant, Navy Yard, New York, N. Y.; Philadelphia, Pa.; Norfolk, Va.; Mare Island, Calif. Inspector of Naval Material, United States Navy, Boston, Mass.; Hartford, Conn.; Cincinnati, Ohio; Chicago, Ill.; Atlanta, Ga.; San Francisco, Calif.; Seattle, Wash.

Source: https://assist.dla.mil -- Dow
Check the source to verify that this is

**H–3a.** *Packing.*—Unless otherwise specified the subject commodity shall be delivered in substantial wooden cases or boxes so constructed as to insure safe delivery by common or other carriers to the point of delivery at the lowest rate. Cases or boxes may be of nailed, wire-bound or plywood construction, and shall weigh not in access of approximately 250 pounds gross when packed for shipment. Not more than one size, kind, or color of bunting shall be packed in a single container.

**H–3b.** *Marking—shipping containers.*—Unless otherwise specified, shipping containers shall be marked with the name of the material, the color, the width, type, and the quantity contained therein, as defined by the contract or order under which shipment is made, the name of the contractor, the number of the contract or order, and the gross weight.

**I. NOTES.**

**I–1.** Type A is intended to be used for signal flags, semaphore flags, and other uses. Type B is intended to be used for the manufacture of ensigns and other flags where the strength and durability of type A is inadequate for the intended service.

**I–2.** It is believed that this specification adequately describes the characteristics necessary to secure the desired material, and that normally no samples will be necessary prior to award to determine compliance with this specification. If, for any particular purpose, samples with bids are necessary, they should be specifically asked for in the invitation for bids, and the particular purpose to be served by the bid sample should be definitely stated, the specification to apply in all other respects.

**I–3.** An index of Federal specifications may be purchased as noted in the paragraph next below, price 10 cents.

**I–4.** Copies of this specification, and of CCC–T–191 and TT–C–591 may be obtained upon application, accompanied by money order, check, coupon, or cash, to the Superintendent of Documents, Government Printing Office, Washington, D. C. Price 5 cents each.

**Notice.**—When Government drawings, specifications, or other data are used for any purpose other than in connection with a definitely related Government procurement operation, the United States Government thereby incurs no responsibility nor any obligation whatsoever; and the fact that the Government may have formulated, furnished, or in any way supplied the said drawings, specifications, or other data, is not to be regarded by implication or otherwise as in any manner licensing the holder or any other person or corporation or conveying any rights of permission to manufacture, use, or sell any patented invention that may in any way be related thereto.

Source: https://assist.dla.mil -- Downlo
Check the source to verify that this is the