CCC-C-1798
December 27, 1972

FEDERAL SPECIFICATION

CLOTH, COATED COTTON, PLASTIC COATED TICKING

This specification was approved by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal agencies.

1. SCOPE AND CLASSIFICATION

1.1 Scope. This specification covers one type of flame resistant plastic coated ticking (see 6.1).

2. APPLICABLE DOCUMENTS

2.1 The following documents, of the issues in effect on date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein:

Federal Specifications:

CCC-C-436 - Cloth, Ticking Twill, Cotton.
PPP-P-1136 - Packaging, Packing of Coated (Plastic; Rubber) and Laminated Fabrics.

Federal Standards:

Fed. Std. No. 191 - Textile Test Methods.
Fed. Std. No. 406 - Plastics: Methods of Testing.
Fed. Std. No. 601 - Rubber: Sampling and Testing.

(Activities outside the Federal Government may obtain copies of Federal Specifications, Standards, as outlined under General Information in the Index of Federal Specifications and Standards and at the prices indicated in the Index. The Index, which includes cumulative monthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, U.S. Government Printing Office, Washington, D.C. 20402.

(Single copies of this specification and other Federal specifications required by activities outside the Federal Government for bidding purposes are available without charge from Business Service Centers, at the General Services Administration Regional Offices in Boston, New York, Washington, D.C., Atlanta, Chicago, Kansas City, Mo., Fort Worth, Denver, San Francisco, Los Angeles, and Seattle, Washington.

FSC 8305

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:31Z
Check the source to verify that this is the current version before use.

(Federal Government activities may obtain copies of Federal Specifications, Standards, and the Index of Federal Specifications and Standards from established distribution points in their agencies.)

Military Standards:

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes.

MIL-STD-1487 - Glossary of Cloth Coating Imperfections.

(Copies of Military Standards required by suppliers in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

3. REQUIREMENTS

3.1 Materials.

3.1.1 Base cloth. The base cloth shall conform to type II, class 2 of CCC-C-436.

3.1.2 Coating compound. The coating compound shall be formulated from vinyl chloride polymer or vinyl chloride acetate copolymer. Only phosphate or phthalate ester plasticizers shall be used. The coating compound shall be transparent, and when applied to the face side of the mattress ticking, shall not change the color or shade of the mattress ticking.

3.2 Coated cloth. The coating compound specified in 3.1.2 shall be applied to the face side, only, of the base cloth specified in 3.1.1 and the finished coated cloth shall meet all the requirements specified in table I

TABLE I. Coated cloth requirements

Characteristics	Requirement
Overall weight, oz./sq. yd. (maximum)	13.5
Breaking strength, pounds, minimum:	
Warp	90
Fill	50
Tearing strength, grams, minimum:	
Warp	1300
Fill	1500

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:31Z
Check the source to verify that this is the current version before use.

TABLE I. Coated Cloth requirements (cont'd)

Characteristics	Requirement
Hydrostatic resistance, psi, minimum:	
Initial	40
After stretch of coated cloth	40
Adhesion of coating, lbs./2 inches, minimum:	
Dry	6.0
Wet	5.0
Blocking, maximum	No. 2
Stiffness, cms, max 70°F (warp only)	11.0
Flame resistance:	
After flame, seconds, maximum	
Warp	3.5
Fill	3.5
Char length, inches, maximum:	
Warp	4.5
Fill	4.5
Anti-static surface resistance, maximum	5 x 10" ohms per sq.

3.3 Width. The width shall be as specified (see 6.2), and shall be the minimum acceptable width inclusive of selvage.

3.4 Length. Unless otherwide specified (see 6.2) the coated cloth shall be in one continuous length of not less than 40 yards.

3.5 Workmanship. The finished cloth shall be clean, evenly coated and shall conform to the quality and grade of product established by this specification. The occurrence of defects shall not exceed the applicable acceptable quality levels (AQLs).

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or order, the supplier may use his own or any other facilities

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:31Z
Check the source to verify that this is the current version before use.

suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure that supplies and services conform to prescribed requirements.

4.2 Certificate of compliance. Where certificates of compliance are submitted, the Government reserves the right to check test such items to determine the validity of the certification.

4.3 Inspection. Sampling for inspection shall be performed in accordance with MIL-STD-105, except where otherwise indicated hereinafter.

4.3.1 Inspection of components. In addition to the quality assurance provisions of applicable subsidiary specifications, the coating composition will be accepted on the basis of a supplier's certificate of compliance with requirements specified for such characteristics.

4.3.2 Examination of the end item. The end item shall be examined in accordance with the classification of defects at the inspection levels and acceptable quality levels (AQLs) set forth below. The lot size for purposes of determining the sample size in accordance with MIL-STD-105 shall be expressed in units of yards for the examination in 4.3.2.1 and 4.3.2.2.

4.3.2.1 Yard-by-yard examination. The required yardage of each roll shall be inspected on one side only. However, the sample shall be so alternated that in one out of every three pieces in the sample, the required yardage is examined on the uncoated side as applicable. Visual defects shall be classified as listed. The same yardage shall be given a thru-lighting inspection, for pinholes, areas of missing film and base cloth defects when visible. The through lighting equipment shall be as specified in MIL-STD-1487. The defects found shall be counted regardless of their proximity to each other except where two or more defects represent a single local condition of the cloth, in which case only the more serious defects shall be counted as one defect for each warpwise yard or fraction thereof in which it occurs. The sample unit shall be 1 linear yard. The acceptable quality level (AQL) for this examination shall be 4.0 major defects and 10.0 total defects per 100 units. The sample size shall be based upon inspection level III of MIL-STD-105. The number of rolls from which the sample is to be selected shall be in accordance with table II. An approximately equal number of yards shall be examined in each roll of the sample.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:31Z
Check the source to verify that this is the current version before use.

Defects	Classification	
	Major	Minor
Hole, cut or tear, including edges - any.	X	
Pinholes - any - clearly visible by thru-lighting.	X	
Abrasion - resulting in a thin or weak place or exposure of cloth structure.	X	
Blister, tunnels or delamination of coating - any size.	X	
Lump or heavier coated area - exceeding 1/2 inch in combined length and width dimensions or area not uniformly coated, clearly visible.		X
Crease or wrinkle - resulting in doubling that cannot be corrected by manual pressure, or adhesion of surfaces against each other, or any diagonal distortions of surface.	X	
Coating missing or noticeably thinner than normal.	X	
Coating noticeably heavier than normal.		X
Cloth edges rolled, folded or doubled.		X
Spot, stain or streak - one inch or more in combined directions, clearly visible. 1/	X	
-less than 1 inch but greater than 1/2 inch in combined direction, clearly visible. 1/		X
Width (overall) - less than specified.		X
Any tackiness.	X	
Coating not uniform in thickness.		X
Cloth baggy, wavy or puckered - will not stay flat upon manual pressure.	X	
Objectionable odor. 2/		X

1/ Clearly visible at normal inspection distance of 3 feet.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:31Z
Check the source to verify that this is the current version before use.

2/ Aromatic odors usually associated with specific types of coating compounds or solvents shall not be regarded as objectionable.

TABLE II. Sample size

Lot size in yards	Sample size in rolls	Acceptance number
1200 or less 1/	3	0
1201 up to and including 3200	5	0
3201 up to and including 10,000	8	0
10,001 up to and including 35,000	13	0
35,001 up to and including 150,000	20	1
150,001 and over	32	2

1/ If lot contains fewer than three rolls, each roll in the lot shall be examined.

4.3.2.2 Examination for length.

4.3.2.2.1 Individual rolls. The sample unit shall be one roll. The number of rolls to be examined and the acceptance number shall be in accordance with table II. The following shall be considered a defect:

Any roll (gross length) less than 40 yards.
Any roll containing more than 1 piece.

4.3.2.2.2 Total yardage in sample. The lot shall be unacceptable if the total of the gross lengths of the rolls in the sample is less than the total of the gross lengths marked on the tickets.

4.3.2.3 Examination of preparation for delivery requirements. An examination shall be made to determine whether the put-up, packaging, packing, and marking specified in section 5 complies with the applicable requirements of PPP-P-1136.

4.3.3 Testing of the end item. The methods of testing specified in Fed. Std. No. 191, wherever applicable, and as listed in table IV shall be followed. The physical and chemical values specified in Section 3 apply to the average of the determinations made on a sample unit for test purposes as specified in the applicable test method. The sample unit shall be 5 continuous yards, full width, of the finished cloth. The sample size shall be in accordance with table III. The lot will be unacceptable if one or more units fail to meet any requirement specified.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:31Z
Check the source to verify that this is the current version before use.

TABLE III. Sample size (end item)

Lot size (yards)	Sample size
801 or less	2
801 up to and including 22,000	3
22,001 and over	5

4.4 Test methods. Results of physical tests obtained under testing conditions defined in Fed. Std. No. 191, Fed. Std. No. 406, and Fed. Std. No. 601 will be acceptable except in case of dispute; in dispute cases tests shall be conducted with both specimen and test apparatus under standard conditions as defined in Fed. Std. No. 191.

TABLE IV. Instructions for testing

Characteristic	Requirement	Test method Fed. Std. No. 191
Weight	Table I	5041
Breaking strength:	"	
Warp		5100
Filling		5100
Tearing strength:	"	
Warp		5132
Filling		5132
Hydrostatic resistance:	"	
Initial		5512
After stretch of coated cloth		5972 1/ and 5512
Adhesion of coating:	"	
Dry		5970 2/
Wet		5970 3/
Blocking	"	5872
Stiffness	"	5204 4/
Flame resistance:	"	
After flame		
Warp		5903
Filling		5903

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:31Z
Check the source to verify that this is the current version before use.

TABLE IV. Instructions for testing (cont'd)

Characteristic	Requirement	Test method Fed. Std. No. 191
Char length		
Warp		5903
Filling		5903
Anti-static surface resistance	"	5930

1/ The samples shall be stretched in accordance with method 5972 except that a 30-pound load shall be applied parallel to the twill line only.

2/ Except that the length of the test specimen shall be eight inches.

3/ The original dry adhesion test shall be stopped after a 3-inch separation. The specimen immersed in distilled water at room temperature for 24 hours, withdrawn from the water, blotted dry, and the wet adhesion determined on the rest of the specimen.

4/ Specimens for stiffness test at 70°F shall be conditioned at test conditions for not less than 4 hours prior to the test. All tests shall be made in still air.

5. PREPARATION FOR DELIVERY

5.1 Put-up and packaging. Put-up and packaging shall be level A, B, or C as specified (see 6.2).

5.1.1 Level A. The coated cloth shall be put-up and packaged in accordance with the applicable level A requirements of PPP-P-1136.

5.1.2 Level B (civil agencies). The coated cloth shall be put-up and packaged in accordance with the applicable requirements specified in 5.1.1 (see 6.2).

5.1.3 Level C. The coated cloth shall be put-up and packaged in accordance with the applicable level C requirements of PPP-P-1136.

5.2 Packing. Packing shall be level A, B, or C as specified (see 6.2).

5.2.1 Levels A, B and C. The coated cloth of one description only, put-up and packaged as specified in 5.1, shall be packed in accordance with the applicable requirements of PPP-P-1136.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:31Z
Check the source to verify that this is the current version before use.

5.3 Marking.

5.3.1 Civil agencies. In addition to any special marking required by the contract or order, interior packages and shipping containers shall be marked in accordance with the applicable requirements of PPP-P-1136.

5.3.2 Military requirements. In addition to any special marking required by the contract or order, interior packages and shipping containers shall be marked in accordance with the applicable requirements of PPP-P-1136.

6. NOTES

6.1 Intended use. The coated cloth covered by this specification is intended for use in the manufacture of hospital mattresses.

6.2 Ordering data. Purchasers should select the preferred options permitted herein and include the following information in procurement documents:

(a) Title, number, and date of this specification.
(b) Width of cloth required (see 3.3).
(c) Length, if other than specified (see 3.4).
(d) Selection of the applicable levels of put-up, packaging and packing (see 5.1 and 5.2).

(e) When level B packaging is required for civil agencies (see 5.1.2).

Custodians:

Army - GL
Navy - SA

Preparing activity:

Army - GL

Civil Agency Coordinating Activities:

GSA-FSS

Review activities:

Army - MD
Navy - MS

User activities:

Navy - MC
Air Force - 03
DSA - DM

☆U. S. GOVERNMENT PRINTING OFFICE : 1973 O - 514-176 (298)

Orders for this publication are to be placed with General Services Administration, acting as an agent for the Superintendent of Documents. See section 2 of this specification to obtain extra copies and other documents referenced herein. Price 15 cents each.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:31Z
Check the source to verify that this is the current version before use.

SPECIFICATION ANALYSIS SHEET

Form Approved
Budget Bureau No. 22-R255

INSTRUCTIONS: This sheet is to be filled out by personnel, either Government or contractor, involved in the use of the specification in procurement of products for ultimate use by the Department of Defense. This sheet is provided for obtaining information on the use of this specification which will insure that suitable products can be procured with a minimum amount of delay and at the least cost. Comments and the return of this form will be appreciated. Fold on lines on reverse side, staple in corner, and send to preparing activity. Comments and suggestions submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or serve to amend contractual requirements.

SPECIFICATION

CCC-C-1798 Cloth, Coated Cotton, Plastic Coated Ticking

ORGANIZATION

CITY AND STATE

CONTRACT NUMBER

MATERIAL PROCURED UNDER A

☐ DIRECT GOVERNMENT CONTRACT ☐ SUBCONTRACT

1. HAS ANY PART OF THE SPECIFICATION CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE?

A. GIVE PARAGRAPH NUMBER AND WORDING

B. RECOMMENDATIONS FOR CORRECTING THE DEFICIENCIES

2. COMMENTS ON ANY SPECIFICATION REQUIREMENT CONSIDERED TOO RIGID

3. IS THE SPECIFICATION RESTRICTIVE?

☐ YES ☐ NO *(If "yes", in what way?)*

4. REMARKS *(Attach any pertinent data which may be of use in improving this specification. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity)*

SUBMITTED BY *(Printed or typed name and activity - Optional)*

DATE

DD FORM 1 JAN 66 1426

REPLACES EDITION OF 1 OCT 64 WHICH MAY BE USED

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:31Z
Check the source to verify that this is the current version before use.

FOLD

DEPARTMENT OF THE ARMY
U. S. Army Natick Laboratories
Natick, Massachusetts 01760

POSTAGE AND FEES PAID
DEPARTMENT OF THE ARMY

U.S.MAIL

OFFICIAL BUSINESS

Commanding General
U. S. Army Natick Laboratories
ATTN: AMXRES-BQS
Natick, Massachusetts 01760

FOLD

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:31Z
Check the source to verify that this is the current version before use.