CCC-M-911
AUGUST 26, 1936

FEDERAL STANDARD STOCK CATALOG

Section IV

(Part 5)

FEDERAL SPECIFICATION

FOR

MUSLIN; BLEACHED

This specification was approved by the Director of Procurement, for the use of all departments and establishments of the Government, and shall become effective not later than April 1, 1937. It may be put into effect, however, at any earlier date after promulgation.

A. APPLICABLE FEDERAL SPECIFICATIONS.

A–1. The following Federal Specification of the issue in effect on date of invitation for bids, shall form a part of this specification:

F. S. CCC–T–191, Textiles, Test Methods.

A–2. Any special requirements of the individual departments of the Government are noted under section H.

B. TYPES.

B–1. Muslin; bleached, shall be furnished in two types as specified:

Type I. Minimum weight, 3.1 ounces per square yard.
Type II. Minimum weight, 2.4 ounces per square yard.

C. MATERIAL AND WORKMANSHIP.

C–1. *Material.*—Shall be manufactured from well-carded cotton yarns.

C–2. *Workmanship.*—The material shall be free from defects affecting its appearance or which may affect its serviceability.

D. GENERAL REQUIREMENTS.

D–1. *Finish.*—Shall be bleached white. Shall be of nainsook or pure finish.

D–2. *Tolerance.*—A width tolerance of plus or minus ½ inch will be permitted.

D–3. *Widths.*—Shall be 36 inches unless otherwise specified.

D–4. *Length of bolt or roll.*—Unless otherwise specified, any commercial length of 40 yards or over will be acceptable.

E. DETAIL REQUIREMENTS.

E–1. The requirements shall be as shown in table I.

448250 O - 42

Source: https://assist.dla.mil -- Download
Check the source to verify that this is the

TABLE I

Type	Weight per square yard (minimum)	Ends and picks		Weave	Breaking strength minimum (pounds)	
		Ends (minimum)	Picks (minimum)		Warp	Filling
	Ounces					
I	3.1	85	72	Plain	45	30
II	2.4	64	56	Plain	35	25

F. METHODS OF SAMPLING, INSPECTION, AND TESTS.

F–1. Any requirements applicable to the individual departments are noted under section H.

F–2. *Sampling.*—Not less than one sample not less than one yard full width shall be taken at random from each 1,000 units or fraction thereof, except when the shipment is over 10,000 units, in which case a sample shall be taken from each one-tenth of the shipment.

F–3. *Inspection and tests.*—Shall be conducted in accordance with Federal Specification CCC–T–191, referred to in section A.

G. PACKAGING, PACKING, AND MARKING.

G–1. Any special requirements of the individual departments of the Government are noted under section H.

G–2. *Packaging.*—Unless otherwise specified, commercial packages are acceptable under this specification.

G–3. *Packing.*—Unless otherwise specified, the subject commodity shall be delivered in standard commercial containers, so constructed as to insure acceptance by common or other carriers, for safe transportation, at the lowest rate, to the point of delivery.

G–4. *Marking.*—Unless otherwise specified, shipping containers shall be marked as to the name of the material, the type, width, and quantity contained therein, as defined by the contract or order under which the shipment is made, the name of the contractor, and the number of the contract or order.

H. REQUIREMENTS APPLICABLE TO INDIVIDUAL DEPARTMENTS.

H–1. The following departmental specifications of the issue in effect on the date of invitation for bids shall form a part of this specification:

H–1a. Army: U. S. Army Specification No. 100–2, Standard Specification for Marking Shipments. Copies of this specification may be obtained by prospective bidders, without cost, upon application to the distributing agency indicated in the Invitation for Bids.

H–1b. Navy: Navy Department General Specifications for Inspection of Material, copies of which may be obtained, without cost, upon application to the Bureau of Supplies and Accounts, Navy Department, Washington, D. C.

Source: https://assist.dla.mil -- Dowr
Check the source to verify that this is

I. NOTES.

I–1. Purchasers should exercise all options offered herein, and should specify type and width desired.

I–2. It is believed that this specification adequately describes the characteristics necessary to secure the desired material, and that normally no samples will be necessary prior to award to determine compliance with this specification. If, for any particular purpose, samples with bids are necessary, they should be specifically asked for in the invitation for bids, and the particular purpose to be served by the bid sample should be definitely stated, the specification to apply in all other respects.

I–3. An index of Federal specifications may be purchased as noted in the paragraph next below, price 10 cents.

I–4. Copies of this specification, and of Federal Specification CCC–T–191, may be obtained upon application, accompanied by money order, or coupon, or cash to the Superintendent of Documents, Government Printing Office, Washington, D. C. Price, 5 cents.

Notice.—When Government drawings, specifications, or other data are used for any purpose other than in connection with a definitely related Government procurement operation, the United States Government thereby incurs no responsibility nor any obligation whatsoever; and the fact that the Government may have formulated, furnished, or in any way supplied the said drawings, specifications, or other data is not to be regarded by implication or otherwise as in any manner licensing the holder or any other person or corporation, or conveying any rights or permission to manufacture, use, or sell any patented invention that may in any way be related thereto.

[CCC–M–911]

Source: https://assist.dla.mil -- Downloa
Check the source to verify that this is the