DDD-C-95
INT. AMENDMENT-2(GSA-FSS)
July 9, 1970
SUPERSEDING
INT. AMENDMENT-1(GSA-FSS)
March 10, 1969

INTERIM AMENDMENT

TO

FEDERAL SPECIFICATION

CARPETS AND RUGS, WOOL, NYLON, ACRYLIC, MODACRYLIC

This interim amendment was developed by the Standardization Division, Federal Supply Service, General Services Administration, Washington, D.C. 20406, based on currently available technical information. It is recommended that Federal agencies use it in procurement and forward recommendations for changes to the preparing activity at the address shown above.

The General Services Administration has authorized Federal agencies to use this amendment as a valid exception to Federal Specification DDD-C-95, dated April 16, 1965.

PAGE 1

Title - After "MODACRYLIC" add "POLYESTER, POLYPROPYLENE".

Paragraph 1.2.1 - Under Type II - velvet, delete the following categories in their entirety:

Class 1, Subclass A
Class 4, Subclass A
Class 4, Subclass B

Paragraph 1.2.1 - Under Type III - Wilton, delete the following categories in their entirety:

Class 1
Class 2
Class 4

Paragraph 1.2.1 - Under Type IV, add new Subclass C under Class 3 as follows:

"Subclass C - (42 oz./sq. yd. pile)"

Paragraph 1.2.1 - Under Type IV, add new Class 6 and Subclasses A and B as follows:

"Class 6 - Single level loop - filament nylon or filament polypropylene
Subclass A - (21 oz./sq. yd. pile)
Subclass B - (28 oz./sq. yd. pile)"

Paragraph 1.2.1 - Under Type V, class 1, opposite Subclass B, delete "37 oz " and substitute "49 oz."

PAGE 3

Paragraph 3.2.1 - lines 2 and 3 - delete "acrylic or modacrylic" and substitute "acrylic, modacrylic, polyester or polypropylene".

Paragraph 3.2.1.1 - line 5 - delete "97" and substitute "95".

Paragraph 3.2.1.1 - lines 6 and 7 - delete "dry weight of the specimen" and substitute "weight of the original dry specimen".

FSC 7220

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:32Z
Check the source to verify that this is the current version before use.

Add new paragraphs 3.2.1.6 and 3.2.1.7 as follows:

3.2.1.6 Polyester. Polyester shall be carpet type fiber, with average fiber size of 15 denier or coarser, which has never been reclaimed from any woven, tufted, knitted, or felted products. The finished yarn shall contain not more than 2.0 percent chloroform soluble material when tested as specified in 4.2.1.

3.2.1.7 Filament polypropylene. Filament polypropylene shall be continuous filament high bulk or textured carpet type yarn. Individual filament size shall average 15 denier or coarser. Filament polypropylene shall be used only in those fabrics where specified in the table of physical requirements. The finished yarn shall contain not more than 2.0 percent cold isopropanol soluble material.

Paragraph 3.2.3 - delete in its entirety and substitute:

3.2.3 Backing material. The backing material shall be a woven fabric of either jute weighing not less than 9.2 ounces per square yard, or polypropylene weighing not less than 3.2 ounces per square yard, or a nonwoven fabric consisting of not less than 75% polypropylene fibers with the balance cellulosic, nylon or polyester fibers weighing not less than 4.0 ounces per square yard.

Paragraph 3.2.4 - add new sentence as follows

"When specified in the contract or order, the backing reinforcement may be polypropylene fabric weighing not less than 4.0 ounces per square yard."

Paragraph 3.7.2 - subparagraph b. - delete in its entirety and substitute

"b. Cushioning for carpets and rugs other than for wall-to-wall installation shall cover the entire carpet or rug. All carpet or rug edges may be straight cut."

Paragraph 3.7.2.1 - after first sentence insert the following sentence

"Cotton tape not less than 3/4 inch wide of the same number of ends and picks per square inch may be used."

Paragraph 3.7.3 - delete in its entirety and substitute

3.7.3 Seaming. Standard seamless broadloom widths shall be used unless the size required necessitates seaming. Seams shall be kept to the minimum practicable. Seams, where required, are to be sewn or taped (or both) as specified. Seams on carpets and rugs without attached rubber cushioning shall have a breaking strength of not less than 100 pounds when tested as specified in 4.4. Tape used in making seams shall be a minimum of 2-1/2 inches wide. Seams of rugs with attached rubber cushioning, not installed wall-to-wall, shall be made with carpet type, single face, pressure sensitive adhesive tape with a minimum width of three inches. The tape used should be that recommended by the carpet manufacturer, or equal. In addition, adhesive shall be applied to both edges of the carpet at the joint. These edges shall be brought together to insure direct contact of the adjoining edges after application of the adhesive. For seams on carpets with attached rubber cushioning, used in wall-to-wall installations, the edges shall be brought together to insure good contact. Unless otherwise specified by the ordering activity, the contractor shall secure seams by tape or adhesive, or a combination of these. Such tape or adhesive shall be those recommended by the carpet manufacturer or equal. The finished seams shall be secure and able to withstand conventional commercial rug cleaning processes.

Paragraph 3.8 - delete in its entirety and substitute

3.8 Flame resistance. Charred portion shall not extend to within 1 inch of the edge of the hole in the flattening frame at any point.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:32Z
Check the source to verify that this is the current version before use.

TABLE I - Type I - insert footnote reference "1/" after "See 3.2.1" opposite "Pile." Also, insert footnote reference under table as follows:

"1/ When 100 percent staple nylon is used, a minimum fiber size of 6 denier is acceptable, provided not less than 40 percent of the fibers used in the pile yarn are 15 denier or coarser."

TABLE II - Type II - Class 1, Subclass A - delete physical requirements in their entirety.

PAGE 7

TABLE II - Type II - Class 4, Subclasses A and B - delete physical requirements in their entirety.

TABLE II - Type II - delete class 7 physical requirements in their entirety and substitute the following:

Class	7 2/
Description	Two level loop pile woven thru back
Tufts/sq. in.	49
Shots/wire	2
Weight oz./sq/ yd.	
Pile	22
Total	40
Pile height (in.) Min.	0.200
Max	0.290
Material	
Pile	100 percent filament nylon see 3.2.1.3
Chain	Cotton and/or rayon
Filling	Cotton and/or rayon or jute
Stuffer	Cotton, jute or kraftcord
Back coating oz./sq yd	8
Tuft bind (oz.)	80
Ply twist turns (per inch) Min.	1.0
Max.	3.0

TABLE III - Type III - Classes 1, 2 and 4 - delete physical requirements in their entirety.

PAGE 8

TABLE IV - Type IV - under class 3, Subclass B, opposite Pile Height, delete "Max. 0.500" and substitute "Max. 0.600"

TABLE IV - Type IV - under class 3, insert new Subclass C physical requirements as follows:

Subclass	C
Tufts/sq/ in.	35
Weight oz sq. yd pile	42
Pile height (in.) Min.	0.400
Max.	0.700
Materials Pile	See 3.2.1
Tuft bind (oz.)	50
Ply twist turns (per inch) Min	2.0
Max	4.0

TABLE IV - Type IV - Class 4 - Opposite "Pile height" under Subclasses A and B delete "Min. 0.320" and substitute "Max 0.320".

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:32Z
Check the source to verify that this is the current version before use.

CDD-C-95

TABLE IV - Type IV - insert new Class 6, Subclasses A and B, physical requirements as follows:

Class	6 1/	
Description	Single level loop	
Subclass	A	B
Tufts/sq. in.	54	54
Weight oz. sq yd. pile	21	28
Pile height (in.) Min.	0.150	0.175
Max.	0.200	0.225
Materials Pile	100 percent filament nylon or filament polypropylene	
Tuft bind (oz.)	100	100

TABLE IV - Footnote 1/ - insert "and 6" after "1".

TABLE V - Type V - under class 1, Subclass A, delete and substitute specified requirements as follows.

	Delete	Substitute
Weight oz./sq. yd., total	52	62
Back coating, oz./sq. yd.	14	18

TABLE V - Type V - under Class 1, Subclass B, delete and substitute specified requirements as follows:

	Delete	Substitute
Tufts/sq in.	26	40
Weight oz./sq. yd., pile	37	49
total	58	85
Pile height, Min.	0.230	0.240
Max.	0.290	0.270
Back coating, oz. sq. yd.	14	18
Tuft bind	—	32

TABLE V - Type V - under Class 2, delete and substitute specified requirements as follows.

	Delete	Substitute
Tufts/sq. in.	25	39
Weight oz./sq. yd., pile	25	33
total	45	68

PAGE 9

TABLE VII - opposite "Pile yarn (lbs.)" add the following in the column specified:

Characteristic	Requirement paragraph	Test method
Isopropanol sol. material	3.2.1.7	Std Commercial 3/

TABLE VII - add new footnote 3/ under table as follows.

"3/ The contractor shall submit a certificate of compliance for this characteristic. The certificate shall be accompanied by actual test or other verifiable quality data Tes may be conductec on finished carpet specimens."

PAGE 14

Paragraph 4.5.8.. - after first sentence insert the following sentence

"Surface roughness left on rubber sample because of removal of carpet material shall when necessary be buffed to present a suitable flat surface for testing."

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:32Z
Check the source to verify that this is the current version before use.

Paragraph 4.5.13 - delete in its entirety and substitute

4.5.13 Flame resistance.

4.5.13.1 Test specimens Each test specimen shall be a 9 ± 1/4 inches square section of the carpet or rug to be tested. Eight specimens are required.

4.5.13.2 Apparatus.

a Test chamber. The test chamber shall consist of an open top hollow cube made of noncombustible material 2/ with inside dimensions 12 by 12 by 12 inches and a minimum of 1/4 inch wall thickness The flat bottom of the box shall be made of the same material as the sides and shall be easily removable. The sides shall be fastened together with screws or brackets and taped to prevent air leakage into the box during use.

NOTE: A minimum of two chambers and two extra bottoms is suggested for efficient operation.

b Flattening frame A steel plate, 9 by 9 inches, 1/4 inch thick with a 8 inch diameter hole in its center is required to hold the carpet or rug flat during the course of the test. It is recommended that one be provided for each test chamber.

c. Standard igniting source No. 1588 methenamine timed burning tablet or an equal tablet. These tablets shall be stored in a desiccator over a desiccant for 24 hours prior to use (Small quantities of sorbed water may cause the tablets to fracture when first ignited. If a major fracture occurs, any results from that test shall be ignored, and it shall be repeated.)

d Circulating air oven A forced circulation drying over capable of removing the moisture from the specimens when maintained at 105°C. (221°F.) for 2 hours. 3/

e Desiccating cabinet. An airtight and moisturetight cabinet capable of holding the floor covering specimens horizontally without contacting each other during the cooling period following drying and containing silica gel desiccant

f Gloves Nonhygroscopic gloves (such as rubber polyethylene) for handling the sample after drying, and raising the pile on specimens prior to testing.

g Hood. A hood capable of being closed and having its draft turned off during each test and capable of rapidly removing the products of combustion following each test. The front or sides of the hood should be transparent to permit observation of the tests in progress

h Mirror A small mirror mounted above each test chamber at an angle to permit observation of the specimen from outside of the hood.

i Vacuum cleaner A vacuum cleaner to remove all loose material from each specimen prior to conditioning All surfaces of the vacuum cleaner contacting the specimen shall be flat and smooth.

4.5.13.3 Procedure

a Cutting and when specified washing procedure of fire retardant treated Cut eight 9 ± 1/4 inch square specimens of each carpet or rug to be tested. Note, if the carpet or rug has had a fire-retardant treatment, or is made of fibers which have had a fire-retardant treatment, and when specified in the contract or order (6.2), the selected sample or oversized specimens thereof shall be washed, prior to cutting of test specimens, 10 times under the washing and drying procedure prescribed in Method 124-1967 of the American Association of Textile Chemists and Colorists (washing procedure 6.2 (III) with a water temperature of 60° ± 2.8°C. (140° ± 5°F.), drying procedure 6.3.. (B), maximum load 3.64 kg. (8 pounds), unless otherwise specified.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:32Z
Check the source to verify that this is the current version before use.

b Conditioning. Clean each specimen with the vacuum cleaner until it is free of all loose ends left during the manufacturing process and from any material that may have been worked into the pile during handling. 3/ Care must be exercised to avoid "fuzzing" of the pile yarn.

Place the specimens in the drying oven in a manner that will permit free circulation of the air at 105°C. (221°F.) around them for 2 hours 4/ Remove the specimens from the oven with gloved hands and place them horizontally in the desiccator with traffic surface up and free from contact with each other until cooled to room temperature, but in no instance less than 1 hour

c Testing Place the test chamber in the draft-protected environment (hood with draft off) with its bottom in place Wearing gloves, remove a test specimen from the desiccator and brush its surface with a gloved hand in such a manner as to raise its pile. Place the specimen on the center of the floor of the test chamber, traffic surface up, exercising care that the specimen is horizontal and flat. Place the flattening frame on the specimen and position a methenamine tablet on one of its flat sides in the center of the 8 inch hole

Ignite the tablet by touching a lighted match or an equivalent igniting source carefully to its top If more than 2 minutes elapse between the removal of the specimen from the desiccator and the ignition of the tablet the conditioning must be repeated

Continue each test until one of the following conditions occurs

(1) The last vestige of flame or glow disappears (This is frequently accompanied by a final puff of smoke.)

(2) The flaming or smoldering has approached within 1 inch of the edge of the hole in the flattening frame at any point

When all combustion has ceased, ventilate the hood and measure the shortest distance between the edge of the hole in the flattening frame and the charred area Record the distance measured for each specimen.

Remove the specimen from the chamber and remove any burn residue from the floor of the chamber Before proceeding to the next test, the floor must be cooled to normal room temperature or replaced with one that is at normal room temperature

d Report The number of specimens of the eight tested in which the charred area does not extend to within 1 inch of the edge of the hole in the flattening frame shall be reported.

e Interpretation of results If the charred area does not extend to within 1 inch of the edge of the hole in the flattening frame at any point for at least seven of the eight specimens, the carpet or rug meets the acceptance criterion

Footnotes.

1/ 6 mm. (1/4 inch) cement asbestos board is a suitable material

2/ Option 1 of ASTM D 2654-07, Methods of Test for "Amount of Moisture in Textile Materials" describes a satisfactory oven.

3/ The vacuum cleaning described is not intended to simulate the effects of repeated vacuum cleaning in service

4/ If the specimens are moist, permit them to air-dry at laboratory conditions prior to placement in the oven

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:32Z
Check the source to verify that this is the current version before use.

PAGE 17

Paragraph 6.1 - 2nd column - line 13 - delete "wool, acrylic or modacrylic".

Paragraph 6.1 - 2nd column - line 21 - delete "Carpet" and substitute "Exceptions are carpet"

Paragraph 6.1 - 2nd column - line 22 - after "nylon" insert "or, in the carpet constructions specified herein, continuous filament polypropylene".

Paragraph 6.2 - 2nd column - line 24 - delete "traffic. Those" and substitute "traffic and those

Paragraph 6.2 - subparagraph (b) - after "pile fiber" insert "(a maximum pile height of 0.250 inch is recommended when polypropylene filament is specified)"

Paragraph 6.2 - add subparagraph (m)

(m) Specify when washing procedure is applicable, if fire retardant treated (4.5.12.3)

PAGE 18

Add new paragraph 6.6 as follows

6.6 Special flame resistance. Federal agencies responsible for hospitals and medical facilities are directed to the publication General Standards of Construction and Equipment for Hospital and Medical Facilities, issued by the U.S. Department of Health, Education, and Welfare. This publication contains regulations relating to the implementation of the Hill-Burton program, including special construction and fire-resistive requirements.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:32Z
Check the source to verify that this is the current version before use.

GENERAL SERVICES ADMINISTRATION FEDERAL SUPPLY SERVICE

SPECIFICATION COMMENT SHEET

BUREAU NO 29-R0175

INSTRUCTIONS

This form provides a way for users of this specification to inform the originator of problems encountered in its use It is not to be used to request changes to accommodate proprietary features All comments will be considered and appreciated, but please do not expect a reply To comment detach, complete, and mail to: General Services Administration, FSS (FMSF), Washington, D.C. 20406.

NOTE Comments on this form do not constitute or imply authorization to waive any part of the document or serve to amend contractual requirements

1 SPECIFICATION
DDD-C-95 Int Amd 2
Carpets and Rugs, Wool, Nylon, Acrylic, Modacrylic

2 CONTRACT NO *(If any)*	3 QUANTITY ON CONTRACT *(Optional)*	4 DOLLAR VALUE *(Optional)*

5 GENERAL NATURE OF PROBLEM *(e g inspection difficulties manufacturers unable to meet tolerances containers collapse under normal warehousing conditions etc)*

6 SPECIFIC REQUIREMENTS AFFECTED *(Include paragraph number and lines of wording)*

7 SPECIFIC PROBLEMS *(e g tests in 4 2 2 will not assure that the batten will has required time temperature ranges in table 2 do not conform to commercially available items)*

8 RECOMMENDATIONS

9 NAME OF MANUFACTURER ASSOCIATION GOVT AGENCY ETC	10 ADDRESS *(Number Street City State and Zip Code)*

11 NAME AND TITLE OF SUBMITTER	12 DATE

FORM GSA FEB 69 2200

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:32Z
Check the source to verify that this is the current version before use.