FEDERAL SPECIFICATION

LABEL (COTTON, WOVEN, GENERAL USE)

This specification was approved by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal agencies.

1. SCOPE AND CLASSIFICATION

1.1 Scope.—This specification covers the requirements for printed labels made of a coated or impregnated fabric.

1.2 Classification.—The labels shall be of one type and three classes, as specified (see 6.2).

Class 1.—Instruction
Class 2.—Identification
Class 3.—Size marking

2. APPLICABLE SPECIFICATIONS AND STANDARDS

2.1 The following specifications and standards, of the issues in effect on date of invitation for bids, form a part of this specification:

Federal Specifications:

UU–T–111 — Tape; Paper, Gummed (Sealing and Securing).
CCC–T–191—Textile Test Methods.
PPP–B–566 — Boxes; Folding, Paperboard.
PPP–B–585—Boxes; Wood, Wirebound.
PPP–B–591—Boxes; Fiberboard, Wood-Cleated (For Domestic Shipment).
PPP–B–601—Boxes; Wood, Cleated-Plywood.
PPP–B–621—Boxes, Wood, Nailed and Lock-Corner.
PPP–B–676 — Boxes, Set-Up, Paperboard.
PPP–P–31 — Preservation, Packaging, Packing, and Marking of Material; and Shipping Instructions (Domestic Shipment and Storage).

Federal Standards:

FED–STD–102—Preservation, Packaging, and Packing Levels.

(Activities outside the Federal Government may obtain copies of Federal Specifications and Standards as outlined under General Information in the Index of Federal Specifications and Standards and at the prices indicated in the Index. The Index, which includes cumulative monthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, U. S. Government Printing Office, Washington 25, D. C.

(Single copies of this specification and other product specifications required by activities outside the Federal Government for bidding purposes are available without charge at the General Services Administration Regional Offices in Boston, New York, Atlanta, Chicago, Kansas City, Mo., Dallas, Denver, San Francisco, Los Angeles, Seattle, and Washington, D. C.

(Federal Government activities may obtain copies of Federal Specifications and Standards and the Index of Federal Specifications and Standards from established distribution points in their agencies.)

Military Specifications:

MIL–B–10377 — Box, Wood, Cleated, Veneer, Paper Overlaid.
MIL–L–10547 — Liners, Case, Waterproof.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:32Z
Check the source to verify that this is the current version before use.

Military Standards:

MIL–STD–105 — Sampling Procedures and Tables for Inspection by Attributes and Appendix.

MIL–STD–129—Marking for Shipment and Storage.

(Copies of Military Specifications and Standards required by the contractor in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

3. REQUIREMENTS

3.1 Standard samples.—When specified, standard samples will be furnished by the Government to illustrate the size and the required information to be printed on the labels (see 6.2).

3.2 Material.

3.2.1 *Basic fabric.*—The basic fabric for the label shall be cloth, cotton, print, bleached white, having not less than 80 ends in the warp and 72 ends in the filling, per inch.

3.2.2 *Coating.* — The fabric shall be impregnated or surface coated with a synthetic resin or rubber, suitably compounded and pigmented to meet the performance requirements of the finished labels. The surface coating or impregnating material shall not be affected when subjected to colorfastness tests specified in 4.3.

3.3 Label.

3.3.1 *Weight of fabric.*—The weight of the finished fabric, used for the labels, shall be not less than 3.6 nor more than 4.8 ounces per square yard when tested as specified in 4.3.

3.3.2 *Color.*—The color of the label shall be white.

3.3.3 *Resistance to raveling and fraying.*—The label shall not ravel or fray when tested as specified in 4.3.1.

3.3.4 *Blocking.*—The label shall show no "blocking," after being subjected to the blocking test specified in 4.3.2.

3.3.5 *Mildew resistance.* — When mildew resistance is specified (see 6.2) the finished cloth shall not support mildew growth when tested as specified in 4.3.

3.3.6 *Printing medium.*—The labels shall be printed with a black marking medium. The printing shall not show off-setting, smearing or bleeding and shall be legible and not show objectionable transference after testing for colorfastness as specified in 4.3.

3.3.7 *Printing.*—The labels shall be printed with one of the following type faces in 10 point size, plain or italics: Antique No. 1, Bodoni, Caslon, Cheltenham, Garamond, or Old Style No. 1. The type shall be set capitals and lower case, 18 picas wide on 10 point slug, leaded 2 points between lines. The label shall be provided with a $\frac{3}{16} \pm \frac{1}{16}$ inch margin on four sides for sewing purposes. The label shall contain the information and illustrations as specified (see 6.2).

3.3.8 *Size of labels.*—The labels shall be furnished in the sizes specified (see 6.2). A tolerance of plus or minus $\frac{1}{8}$ inch in length and width shall be permitted.

3.4 Workmanship. — The finished labels shall conform to the quality of product established by this specification. Occurrence of defects shall be limited in accordance with the acceptable quality levels (see 4.2.1.4).

4. SAMPLING, INSPECTION, AND TEST PROCEDURES

4.1 General.—The quality assurance provisions contained in this section are applicable to inspection by and for the Government. Quality assurance provisions for components or materials described shall be in accordance with this specification and with subsidiary specifications referenced herein to the extent applicable, except that this specification shall govern in the event of conflict.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:32Z
Check the source to verify that this is the current version before use.

4.2 Inspection for acceptance. — Except when otherwise specified by civilian government agencies, inspection shall be in accordance with the provisions of Military Standard MIL–STD–105 and Appendix thereto except where otherwise indicated.

4.2.1 *Inspection of the end item.*

4.2.1.1 *Visual examination.*—Defects found during this examination shall be classified in accordance with the list below. The Government reserves the right to require examination for any defect not included herein and to classify such defects in accordance with the definitions contained in Military Standard MIL–STD–105. All defective units of product (labels) shall be counted, basing the count on the most serious defect occuring in the unit of product. The unit of product for this inspection shall be one label.

TABLE I.—*Classification of defects*

Defect	Classification	
	Major	Minor
Any cut, holes or tears	X	
Any weak or tender spot	X	
Crease resulting from faulty coating	X	
Uncoated	X	
Uneven coating—thin area where coating compound is missing or insufficient		X
Blisters or lumps—any size		X
Single, broken or missing yarn—clearly noticeable		X
Two or more broken or missing yarns	X	
Spot or stain—clearly noticeable		X
Printing—Not legible, incorrect or incomplete	X	
Not type and style of lettering and script specified		X
Other than black letters		X
Color of label other than white		X

4.2.1.2 *Dimensional examination.* — The unit of product for this examination shall be one label each. A label shall be considered defective with respect to measurements if the overall dimensions, the size of print, illustrations or margins are not as specified.

4.2.1.3 *Examination for packaging.*—The unit of product for this examination shall be one bundle of labels each.

Defective:

Class 1 labels — More than five below specified quantity.

Classes 2 and 3 labels—More than twelve below specified quantity.

Bundles consisting of more than one class of labels.

Bundle not securely tied with cord or twine.

4.2.1.4 *Acceptable quality levels.*—Acceptable quality levels shall be as follows:

(*a*) Visual examination (4.2.1.1) : 2.5 percent defective (major) and 6.5 percent defective (major and minor combined).

(*b*) Examination for dimensions (4.2.1.2) : 2.5 percent defective.

(*c*) Examination for packaging (4.2.1.3) : 4.0 percent defective.

4.2.1.5 *Inspection levels.*

(*a*) Visual examination (4.2.1.1). — Inspection level II of Military Standard MIL–STD–105. The lot size shall be expressed in units of one individual label.

(*b*) Examination for dimensions (4.2.1.2). —Inspection level I of Military Standard MIL–STD–105. The lot size shall be expressed in units of one individual label.

(*c*) Examination for packaging (4.2.1.3). —Inspection level L–1 of Appendix to Military Standard MIL–STD–105. The lot size shall be expressed in units of one bundle each.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:32Z
Check the source to verify that this is the current version before use.

4.3 Test.—The methods of testing specified in Federal Specification CCC–T–191, wherever applicable, and as listed in table II shall be followed. The physical and chemical values specified in section 3 apply to the average of the determinations made on a unit of product for test purposes as specified in the applicable test methods. Except when otherwise specified by Civilian Government agencies, for each characteristic, the acceptable quality level shall be 4.0 test failures per 100 units. The unit of product shall be 1 yard of coated fabric and fifteen printed labels. Except when otherwise specified by Civilian government agencies, the inspection level shall be level L–1, table VII, Appendix to Military Standard MIL–STD–105. The lot size shall be expressed in units of one label each.

TABLE II.—*Tests*

Test	Requirement reference	Method no.
Yarns per inch	3.2.1	5050
Weight (oz. sq. yd. basis)	3.3.1	5041
Raveling and fraying	3.3.3	Par. 4.3.1
Blocking	3.3.4	5872
Mildew resistance	3.3.5	5752
Colorfastness (printing)	3.3.6	
Color transference		5640
Fastness to laundering[1]		5610
Fastness to perspiration		5682
Fastness to dry cleaning		5620

[1] The laundering test shall be repeated five times. The transfer test cloth shall be placed over the printing and attached at four corners.

4.3.1 *Resistance to raveling and fraying.*—The resistance to raveling and fraying shall be determined by visual examination of the sample used in the fastness to laundering test specified in table II.

4.3.2 *Blocking test.*—Blocking test shall be conducted in accordance with method 5872 except that the temperature of testing shall be 104.4° ± 1°C. (220° ± 1.8°F.).

5. PREPARATION FOR DELIVERY

5.1 Packaging.

5.1.1 *Level A.*—Two hundred class 1 labels; or 500 class 2 labels; or 500 class 3 labels shall be neatly stacked in a bundle and cross-tied with suitable cord or twine. Labels of one class only, tied in quantities as specified, shall be packaged in a snug-fitting set-up paperboard box conforming to type I, class A, style 3 or 4 of Federal Specification PPP–B–676; or in a folding paperboard box conforming to style III or IV, type A or B, class A of Federal Specification PPP–B–566. Thumb hold requirements shall be waived. Closure shall be effected by means of a strip of gummed paper tape, a minimum of 2 inches in width, centered girthwise, conforming to class 2 of Federal Specification UU–T–111. In no case shall the net weight of each paperboard box exceed 10 pounds.

5.1.2 *Level C.*—Labels shall be packaged in accordance with the manufacturer's normal practice.

5.2 Packing.

5.2.1 *Level A.*—Labels of one class only, packaged as specified in 5.1, shall be packed in snug-fitting shipping containers constructed and strapped to conform to overseas type of Federal Specifications PPP–B–591, PPP–B–601, or Military Specification MIL–B–10377; class 2, style 2 or 4 of Federal Specification PPP–B–621; style 1, 2, or 2A, class 3 use, type 2 load of Federal Specification PPP–B–585. Each shipping container shall be provided with a type I or II, grade B or C, class 2 case liner conforming to Military Specification MIL–L–10547. The gross weight of each shipping container shall not exceed 100 pounds. Only one type, style, and size container shall be used for any one item on any one contract.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:32Z
Check the source to verify that this is the current version before use.

5.2.2 *Level B.*—Labels of one class only, packaged as specified in 5.1, shall be packed as specified in 5.2.1, except that waterproof case liners shall not be required, and shipping containers shall be constructed to conform to domestic type, style A or B of Federal Specification PPP–B–591 or PPP–B–601; Military Specification MIL–B–10377 (domestic type); class 1, style 2 or 4 of Federal Specification PPP–B–621; or style 1, 2 or 2A, class 1 use type 2 load of Federal Specification PPP–B–585.

5.2.3 *Level C.*—Labels, packaged as specified in 5.1, shall be packed in a manner acceptable to common carriers for safe transportation to point of destination specified in shipping instructions at the lowest transportation rate for such supplies.

5.3 Federal Standard 102 shall be referred to for definitions and applications of the various levels of packaging protection for supplies and equipment.

5.4 **Marking.**

5.4.1 *Civilian agencies.*—Shipping containers shall be marked in accordance with Federal Specification PPP–P–31.

5.4.2 *Military agencies.* — Interior packages and shipping containers shall be marked in accordance with Military Standard MIL–STD–129.

6. NOTES

6.1 **Intended use.**—The labels covered by this specification are intended for use in items for clothing, tentage and equipage.

6.2 **Ordering data.** — Procurement documents should specify the following:

(*a*) Title, number and date of this specification.

(*b*) Class required (see 1.2).

(*c*) Size required (see 3.3.8).

(*d*) When mildew resistance is required (see 3.3.5).

(*e*) Availability of standard sample (see 3.1).

(*f*) Information and illustrations to be printed on label and whether the type used is to be plain or italics (see 3.3.7).

(*g*) Both the level of packaging and the level of packing required (see sec. 5).

6.3 **Transportation description.**—The transportation description applicable to this item is:

Labels, Cloth.

Carload minimum weight 24,000 pounds, subject to Rule 34, Uniform Freight Classification.

Truckload minimum weight 24,000 pounds.

Notice. — When Government drawings, specifications, or other data are used for any purpose other than in connection with a definitely related Government procurement operation, the United States Government thereby incurs no responsibility, nor any obligation whatsoever; and the fact that the Government may have formulated, furnished, or in any way supplied the said drawings, specifications, or other data, is not to be regarded by implication or otherwise, as in any manner licensing the holder or any other person or corporation, or conveying any rights or permission to manufacture, use, or sell any patented invention that may in any way be related thereto.

MILITARY INTERESTS:

Army—M Q
Navy—MC
Air Force.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:32Z
Check the source to verify that this is the current version before use.