DDD-P-0054a (GSA-FSS)
August 8, 1962
Interim Revision of
Fed. Spec. DD-P-54
March 11, 1957

INTERIM FEDERAL SPECIFICATION

PAD, GAUZE, GAUZE AND CELLULOSE OR REGENERATED VISCOSE CELLULOSE FIBER

This Interim Federal Specification was developed by General Services Administration, Federal Supply Service, Washington 25, D. C., based upon currently available technical information. It is recommended that Federal agencies use it in procurement and forward recommendations for changes to the preparing activity at the address shown above. The General Services Administration has authorized Federal agencies to use this Interim Federal Specification as a valid exception to Federal Specification DDD-P-54, dated March 11, 1957.

1. SCOPE AND CLASSIFICATION

1.1 Scope. This specification covers sterile and non-sterile surgical pads for use in treatment of injuries of multiple types.

1.2 Classification.

1.2.1 Types, classes, and sizes. Surgical pads shall be furnished in the following types, classes, and sizes, as specified in the invitation for bids:

Type I. - All gauze.

Class A. - 8 ply.

2- by 2-inch size.
4- by 4-inch size.
4- by 4-inch size, X-ray detectable.

Class B. - 12 ply.

2- by 2-inch size.
3- by 3-inch size.
3- by 3-inch size, X-ray detectable.
4- by 4-inch size.
4- by 4-inch size, X-ray detectable.
4- by 8-inch size.
4- by 8-inch size, X-ray detectable.

FSC 6510

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:31Z
Check the source to verify that this is the current version before use.

Class C. - 16 ply.

4- by 4-inch size.
4- by 4-inch size, X-ray detectable.

Type II. Gauze, cellulose and cotton or regenerated viscose cellulose fiber.

Class A. - 2 plies of gauze.

4- by 8-inch size.

Class B. - 4 plies of gauze.

3- by 3-inch size.
4- by 4-inch size.

2. APPLICABLE SPECIFICATIONS, STANDARDS, AND OTHER PUBLICATIONS

2.1 Specifications and standards. The following specifications ans standards, of the issues in effect on date of invitation for bids, shall form a part of this specification:

Federal Specifications:

UU-P-31 - Paper; General Specification and Methods of Testing.
CCC-G-101 - Gauze, Absorbent.
JJJ-C-561 - Cotton, Sterile, (Purified) and Nonsterile.
PPP-B-576 - Box, Wood, Cleated, Veneer, Paper Overlaid.
PPP-B-585 - Boxes, Wood, Wirebound.
PPP-B-591 - Boxes, Fiberboard, Wood-Cleated.
PPP-B-621 - Boxes, Wood, Nailed and Lock Corner.
PPP-B-636 - Box, Fiberboard.
PPP-T-76 - Tape, Pressure Sensitive Adhesive.

Federal Standards:

Fed. Std. No. 102 - Preservation, Packaging and Packing Levels.
Fed. Std. No. 123 - Marking for Domestic Shipment (Civilian Agencies).

(FOR INSTRUCTIONS ON OBTAINING COPIES OF FEDERAL SPECIFICATIONS AND STANDARDS, SEE LAST PAGE)

Source: https://assist.dla.mil -- Downloaded: 202640-26T12:31Z
Check the source to verify that this is the current version before use.

Military Specifications:

MIL-L-10547 - Liners, Case, Waterproof

Military Standards:

MIL-STD-129 - Marking for Shipment and Storage.

(Copies of Military Specifications and Standards required by contractors in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publications. The following publication, of the issue in effect on date of invitation for bids, forms a part of this specification:

U. S. Pharmacopoeial Convention Publication:

The Pharmacopoeia of the United States (latest revision).

(Copies of the Unites States Pharmacopoeial Convention Publication may be obtained upon application to the Mack Publishing Company, Easton, Pa.)

3. REQUIREMENTS

3.1 Material.

3.1.1 Gauze. Gauze shall be of type VII gauze in accordance with CCC-G-101, of the issue in effect on date of invitation for bids (see 2.1).

3.1.2 Absorbent fiber. The words "absorbent fiber" as used in this specification include cotton as specified in 3.1.2.1 and regenerated viscose cellulose fiber as specified in 3.1.2.2. The manufacturer may use either material or a combination of the two.

3.1.2.1 Cotton. Cotton shall be grade B in accordance with JJJ-C-561 of the issue in effect on date of invitation for bids (see 2.1).

3.1.2.2 Regenerated viscose cellulose fiber. The cellulose fibers shall be white, substantially free from lumps, oil spots, dirt, and other foreign materials. When tested as specified in 4.4.6, the Cellulose fiber shall meet the absorbency rate and capacity requirements for grade B cotton in JJJ-C-561. The fiber shall be free of acid, alkali or dyes; ash shall not exceed 2.0 percent. Water soluble

Source: https://assist.dla.mil -- Downloaded: 20261O-26T12:31Z
Check the source to verify that this is the current version before use.

substances shall not exceed 1.0 percent. The viscose cellulose fiber shall contain not more than 30 parts per million of lead or not more than 30 parts per million of free heavy metals, as U.S.P. tested.

3.1.3 Absorbent cellulose. Absorbent cellulose shall be made from fully bleached chemical pulps and shall be a good white, substandially free from stock spots, slime spots, oil and dirt. It shall consist of one ply of crepe cellulose and the basis weight shall average not less than 11 pounds, with no value below 10 pounds (based on a 24 by 36 inch - 480 ream). The wetting time shall average not more than eight seconds in five tests with no value above twelve seconds before sterilization and average not more than twenty seconds in five tests with no value above thirty seconds after sterilization. The cellulose shall have an average minimum capacity of 16 times its weight in five tests with not over one value under 15 times its own weight when tested as described in 4.4.5.

3.1.4 Paper for bags for bulk pack non-sterilized pads. The paper shall be a white or brown sulphite or sulphate paper averaging not less than 25 pounds per 500 sheets (24 by 36 inches) and having an average Mullen test of not less than 10 pounds.

3.1.5 Paper for envelopes for sterilized pads. The paper shall be white, sterilizable kraft paper, having a porosity of not less than 65 seconds per 100 cc. of air passing through a 1 cc. center of area, when determined by a Gurley Densometer. The basis weight of the paper shall be not less than 30 pounds per 24 by 36 - 500 sheets. The tensile strength shall be not less than 20 pounds per 1 inch width in the machine direction and not less than 7 pounds per 1 inch width in the cross direction.

3.1.6 Adhesive - The adhesive shall be of good quality and of a type to withstand sterilization by autoclaving at 250°F. for 20 minutes without disintegration or loss of adherant quality (see 4.4.9).

3.1.7 Ink. The quality of the printing ink used on the envelopes for the sterile pads shall be such as to withstand sterilization by steam under pressure at 250°F. for not less than 20 minutes; there shall be no flowing or bleeding of print on the surface of the envelope when the ink is tested as specified in 4.4.9.

3.2 Construction.

3.2.1 Type I. All gauze. All gauze surgical pads shall be made in plies as specified in 1.2.1 of type VII gauze, 20 by 12 mesh, in

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:31Z
Check the source to verify that this is the current version before use.

accordance with CCC-G-101 (see 3.1.1), shall be substantially even in shape, size and thickness, and shall be folded in such a manner that they may be opened to approximately the sizes in table I without exposing any raw edges or loose threads. The area of the piece of gauze shall be not less than as shown in table I.

Table I. - Type I - All-Gauze Pads

Class and size	Minus Tolerance *	Number of plies	Open size (approximate)	Area of gauze (minimum)
Class A:	Inch		Inches	Square inches
2 by 2 inch	3/16	8	2 by 4	32
4 by 4 inch	1/4	8	4 by 8	128
Class B:				
2 by 2 inch	3/16	12	2 by 6	48
3 by 3 inch	1/4	12	3 by 9	108
4 by 4 inch	1/4	12	4 by 12	192
4 by 8 inch	1/2	12	4 by 24	380
Class C:				
4 by 4 inch	1/4	16	4 by 16	256

* Maximum minus tolerance allowed in either dimension or in the sum of two dimensions.

3.2.1.1 X-ray detectable. When specified in the request for bids, the pads shall include an X-ray detectable insert. The insert shall be either in the form of a monofilament or rectangular tab. Monofilament or tab shall be fabricated of either textile or plastic material, and shall be impregnated with an inert, nontoxic substance which is opaque to X-rays. If a monofilament is used, it shall be approximately equal to the length of the gauze in the warp direction; if a tab is used, it shall measure not less than .5 square inch and the length shall be a minimum of four times the width. The monofilament or tab shall be inserted and so anchored between the layers of gauze that it will not fall out of the pad when the pad is completely unfolded and vigorously shaken. The insert shall appear prominent and conspicuous when covered by at least 5/8 inch of aluminum when tested as specified in 4.4.4. The insert, after being inserted and anchored in the pad, shall be capable of withstanding sterilization by live steam at a temperature of 250°F. for 1 hour without bleeding, becoming tacky, or showing any other signs of deterioration.

3.2.2 Type II gauze, cellulose and absorbent fiber. Each pad shall be machine made with absorbent fiber between the gauze and one ply of absorbent cellulose. The absorbent fiber may be filmated to either the gauze or the single ply of absorbent cellulose. The pad shall be folded with the gauze outside so that it is at least 95 percent free from raw edges in its opened size.

Source: https://assist.dla.mil -- Downloaded: 20261O-26T12:31Z
Check the source to verify that this is the current version before use.

3.2.2.1 The area of the piece of gauze and the weight of the absorbent fiber and cellulose for each class and size shall be as shown in table II.

Table II. - Type II. - Gauze, Cellulose and Absorbent Fiber Pads

Class and size	Minus Tolerance *	Open size (approx.)	Weight of absorbent fiber (min.)	Weight of cellulose (min.)	Area of gauze (min.)
	Inch	Inches	Milligrams	Milligrams	Square inches
Class A:					
4 by 8 inch	1/2	4 by 8	1425	770	72
Class B:					
3 by 3 inch	1/4	3 by 6	260	410	37
4 by 4 inch	1/4	4 by 8	615	770	72

*Maximum minus tolerance allowed in either dimensions or in the sum of two dimensions.

3.3 Bag for non-sterile bulk pack. The number of packs listed in column 4, table III, shall be packaged in a bag. The bag shall be of proper size, made of paper that complies with the requirements of 3.1.4. The folded-over top of the bag shall be secured with a gummed sticker or tape.

3.4 Envelope for sterile pads. Two pads shall be enclosed in a paper envelope of a design to provide a secure, sterile closure that can be readily opened and pads removed without danger of contamination through contact with outer non-sterile edges. Paper shall meet the requirements of 3.1.5. The envelope shall be printed or labelled as specified in Marking section.

3.5 Sterilization.

3.5.1 Sterilization procedure. Sterilization shall be accomplished by high pressure steam or other suitable means so as to render the pads sterile in the final package. After sterilization, pads shall be thoroughly dry.

3.5.2 Certificate of sterility. A certificate of sterility, listing all lot or control numbers, stating that samples from each sterilizer charge have been tested and found sterile, shall be submitted by the contractor to the procuring activity.

Source: https://assist.dla.mil -- Downloaded: 202610-26T12:31Z
Check the source to verify that this is the current version before use.

3.6 Workmanship. Workmanship shall be first class throughout. The finished pads and containers shall be free, within commercial tolerances, from all defects which will detract from their appearance or may impair their serviceability.

4. SAMPLING, INSPECTION, AND TEST PROCEDURES

4.1 Supplier responsibilities for inspection. The supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified, the supplier may utilize his own or any other inspection facilities and services acceptable to the Government. Inspection records of the examination and tests shall be kept complete and available to the Government as specified in the contract or order. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.1.1 Inspection. Inspection, as used in this specification, is defined as both examination (such as visual, auditory, etc., investigation without the use of special laboratory appliances or procedures) and testing (determination by technical means of physical and chemical properties) of the item.

4.1.2 Certificates of quality. When available, certificates of quality, supplied by the manufacturer of the component or material, listing the specified test method and test results obtained, may be furnished in lieu of actual performance of such testing by the contractor.

4.2 Sampling. One unit of issue from each 100, or fraction thereof, but not more than a total of 5, shall be taken at random from each type, class, and size delivered. A total of 20 pads shall be taken from the containers to determine compliance with the requirements of this specification. The minimum weight of the pad filler shall be the average of the parts of 10 pads picked at random.

4.3 Examination. Samples shall be examined to determine compliance with the specification requirements.

4.4 Tests.

4.4.1 Gauze. Gauze shall be tested in accordance with CCC-G-101. A tolerance of 12 percent above or below standard weight of the gauze is permitted if pieces of less than 1 square yard are available for testing.

4.4.2 Cotton. Shall be tested in accordance with JJJ-C-561.

4.4.3 Containers. Shall be tested for bursting strength and weight in accordance with UU-P-31.

Source: https://assist.dla.mil -- Downloaded: 202640-26T12:31Z
Check the source to verify that this is the current version before use.

4.4.4 X-ray opaque material. In testing for opacity, the insert or inserts shall be placed on an unexposed X-ray film and covered with an aluminum ladder ranging in thickness from at least 1/8 to 3/4 inch in steps of 1/8 inch. Using an exposure such that the steps of at least 1/4 inch, 3/8 inch, 1/2 inch, and 5/8 inch are clearly delineated from each other, the insert shall appear prominent and conspicuous when covered by at least 5/8 inch of aluminum.

4.4.5 Absorbent cellulose, wetting time and capacity. To determine the wetting time and capacity, construct a basket as follows: Prepare a test basket from copper wire approximately 0.4 mm. in diameter(No. 26 B. and S.) in the form of a cylinder approximately 5 cm. in diameter and 8 cm. deep with spaces between the wires of approximately 2 cm., in basket weighing not more than 3 gm. Take sufficient plies of cellulose, cut approximately 2 inch square, to make a 5 gram sample. Insert the stack of cellulose plies into the test basket. The plane of the cellulose plies shall be approximately perpendicular to the axis of the basket. Pack the tissues loosely so that it fills the basket. Hold the filled basket in a horizontal position, about one-half inch above the surface of the distilled water (25°C ± 1°). Drop the cellulose filled basket into the water and start watch. Measure the time at which the sample has become completely moistened. Allow the sample to remain submerged for at least 10 seconds. Grasp the submerged basket by one of the center wires with a tong and remove gently from the water. Allow to drain in the horizontal position for exactly 10 seconds. Place basket and sample on a tared watch glass and weight on a suitable scale. Determine capacity as follows:

$$\frac{\text{Weight of Basket, Cellulose \& Water - Weight of Basket and Cellulose}}{5.0 \text{ grams}}$$

4.4.6 Absorbency test for absorbent fibers. Obtain a total 5-gram sample taken from various pads in different parts of the package, pulling, not cutting, the samples. Prepare a test basket from copper wire approximately 0.4 mm. in diameter (No. 26 B. and S.) in the form of a cylinder approximately 5 cm. in diameter and 8 cm. deep, with spaces between the wires of approximately 2 cm., the basket weighing not more than 3 gm. Place 5-grams of the fiber in the basket, and hold the basket on its side approximately 12 mm. above the surface of the water at 25° ± 1°C. Allow the basket to drop to the water and determine the time in seconds required for complete submersion, using a stop watch. Remove the basket from the water and allow to drain for 10 seconds in the same horizontal position, then place it immediately in a tared beaker, cover with a tared watch glass, and weigh, deducting the weight of the test basket and of the test basket and of the absorbent fiber to find the weight of water absorbed.

Source: https://assist.dla.mil -- Downloaded: 202640-26T12:31Z
Check the source to verify that this is the currentversion before use.

4.4.7 Test for heavy metals. Ash a 2.5-gram sample of rayon in a platinum dish. Dissolve the ash in 5 mls. dilute acetic acid, filter into a 25 ml. volumetric flask, wash with water to the mark. Pour into a Nessler tube and add 10 mls. saturdated hydrogen sulfide water. Compare with a tube containing (1) 1.5 mls. of a solution of 0.080 gm. of lead nitrate in 100 mls. of water; (2) 5 mls. of dilute acetic acid; (3) 18.5 mls. of distilled water; (4) 10 mls. of saturdated hydrogen sulfide water. The sample shall be no darker than the control.

4.4.8 Sterility. Sterility shall be determined in accordance with methods prescribed in the latest revision of the U.S. Pharmacopoeia.

4.4.9 Adhesive and ink. Sample envelopes shall be autoclaved at 250°F for 20 minutes. After autoclaving and cooling to room temperature, the adhesive and ink shall meet the requirements of paragraphs 3.1.6 and 3.1.7.

5. PREPARATION FOR DELIVERY

(For civil agency procurement the levels of preservation, packaging and packing protection used are defined in Fed.Std.No. 102).

5.1 Packaging.

5.1.1 Unit of issue, non-sterile bulk pack. The number of pads specified in column 4 of table III, packaged in a bag as specified in 3.3 constitutes the unit of issue. A two percent variation in the quantity of pads to be contained in each bag as specified in column 4 will be permitted in not more than two percent of the bags of each lot.

5.1.2 Unit of issue, sterile pack. The number of sealed envelopes of pads specified in column 4 of table IV, packed in a suitable chipboard tray constitutes a unit of issue. The envelopes shall meet the requirements of 3.4.

Table III - Non-Sterile Bulk Pack.

Type	Class	Size	Number of Pads Per Unit	Number of Units Per Case	Number of Pads Per Case
I	A	2x2	100	50	5000
I	A	4x4	200	20	4000
I	A	4x4 X	200	20	4000
I	B	2x2	100	80	8000
I	B	3x3	100	40	4000
I	B	3x3 X	100	40	4000
I	B	4x4	100	20	2000
I	B	4x4 X	100	20	2000
I	B	4x8	100	20	2000
I	B	4x8 X	100	20	2000
I	C	4x4	100	20	2000
I	C	4x4 X	100	20	2000
II	A	4x8	100	20	2000
II	B	3x3	100	40	4000
II	B	4x4	100	20	2000

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:31Z
Check the source to verify that this is the current version before use.

Table IV - Sterile Pack

Type	Class	Size	No. of Envelopes Per Unit	No. of Units Per Case	No. of Pads Per Case
I	A	2x2	25	60	3000
I	B	3x3	25	48	2400
I	B	4x4	25	24	1200
II	B	3x3	25	48	2400
II	B	4x4	25	24	1200

5.2 Packing.

5.2.1 Quantities. Packing quantities shall be as specified in table III and IV.

5.2.2 Packing variation permitted. If the required number of units to be shipped is less than the number of units specified to be overpacked in an exterior container, such units shall be packed in an exterior container of suitable size and design, acceptable to a common carrier, which will insure safe delivery to destination.

5.2.3 Level A.

5.2.3.1 Exterior containers. The number of units specified in column 5 of tables III and IV shall be overpacked in an exterior container designed for type 2 load and constructed in accordance with PPP-B-585, style 3, for class 3 use; PPP-B-621 or PPP-B-636, compliance symbol V-3s; or PPP-B-576.

5.2.3.2 Case liner. If intermediate cartons fabricated from W-5c or W-5s board are furnished they shall be secured with a single 2 inch or wider tape conforming to PPP-T-76 over center seam and on the ends. A case liner will not be required. When other or no intermediate cartons are furiished, each overseas box shall be lined with a waterproof case liner conforming to MIL-L-10547. Closure and sealing shall conform to applicable paragraphs of appendix thereto.

5.2.3.3 Strapping. Strapping (when required) shall be in accordance with applicable box specification.

Note.- Strapping will not be required for shipments forwarded to a receiving activity within the continental limits of the United States for storage and redistribution.

5.2.4 Level B.

5.2.4.1 Exterior container. The number of units specified in column 5 of tables III or IV shall be overpacked in an exterior container designed for type 2 load and constructed in accordance with PPP-B-591; PPP-B-621; PPP-B-636, PPP-B-585, style 3 for class 1 use; or PPP-B-576.

Source: https://assist.dla.mil -- Downloaded: 202640-26T12:31Z
Check the source to verify that this is the current version before use.

5.2.5 Level C. The subject commodity shall be packed in substantial commercial containers of the type, size, and kind commonly used for the purpose, so constuucted as to insure acceptance and safe delivery by common or other carriers, at the lowest rate, to point of delivery called for in the contract or purchase order.

5.3 Marking. (Civilian agencies)

5.3.1 Unit packages. Each package shall be commercially identified. Packages of non-sterile pads shall bear the legend "NOT STERILIZED". Packages containing x-ray detectable pads shall bear the additional legend "X-RAY DETECTABLE". Each envelope of sterile pads shall be commercially identified and shall bear the legend "STERILITY GUARANTEED UNLESS ENVELOPE IS DAMAGED OR OPENED", and "X-RAY DETECTABLE" where applicable.

5.3.2 Shipping containers. In addition to any special marking required by the contract or order, shipping containers shall be marked in accordance with Fed. Std. No. 123.

5.4 Marking. (Military).

5.4.1 Intermediate cartons and shippings containers. Each intermediate carton and each shipping container shall be marked in accordance with MIL-STD-129. Service color marking and data are not required on containers for level A packs when addressed to domestic establishments, for the Medical Services of the Armed Forces.

6. NOTES

6.1 Ordering data. Purchasers should exercise any desired options offered herein, and procurement documents should specify the following:

(a) Title, number, and date of this specification.
(b) Types, classes and sizes required (see 1.2.1).
(c) Selection of applicable levels of packaging and packing.

(1) Level B packing is intended to provide economical but limited protection, and should be specified unless special packing is required for overseas shipping or long term storage. Effective period of protection is estimated to be twelve months from date of initial packaging.

6.2 Storage surveillance. Units packaged in accordance with level B requirements must be inspected to determine condition when not used within the time period indicated in paragraph 6.2(c) (1). Units not used within such time period must either be repackaged in accordance with level B requirements in this specification or with level A requirements if storage beyond an additional year is anticipated.

Source: https://assist.dla.mil -- Downloaded: 202640-26T12:31Z
Check the source to verify that this is the currentversion before use.

6.3 It is believed that this specification adequately describes the characteristics necessary to secure the desired material, and that normally no samples will be necessary prior to award to determine compliance with this specification. If, for any particular purpose, samples with bids are necessary, they should be specifically asked for in the invitation for bids, and the particular purpose to be served by the bid sample should be definitely stated, the specification to apply in all other respects.

6.4 This specification does not include all types, classes, grades, etc., of the commodity indicated by the title of the specification, or which are commercially available, but is intended to cover the type, etc., normally procured to meet Federal Government requirements.

6.5 Transportation description. Transportation description applicable to this item is:

Bandages or dressings, physicians' or surgeons'.
Carload minimum weight 24,000 pounds subject to Rule 34, Uniform Freight Classification.
Truckload minimum weight 30,000 pounds.

NOTICE: (SEE LAST PAGE)

MILITARY INTERESTS:
Army - M
Navy -- MD
Air Force- AF

GSA-WASH DC 63-2480 Source: https://assist.dla.mil -- Downloaded: 202610-26T12:31Z
Check the source to verify that this is the current version before use.

INSTRUCTIONS ON OBTAINING COPIES OF FEDERAL SPECIFICATIONS AND STANDARDS

(Activities outside the Federal Government may obtain copies of Federal Specifications, Standards, and Handbooks as outlined under General Information in the Index of Federal Specifications, Standards and Handbooks and at the prices indicated in the Index. The Index, which includes cumulative monthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, U. S. Government Printing Office, Washington 25, D. C.

(Single copies of this specification and other product specifications required by activities outside the Federal Government for bidding purposes are available without charge at the General Services Administration Regional Offices in Boston, New York, Washington, D. C., Atlanta, Chicago, Kansas City, Mo., Dallas, Denver, San Francisco, and Auburn, Wash.

(Federal Government activities may obtain copies of Federal Specifications, Standards, and Handbooks and the Index of Federal Specifications, Standards and Handbooks from established distribution points in their agencies.)

NOTICE

When Government drawings, specifications, or other data are used for any purpose other than in connection with a definitely related Government procurement operation, the United States Government thereby incurs no responsibility nor any obligation whatsoever; and the fact that the Government may have formulated, furnished, or in any way supplied the said drawings, specifications, or other data is not to be regarded by implication or otherwise as in any manner licensing the holder or any other person or corporation, or conveying any rights or permission to manufacture, use, or sell any patented invention that may in any way be related thereto.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:31Z
Check the source to verify that this is the current version before use.