DDD-P-54
MARCH 11, 1957
SUPERSEDING
Int.Fed.Spec. DDD-P-0057(GSA-FSS)
December 28, 1955, and
Fed.Spec. DDD-S-621
March 21, 1945

FEDERAL SPECIFICATION

PADS GAUZE, GAUZE AND COTTON, AND GAUZE, CELLULOSE AND COTTON

This specification was approved by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal agencies.

1. SCOPE AND CLASSIFICATION

1.1 Scope.—This specification covers surgical pads for use in treatment of injuries of multiple types.

1.2 Classification.

1.2.1 *Types, classes, and sizes.*—Surgical pads shall be furnished in the following types, classes and sizes; as specified in the invitation for bids:

Type I.—All gauze.

Class A.—8 ply.
- 4- by 4-inch size.
- 4- by 4-inch size, radiopaque.

Class B.—12 ply.
- 2- by 2-inch size.
- 3- by 3-inch size.
- 3- by 3-inch size, radiopaque.
- 4- by 8-inch size.
- 4- by 8-inch size, radiopaque.

Class C.—16 ply.
- 4- by 4-inch size.
- 4- by 4-inch size, radiopaque.

Type II.—Gauze and cotton.

Class A.—4 plies of gauze.
- 4- by 8-inch size.

Class B.—8 plies of gauze.
- 2- by 2-inch size.
- 3- by 3-inch size.
- 4- by 4-inch size.

Type III.—Gauze, cellulose and cotton.

Class A.—2 plies of gauze.
- 4- by 8-inch size.

Class B.—4 plies of gauze.
- 3- by 3-inch size.
- 4- by 4-inch size.

2. APPLICABLE SPECIFICATIONS, STANDARDS, AND OTHER PUBLICATIONS

2.1 Specifications and standards.—The following specifications and standards, of the issues in effect on date of invitation for bids, shall form a part of this specification:

Federal Specifications:

UU-P-31 — Paper; General Specifications and Methods of Testing.

CCC-G-101—Gauze; Plain.

JJJ-C-561 — Cotton; Sterile and Nonsterile.

LLL-B-631—Boxes; Fiber, Corrugated (for Domestic Shipment).

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:31Z
Check the source to verify that this is the current version before use.

PPP-B-585—Boxes; Wood, Wirebound.
PPP-B-591—Boxes; Fiberboard, Wood-Cleated.
PPP-B-621—Boxes, Wood, Nailed and Lock Corner.

(Activities outside the Federal Government may obtain copies of Federal Specifications and Standards as outlined under General Information in the Index of Federal Specifications and Standards and at the prices indicated in the Index. The Index, which includes cumulative monthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, U. S. Government Printing Office, Washington 25, D. C.

(Single copies of this specification and other product specifications required by activities outside the Federal Government for bidding purposes are available without charge at the General Services Administration Regional Offices in Boston, New York, Atlanta, Chicago, Kansas City, Mo., Dallas, Denver, San Francisco, Los Angeles, Seattle, and Washington, D. C.

(Federal Government activities may obtain copies of Federal Specifications and Standards and the Index of Federal Specifications and Standards from established distribution points in their agencies.)

Military Specifications:

JAN-P-108 — Packaging and Packing for Overseas Shipment—Boxes, Fiberboard Corrugated and Solid (Military Type).
MIL-B-10377 — Box, Wood, Cleated, Veneer, Paper Overlaid.
MIL-L-10547 — Liners, Case, Waterproof.

Military Standard:

MIL-STD-129 — Marking for Shipment and Storage.

(Copies of Military Specifications and Standards required by the contractor in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publications. — The following publication, of the issue in effect on date of invitation for bids, forms a part of this specification:

U. S. Pharmacopoeial Convention Publication:

The Pharmacopoeia of the United States (latest revision).

(Copies of United States Pharmacopoeial Convention Publication may be obtained upon application to the Mack Publishing Company, Easton, Pa.)

3. REQUIREMENTS

3.1 Material.

3.1.1 *Gauze.*—Shall be of type VII gauze in accordance with Federal Specification CCC-G-101 of the issue in effect on date of invitation for bids. (See 2.1.)

3.1.2 *Absorbent cotton.* — The absorbent cotton shall be grade B in accordance with applicable Federal Specification JJJ-C-561 of the issue in effect on date of invitation for bids. (See 2.1.)

3.1.3 *Absorbent cellulose.*—Absorbent cellulose shall be made from fully bleached chemical pulps and shall be a good white, substantially free from stock spots, slime spots, oil and dirt. It shall consist of one ply of crepe cellulose and the basis weight shall average not less than 11 pounds, with no value below 10 pounds (based on a 24 by 36 inches - 480 ream). The wetting time shall average not more than eight seconds in five tests with no value above twelve seconds before sterilization and average not more than twenty seconds in five tests with no value above thirty seconds after sterilization. The cellulose shall have an average minimum capacity of 16 times its weight in five tests with not over one value under 15 times its own weight when tested as discussed in 4.3.6.

3.1.4 *Regenerated viscose cellulose fiber.*— The absorbent cellulose fibers shall at least be equal to all specifications for fully bleached grade B absorbent cotton as specified in JJJ-C-561, except that the fibers shall be regenerated cellulose rather than cotton. The rayon shall contain not more than 30 parts per million of heavy metals.

Source: https://assist.dla.mil -- Downloaded: 202640-26T12:31Z
Check the source to verify that this is the currentversion before use.

3.1.5 *Paper bag.*—The paper bag shall be a white *or brown* sulphite or sulphate paper averaging not less than 25 pounds per 500 sheets (24 by 36 inches) and having *an average* Mullen test of not less than 10 pounds.

3.1.6 *Laminated bag container.* — Unless otherwise specified, shall be made of laminated material consisting of an outside sheet of 30 pounds dense northern kraft, laminated with an asphaltic base compound, minimum melting point 175°F., minimum 15 pounds per 3,000 square feet, to a layer of lead foil or aluminum foil 0.001 inch commercial thickness, thermoplastically laminated to a cellulose-base sheet, minimum 0.0009-inch commercial thickness, coated with a thermo-sealing compound, minimum 2½ pounds per 3,000 square feet. The weight of the laminated sheet shall be not less than 225 pounds per 500 sheets (24 by 36 inches) and the bursting strength measured on a Mullen paper tester shall be not less than 40 pounds. A coat of 4 pounds of petroleum-base wax per 3,000 square feet shall be placed on the kraft surface of the laminated paper after printing.

3.2 Labeling.—Each paper bag and laminated bag container shall be labeled or printed. *Commercial markings shall be acceptable if they contain the name of the item, the size, content, and "nonsterile" or equivalent, and the name of the manufacturer, and comply with U.S.P. requirements.*

3.3 Packaging (not waterproof).—Unless waterproof packaging is specified in the invitation for bids, pads shall be protected by packaging in a bag of proper size, made of paper complying with the requirements of 3.1.5 and closed by folding over the top and securing with a small gummed sticker or tape.

3.4 Packaging (waterproof).—When specified in the invitation for bids, pads shall be packed in paper bags exactly as specified in 3.3. Each enclosed bag shall then be enclosed and sealed in a laminated bag container complying with the requirements of 3.1.6. This package shall be sufficiently watertight so that there shall be no evidence of leakage into the pads when tested in accordance with 4.3.4

3.5 Construction.

3.5.1 *Type I.*—All-gauze surgical pads shall be made in plies as specified in 1.2.1 of type VII gauze, 20 by 12 mesh, in accordance with Federal Specification CCC–G–101 (see 3.1.1), shall be substantially even in shape, size and thickness; and shall be folded in such a manner that they may be opened to approximately the sizes in table I without exposing any raw edges or loose threads.

3.5.1.1 The area of the piece of gauze shall be not less than as shown in table I.

TABLE I.—*Type I—all-gauze pads*

Class and size	Minus tolerance [1]	Number of plies	Open size (approximate)	Area of gauze (minimum)
	Inch		*Inches*	*Square inches*
Class A:				
4 by 4 inch	¼	8	4 by 8	128
Class B:				
2 by 2 inch	1/16	12	2 by 6	48
3 by 3 inch	¼	12	3 by 9	108
4 by 8 inch	½	12	4 by 22	380
Class C:				
4 by 4 inch	¼	16	4 by 16	256

[1] Maximum minus tolerance allowed in either dimension or in the sum of the two dimensions.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:31Z
Check the source to verify that this is the current version before use.

3.5.1.2 *X-ray opaque insert.*—The X-ray opaque insert shall be either in the form of a *monofilament* or rectangular or square tab. Monofilament or tab shall be fabricated of either textile or plastic material, and shall be impregnated with an inert, nontoxic substance which is opaque to X-rays. If a *monofilament* is used, *it shall* be approximately equal to the length of the gauze in the warp direction; if a tab is used, it shall measure not less than .5 square inch and the length shall be a minus of four times the width. The *monofilament* or tab shall be inserted and so anchored between the layers of gauze that it will not fall out of the pad when the pad is completely unfolded and vigorously shaken. The insert shall appear prominent and conspicuous when covered by at least $\frac{5}{8}$ inch of aluminum when tested as specified in 4.3.5. The insert, after being inserted and anchored in the pad, shall be capable of withstanding sterilization by live steam at a temperature of 250°F. for 1 hour without bleeding, becoming tacky, or showing any other signs of deterioration.

3.5.2 *Type II.*—Gauze and cotton pads shall be made of a combination of cotton (or regenerated viscose cellulose fiber, or combinations of cotton and cellulose fibers, and type VII gauze 20 by 12 mesh in accordance with Federal Specification CCC–G–101 (see 3.1.1), folded in such a manner that the cotton shall be covered by at least one layer of gauze. When the pads are unfolded to approximately the opened sizes as shown in table II the cotton shall extend substantially over the opened area and no raw edges or loose threads shall be exposed nor any of the cotton uncovered.

3.5.2.1 The area of the piece of gauze and the weight of the cotton (or regenerated viscose cellulose fiber or combinations of cotton and cellulose fibers) used shall be not less than as shown in table II.

3.5.3 *Type III.*—Each pad shall be machine made with cotton (or regenerated viscose-cellulose fiber or combinations thereof) interposed between gauze and one ply of absorbent cellulose. The cotton may be filmated to either the gauze or the single ply of absorbent cellulose. The pad shall be folded with the gauze outside so that it is at least 95 percent free from raw edges in its opened size.

3.5.3.1 The area of the piece of gauze and the weight of the cotton (or regenerated viscose-cellulose fiber or combinations of cotton and cellulose fibers) and cellulose used shall be not less than is shown in table III.

3.6 **Workmanship.** — Shall be first class throughout. The finished pads and containers shall be free *within commercial tolerances* from all defects which will detract from their appearance or impair their serviceability.

TABLE II.—*Type II—gauze-and-cotton pads*

Class and size	Minus tolerance [1]	Open size (approximate)	Weight of cotton [2] (minimum)	Area of gauze (minimum)
	Inch	*Inches*	*Milligrams*	*Square inches*
Class A:				
4 by 8 inch	$\frac{1}{4}$	4 x 8	1600	128
Class B:				
2 by 2 inch	$\frac{1}{16}$	2 x 4	130	32
3 by 3 inch	$\frac{1}{4}$	3 x 6	260	72
4 by 4 inch	$\frac{1}{4}$	4 x 8	650	128

[1] Maximum minus tolerance allowed in either dimension or in the sum of the two dimensions.

[2] Or regenerated viscose-cellulose fiber or combination of cotton and cellulose fibers.

Source: https://assist.dla.mil -- Downloaded: 2026l0-26T12:31Z
Check the source to verify that this is the currentversion before use.

TABLE III.—*Type III—gauze, cellulose and cotton*

Class and size	Minus tolerance [1]	Open size (approximate)	Weight of cotton [2] (minimum)	Weight of cellulose (minimum)	Area of gauze (minimum)
	Inch	*Inches*	*Milligrams*	*Milligrams*	*Square inches*
Class A:					
4 by 8 inch	½	4 x 8	1425	770	72
Class B:					
4 by 4 inch	½	4 x 8	615	770	72
3 by 3 inch	¼	3 x 6	260	410	37

[1] Maximum minus tolerance allowed in either dimensions or in the sum of the two dimensions
[2] Or regenerated viscose-cellulose fiber, or combinations of cotton and cellulose fibers.

4. SAMPLING, INSPECTION, AND TEST PROCEDURES

4.1 Sampling.—One paper bag from each 100, or fraction thereof, but not more than a total of 5, shall be taken at random from each type, class, and size delivered. A total of 20 pads shall be taken from these paper bags to determine compliance with the requirements of this specification. The minimum weight of the pad filler shall be the average of the parts of 10 pads picked at random.

4.2 Inspection.—Samples shall be inspected to determine compliance with the specification requirements.

4.3 Tests.

4.3.1 *Gauze.*—Shall be tested in accordance with Federal Specification CCC–G–101. A tolerance of 12 percent above or below standard weight of the gauze is permitted if pieces of less than 1 square yard are available for testing.

4.3.2 *Cotton.*—Shall be tested in accordance with Federal Specification JJJ–C–561.

4.3.3 *Paper bags.* — Shall be tested for bursting strength and weight in accordance with Federal Specification UU–P–31.

4.3.4 *Waterproofing.* — Waterproof packaging shall be tested by submerging in tap water at room temperature for 10 minutes without pressure to the sealed package.

4.3.5 *X-ray opaque material.*—In testing for opacity, the insert or inserts shall be placed on an unexposed X-ray plate and covered with an aluminum ladder ranging in thickness from at least ⅛ to ¾ inch in steps of ⅛ inch. Using an exposure such that the steps of at least ¼ inch, ⅜ inch, ½ inch, and ⅝ inch are clearly delineated from each other, the insert shall appear prominent and conspicuous when covered by at least ⅝ inch of aluminum.

4.3.6 *Absorbent cellulose — wetting time and capacity.*—To determine the wetting time and capacity, construct a basket as follows: Prepare a test basket from copper wire approximately 0.4 mm. in diameter (No. 26 B. and S.) in the form of a cylinder approximately 5 cm. in diameter and 8 cm. deep with spaces between the wires of approximately 2 cm., the basket weighing not more than 3 cm. Take sufficient plies of cellulose and prepare a 5-gram sample. The sample of cellulose, in turn, (all tears are made with a pinching type of motion, holding the hand closely together to avoid stretching the tissue) into five separate pieces approximately equal in area. Place the pieces into the test basket, one at a time, with the plane of the tissue approximately

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:31Z
Check the source to verify that this is the current version before use.

perpendicular to the axis of the basket. Pack the tissue loosely so that it fills the basket. Hold the filled basket in a horizontal position, one inch above the surface of distilled water (temperature at 25°C. ± 1°), drop into water and start watch. Note wetting time at which sample becomes completely moistened. Allow sample to remain submerged for 10 seconds. Grasp the submerged basket by one of the center wires with a tong and remove gently from the water. Allow to drain in a horizontal position for exactly 10 seconds without further motion. Place basket and sample on a tared watch glass and weigh on a suitable scale. Determine capacity as follows:

$$\text{Capacity} = \frac{\text{Wt. of basket, cellulose and water} - \text{basket and cellulose}}{5.0 \text{ grams}}$$

4.3.7 *Absorbency test for regenerated cellulose fiber or combinations of cotton and regenerated viscose cellulose fibers.*—Obtain a total 5-gram sample taken from various pads in different parts of the package, pulling, not cutting, the samples. Prepare a test basket from copper wire approximately 0.4 mm. in diameter (No. 26 B. and S.) in the form of a cylinder approximately 5 cm. in diameter and 8 cm. deep, with spaces between the wires of approximately 2 cm., the basket weighing not more than 3 gm. Place 5-gm. of the regenerated viscose cellulose fiber in the basket, and hold the basket on its side approximately 12 mm. above the surface of the water at 25°C. ± 1°. Allow the basket to drop to the water and determine the time in seconds required for complete submersion, using a stop watch. Remove the basket from the water and allow it to drain for 10 seconds in the same horizontal position, then place it immediately in a tared beaker, cover with a tared watch glass, and weigh, deducting the weight of the test basket and of the regenerated viscose cellulose fiber to find the weight of water absorbed.

4.3.8 *Test for heavy metals.*—Ash a 2.5-gram sample of rayon in a platinum dish. Dissolve the ash in 5 mls. dilute acetic acid, filter into a 25 ml. volumetric flask, wash with water to the mark. Pour into a Nessler tube and add 10 mls. saturated hydrogen sulfide water. Compare with a tube containing (1) 1.5 mls. of a solution of 0.080 gm. of lead nitrate in 100 mls. of water; (2) 5 mls. of dilute acetic acid; (3) 18.5 mls. of distilled water; (4) 10 mls. of saturated hydrogen sulfide water. The sample shall be no darker than the control.

5. PREPARATION FOR DELIVERY

(For definitions and levels, see 6.1).

5.1 Packaging.

5.1.1 *Unit of issue.*—The number of pads specified in column 4 of table IV constitutes one unit.

5.1.2 *Quantities.*—Packaging and packing quantities shall be as specified in table IV.

TABLE IV.—*Packaging and packing quantities*

Col. 1	Col. 2	Col. 3	Col. 4	Col. 5	Col. 6	Col. 7
Stock No.	Type	Class	Number of pads constituting one unit of issue	Number of units to be contained in each intermediate carton	Number of intermediate cartons to be overpacked in each shipping container	Total number of units in each shipping container
6510-203-8415	I	B	100	80	4	320
6510-203-8448	I	A	200	20	3	60
6510-203-8480	I	B	100	20	2	40
6510-203-8488	I	A	200	20	3	60
6510-203-8490	I	B	100	20	2	40

Source: https://assist.dla.mil -- Downloaded: 202640-26T12:31Z
Check the source to verify that this is the current version before use.

5.1.2.1 *Packing variation permitted.*—If the required number of units to be shipped is less than the number of units specified to be overpacked in an exterior container, such units shall be packed in an exterior container of suitable size and design, acceptable to a common carrier, which will insure safe delivery to destination.

5.1.3 *Level A.*

5.1.3.1 *Unit packaging.*—Each unit shall be packaged in a bag fabricated from white or brown sulphite or sulphate paper weighing not less than 25 pounds per 500 sheets (24 by 36 inches) and having an average Mullen test of not less than 10 pounds. Bag shall be closed by folding over the top and securing with a small gummed sticker. Each paper bag shall be further packaged in a bag fabricated from virgin polyethylene seamless tubing having an average wall thickness of 0.004 inch, with no wall thickness at any point below 0.00325 inch. Excess air shall be expelled or evacuated and closure effected by heat sealing.

5.1.3.2 *Intermediate packaging.*—The number of unit packages specified in column 5 of table IV shall be packaged in a carton conforming to the requirements of Federal Specification LLL–B–631 or Military Specification JAN–P–108, compliance symbol W–5c or W–5s. Carton shall be adequately secured to prevent accidental opening. All seams of cartons fabricated from W–5c or W–5s board shall be sealed with water-resistant tape.

5.1.4 *Level B.*

5.1.4.1 *Unit packaging.*—Each unit shall be packaged in a bag fabricated from white or brown sulphite or sulphate paper weighing not less than 25 pounds per 500 sheets (24 by 36 inches) and having an average Mullen test of not less than 10 pounds. Bag shall be closed by folding over the top and securing with a small gummed sticker.

5.1.4.2 *Intermediate packaging.*—The number of units specified in column 5 of table IV shall be packaged in a carton conforming to the requirements of Federal Specification LLL–B–631, table I. Carton shall be adequately secured to prevent accidental opening.

5.1.5 *Level C.*

5.1.5.1 *Unit packaging.*—Each unit shall be packaged as specified in 5.1.4.1.

5.1.5.2 *Intermediate packaging.* — A convenient number of units shall be packaged in a carton of suitable size and design which will afford the degree of protection required for shipment and use of the end product for its intended purpose within the continental limits of the United States of America.

5.2 Packing.

5.2.1 *Level A.*

5.2.1.1 *Exterior container.*—The number of intermediate cartons specified in column 6 of table IV shall be overpacked in an exterior container designed for type 2 load and constructed in accordance with Federal Specification PPP–B–585, style 3, for class 3 use; Federal Specification PPP–B–621 or Military Specification JAN–P–108, compliance symbol V–3s; or, MIL–B–10377, table II.

5.2.1.2 *Case liner.* — When intermediate cartons fabricated from W–5c or W–5s board are furnished, case liner will not be required. When other intermediate cartons are furnished, each overseas box shall be lined with a waterproof case liner conforming to Military Specification MIL–L–10547. Closure and sealing shall conform to applicable paragraphs of appendix thereto.

5.2.1.3 *Strapping.*—Strapping (when required) shall be in accordance with applicable box specification.

Note.—Strapping will not be required for shipments forwarded to a receiving activity within the continental limits of the United States for storage and redistribution.

Source: https://assist.dla.mil -- Downloaded: 202610-26T12:31Z
Check the source to verify that this is the current version before use.

5.2.2 *Level B.*

5.2.2.1 *Exterior container.*—The number of intermediate cartons specified in column 6 of table IV shall be overpacked in an exterior container designed for type 2 load and constructed in accordance with Federal Specifications PPP-B-591; PPP-B-621; LLL-B-631, table II: PPP-B-585, style 3, for class 1 use; or Military Specification MIL-B-10377, table I.

5.2.3 *Level C.* — The subject commodity shall be packed in substantial commercial containers of the type, size, and kind commonly used for the purpose, so constructed as to insure acceptance and safe delivery by common or other carriers, at the lowest rate, to point of delivery called for in the contract or purchase order.

5.3 Marking.

5.3.1 *Unit packages.*—Each unit package shall be commercially identified and shall bear the legend: "NOT STERILIZED". Packages containing radiopaque pads shall bear the additional legend: "RADIOPAQUE" or "X-RAY DETECTABLE."

5.3.2 *Intermediate cartons and shipping container.* — Each intermediate carton and each shipping container shall be marked in accordance with Military Standard MIL-STD-129. Service color marking and data are not required on containers for level A packs when addressed to domestic establishments, for the Medical Services of the Armed Forces.

6. NOTES

6.1 Federal Standard 102 should be referred to for definitions and applications of the various levels of packaging protection for supplies and equipment.

6.2 Ordering data. — Purchasers should exercise any desired options offered herein, and should specify the following:

(*a*) Title, number, and date of this specification.

(*b*) Types, classes, and sizes required (see 1.2.1).

(*c*) Selection of applicable levels of packaging and packing.

(1) Level B packaging is intended to provide economical but limited protection, and should be specified only when it is determined to be appropriate. Effective period of protection is estimated to be twelve (12) months from date of initial packaging.

6.3 Storage surveillance.—Units packaged in accordance with level B requirements must be inspected to determine condition when not used within the time period indicated in paragraph 6.2 (c) (1). Units not used within such time period must either be repackaged in accordance with level B requirements in this specification or with level A requirements if storage beyond an additional year is anticipated.

6.4 It is believed that this specification adequately describes the characteristics necessary to secure the desired material, and that normally no samples will be necessary prior to award to determine compliance with this specification. If, for any particular purpose, samples with bids are necessary, they should be specifically asked for in the invitation for bids, and the particular purpose to be served by the bid sample should be definitely stated, the specification to apply in all other respects.

6.5 This specification covers the following items appearing in the Armed Services Medical Stock List:

6510-203-8415—Pad, Gauze, Surgical, 2 by 2 inches, 100s.

6510-203-8448—Pad, Gauze, Surgical, 4 by 4 inches, 200s.

6510-203-8480—Pad, Gauze, Surgical, 4 by 8 inches, 100s.

6510-203-8488—Pad, Gauze, Surgical, Radiopaque, 4 by 4 inches, 200s.

6510-203-8490—Pad, Gauze, Surgical, Radiopaque, 4 by 8 inches, 100s.

Source: https://assist.dla.mil -- Downloaded: 2026l0-26T12:31Z
Check the source to verify that this is the currentversion before use.

6.6 This specification does not include all types, classes, grades, etc., of the commodity indicated by the title of the specification, or which are commercially available, but is intended to cover the type, etc., normally procured to meet Federal Government requirements.

6.7 **Transportation description.**—Transportation description applicable to this item is:

Bandages or dressings, physicians' or surgeons'.

Carload minimum weight 24,000 pounds, subject to Rule 34, Uniform Freight Classification.

Truckload minimum weight 30,000 pounds.

Patent notice.—When government drawings, specifications, or other data are used for any purpose other than in connection with a definitely related Government procurement operation, the United States Government thereby incurs no responsibility, nor any obligation whatsoever and the fact that the Government may have formulated, furnished, or in any way supplied the said drawings, specifications, or other data, is not to be regarded by implication or otherwise, as in any manner licensing the holder or any other person or corporation, or conveying any rights or permission to manufacture, use, or sell any patented invention that may in any way be related thereto.

MILITARY INTERESTS:
Army—M
Navy—Md
Air Force—AF.

Copies of this specification may be purchased for 10 cents each.

Source: https://assist.dla.mil -- Downloaded: 202610-26T12:31Z
Check the source to verify that this is the current version before use.