DDD-P-56a
JULY 27, 1960
SUPERSEDING
Int. Fed. Spec. DDD–P–0056(GSA–FSS)
May 2, 1960

FEDERAL SPECIFICATION

PAD, MATTRESS, COTTON, QUILTED, WHITE

This specification was approved by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal agencies.

1. SCOPE AND CLASSIFICATION

1.1 Scope.—This specification covers the requirements for a quilted cotton mattress pad primarily intended for use on beds for the protection of mattresses.

1.2 Classification.

1.2.1 *Type and sizes.*—Mattress pads covered by this specification shall be of one type and two sizes, as specified.

Size 1.—36 by 76 inches.

Size 2.—52 by 75 inches.

2. APPLICABLE SPECIFICATIONS, STANDARDS, AND OTHER PUBLICATIONS

2.1 Specifications and standards.—The following specifications and standards of the issues in effect on date of invitation for bids, form a part of this specification:

Federal Specifications:

V–T–276—Thread, Cotton.

UU–P–268—Paper, Kraft, Wrapping.

CCC–C–430—Cloth, Cotton, Sheeting.

CCC–T–191—Textile Test Methods.

DDD–L–0020 — Label, Printed and Markings; General Use. (For Clothing, Equipage and Tentage).

PPP–B–591—Boxes, Fiberboard, Wood-Cleated.

PPP–B–601—Boxes, Wood, Cleated Plywood.

PPP–B–621—Boxes, Wood, Nailed and Lock-Corner.

PPP–B–636—Box, Fiberboard.

Federal Standards:

Fed. Std. No. 102—Preservation, Packaging, and Packing Levels.

Fed. Std. No. 123—Marking for Domestic Shipment (Civilian agencies).

Fed. Std. No. 751—Stitches, Seams and Stitching.

(Activities outside the Federal Government may obtain copies of Federal Specifications, Standards, and Handbooks as outlined under General Information in the Index of Federal Specifications, Standards, and Handbooks and at the prices indicated in the Index. The Index, which includes cumulative monthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, U. S. Government Printing Office, Washington 25, D. C.

(Single copies of this specification and other product specifications required by activities outside the Federal Government for bidding purposes are available without charge at the General Services Administration Regional Offices in Boston, New York, Atlanta, Chicago, Kansas City, Mo., Dallas, Denver, San Francisco, Los Angeles, Seattle, and Washington, D. C.

(Federal Government activities may obtain copies of Federal Specifications, Standards, and Handbooks and the Index of Federal Specifications, Standards,

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:32Z
Check the source to verify that this is the current version before use.

and Handbooks from established distribution points in their agencies.)

Military Specifications:

MIL–B–10377—Box, Wood, Cleated, Veneer, Paper Overlaid.

MIL–L–10547 — Liners, Case, Waterproof.

Military Standards:

MIL–STD–105 — Sampling Procedures and Tables for Inspection by Attributes.

MIL–STD–129—Marking for Shipment and Storage.

MS16686—Medical Service Symbol.

(Copies of Military Specifications and Standards required by contractors in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publications. — The following documents form a part of this specification. Unless otherwise indicated, the issues in effect on date of invitation for bids shall apply.

U. S. Department of Agriculture:

Pamphlet—SRA–AMS. 180-Cotton and Cotton Linters Standards.

(Application for copies should be addressed to the U.S. Department of Agriculture, Agricultural Marketing Service, Cotton Division, Washington 25, D.C.).

Textile Fiber Products Identification Act:

Rules and Regulations dated March 3, 1960.

(Copies may be obtained, free of charge, from the Federal Trade Commission, Washington 25, D. C.)

3. REQUIREMENTS

3.1 Sample.—Samples are furnished solely for guidance and information to the contractor (see 6.3). Variations from this specification may appear in the sample, in which case this specification shall govern.

3.2 Materials.

3.2.1 *Linters.*—The cotton linters shall be new (not previously used) and not lower in grade than United States Standard Grade No. 3 and Staple 3 conforming to U. S. Department of Agriculture Pamphlet, SRA–AMS. 180 (see 2.2).

3.2.2 *Felt.*—The felt for the padding shall be made from 100-percent cotton linters conforming to 3.2.1. The felt shall be cleaned and garnetted so as to produce unbroken laminated sheets of interlaced garnetted felt and shall be trimmed on all four sides to produce an even thickness throughout the batt. To facilitate handling, a single ply of cellulosic wadding may be applied to the sheets of felt.

3.2.3 *Cloth.*—The basic cloth for the cover and the binding of the mattress pads shall be seamless, bleached white, cotton sheeting conforming to type II, class 2, style B of Federal Specification CCC–C–430.

3.2.4 *Thread, cotton.*—The thread used for quilting and stitching the binding shall be bleached white cotton thread and shall conform to type IA2 of Federal Specification V–T–276. The thread for quilting shall be ticket No. 50, 3-ply; thread for binding shall be ticket No. 30, 3-ply.

3.3 Labels.—Each mattress pad shall conform to the requirements of 3.3.1 and in addition shall have a cloth identification label conforming to 3.3.1.1 and a state label conforming to 3.3.2 attached to one end of the pad.

3.3.1 *Fiber identification.*—Each mattress pad shall be labeled, ticketed, or invoiced for fiber content in accordance with the Rules and Regulations of the Textile Fiber Products Identification Act dated March 3, 1960.

3.3.1.1 *Identification label.* — The identification label shall measure not less than 3 by 3 inches and shall conform to type I, class 5 of Interim Federal Specification DDD–L–0020 except as specified in 3.3.1.1.1.

3.3.1.1.1 *Printing.* — The label shall be printed in letters and numerals not less than

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:32Z
Check the source to verify that this is the current version before use.

3/32 inch in height, except the nomenclature, which shall be not less than 1/8 inch in height. The content of the label shall be as follows:

Nomenclature
Contract number
Stock number

3.3.2 *State label.*—Each mattress pad shall have a label attached conforming to the legal requirements of the state in which the mattress pad is manufactured.

3.3.3 *Military requirements for labels.*

3.3.3.1 *Medical procurements.*—In addition to the requirements of 3.3.1.1.1, the label shall have a caduceus approximately one inch in height centered between the letters "U" and "S", conforming to type I, of Military Standard MS16686.

3.4 **Size.**—The mattress pads shall measure not less than 36 inches in width and 76 inches in length for size 1 and 52 inches in width and 75 inches in length for size 2, when measured as specified in 4.2.3.1.2.1.

3.5 **Weight.**—The weight of the finished mattress pad shall be not less than 20 ounces per square yard, based on the finished size, when weighed as specified in 4.2.3.1.3.1.

3.6 **Construction.**—(See 3.7 and table I.)

3.6.1 *Stitches, seams; and stitching.*—The seams, stitches and stitching types specified in table I are those covered by Federal Standard No. 751. The seam type as specified in table I shall be with seam allowance maintained and seams sewn so that no raw edges, runoffs, broken or skipped stitches, twists, pleats or puckers result.

3.6.2 *Thread breaks and back stitching.*—Thread breaks and ends of all seams and stitches when not caught in other seams or stitching shall be backstitched not less than three-eighths of an inch.

3.6.3 *Stitches per inch.*—The minimum and maximum number of stitches per inch shall be as specified in table I.

3.6.4 *Gage of stitching.* — The gage of stitching shall be as specified in the applicable operation.

3.6.5 *Stitch tension.* — Top and bottom thread shall be adjusted to fabric with proper tension so there will be no looped stitches or puckering of materials.

3.7 **Manufacturing operations requirement.** — The mattress pads shall be manufactured in accordance with all operations specified in table I. The contractor is not required to follow the exact sequence of operations.

3.8 **Workmanship.**—The finished mattress pad shall conform to the quality and grade of product established by this specification. The occurrence of defects shall not exceed acceptable quality levels.

4. SAMPLING, INSPECTION, AND TEST PROCEDURES

4.1 **Contractor inspection responsibility.** Unless otherwise specified herein, the supplier is responsible for the performance of all inspection requirements prior to submission for Government inspection and acceptance. Except as otherwise specified, the supplier may utilize his own facilities or any commercial laboratory acceptable to the Government. Inspection records of the examinations and tests shall be kept complete and available to the Government as specified in the contract or order.

4.2 **Inspection for acceptance.** — Except when otherwise specified by Civil Agencies, inspection shall be in accordance with the provisions of Military Standard MIL–STD–105 except where otherwise indicated.

4.2.1 *Inspection of components.*—In addition to the quality assurance provisions of the

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:32Z
Check the source to verify that this is the current version before use.

TABLE I.—*Manufacturing requirements*

No.	Manufacturing operations requirements	Stitch type	Seam and stitching type	Stitches per inch	Thread	
					Needle	Bobbin or looper
1	*Cutting:* *a.* The covers shall be cut with no piecing seams on either face. *b.* The binding shall be cut on the bias, not less than 1 9/16 inches wide. *c.* The felt shall be trimmed on all four sides.					
2	*Quilting:* *a.* Position felt padding between two coverpieces. *b.* Quilting shall be accomplished with zig-zag or criss-cross rows of stitching with the gauge of stitching not more than 1½ inches.	301	-----	5–9	50/3	50/3
3	*Binding:* *a.* Bind the edges of the mattress pad with a continuous binding with the raw edges of the binding turned under and stitched ⅛ ± 1/16 inch from turned edge catching all raw edges in the stitching. The binding shall begin on the short side at a corner and continue around pad finishing not less than 12 inches beyond the starting end on the short side of pad.	301	BSc–1	6–10	30/3	30/3
	b. The labels shall be centered on one end of the pad, positioned adjacent to each other and the bottom edges of labels caught in the binding seam.	301	BSc–1	6–10	30/3	30/3
4	Remove all spots and stains.					

subsidiary specifications, inspection shall be performed on components and material listed in table II for the characteristics shown therein.

4.2.2 *In-process inspection.* — Inspection shall be made at any point or during any phase of the manufacturing process to determine whether operation or assemblies are accomplished as specified. The Government reserves the right to exclude from consideration for acceptance any material for which in-process inspection has indicated non-conformance.

4.2.3 *Inspection of the end item.*

4.2.3.1 *Visual examination of mattress pad.* —The defects found during examination shall be classified in accordance with 4.2.3.1.1, 4.2.3.1.2 and 4.2.3.1.3. The lots shall be inspected in accordance with 4.2.3.1.4. The unit of product for these examinations shall be one completely fabricated mattress pad.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:32Z
Check the source to verify that this is the current version before use.

TABLE II.—*Tests*

Component and (end item) lot expressed in terms of	Characteristic	Requirement paragraph	Test method	Requirement applicable to		Number determinations per sample unit	Results reported as	Sample unit	Inspection level
				Indiv. unit	Lot avge.				
Linters (1 bale)	Grade	3.2.1	Visual	--	X	1	Pass or fail	½ pound	L–1
Garnetted felt (100 pounds)	Quality	3.2.2	Visual	--	X	1	Pass or fail	12 in. by 12 in.	L–1
Mattress pads (each)	Iden. of cotton	3.2.1	CCC–T–191 1200	X	--	1	Pass or fail	1 pad	L–1

NOTE.—Samples of cotton linters shall not be sent to the Government laboratory for grading if the linters have been officially graded by the United States Department of Agriculture. The inspector shall obtain from the contractor a certificate or an attested or photostatic copy of the certificate showing the number of bales, the number or identifying mark on each bale graded, and the identity of the grades when United States Department of Agriculture graded contractor-supplied material is used. Whenever contractor-furnished cotton linters have not been graded by a properly qualified employee of the Government or a Government licensed classifier, the sample of linters shall be sent to the Government laboratory for grading. Grading by any other than Government employed graders or Government licensed classifiers shall not be acceptable.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:32Z
Check the source to verify that this is the current version before use.

4.2.3.1.1 *Examination of mattress pad for defects in design, material, construction and workmanship:*

Examine	Defects	Classification	
		Major	Minor
Material defects (sheeting)	Any hole, cut or tear	X	
	Any weak place seriously affecting serviceability	X	
	Any weak place affecting serviceability but not seriously		X
	Any smash	X	
	Rancid or other objectionable odor	X	
	Not fabric specified	X	
	Not bleached (white)		X
	Multiple floats or skips ½ inch or more in combined directions	X	
	Multiple floats or skips less than ½ inch in combined directions		X
	Single float or skips over 12 inches in length		X
	Four or more single floats or skips regardless of length in entire pad		X
	Three or more contiguous broken or missing warp or filling threads	X	
	Two contiguous broken or missing warp or filling threads		X
	Tight ends or tight picks resulting in a pronounced ridge or clearly noticeable puckering		X
	Loose and weakening slub, ⅛ inch or more in thickness, at widest point	X	
	Slub more than 1/16 inch but less than ⅛ inch in diameter at widest point		X
Cleanness	Any spot or stain, attributable to the sheeting material only, more than ¼ inch square in area, clearly noticeable at a distance of 6 feet		X
	More than three spots or stains attributable to the sheeting material only, up to ¼ inch square in area, clearly noticeable at a distance of 6 feet		X
	Any oil or grease spot or stain attributable to the padding	X	
	Any colored or dyed yarns attributable to the padding	X	
Workmanship	Any thin place devoid of padding 2 inches square or more in area	X	

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:32Z
Check the source to verify that this is the current version before use.

Examine	Defects	Classification	
		Major	Minor
Workmanship (continued)	Any thin place devoid of padding, more than 1 inch square in area, but less than 2 inches square in area		X
	Three or more thin places devoid of padding regardless of area	X	
	Furrow, lump or bulge resulting from uneven or improper distribution of the padding (lapped padding is not considered improper distribution)	X	
	More than four untrimmed thread ends or loose threads, one inch or more in length		X
	Edges badly twisted, pleated, wavy or puckered		X
	Three or more pleats less than 8 inches in length and ¼ inch or more in depth at widest point regardless of area per pad		X
	Any pleat regardless of area, 8 inches or more in length and ¼ inch or more in depth at widest point, or any pleat not within 5 inches from any edge extending more than 2 inches in length	X	
	Any splice in sheeting fabric	X	
	Needle chews expected to develop into a hole	X	
Binding	Not cut in bias direction	X	
	Torn or chewed	X	
	Not one continuous length per pad		X
	Closing end extends less than 12 inches beyond the starting end		X
	Binding not securely caught in binding seam		X
Seams and stitching	Binding not seamed with seam type BSc–1		X
	Not stitch type 301 throughout		X
	Stitching margin of binding less than 1/16 inch or more than 3/16 inch		X
	Binding seam does not begin at corner on short side of pad		X
	Binding sewn with less than 6 stitches per inch		X
	Binding sewn with more than 10 stitches per inch		X
	Any open seam or run-off more than 1 inch in length	X	
	Any open seam or run-off 1 inch or less in length		X
	Edge of pad not securely caught in binding		X
	Any raw edge of binding more than ½ inch in length		X

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:32Z
Check the source to verify that this is the current version before use.

Examine	Defects	Classification	
		Major	Minor
Seams and stitching (continued)	Three or more raw edges of binding per pad up to and including ½ inch in length		X
	Raw edge of pad covering, over 2 inches in length		X
	Two or more raw edges of pad covering, up to and including 2 inches in length		X
	Any raw edge of the pad covering regardless of length, not caught in binding stitching	X	
	Note: This examination will be made by turning back the edge of the binding at the raw edge locale and determining visually whether the pad covering is caught in the binding stitches		
	Stitch tension loose, resulting in a loosely secured seam or looped stitches		X
	Stitch tension tight, stitches break when normal strain is applied to the seam or stitching		X
	Note: Puckering is evidence of tight tension.		
	Thread breaks or ends of any seam not backstitched as specified, except when end of seam is caught in another seam or stitching		X
	One or more broken stitches at four or more places in quilting		X
	Continuous skipped stitches for a distance of 1 inch or more at two or more places in quilting		X
	Rows of quilting stitches more than 1½ inches apart		X
	Less than 5 stitches per inch in quilting		X
	More than 9 stitches per inch in quilting		X
Labels	Missing or misplaced or text incomplete, incorrect, illegible or wrong color		X

4.2.3.1.2 *Examination of mattress pad for defects in dimension:*

Examine	*Defect*
Width (size 1)	Less than 36 inches
Width (size 2)	Less than 52 inches
Length (size 1)	Less than 76 inches
Length (size 2)	Less than 75 inches

4.2.3.1.2.1 *Measurement of length and width.*—Length and width shall be taken as the average of three measurements in each direction. Before measuring, the mattress pads shall be laid in a flat position without tension.

4.2.3.1.3 *Examination of mattress pad for defects in weight.*—Any weight that is less than 20 ounces per square yard, based on the finished size shall be classified as a defect.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:32Z
Check the source to verify that this is the current version before use.

4.2.3.1.3.1 *Determination of weight.* — Weight may be determined under prevailing atmospheric conditions; except in the settlement of disputes. The weight of the mattress pad shall then be determined after having been brought to equilibrium with an atmosphere having a relative humidity of 65 percent plus or minus 2 percent and a temperature of from 70° to 80° F. The material shall be considered to be in equilibrium when it shows no progressive change in weight. The weight of the mattress pad shall be calculated by the following method:

$$\text{Ounces per square yard} = \frac{\text{Weight of pad in pounds x 16 x 36}}{\text{length in yards} \times \text{width in inches}}$$

4.2.3.1.4 *Inspection levels and acceptable quality levels (AQL's).* — The inspection levels and acceptable quality levels (AQL's) expressed in defects per hundred units shall be as follows:

	Inspection level	*AQL*
For examination in 4.2.3.1.1	II	Major 4.0, Total 10.0
For examination in 4.2.3.1.2	L–6	1 class 4.0
For examination in 4.2.3.1.3	L–6	1 class 4.0

4.2.4 *Examination of preparation for delivery requirements.*—An examination shall be made to determine that packaging, packing, and marking requirements of Section 5 of this specification are complied with. Defects shall be scored in accordance with the list below. The sample unit shall be one shipping container fully packed, selected just prior to the closing operation. Defects of closure listed below shall be examined on shipping containers fully prepared for delivery. The lot size shall be the number of containers in the inspection lot. The inspection level shall be L–4 and the AQL shall be 4.0 defects per hundred units.

Examine	Defects
Marking (exterior and interior)	Omitted, incorrect, illegible, of improper size, location, sequence, or method of application.
Materials	Any component missing. Any component damaged, affecting serviceability.
Workmanship	Inadequate application of components, such as: incomplete closure of case liners, container flaps, loose strapping, inadequate stapling. Bulging or distortion of containers.
Content	Number per container is more or less than required.

5. PREPARATION FOR DELIVERY

(Federal Standard No. 102 shall be referred to for definitions and applications of the various levels of packaging and packing protection for supplies and equipment (for civil agencies only).)

5.1 **Packaging.**—Packaging shall be level A or C as specified (see 6.2).

5.1.1 *Level A.*—Each pad shall be neatly folded to form a bundle approximately 18 by 25 inches.

5.1.2 *Level C.*—Pads shall be packaged in accordance with the manufacturer's commercial practice.

5.2 **Packing.**—Packing shall be level A, B, or C as specified (see 6.2).

5.2.1 *Level A.*—Eighteen pads, packaged as specified in 5.1, shall be packed in a fiberboard shipping container conforming to class 2, V3c, or V3s, style OSC–L of Federal Specification PPP–B–636. The inside of each fiberboard container shall be fitted with a taped one-piece double-faced corrugated fiberboard liner having a minimum bursting strength of 275 p.s.i. conforming to Federal Specification PPP–B–636. Alternatively, shipping containers may be used that conform to overseas

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:32Z
Check the source to verify that this is the current version before use.

type contained in Federal Specifications PPP–B–591, PPP–B–601, or Military Specification MIL–B–10377; or class 2, style 2 or 4 of Federal Specification PPP–B–621, except that the requirements for additional battens shall not apply. Packages for level A shall be packed flat within a shipping container having inside dimensions of approximately 25½ inches in length, 18½ inches in width, and 18½ inches in depth. Exact dimensions shall be determined by the contractor to insure that contents fit snugly in the shipping container. For fiberboard shipping containers, the specified length and width dimensions shall be inside the corrugated liner. Each container shall be provided with a type I or II, grade B or C, class 2 sealed case liner conforming to Military Specification MIL–L–10547. The fiberboard shipping container shall have the case liner placed between the corrugated liner and the inner surfaces of the container. Each shipping container shall be closed and strapped in accordance with the appendix of the applicable container specification.

5.2.2 *Level B.*—Eighteen pads, packaged as specified in 5.1, shall be packed in a fiberboard shipping container conforming to type I or II, class 1, style OSC–L of Federal Specification PPP–B–636, except that the minimum bursting strength of the fiberboard shall be 275 p.s.i. The inside of each fiberboard container shall be fitted with a taped one-piece, double-faced corrugated fiberboard liner having a minimum bursting strength of 275 p.s.i. conforming to Federal Specification PPP–B–636. All flaps of the fiberboard shipping container shall be securely sealed with an adhesive commercially used for the specific product being packed by application throughout the entire area of contact between the flaps, or by a combination of metal stitching the bottom flaps and sealing the top flaps with adhesive. Alternatively, shipping containers may be used that conform to domestic type, style A or B of Federal Specifications PPP–B–591, PPP–B–601, or Military Specification MIL–B–10377; or class 1, style 2 or 4 of Federal Specification PPP–B–621, except that the requirements for additional battens shall not apply. Packages for level B shall be packed flat within a shipping container having inside dimensions of approximately 25½ inches in length, 18½ inches in width, and 18½ inches in depth. Exact dimensions shall be determined by the contractor to insure that contents fit snugly in the shipping container. For fiberboard shipping containers, the specified length and width dimensions shall be inside the corrugated liner. Each shipping container, except fiberboard containers, shall be provided with a 40-pound kraft paper liner conforming to grade B of Federal Specification UU–P–268, consisting of not more than two pieces with the edges overlapping not less than 4 inches. Each fiberboard container shall have the contents completely covered on the top and bottom with a sheet of the specified kraft paper.

5.2.3 *Level C.*—Pads, packaged as specified in 5.1, shall be packed in a manner to insure carrier acceptance and safe delivery at destination. Shipping containers shall conform to carrier rules and regulations applicable to the mode of transportation.

5.3 Marking.

5.3.1 *Civil agencies.*—In addition to any special marking required by the contract or order, shipments shall be marked in accordance with Federal Standard No. 123.

5.3.2 *Military agencies.*—In addition to any special marking required by the contract or order, shipping containers shall be marked in accordance with Military Standard MIL–STD–129.

6. NOTES

6.1 Intended use.—The mattress pads are intended for use by military and nonmilitary agencies.

6.2 Ordering data. — Purchasers should exercise any desired options offered herein and procurement documents should specify the following:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:32Z
Check the source to verify that this is the current version before use.

(*a*) Title, number and date of this specification.

(*b*) Sizes required (see 1.2.1).

(*c*) Selection of applicable levels of packaging and packing (see 5.1 and 5.2).

6.3 Samples.—For access to samples address the contracting activity issuing the invitation for bids.

6.4 Transportation description. — The transportation descriptions and minimum weights applicable to this item are:

Rail:

Pads, Cotton, not otherwise indexed by name, quilted.

Carload minimum weight 20,000 pounds, subject to Rule 34 Uniform Freight Classification.

Motor:

Pads, Cotton, not otherwise indexed, quilted.

Motor volume minimum weight 20,000 pounds.

6.5 Packaging and packing.—Level B packaging and packing should be used by ordering agencies only when shipment is known to be made to a holding Supply Depot or Warehouse from which partial shipments will be made to ultimate consumers.

Notice. — When Government drawings, specifications, or other data are used for any purpose other than in connection with a definitely related Government procurement operation, the United States Government thereby incurs no responsibility nor any obligation whatsoever; and the fact that the Government may have formulated, furnished, or in any way supplied the said drawings, specifications, or other data, is not to be regarded, by implication or otherwise as in any manner licensing the holder or any other person or corporation, or conveying any rights or permission to manufacture, use, or sell any patented invention that may in any way be related thereto.

MILITARY INTERESTS:
Army—M Q
Navy—S
Air Force—MOAMA

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:32Z
Check the source to verify that this is the current version before use.