MIL-P-50774A(AR)
27 October 1977
SUPERSEDING
MIL-P-50774(MU)
27 June 1972

MILITARY SPECIFICATION

PROJECTILE, 20MM, TARGET PRACTICE, M55A3 and M55A3Bl

This specification is approved for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This specification covers two models of 20mm target practice projectiles manufactured from bar stock; M55A3 with machined bodies and M55A3B1 with impact extruded bodies. (see 6.1)

2. APPLICABLE DOCUMENTS

2.1 Issues of documents. The following documents of the issue in effect on date of invitation for bids, or request for proposal, form a part of this specification to the extent specified herein.

SPECIFICATIONS

FEDERAL

TT-C-490 - Cleaning Methods and Pretreatment of Ferrous Surfaces for Organic Coatings

MILITARY

MIL-A-2550 - Ammunition, General Specification for

STANDARDS

MILITARY

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes
MIL-STD-109 - Quality Assurance Terms and Definitions

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: Commander, US Army Armament Research and Development Command, ATTN: DRDAR-TST-S, Dover, New Jersey 07801 by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

FSC 1305

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T20:37Z
Check the source to verify that this is the current version before use.

2.1 (Cont)

MIL-STD-651 - Visual Inspection Standards for 20mm Ammunition and Components
MIL-STD-1168 - Ammunition Lot Numbering
MIL-STD-1169 - Packaging, Packing and Marking for Shipment of Inert Ammunition Components
MIL-STD-1235 - Single and Multilevel Continuous Sampling procedures and Tables for Inspection by Attributor

DRAWINGS

ARMAMENT RESEARCH AND DEVELOPMENT COMMAND

D11075781 - Projectile, 20mm, Target Practice, M55A3 and M55A3B1
F7258861 - Carton, for Interplant Shipment of Projectiles, 20mm Assemblies and Metal Parts Assemblies (200)
D7259136 - Shipping Container for Inert Projectile, 20mm Assemblies and Metal Parts Assemblies (10,000)
D7259191 - Cartridge, 20mm, for M55 Type, Target Practice, Projectile Metal Parts Test
LI 11075781 - Index of Inspection Equipment Lists for: Projectile, 20mm, Target Practice, M55A3 and M55A3B1

PUBLICATIONS

U.S. ARMY MATERIEL DEVELOPMENT AND READINESS COMMAND

DARCOM-R 715-505 - Ammunition Ballistic Acceptance Test Methods, Volume 8, Test Procedures for 20mm Cartridges

(Copies of specifications, standards, drawings, and publications required by contractors in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitation for bids or request for proposal shall apply.

American Society for Testing and Materials (ASTM)
ASTM B117 - Method of Test for Salt Spray (Fog) Testing

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103)

Technical society and technical association specifications and standards are generally available for reference from libraries. They are also distributed among technical groups and using Federal agencies.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T20:37Z
Check the source to verify that this is the current version before use.

3. REQUIREMENT

3.1 General. The projectile shall be in accordance with the requirements of Drawing (Dwg.) D11075781 and with all requirements of the drawings and specifications shown thereon.

3.2 Manufacturing process. All parts and assemblies shall be manufactured by a process approved by the contracting officer and no deviation from that process shall be made without his prior approval. (see 6.4)

3.3 First article sample. Unless otherwise directed by the contracting officer, a first article sample shall be required.

3.4 Banding. The rotating band blank and the rotating band seat shall be clean and dry at the time of banding. Shot or sandblasting shall not be used to clean the band seat after knurling. The rotating band blank shall fill the band seat.

3.5 Soundness. Metal discontinuity in the projectile body, as determined by eddy current inspection, shall be less than that represented by Production Check Standard (PCS) No. 1.

3.6 Protective coating.

3.6.1 Phosphate coating. The pretreatment process used shall be in accordance with applicable requirements of Dwg. D11075781. The phosphate coating shall be in accordance with the requirements of TT-C-490 for appearance and minimum weight, as applicable to the type of phosphate coating.

3.6.2 Paint coating. The paint coating shall be in accordance with applicable requirements of Dwg. D11075781. Exterior paint adhesion shall be in accordance with applicable requirements of TT-C-490.

3.6.3 Corrosion resistance. The painted projectile body shall show no evidence of corrosion (red rust) after exposure to a 5 percent solution of atomized salt spray for 24 hours.

3.7 Metal parts security. The sample projectiles, assembled into test cartridges loaded in accordance with the requirements of Dwg. D7259191, shall not separate or breakup in the test for metal parts security.

3.8 Workmanship. The requirements for workmanship are as specified by applicable drawings, referenced specifications and the following:

3.8.1 Processing defects. The projectile shall be free of dents, deep scratches, cuts, sharp edges, burrs, metal flaws, excessive surface roughness and other forms of substandard workmanship.

3.8.2 Cleanliness. The projectile shall be free of all foreign matter.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T20:37Z
Check the source to verify that this is the current version before use.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.1.1 Quality assurance terms and definitions. Reference shall be made to MIL-STD-109 for definition of quality assurance terms.

4.2 Classification of inspections. The inspection requirements specified herein are classified as follows:

1. First article inspection (see 4.3).
2. Quality conformance inspection (see 4.4).

4.3 First article inspection.

4.3.1 First article sample. The sample shall be delivered for inspection in accordance with first article approval provisions of the contract and MIL-A-2550, and shall consist of:

a. Inspection and nonfiring tests:

3	Standard test panels (see TT-C-490)
32	Rotating band blanks
125	Noses
125	Bodies, projectile
125	Projectiles, uncoated
125	Projectiles, painted

b. Firing test:

4,000	Projectiles, painted

The sample shall be manufactured using the same materials, equipment, processes and procedures as will be used in regular production. Identification shall be in accordance with MIL-STD-1168.

4.3.1.1 Inspection. After inspection by the contractor and provisional acceptance by the Government activity, the sample will be inspected in accordance with the provisions of MIL-A-2550. Failure of the original first article sample to be in accordance with the applicable drawings and the requirements of Para. 3, as specified herein, will result in sample disapproval. (see 6.3)

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T20:37Z
Check the source to verify that this is the current version before use.

4.4 Quality nformance inspection.

4.4.1 Submission of product. The product shall be submitted in accordance with MIL-STD-105 or MIL-STD-1235, as applicable.

4.4.1.1 Lot. A lot shall consist of one model of projectiles produced by one manufacturer in one unchanged process, in accordance with the contract and the same drawings and drawing revisions, and same specification and specification revision.

4.4.1.2 Lot identification. Each projectile and each packed projectile lot shall be identified in accordance with applicable drawings and MIL-STD-1168.

4.4.2 Examination. One hundred percent examination shall be performed by the contractor for all critical defects. Examination for major and minor defects shall be performed as specified herein. Each part and each assembly found to be defective shall be rejected.

4.4.2.1 Sampling and acceptance criteria. The sampling plans and procedures shall be in accordance with MIL-STD-105 or MIL-STD-1235. To determine product acceptability, major or minor defects as listed herein may be considered collectively on a class basis or they may be considered individually. However, where major defects are considered collectively on a class basis, the acceptance number for any individual defect of the class shall be limited by the assigned Acceptable Quality Level (AQL) for individual defect associated with the class. (see 4.4.2.2.c) In addition, where three or less defects appear in a classification, or where MIL-STD-1235 is used, sampling plans applicable to a class shall not be used for major defects. (see 6.5)

4.4.2.2 AQL's. The following AQL's are assigned to major and minor defects:

a. Individual:

Major	0.25%
Minor	0.40%

b. Class basis:

Major	1.50%
Minor	2.50%

c. Individual defects associated with the class basis:

Major	0.40%

4.4.3 Classification of defects. 1/ The classification of defects shall be as specified herein. (see 6.6)

Source: https://assist.dla.mil -- Downloaded: 20261O-22T20:37Z
Check the source to verify that this is the current version before use.

4.4.3.1 Rotating band blank (see Dwg. B7258816, covering a detail of Dwg. D11075781).

Categories and Defects	Method of Inspection
Critical: None defined.	
Major:	
101. Foreign matter	Visual (see 3.4)
102. Defective metal, including lamination	Visual
103. Incomplete or deformed	Visual 2/
Minor:	
201. Width, max.	Gage

4.4.3.2 Nose (see Dwg. C11075784, covering a detail of Dwg. D11075781).

Categories and Defects	Method of Inspection
Critical: None defined.	
Major:	
101. Diameter, ogive at shoulder, min.	Gage
102. Length, spherical surface to shoulder, max.	Gage
Minor:	
201. Diameter, ogive at shoulder, max.	Gage
202. Length, spherical surface to shoulder, min.	Gage
203. Diameter, cylindrical surface	Gage
204. Length, overall, min.	Gage
205. profile, ogive, except length, spherical surface to shoulder	Gage
206. Finish	Visual/Feel
207. Foreign matter	Visual
208. Mutilated	Visual

4.4.3.3 Body (see Dwg. D11075783, covering a detail of Dwg. D11075781).

Categories and Defects	Method of Inspection
Critical: None defined.	
Major:	
101. Knurling missing or incomplete	Visual
102. Score missing	Visual
103. Diameter, bourrelet, min.	Gage
104. Length, overall, max.	Gage
105. Length, mouth to rear edge of rotating band seat	Gage
106. Depth, knurling, min.	Visual/Gage 3/
107. Foreign matter in rotating band seat	Visual (see 3.4)

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T20:37Z
Check the source to verify that this is the current version before use.

4.4.3.3 (Cont)

Categories and Defects	Method of Inspection
Minor:	
201. Diameter, rotating band seat (knurled)	Gage
202. Width, rotating band seat	Gage
203. Inside diameter	Gage
204. Width, knurling, min.	Visual/Gage 3/

4.4.3.4 Projectile, unpainted (see Dwg. D11075782, covering a detail of Dwg. D11075781).

Categories and Defects	Method of Inspection
Critical:	
1. Ferrous metal discontinuity	Soundness test
Major:	
101. Runout, nose with datum surface	Gage
102. Diameter, bourrelet, min.	Gage
103. Gap between nose and body	Gage
104. Body not flush or below at junction with nose	Visual
105. Length, overall	Gage
106. Length, nose to rear edge of rotating band	Gage
107. Diameter, body, rear of rotating band, min.	Gage
108. Diameter, rotating band	Gage
109. Runout, rotating band with datum surface	Gage
110. Runout, body, rear of rotating band with datum surface	Gage
111. Location, crimp groove	Gage
112. Profile, crimp groove	Gage
113. Radius, rear edge of crimp groove, max.	Gage
114. Void at junction of rotating band and projectile body	Visual
115. Base face machined (impact extruded)	Visual
Minor:	
201. Finish improper	visual 4/
202. Diameter of bourrelet, max.	Gage
203. Depth and width of undercut, front and rear of rotating band, max.	Gage
204. Mutilated	Visual
205. Loose nose	Manual 5/
206. Width of rotating band	Gage

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T20:37Z
Check the source to verify that this is the current version before use.

4.4.3.5 Projectile, painted (see Dwg. D11075781).

Categories and Defects	Method of Inspection
Critical: None defined.	
Major:	
101. Diameter, bourrelet, max.	Gage
102. Diameter, body, rear of rotating band, max.	Gage
103. Radius, base of projectile	Visual/Ga
104. Weight	Balance
Minor:	
201. Paint not dry	Tactile
202. Marking incorrect, incomplete, illegible, or missing	Visual
203. Paint inadequate	Visual
204. Paint on rotating band	Visual
205. Foreign matter	Visual
206. Rotating band damaged	Visual

1/ MIL-STD-651 shall apply in defining and evaluating visual defects.

2/ A rotating band blank which is deformed or judged to lack sufficient metal in any-part of its width or thickness to provide for complete band seat fill and minimum rotating band profile dimensions shall be classed defective.

3/ Measurement of knurling for compliance with the minimum depth and width requirements shall apply where visual inspection indicates that the depth or width dimension is borderline.

4/ Measurement of surface roughness shall apply where visual inspection indicates that the specified finish is exceeded.

5/ If the nose moves with respect to the projectile body under thumb and finger pressure applied in the lateral or axial direction, the projectile shall be classified defective.

6/ Measurement of the base radius shall apply where visual inspection indicates that the base radius of the projectile is borderline.

4.4.4 Tests. The tests listed in Table I shall be performed on each projectile lot in accordance with the test methods prescribed in 4.5. Only projectiles having met the visual and dimensional requirements and having been selected in such a manner that the sample is representative of the entire lot shall be used in the tests. The selected projectiles shall be thoroughly mixed before being divided into samples for the various tests. Sample size and acceptance criteria for each test shall be as specified.

Source: https://assist.dla.mil -- Downloaded: 202640-22T20:37Z
Check the source to verify that this is the current version before use.

4.4.4 (Cont)

Table I

Test	Sample Size		Item	Rqmt Para
Band tightness	1/	315	Projectiles, uncoated or painted	3.4
Automatic inspection effectiveness	2/	--	PCS No. 1 (see 4.5.3)	- -
Soundness verification	3/	315	Projectiles, uncoated (see 4.5.4)	3.5
Phosphate coating (appearance & weight)	4/	--	3 Standard panels (see TT-C-490)	3.6.1
Paint adhesion	5/	13	Projectiles, painted	3.6.2
Corrosion resistance	6/	32	Projectiles, painted	3.6.3
Metal parts security	7/	250	projectiles, painted	3.7

1/ If two or more units of the sample have an average radial void, between the seated band and the band seat, greater than 0.004 inch, the lot shall be rejected. If one unit of the sample has an average radial void greater than 0.004 inch, a second sample consisting of the same number of units as specified for the first sample shall be tested. If in the accumulated samples, two or more units have an average radial void greater than 0.004 inch, the lot shall be rejected.

2/ Failure of the flaw detector to reject PCS No. 1 shall be cause for rejection of all assemblies inspected for "soundness" since the preceding test and shall require requalification of the equipment for automatic inspection. (see 4.5.3)

3/ Rejection of one or more units of the sample by the flaw detector in the test for body metal soundness shall be cause for rejection of the lot.

4/ Failure of the phosphate coating on the standard panels to comply with the applicable requirements shall be cause for rejection of all projectiles phosphate since the preceding test.

5/ If two or more units of the sample fail to comply with the requirement for paint adhesion, the lot shall be rejected. If one unit of the sample fails to comply with the requirement, a second sample consisting of the same number of units *as* specified for the first sample shall be tested. If in the accumulated samples, two or more units fail to comply with the requirement for paint adhesion, the lot shall be rejected.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T20:37Z
Check the source to verify that this is the current version before use.

4.4.4 (Cont)

6/ If two or more units of the sample fail to comply with the corrosion resistance requirement, the lot shall be rejected. If one unit fails to comply with the requirement, a second sample consisting of the same number of units as specified for the first sample shall be tested. If in the accumulated samples, two or more units fail to comply with the corrosion resistance requirement, the lot shall be rejected.

7/ The occurrence of one or more of the following casualties, as witnessed by hole(s) in the fragmentation screen(s), or recovery of the Part(s) or fragment(s) shall be cause for rejection of the lot, except *as* otherwise provided:

a. Body breakup.

b. Loss of nose.

c. Complete rotating band separation. This is defined as detachment of all of the band having band seat knurling imprint.

d. partial rotating band separation. This is defined as detachment of part of the band having band seat knurling imprint.

e. The following acceptance criteria shall apply to thrown band fragments having no evidence of band seat knurling imprint:

(1) The lot will be accepted if two or less assmblies throw band fragments having length not greater than 0.500 inch.

(2) The lot will be rejected if three or more assemblies throw band fragments having length not greater than 0.500 inch.

(3) The lot will be rejected if any assembly throws a band fragment having length greater than 0.500 inch (indicative of deep-seated band lamination).

(4) The lot will not be penalized for band particles thrown as a result of normal band fringing or slivering.

4.4.5 Packaging, packing, and marking inspection. Inspection for packaging, packing and container marking shall be in accordance with the quality assurance provisions of MIL-STD-1169.

4.4.6 Inspection equipment. Index of Inspection Equipment List (LI) 11075781 identifies the applicable inspection equipment required to perform examination and tests as specified herein. Equipment design(s) shall be in accordance with the applicable code designations. The code designations are defined on Dwg. B11075228, a detail of LI 11075781. The provisions of MIL-A-2550 shall apply.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T20:37Z
Check the source to verify that this is the current version before use.

4.5 Test methods and procedures.

4.5.1 Band tightness. The method of test shall comply with all requirements of the operating instructions for the band tightness tester (Dwg. B7259545, a detail of LI 11075781). The inspection sample shall be cycled through the tester to determine compliance with the rotating band tightness requirement. The total measurement of radial void, registered on the tester indicator at final ram pressure, shall be divided by four (number of indenters) to determine the average radial void.

4.5.2 Soundness. The method of inspection shall be as specified in requirements of Operating Instructions for Eddy Current Flaw Detector (Dwg. D11075203, a detail of LI 11075781), except for those inspection requirements which are reserved for Government application, as specified herein.

4.5.2.1 Application of defect standards. Master defect standards, referenced in the operation instructions, shall apply to resolve inspection discrepancies occurring between the results of defect standards supplied for contractor "soundness" inspection and those supplied for Government "soundness" verification. (see 6.7)

4.5.3 Automatic eddy current inspection effectiveness. Equipment checkout shall be performed as stated in the operating instructions at the start of each shift and after any adjustment or shutdown. Upon completion of checkout, cycle the PCS No. 1, front slot and rear slot standards through the inspection system during automatic operation. All three standards must be rejected to assure correct adjustment for reject level and scan limits. During remainder of shift the PCS No. 1 shall be cycled through the equipment at intervals of 20 ± 5 minutes during automatic operation.

4.5.3.1 Equipment verification. The government inspector will maintain, independent of the contractor, a set of standards and may cycle these standards through the equipment at any time. Failure of equipment to reject standards will be evidence that the equipment is not properly adjusted and the contractor will be so notified.

4.5.4 Soundness verification. After equipment checkout and verification as specified in 4.5.3 and 4.5.3.1 the entire lot sample will be inspected with the equipment operating automatically. Any rejected unit of the sample will be automatically cycled through the equipment with the CAL. button pressed (to lower the sensitivity one step below that used for production inspection). Any unit which is rejected at the lower sensitivity shall be classed as a defective.

4.5.5 Phosphate coating. The method of test shall be as prescribed by TT-C-490 for the type of coating used (see Dwg. D11075781). The prescribed panels shall be processed, with the projectiles to be represented, at the start of daily production and at 4-hour intervals, maximum, thereafter. Appearance and-weight of the coating shall be recorded.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T20:37Z
Check the source to verify that this is the current version before use.

4.5.6 Paint adhesion. The method of test shall be as prescribed by TT-C-490. The test shall be made on the painted bourrelet of each unit of the sample forward of the rotating band. Visible exposure of underlying phosphate coating or ferrous metal of any unit of the sample, as a result of the test, shall be recorded as a defect.

4.5.7 Corrosion resistance. The method of test shall be as prescribed in American Society for Testing and Materials (ASTM), ASTM B117. The paint shall not be disturbed, however, the rotating band and unpainted surfaces of the sample projectiles may be masked out by a wax coating or other suitable material. The salt spray solution and exposure time shall be as specified in 3.6.3.

4.5.8 Metal parts security. The method of test will be as prescribed by DARCOM-R 715-505, Volume 8, *as* applicable. The test sample will be assembled to comply with requirements of Dwg. D7259191, Cartridge, 20mm, for M55 Type, Target Practice, projectile metal parts test. The test cartridges, at ambient temperature, will be fired in bursts of 50 shots in an M39 gun. The gun barrel will be at ambient temperature for the firing of each burst. The cyclic rate of fire will be recorded for informational purposes.

5. PACKAGING

5.1 Packaging and packing, level C. Each lot of projectiles shall be packed as specified by Dwg. F7258861 or Dwg. D7259136.

5.2 Marking, level C. Marking or labeling of packed cartons or containers shall comply with applicable requirements of MIL-STD-1169.

6. NOTES

6.1 Intended use. These projectiles are intended for use with the M103 type cartridge case in the assembly of target practice cartridges.

6.2 Ordering data. procurement documents should specify the following:

6.2.1 Title, number, and date of this specification.

6.2.2 Projectile model and type.

6.2.3 Place of inspection, if not place of manufacture.

6.2.4 First article sample requirements. (see 3.3, 4.3 and 6.3)

6.2.5 Packaging, packing and marking instructions. (see 5.1 and 5.2)

6.2.6 Provision for shipment and testing of first article and production lot samples for metal parts security. (see 4.5.8)

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T20:37Z
Check the source to verify that this is the current version before use.

6.2.7 Provision for the supply, maintenance and disposition of Government furnished test equipment for acceptance inspection purposes.

6.2.8 Provisions for the inclusion of MIL-STD-1167, Ammunition Data Cards on DD form 1423, Contract Data Requirements List.

6.3 First article sample. When a first article sample is required by the contract, the contracting officer will notify the test facility when to proceed with the metal parts security test. (see 4.3) Additional projectiles may be required by the test facility.

6.4 Process deviation. A process deviation is defined as a change in the approved basic method of manufacture, or an operational change which alters the metallurgical or physical properties of the item of contract.

6.5 AQL's. The optional use of AQL values for either individual defects or classes of defects, with individual major defect limitation, is intended to minimize inspection agency administrative burden which might result from an exclusive assignment of individual defect AQL's. The option also permits flexibility where sampling inspection for acceptance is integrated into the manufacturing process.

6.6 Intermediate point inspection. The classification of defects identifies the defect characteristics (among other things) for acceptance inspection. It may be necessary to modify the sequence of inspection stations to best suit the manufacturing process. Inspection for defect characteristics which will be hidden or altered by subsequent processing operations (including unrelated operations), should be scheduled to prevent premature acceptance which could be detrimental to the attainment of optimum product quality in the end item.

6.7 Defect standards. The initial supply of defect standards and instructions for contractor and Government application to the eddy current method of inspection, will be furnished with the inspection equipment. Replacement standards shall be requisitioned through normal channels by the Government agency having contract administration responsibility.

6.8 Changes from previous issue. Asterisks are not used in this revision to identify changes with respect to the previous issue, due to the extensiveness of the changes.

Custodian:

Army - AR

Preparing Activity:

Army - AR

Project No. 1305-A816

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T20:37Z
Check the source to verify that this is the current version before use.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T20:37Z
Check the source to verify that this is the current version before use.

FOLD

POSTAGE AND FEES PAID
DEPARTMENT OF THE ARMY
DOD – 314

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300

Commander
U.S. Army Armament Research and
Development Command
ATTN: DRDAR-TST-S
Dover, NJ 07801

FOLD

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T20:37Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

OMB Approval
No. 22-R255

INSTRUCTIONS: The purpose of this form is to solicit beneficial comments which will help achieve procurement of suitable products at reasonable cost and minimum delay, or will otherwise enhance use of the document. DoD contractors, government activities, or manufacturers/vendors who are prospective suppliers of the product are invited to submit comments to the government. Fold on lines on reverse side, staple in corner, and send to preparing activity. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements. Attach any pertinent data which may be of use in improving this document. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity.

DOCUMENT IDENTIFIER AND TITLE MIL-P-50774A(AR)
Projectile, 20mm, Target Practice, M55A3 and M55A3B1

NAME OF ORGANIZATION AND ADDRESS

CONTRACT NUMBER

MATERIAL PROCURED UNDER A

☐ DIRECT GOVERNMENT CONTRACT ☐ SUBCONTRACT

1. HAS ANY PART OF THE DOCUMENT CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE?

A. GIVE PARAGRAPH NUMBER AND WORDING.

B. RECOMMENDATIONS FOR CORRECTING THE DEFICIENCIES

2. COMMENTS ON ANY DOCUMENT REQUIREMENT CONSIDERED TOO RIGID

3. IS THE DOCUMENT RESTRICTIVE?

☐ YES ☐ NO *(If "Yes", in what way?)*

4. REMARKS

SUBMITTED BY *(Printed or typed name and address - Optional)*

TELEPHONE NO.

DATE

DD FORM 1 JAN 72 1426 REPLACES EDITION OF 1 JAN 68 WHICH MAY BE USED

Source: https://assist.dla.mil -- Downloaded: 202640-22T20:37Z
Check the source to verify that this is the current version before use.