INCH-POUND

MIL-D-48111A (AR)
AMENDMENT 2
1 April 1992
SUPERSEDING
AMENDMENT 1
7 February 1983

MILITARY SPECIFICATION

DETONATOR, STAB, M94
PARTS FOR AND LOAD, ASSEMBLING AND PACKING

This Amendment forms a part of Military Specification MIL-D-48111A (PA) dated 1 April 1975 and is approved for use by the US Army Armament Munitions and Chemical Command and is available for use by all Departments and Agencies of Department of Defense.

PAGE 9

4.4.2.4 Critical. Delete: "4. Slide cover assembly reversed" and substitute the following:

"4. Slide cover assembly reversed (not applicable to alternate design)".

PAGE 10

4.4.2.5 Critical. Delete: "2. Stiffener not facing one direction" and substitute the following:

"2. Black surfaces on inner set up boxes do not alternate on same side of outer set up boxes."

PAGE 15

* 4.5.1.1: Delete paragraph 4.5.1.1 in its entirety and substitute the following:

"4.5.1.1 Primer mixture NOL #130 (See 4.4.3.2). Transfer an accurately weighed portion of approximately one gram of the primer mixture to a tared aluminum weighing dish provided with a teflon cover while both the dish and the cover are on the balance pan. Place the dish and contents with the cover removed, in an oven maintained at 60 degrees ± 5 degrees C. for 2 hours. The cover shall be placed in a desiccator during the drying period. After drying, transfer the dish and contents quickly to a desiccator and cool to room temperature. Replace the plastic cover and weigh. Calculate the loss in weight of the dish cover and contents to percent moisture in the sample.

AMSC N/A FSC 1375

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T19:13Z
Check the source to verify that this is the current version before use.

4.5.1.1.1 Moisture content, alternate method (see 4.4.3.2). The procedure is the same as paragraph 4.5.1.1 with the following exception. The sample shall be dried in a vacuum oven at a temperature of 60 ± 5 degrees C and a pressure of 80 ± 10 mm of mercury for 45 minutes."

* 4.5.1.2: Delete paragraph 4.5.1.2 in its entirety and substitute the following:

"4.5.1.2 Determination of moisture content of lead azide (See 4.4.3.2). - A tared dried aluminum dish 2 inches in diameter shall be covered with a sheet of teflon 2 1/2 inches square and sufficiently flat to form a tight cover. An accurately weighed portion of approximately two grams shall be transferred to the moisture dish while both the cover and dish are on the balance pan. The dish and contents shall be transferred to an oven and dried at 95 deg C. plus or minus (±) 5 deg C. for 2 hours. The cover shall be placed in a desiccator during the drying period. After drying, the dish shall be quickly transferred to the desiccator and allowed to cool to room temperature. The teflon cover shall be placed on the dish and the assembly weighed. The loss in weight shall be calculated to percentage of moisture in the lead azide as follows:

$$\text{Percentage of moisture} = \frac{A-B}{A} \times 100$$

Where:
A = the weight of the specimen before drying.
B = the weight of the specimen after drying.

4.5.1.2.1 Determination of moisture content of lead azide, alternate method (See 4.4.3.2). - The procedure is the same as paragraph 4.5.1.2 with the following exception. The sample shall be dried in a vacuum oven at a temperature of 95 ± 5 deg C. and a pressure of 80 ± 10 mm of mercury for 45 minutes."

Source: https://assist.dla.mil Downloaded: 2026-10-22T19:13Z
Check the source to verify that this is the current version before use.

NOTE: The margins of this amendment are marked with an asterisk or vertical line to indicate where changes (additions, modifications, corrections, deletions) from the previous amendment were made. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content irrespective of the marginal notations and relationship to the last previous amendment.

Custodian:
Army-AR

Preparing activity:
Army-AR

(Project 1375 - A482)

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T19:13Z
Check the source to verify that this is the current version before use.